



Designation: ~~D4930–06 (Reapproved 2017)~~ D4930 – 23

Standard Test Method for Dust Control Material on Calcined Petroleum Coke¹

This standard is issued under the fixed designation D4930; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. ~~Scope~~ Scope*

1.1 This test method covers the determination of the amount of material applied to calcined coke to control dust associated with coke handling and transportation.

1.2 This test method is limited to those materials that are soluble in a solvent that can be used in a Soxhlet extraction type of apparatus such as methylene chloride (dichloro-methane).

NOTE 1—Methylene chloride is the most popular solvent for removing dust control oil at the time this procedure is being written. Toluene and methyl chloroform, however, have been used with equal results on all cokes tested which have included only those sprayed with aromatic or waxy materials.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* For specific warning statements, see Section 7.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D346 Practice for Collection and Preparation of Coke Samples for Laboratory Analysis](#)

[D2013 Practice for Preparing Coal Samples for Analysis](#)

[D2234/D2234M Practice for Collection of a Gross Sample of Coal](#)

[D4057 Practice for Manual Sampling of Petroleum and Petroleum Products](#)

[D4175 Terminology Relating to Petroleum Products, Liquid Fuels, and Lubricants](#)

[E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves](#)

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this test method, refer to Terminology [D4175](#).

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.05 on Properties of Fuels, Petroleum Coke and Carbon Material.

Current edition approved Oct. 1, 2017 July 1, 2023. Published November 2017 July 2023. Originally approved in 1989. Last previous edition approved in 2014 2017 as D4930 – 06 (2014) (2017). DOI: [10.1520/D4930-06R17](https://doi.org/10.1520/D4930-06R17); [10.1520/D4930-23](https://doi.org/10.1520/D4930-23).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

***A Summary of Changes section appears at the end of this standard**

3.1.2 *analysis sample, n*—the reduced and divided representative portion of the bulk sample, prepared for use in the laboratory.

3.1.3 *bulk sample, n*—the reduced and divided representative portion of the gross sample as prepared for shipment to and received by a laboratory, to be prepared for analysis.

3.1.4 *test sample, n*—the weighed portion of the analysis sample actually used in a test.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *de-dusting material, n*—a substance, such as a petroleum oil, a petroleum wax, an aqueous latex emulsion, and the like, that is applied to (sprayed on) calcined petroleum coke to control dust associated with coke handling and transport.

4. Summary of Test Method

4.1 The dust control material is dissolved from a weighed dry representative sample of 6.3 mm maximum sized coke by methylene chloride in a Soxhlet extraction apparatus. The mass of the residue remaining after distilling and evaporating the solvent is the mass of dust control material. The amount of residue as a percent of the original mass is calculated.

5. Significance and Use

5.1 The test is designed to quantify the amount of dust control material added to calcined coke. The dust control material is applied to calcined coke to help maintain a dust-free environment. It generally serves no other useful purpose. It adds mass to the coke and can have a negative effect on the quality of carbon and graphite artifacts made from the treated coke. For these reasons the coke customer wants to know the amount of dust control material on the coke and can specify a maximum level.

6. Apparatus

6.1 *Extractor*, with condenser, Soxhlet, 200 mL capacity.³

6.2 *Flask*, round bottom with short neck, 250 mL.

6.3 *Heating Mantle*, for 250 mL flask.

6.4 *Boiling Chips*.

6.5 *Thimbles, Cellulose Extraction*, 43 mm in diameter by 123 mm in height (single thickness; 9 μ m to 11 μ m for *liquid* retention).

6.6 *Analytical Balance*, capable of weighing to 0.1 mg.

6.7 *Hot Plate*, with temperature control $\pm 3^\circ\text{C} \pm 3^\circ\text{C}$ between 90 $^\circ\text{C}$ and 110 $^\circ\text{C}$.

6.8 *Hooked Glass Tube*, 3 mm inside diameter, 225 mm long, bent such that about 75 mm extends into the flask when connected into the neck of the flask.

6.9 *Flexible Tubing*.

6.10 *Drying Oven, Forced Draft or Vacuum* (vacuum preferred if toluene is used).

6.11 *Desiccator*.

³ The sole source of supply of the apparatus known to the committee at this time is the Soxhlet extraction apparatus, Kimax (glass), 24005 series, catalog No. 393-2711, available from Curtin Matheson Scientific, Inc., 9999 Veterans Memorial Dr., Houston, TX 77038. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

6.12 *Rifflers*, encased with hoppers.

6.13 *Hood*.

7. Reagents

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.⁴ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.1.1 *Methylene Chloride*, reagent grade with *residue after evaporation* specification of 0.002 % or less (any other solvent used shall be reagent grade with no greater residue). (**Warning**—The use of methylene chloride is extremely volatile (BP = 40 °C) and mildly toxic.) (**Warning**—All handling of methylene chloride, including volumetric measurement and transfer of the solvent to the extraction apparatus, must be done in an approved fume exhaust hood. Extractions and subsequent methylene chloride drying procedures *must* also be performed in this same hood.⁵)

7.1.2 *Acetone*, reagent grade. (**Warning**—Acetone is extremely flammable.) (**Warning**—Keep away from heat, sparks, and flame and keep container closed when not actually pouring acetone. Use only in a well-ventilated area. Avoid inhalation and contact with the eyes or skin.)

8. Sample Preparation

8.1 Riffle divide the bulk sample to obtain a 200 g analysis sample.

8.2 Reduce the analysis sample to pass a 6.3 mm sieve by one pass through a jaw crusher set to not crush smaller than 6.3 mm (a roll crusher can be used by stage crushing to 6.3 mm).

8.3 Dry the reduced analysis sample at 110 °C to 115 °C to constant mass (about 8 h may be required; overnight drying preferred when convenient). Store in a desiccator until ready to test.

ASTM D4930-23

NOTE 2—The recommended practices for collecting samples and the equipment and procedures for crushing and dividing are described in Practice D346, D4057, and Practice D2013 and Test Methods D2234/D2234M. Specifications for sieves are described in Specification E11.

9. Procedure

9.1 From the dried analysis sample, riffle to obtain a test sample of about 75 g. Weigh the test sample to the nearest 0.01 g and record the mass as W_s .

9.2 Charge an extractor thimble with the test sample, place the thimble in the extractor, and assemble extractor and condenser.

NOTE 3—Do not use grease on joints. Use TFE-fluorocarbon sleeves to control leaking problems.

9.3 Put two or three clean boiling chips into a clean, dry boiling flask and weigh to the nearest 0.1 mg. Record the mass as W_1 .

NOTE 4—Because of the required mass precision, handle the flask with clean tongs or gloves.

9.4 Pour 210 mL of methylene chloride into the boiling flask and assemble it to the extractor.

⁴ *Reagent Chemicals, American Chemical Society Specifications, ACS Reagent Chemicals, Specifications and Procedures for Reagents and Standard-Grade Reference Materials*, American Chemical Society, Washington, DC. For ~~Suggestions~~ suggestions on the testing of reagents not listed by the American Chemical Society, see *Annual Analytical Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

⁵ Occupational Health Guidelines for Chemicals “Methylenechloride,” DHHS (NIOSH) Publication No. 81-123, January 1981.