



Designation: ~~C1567--22a~~ C1567 - 23

Standard Test Method for Determining the Potential Alkali-Silica Reactivity of Combinations of Cementitious Materials and Aggregate (Accelerated Mortar-Bar Method)¹

This standard is issued under the fixed designation C1567; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method permits detection within 16 days of the potential for deleterious alkali-silica reaction of combinations of cementitious materials and aggregate in mortar bars. The cementitious materials are composed of various proportions of hydraulic cement, pozzolans and ~~ground-granulated-blast-furnace-slag-slag cement~~.

1.2 The test results are only valid for the specific combinations of pozzolan, slag, and reactive aggregates tested.

1.3 This test is not suitable for evaluating the potential for deleterious reaction of combinations of hydraulic cement and aggregate (that is, in the absence of pozzolans or ~~ground-granulated-blast-furnace-slag-slag cement~~).

1.4 The text of this test method refers to notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this test method.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars \(Using 2-in. or \[50 mm\] Cube Specimens\)](#)

[C125 Terminology Relating to Concrete and Concrete Aggregates](#)

[C127 Test Method for Relative Density \(Specific Gravity\) and Absorption of Coarse Aggregate](#)

[C128 Test Method for Relative Density \(Specific Gravity\) and Absorption of Fine Aggregate](#)

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.50 on Aggregate Reactions in Concrete.

Current edition approved Dec. 15, 2022; June 1, 2023. Published July 2023. Originally approved in 2004. Last previous edition approved in 2022 as C1567-22. DOI: 10.1520/C1567-22A-22a. DOI: 10.1520/C1567-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

C150/C150M Specification for Portland Cement
C305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency
C490/C490M Practice for Use of Apparatus for the Determination of Length Change of Hardened Cement Paste, Mortar, and Concrete
C494/C494M Specification for Chemical Admixtures for Concrete
C511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes
C618 Specification for Coal Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials
C989/C989M Specification for Slag Cement for Use in Concrete and Mortars
C1240 Specification for Silica Fume Used in Cementitious Mixtures
C1260 Test Method for Potential Alkali Reactivity of Aggregates (Mortar-Bar Method)
C1437 Test Method for Flow of Hydraulic Cement Mortar
C1567 Test Method for Determining the Potential Alkali-Silica Reactivity of Combinations of Cementitious Materials and Aggregate (Accelerated Mortar-Bar Method)
C1778 Guide for Reducing the Risk of Deleterious Alkali-Aggregate Reaction in Concrete
D1193 Specification for Reagent Water
E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms relating to concrete or aggregates, see Terminology C125.

3.2 *relative density (OD), n*—as defined in Test Methods C127 or C128, for coarse and fine aggregates, respectively.

4. Significance and Use

4.1 This test method provides a means for evaluating the ability of pozzolans and ~~ground granulated blast-furnace slag~~ slag cement to control deleterious internal expansion due to alkali-silica reaction when used with an aggregate intended for use in concrete. It is based on the Accelerated Test Method developed at the National Building Research Institute (NBRI) in the Republic of South Africa (1-4).³

4.2 This test method has been developed for evaluating combinations of certain cementitious materials with a single aggregate source in a mortar of standard proportions. It yields an empirical result, which is utilized to compare to criteria within some specifications to accept or reject the combination of materials being evaluated for a particular application. Currently this method has no standard procedure for testing fine and coarse aggregates proposed for use in concrete together in a single batch of mortar, nor for varying the proportions of the constituent materials of the mortar beyond the relative proportions of the individual cementitious material constituents to each other, as the significance of these practices have not been determined nor have appropriate limits been established for evaluating the results of tests conducted using these modifications.

4.3 Different levels of pozzolan and slag cement may require testing to determine the amount required to reduce expansion to an acceptable level. Pozzolans and ground granulated blast-furnace slag may be tested separately or in combination.

4.4 It is recommended to test the same aggregate and hydraulic cement (without pozzolans and slag cement) using Test Method C1260.

4.5 Results of tests conducted as described herein shall form a part of the basis for determining the precautions that shall be taken against excessive expansion due to alkali-silica reaction. Refer to Guide C1778 for the interpretation of the test results from Test Method C1567.

5. Apparatus

5.1 The apparatus shall conform to Practice C490/C490M, except as follows:

³ The boldface numbers in parentheses refer to a list of references at the end of the text.

5.2 *Sieves*—Square hole, woven-wire cloth sieves, shall conform to Specification E11.

5.3 *Mixer, Paddle, and Mixing Bowl*—Mixer, paddle, and mixing bowl shall conform to the requirements of Practice C305, except that the clearance between the lower end of the paddle and the bottom of the bowl shall be $5.1 \text{ mm} \pm 0.3 \text{ mm}$.

5.4 *Tamper and Trowel*—The tamper and trowel shall conform to Test Method C109/C109M.

5.5 *Containers*—The containers shall be of such a nature that the bars can be totally immersed in either the water or 1N sodium hydroxide (NaOH) solution. The containers shall be made of material that can withstand prolonged exposure to $80 \text{ }^\circ\text{C}$ and must be resistant to a 1N NaOH solution (see Note 1). The containers must be so constructed that when used for storing specimens, the loss or gain of moisture is prevented by tight-fitting covers, by sealing, or both (see Note 2). The bars in the solution must be placed and supported so that the solution has access to the entire surface of each bar; therefore, ensure that the specimens do not touch the sides of the container or each other. The specimens, if stood upright in the solution, shall not be supported by the metal gage stud.

NOTE 1—The NaOH solution corrodes glass or metal containers.

NOTE 2—Some microwave-proof food storage containers made of polypropylene or high-density polyethylene have been found to be acceptable.

5.6 *Oven, or Water Bath*—A convection oven or water bath with temperature control maintaining $80.0 \text{ }^\circ\text{C} \pm 2.0 \text{ }^\circ\text{C}$.

6. Reagents

6.1 *Sodium Hydroxide (NaOH)*—USP or technical grade may be used, provided the Na^+ and OH^- concentrations are shown by chemical analysis to lie between 0.99 N and 1.01 N.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Type IV of Specification D1193.

6.3 *Sodium Hydroxide Solution*—Each litre of solution shall contain 40.0 g of NaOH dissolved in 900 mL of water, and shall be diluted with additional distilled or deionized water to obtain 1.0 L of solution. The volume proportion of sodium hydroxide solution to mortar bars in a storage container shall be 4 ± 0.5 volumes of solution to 1 volume of mortar bars. The volume of a mortar bar may be taken as 184 mL. Include sufficient test solution to ensure complete immersion of the mortar bars.

6.3.1 **Warning**—Before using NaOH, review: (1) the safety precautions for using NaOH; (2) first aid for burns; and (3) the emergency response to spills, as described in the manufacturer's Material Safety Data Sheet or other reliable safety literature. NaOH can cause very severe burns and injury to unprotected skin and eyes. Suitable personal protective equipment must always be used. These include full-face shields, rubber aprons, and gloves impervious to NaOH. Gloves must be checked periodically for pinholes.

7. Conditioning

7.1 Maintain the temperature of the molding room and dry materials at not less than $20 \text{ }^\circ\text{C}$ and not more than $27.5 \text{ }^\circ\text{C}$. The temperature of the mixing water, and of the moist closet or moist room, shall not vary from $23 \text{ }^\circ\text{C}$ by more than $2 \text{ }^\circ\text{C}$.

7.2 Maintain the relative humidity of the molding room at not less than 50 %. The moist closet or room shall conform to Specification C511.

7.3 Maintain the storage oven or water bath in which the specimens are stored at a temperature of $80.0 \text{ }^\circ\text{C} \pm 2.0 \text{ }^\circ\text{C}$.

8. Sampling and Preparation of Test Specimens

8.1 *Selection of Aggregate*—Process materials proposed for use as fine aggregate in concrete as described in 8.2 with a minimum of crushing. Process materials proposed for use as coarse aggregate in concrete by crushing to produce as nearly as practical a

graded product from which a sample can be obtained. Grade the sample as prescribed in **Table 1**. The sample shall represent the composition of the coarse aggregate as proposed for use.

8.1.1 When a given quarried material is proposed for use both as coarse and as fine aggregate, test only a selection of the fine aggregate, unless there is reason to expect that the coarse aggregate has a different composition than the fine aggregate. If such a difference is expected and if the differences might significantly affect expansion due to reaction with the alkalis in cement or from the environment of service, test the coarse aggregate in a manner similar to that employed in testing the fine aggregate.

8.2 *Preparation of Aggregate*—Grade aggregates to provide a sample meeting the requirements given in **Table 1**. Crush aggregates in which sufficient quantities of the sizes specified in **Table 1** do not exist until the required material has been produced. In the case of aggregates containing insufficient amounts of one or more of the larger sizes listed in **Table 1**, and if no larger material is available for crushing, the first size in which sufficient material is available shall contain the cumulative percentage of material down to that size as determined from the grading specified in **Table 1**. When such procedures are required, make a special note thereof in the test report. After the aggregate has been separated into the various sieve sizes, wash each size with a water spray over the sieve to remove adhering dust and fine particles from the aggregate. Dry the portions retained on the various sieves and, unless used immediately, store each such portion individually in a clean container provided with a tight-fitting cover.

8.3 *Selection and Preparation of Cement:*

8.3.1 *Hydraulic Cement*—Use a hydraulic cement meeting the requirements of Specification **C150/C150M** (**Note 3**).

NOTE 3—The alkali content of the cement has been found to have negligible (**3**) or minor (**5**) effects on expansion in this test.

8.3.2 *Preparation of Cement*—Pass cement for use in this test through an 850- μm (No. 20) sieve to remove lumps before use.

8.4 *Selection of pozzolan or ~~ground granulated blast furnace slag~~—slag cement*—Use one, or a combination, of the following:

8.4.1 Fly ash or natural pozzolan meeting the requirements of Specification **C618**.

8.4.2 Silica fume meeting the requirements of Specification **C1240**.

8.4.3 ~~Ground granulated blast furnace slag~~ Slag cement meeting the requirements of Specification **C989/C989M**.

<https://standards.iteh.ai/catalog/standards/sist/5206d9d4-4934-49c1-98aa-f502e37abcdd/astm-c1567-23>

8.5 *Preparation of Test Specimens:*

8.5.1 *Number of Specimens*—Make at least three test specimens for each cementitious materials-aggregate combination.

8.5.2 *Preparation of Molds*—Prepare the specimen molds in accordance with the requirements of Practice **C490/C490M** except, the interior surfaces of the molds shall be covered with a release agent (see **Note 4**). A release agent is acceptable if it serves as a parting agent without affecting the time of setting of the cement and without leaving any residue that will inhibit the penetration of water into the specimen.

NOTE 4—TFE-fluorocarbon tape complies with the requirements for a mold release agent.

8.5.3 *Proportioning of Mortar*—Proportion the dry materials for the test mortar using 1 part of cementitious materials (hydraulic cement plus pozzolan or ~~ground granulated blast furnace slag~~—slag cement) to 2.25 parts of graded aggregate by mass for aggregates with a relative density (OD) at or above 2.45. For aggregates with a relative density (OD) below 2.45, determine the aggregate proportion as follows:

TABLE 1 Grading Requirements

Sieve Size		Mass, %
Passing	Retained on	
4.75 mm (No. 4)	2.36 mm (No. 8)	10
2.36 mm (No. 8)	1.18 mm (No. 16)	25
1.18 mm (No. 16)	600 μm (No. 30)	25
600 μm (No. 30)	300 μm (No. 50)	25
300 μm (No. 50)	150 μm (No. 100)	15

$$\text{Aggregate Proportion} = 2.25 \times \frac{D}{2.65}$$

where:

D = relative density (OD) of test aggregate.

8.5.3.1 For aggregates with a relative density (OD) equal to or greater than 2.45, the quantities of dry materials to be mixed at one time in the batch of mortar for making three specimens shall be 440 g of cementitious material and 990 g of aggregate made up by recombining the portions retained on the various sieves in the grading prescribed in **Table 1**. Use a water-cement ratio equal to 0.47 by mass (see **Note 5**).

8.5.3.2 For aggregates with a relative density (OD) less than 2.45, the quantities of dry materials to be mixed at one time in the batch of mortar for making three specimens shall be 440 g of cementitious material and mass of aggregate shall be 440 g multiplied by the aggregate proportion determined in **8.5.3**. This aggregate mass shall be made up by recombining the portions retained on the various sieves in the grading prescribed in **Table 1**. Use a water-cementitious material ratio equal to 0.47 by mass (see **Note 5**).

NOTE 5—Ruggedness tests indicated that mortar bar expansions were less variable at a fixed water-cement ratio than when gauged to a constant flow (**3**).

8.5.3.3 If silica fume or metakaolin are used, a high range water reducer (HRWR), meeting the requirements of Specification **C494/C494M** Type F, shall be used (if necessary) to provide adequate dispersion and workability of the mixture. The water-cementitious material ratio shall remain 0.47 by mass and the amount of HRWR shall be that to obtain a flow of ± 7.5 percentage points of a control mortar without silica fume or metakaolin as determined in accordance with Test Method **C1437** using 10 drops of the flow table. If liquid HRWR is used, the water present in the liquid must be included in the calculation of the water-cementitious material ratio.

8.5.4 *Mixing of Mortar*—Mix the mortar in accordance with the requirements of Practice **C305**.

8.5.5 *Molding of Test Specimens*—Mold test specimens within a total elapsed time of not more than 2 min and 15 s after completion of the original mixing of the mortar batch. Fill the molds with two approximately equal layers, each layer being compacted with the tamper. Work the mortar into the corners, around the gage studs, and along the surfaces of the mold with the tamper until a homogeneous specimen is obtained. After the top layer has been compacted, cut off the mortar flush with the top of the mold and smooth the surface with a few strokes of the trowel.

9. Procedure

9.1 *Initial Storage and Reading*—Place each mold in the moist cabinet or room immediately after molds have been filled. The specimens shall remain in the molds for 24 ± 2 h. Remove the specimens from the molds and, while they are being protected from loss of moisture, properly identify and make an initial comparator reading. Make and record the initial and all subsequent readings to the nearest 0.002 mm. Place the specimens made with each aggregate sample in a storage container with sufficient tap water to totally immerse them. The temperature of the water used to immerse the specimens shall be $23.0 \text{ }^\circ\text{C} \pm 2.0 \text{ }^\circ\text{C}$ at the time of immersion. Seal and place the containers in an oven or water bath at $80.0 \text{ }^\circ\text{C} \pm 2.0 \text{ }^\circ\text{C}$ for a period of $24 \text{ h} \pm 2 \text{ h}$.

9.2 *Zero Readings*—Remove the containers from the oven or water bath one at a time. Remove other containers only after the bars in the first container have been measured and returned to the oven or water bath. The time elapsed between removal and return of the specimens to the oven or water bath shall not exceed 10 min. Remove the bars one at a time from the water and dry their surface with a towel paying particular attention to the two metal gage studs. Take the zero reading (see **Note 6**) of each bar immediately after drying, and read as soon as the bar is in position. Complete the process of drying and reading within $15 \text{ s} \pm 5 \text{ s}$ of removing the specimen from the water. After taking comparator readings, leave the specimen on a towel until comparator readings have been taken on the remainder of the bars. Place all specimens made with each unique cementitious materials-aggregate combination in a separate container with sufficient 1N NaOH, at $80.0 \text{ }^\circ\text{C} \pm 2.0 \text{ }^\circ\text{C}$ for the specimens to be totally immersed. Seal the container and return it to the oven or water bath.

NOTE 6—The reference bar should be read prior to each set of specimens since the heat from the mortar bars may cause the length of the comparator to change.