



Designation: **D8005—18** **D8005 – 23**

Standard Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)¹

This standard is issued under the fixed designation D8005; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers a procedure for the visual measurement of the color of near clear liquids. It is applicable only to materials in which the color-producing bodies present have light absorption characteristics nearly identical with those of the Platinum-Cobalt (Pt-Co) color standards used.

1.2 This test method has been found applicable to the color measurement of clear, liquid samples, free of haze, with nominal Pt-Co color values between 0 and 100. It is applicable to nonfluorescent liquids with light absorption characteristics similar to those of the Pt-Co color standard solutions. Test Methods **D1209**, **D1686**, and **D5386** deal with the visual and instrumental measurement of near-clear liquids.

1.3 In determining the conformance of the test results using this method to applicable specifications, results shall be rounded in accordance with the rounding off methods of Practice **E29**.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D1193 Specification for Reagent Water

D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)

D1686 Test Method for Color of Solid Aromatic Hydrocarbons and Related Materials in the Molten State (Platinum-Cobalt Scale)

D3437 Practice for Sampling and Handling Liquid Cyclic Products

D5386 Test Method for Color of Liquids Using Tristimulus Colorimetry

D6809 Guide for Quality Control and Quality Assurance Procedures for Aromatic Hydrocarbons and Related Materials

¹ This test method is under the jurisdiction of ASTM Committee **D16** on Aromatic, Industrial, Specialty and Related Chemicals and is the direct responsibility of Subcommittee **D16.01** on Benzene, Toluene, Xylenes, Cyclohexane and Their Derivatives.

Current edition approved Feb. 1, 2018; July 1, 2023. Published March 2018; July 2023. Originally approved in 2015. Last previous edition approved in 2015 as D8005 – 15. DOI: 10.1520/D8005-18.18. DOI: 10.1520/D8005-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

2.2 *Other Documents:*

[OSHA Regulations, 29 CFR paragraphs 1910.1000 and 1910.1200](#)³

3. Summary of Test Method

3.1 A specimen is placed in a Nessler tube and compared to a series of prepared Pt-Co standards.

4. Significance and Use

4.1 The major objective of the visual Pt-Co method of color measurement is to rate specific materials for yellowness. The yellowness is frequently the result of the undesirable tendency of liquid hydrocarbons to absorb blue light due to contamination in processing, storage, or shipping.

5. Apparatus

5.1 *Spectrophotometer*, equipped for liquid samples and for measurements in the visible region.

5.1.1 The spectrophotometer used must be clean and in first-class operating condition. The instrument should be calibrated in accordance with the instructions in the Standards for Checking and Calibration of Spectrophotometers (~~200~~200 cm to 1000 cm).⁴

5.2 *Spectrophotometer Cells*, matched having a ~~10-mm~~10 mm light path.

5.3 *Color Comparison Tubes*—Matched ~~100-mL~~100 mL, tall-form Nessler tubes, provided with ground-on, optically clear, glass caps. Tubes should be selected so that the height of the ~~100-mL~~100 mL graduation mark is ~~275~~275 mm to 295 mm above the bottom of the tube.

5.4 *Color Comparator*—A color comparator constructed to permit visual comparison of light transmitted through tall-form ~~100-mL~~100 mL Nessler tubes in the direction of their longitudinal axes. The comparator should be constructed so that white light is passed through or reflected off a white glass plate and directed with equal intensity through the tubes, and should be shielded so that no light enters the tubes from the side.⁵

6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁶ Other grades may be used, provided it is first ascertained that the agent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

TABLE 1 Absorbance Tolerance Limits for No. 500 Platinum-Cobalt Stock Solution

Wavelength, nm	Absorbance
430	0.100 to 0.120
455	0.130 to 0.145
480	0.105 to 0.120
510	0.055 to 0.065

³ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

⁴ See NIST Circular LC-1017.

⁵ The sole source of supply of the apparatus known to the committee at this time is Scientific Glass and Instruments, Inc., P.O. Box 6, Houston, TX 77001. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁶ *Reagent Chemicals, American Chemical Society Specifications, ACS Reagent Chemicals, Specifications and Procedures for Reagents and Standard-Grade Reference Materials*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

6.2 *Purity of Water*—References to water shall be understood to mean reagent water conforming to Type IV-I or II of Specification D1193.

6.3 *Cobalt Chloride* ($\text{CoCl}_2 \cdot 6\text{H}_2\text{O}$).

6.4 *Hydrochloric Acid* (sp gr 1.19)—Concentrated hydrochloric acid (HCl).

6.5 *Potassium Chloroplatinate* (K_2PtCl_6).

6.6 *Pt-Co Stock Solution*—Dissolve 1.245 g of potassium chloroplatinate (K_2PtCl_6) and 1.00 g of cobalt chloride ($\text{CoCl}_2 \cdot 6\text{H}_2\text{O}$) in water. Carefully add 100 mL of hydrochloric acid (HCl, sp gr. 1.19) and dilute to 1 L with water. The absorbance of the 500 Pt-Co stock solution in a cell having a ~~10-mm~~ 10 mm light path, with reagent water in a matched cell as the reference solution,⁷ must fall within the limits given in Table 1.

NOTE 1—This stock solution is commercially available from reputable chemical suppliers.

6.7 *Pt-Co Standards*—From the stock solution, prepare color standards in accordance with Table 2 and Table 3 by diluting the required volumes to 100 mL with water in the Nessler tubes. Cap the tubes and seal the caps with shellac or a waterproof cement. ~~When properly sealed and stored, these standards are stable for at least one year and do not degrade markedly for two years.~~ D16 PTP results show significant changes in the standards. Standards should be replaced within a year. (Table 3)

7. Hazards

7.1 Consult current OSHA regulations, supplier's Safety Data Sheets, and local regulations for all materials used in this test method.

8. Sampling and Handling

8.1 Refer to Practice D3437 for proper sampling and handling of liquid hydrocarbons analyzed by this test method.

9. Procedure

<https://standards.iteh.ai/catalog/standards/sist/e5a5c8ae-5c0f-4139-b2c4-be9b4022ccfa/astm-d8005-23>

9.1 Introduce 100 mL of specimen into a Nessler tube, passing the specimen through a filter if it has any visible turbidity. Cap the tube, place in the comparator, and compare with the standards.

9.1.1 For samples between 1 and 20, use standards that are 1 Pt-Co color unit apart.

9.1.2 For samples between 20 and 100, use standards that are 5 Pt-Co color units apart.

TABLE 2 Platinum-Cobalt Color Standards for Very Light Colors

Color Standard Number	Stock Solution, mL	Color Standard Number	Stock Solution, mL
1	0.20	11	2.20
2	0.40	12	2.40
3	0.60	13	2.60
4	0.80	14	2.80
5	1.00	15	3.00
6	1.20	16	3.20
7	1.40	17	3.40
8	1.60	18	3.60
9	1.80	19	3.80
10	2.00	20	4.00

⁷ See the manufacturer's instruction manual for complete details for operating the spectrophotometer.