



Designation: ~~C331/C331M—17~~ C331/C331M – 23

## Standard Specification for Lightweight Aggregates for Concrete Masonry Units<sup>1</sup>

This standard is issued under the fixed designation C331/C331M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This specification covers lightweight aggregates intended for use in concrete masonry units when a prime consideration is to reduce the density of the units.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. Some values have only SI units because the inch-pound equivalents are not used in practice.

NOTE 1—Sieve size is identified by its standard designation in Specification E11. The alternative designation given in parentheses is for information only and does not represent a different standard sieve size.

1.3 The text of this specification references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<https://standards.iteh.ai/catalog/standards/sist/ca3fd978-09ce-4c69-97e7-0026faf5365d/astm-c331-c331m-23>

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

~~C29/C29M~~ C29/C29M Test Method for Bulk Density (“Unit Weight”) and Voids in Aggregate

~~C40/C40M~~ C40/C40M Test Method for Organic Impurities in Fine Aggregates for Concrete

C114 Test Methods for Chemical Analysis of Hydraulic Cement

C125 Terminology Relating to Concrete and Concrete Aggregates

~~C136/C136M~~ C136/C136M Test Method for Sieve Analysis of Fine and Coarse Aggregates

~~C142/C142M~~ C142/C142M Test Method for Clay Lumps and Friable Particles in Aggregates

~~C151/C151M~~ C151/C151M Test Method for Autoclave Expansion of Hydraulic Cement

C157/C157M Test Method for Length Change of Hardened Hydraulic-Cement Mortar and Concrete

C641 Test Method for Iron Staining Materials in Lightweight Concrete Aggregates

~~C702/C702M~~ C702/C702M Practice for Reducing Samples of Aggregate to Testing Size

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.21 on Lightweight Aggregates and Concrete.

Current edition approved June 15, 2017; June 1, 2023. Published July 2017; July 2023. Originally approved in 1953. Last previous edition approved in 2014; 2017 as C331/C331M – 14. DOI: 10.1520/C0331-C0331M-17.17. DOI: 10.1520/C0331-C0331M-23.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard



~~C1262~~C1262/C1262M Test Method for Evaluating the Freeze-Thaw Durability of Dry-Cast Segmental Retaining Wall Units and Related Concrete Units

D75D75/D75M Practice for Sampling Aggregates

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

### 3. Terminology

#### 3.1 Definitions:

3.1.1 For definitions of terms used in this specification, refer to Terminology C125.

### 4. Aggregate Types

4.1 Three general types of lightweight aggregates are covered by this specification, as follows:

4.1.1 Aggregates prepared by expanding, pelletizing, or sintering products such as blast-furnace slag, clay, diatomite, fly ash, shale, or slate, and

4.1.2 Aggregates prepared by processing natural materials, such as pumice, scoria, or tuff, and

4.1.3 Aggregates consisting of end products of coal or coke combustion.

4.2 The aggregates shall be composed predominately of lightweight-cellular and granular inorganic material.

### 5. Chemical Composition

5.1 Lightweight aggregates shall not contain excessive amounts of deleterious substances, as determined by the following limits:

5.1.1 *Organic Impurities* (Test Method ~~C40~~C40/C40M)—Lightweight aggregates subjected to the test for organic impurities that produce a color darker than the standard shall be rejected, unless it is demonstrated that the discoloration is due to small quantities of materials not harmful to the concrete.

5.1.2 *Staining* (Test Method C641)—An aggregate producing a stain index of 60 or higher shall be rejected when the deposited stain is found upon chemical analysis to contain an iron content, expressed as  $\text{Fe}_2\text{O}_3$  equal to or greater than 1.5 mg/200 g of sample.

5.1.3 *Loss on Ignition* (Test Methods C114)—Loss on ignition of aggregates, consisting of end products of coal or coke combustion, shall not exceed 12 %. Loss on ignition of other aggregates shall not exceed 5 %.

NOTE 2—Some aggregates may contain carbonates or water of hydration that contribute to loss on ignition but may not affect the quality of the product. Therefore, when evaluating an aggregate, consideration should be given to the material characteristics that cause the ignition loss.

### 6. Physical Properties

6.1 Lightweight aggregate under test shall meet the following requirements:

6.1.1 *Clay Lumps and Friable Particles*—The amount of clay lumps and friable particles shall not exceed 2 % by dry mass.

6.1.2 *Grading*—Aggregate grading shall be by mutual agreement between interested parties. See Appendix X1 for aggregate grading guidance.

6.1.3 *Uniformity of Grading*—To ensure reasonable uniformity in the gradation of successive shipments of lightweight aggregate, fineness modulus shall be determined on samples taken from shipments at intervals stipulated by the purchaser. If the fineness modulus of the aggregate in any shipment differs by more than 7 % from that of the sample submitted for acceptance tests, the aggregate in the shipment shall be rejected, unless the supplier demonstrated that it will produce concrete of the required characteristics.

6.1.4 *Loose Bulk Density (Test Method C29/C29M)*—The loose bulk density of lightweight aggregates shall conform to the requirements in **Table 1** using a 14 L [ $\frac{1}{2}$  ft<sup>3</sup>] measure.

6.1.5 *Uniformity of Loose Bulk Density*—The dry loose bulk density of lightweight aggregate shipments sampled and tested shall not differ by more than  $\pm 50$  kg/m<sup>3</sup> [3 lb/ft<sup>3</sup>] or 7 %, whichever is greater, from that of the sample submitted for acceptance tests, and shall not exceed the limits in **Table 1**.

6.2 Concrete specimens containing lightweight aggregate under test shall meet the following requirements:

6.2.1 *Popouts*—Concrete specimens prepared and tested in accordance with **9.1** shall show no surface popouts.

6.2.2 *Resistance to Freezing and Thawing*—When required, the aggregate supplier shall demonstrate by test or proven field performance that the lightweight aggregate when used in manufactured concrete masonry units and related concrete units has the necessary resistance to freezing and thawing to perform satisfactorily in its intended use.

NOTE 3—Methods are available to evaluate the performance of manufactured concrete masonry products made with lightweight aggregates. For example, Test Method ~~C1262~~**C1262/C1262M** includes procedures for evaluating manufactured concrete masonry units and related concrete units, but does not include criteria for determining compliance. Care should be used in evaluating the results of Test Method ~~C1262~~**C1262/C1262M** or any other method since the results are affected by other characteristics of the concrete mixture in addition to the characteristics of the lightweight aggregate, including, but not limited to the following: cement content, cement type, admixtures, and water content.

6.2.3 *Drying Shrinkage*—Drying shrinkage of concrete specimens prepared and tested in accordance with **9.6** shall not exceed 0.10 %.

## 7. Sampling

7.1 Sample lightweight aggregates in accordance with Practice ~~D75~~**D75/D75M**.

7.2 Reduce sample to test sizes in accordance with Practice ~~C702~~**C702/C702M**.

## 8. Number of Tests

8.1 *Tests on Aggregate*—One representative sample is required for each test for organic impurities, staining, clay lumps, loss on ignition, grading, and bulk density.

8.2 *Tests on Concrete Masonry Units*—Three specimens are required for the test for popout materials.

## 9. Test Methods

9.1 *Test for Popout Materials*—Obtain test specimens by one of the following methods: (1) Whole concrete masonry units, free of visible cracks or other structural defects; (2) Portions of concrete masonry units cut from whole units and having a surface area of at least ~~580 cm~~**580 cm**<sup>2</sup> [~~90 in.~~**90 in.**<sup>2</sup>]; (3) Specimens prepared as described in **9.6**. Autoclave test specimens in accordance with Test Method ~~C151~~**C151/C151M**. Visually inspect the autoclaved specimens for the number of popouts that have developed on the surface and report the average number of popouts per specimen.

**TABLE 1 Maximum Bulk Density (Dry Loose) Requirements of Lightweight Aggregates for Concrete Masonry Units**

Nominal Size Designation	Maximum Dry Loose Bulk Density kg/m <sup>3</sup> [lb/ft <sup>3</sup> ]
Fine aggregate 4.75 mm (No. 4) to 0	1120 [70]
Coarse aggregate 9.5 to 2.36 mm (3/8 in. to No. 8)	880 [55]
Coarse aggregate 9.5 mm to 2.36 mm (3/8 in. to No. 8)	880 [55]
Combined fine and coarse aggregate	1040 [65]

9.2 *Test for Resistance to Freezing and Thawing*—Test for resistance to freezing and thawing of manufactured concrete masonry units and related concrete units in accordance with Test Method ~~C1262~~C1262/C1262M.

9.3 *Grading*—Follow the procedures of Test Method ~~C136~~C136/C136M except that the mass of the test sample for fine aggregate shall be in accordance with **Table 2**. The test sample for coarse aggregate shall consist of 2830 cm<sup>3</sup> [0.1 ft<sup>3</sup>] or more of the material used for determination of bulk density. Mechanical sieving of aggregate shall be for 5 ~~min~~minutes ± 0.1 minutes.

9.4 *Bulk Density (Loose)* (Test Method ~~C29~~C29M)—The aggregate shall be tested in an oven-dry condition utilizing the shoveling procedure.

9.5 *Clay Lumps and Friable Particles in Aggregates*, shall be in accordance with Test Method ~~C142~~C142/C142M.

9.6 *Shrinkage of Concrete*, shall be in accordance with Test Method ~~C157~~C157M, with the following exceptions:

9.6.1 Prepare a concrete mix in the proportions of one part portland cement to six parts combined aggregates, measured by dry loose volume. Adjust the water content so as to produce a slump of 50 to 75 mm [2 to 3 in.] and thoroughly consolidate the concrete in steel molds ~~50 by 50~~50 mm by 50 mm by 285 mm [~~2 by 2~~2 in. by 2 in. by 11¼ in.]. The surface of the concrete shall be steel-troweled.

9.6.2 Cure the test specimens in a moist condition for 7 days at a temperature of  $23 \pm 2^\circ\text{C}$  [ $73.5 \pm 3.5^\circ\text{F}$ ] $23^\circ\text{C} \pm 2^\circ\text{C}$  [ $73.5^\circ\text{F} \pm 3.5^\circ\text{F}$ ] and a relative humidity of not less than 95 %. Make the initial length measurements immediately after removal of specimens from moist storage. Store the specimens in an atmosphere of  $23 \pm 2^\circ\text{C}$  [ $73.5 \pm 3.5^\circ\text{F}$ ] $23^\circ\text{C} \pm 2^\circ\text{C}$  [ $73.5^\circ\text{F} \pm 3.5^\circ\text{F}$ ] and a relative humidity of ~~50~~50 % ± 5 % for the duration of the test. Make subsequent measurements at 28 days and 100 days.

9.6.3 Calculate the difference in length of the specimens, when removed from moist storage at an age of 7 days and at the final measurement at the age of 100 days, to the nearest 0.01 % of the effective gage length, and report as the drying shrinkage of the specimen. Report the average drying shrinkage of the specimens tested as the drying shrinkage of the concrete.

## 10. Rejection

10.1 Material that fails to conform to the requirements of this specification shall be subject to rejection. The reason for rejection shall be reported to the producer or supplier promptly and in writing.

## 11. Certification

11.1 When specified in the purchase order or contract, a producer's or supplier's certification shall be furnished to the purchaser that the material was sampled and tested in accordance with this specification and has been found to meet the requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

## APPENDIX

### (Nonmandatory Information)

**TABLE 2 Mass of Sieve Test Sample for Fine Lightweight Aggregates**

Nominal Bulk Density (Loose) of Aggregate		Mass of Test Sample, g
kg/m <sup>3</sup>	[lb/ft <sup>3</sup> ]	
80–240	[5–15]	50
240–400	[15–25]	100
400–560	[25–35]	150
560–720	[35–45]	200
720–880	[45–55]	250
880–1040	[55–65]	300
1040–1120	[65–70]	350