



Designation: D7507 – 23

# Standard Specification for Woven High Stretch Fabrics Used in Apparel<sup>1</sup>

This standard is issued under the fixed designation D7507; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers the performance requirements for woven high stretch fabrics used in apparel.

1.2 The following safety hazards caveat pertains only to the test methods described in this performance specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.3 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

## 2. Referenced Documents (see Note 1)

2.1 ASTM Standards:<sup>2</sup>

D123 Terminology Relating to Textiles

D2905 Practice for Statements on Number of Specimens for Textiles (Withdrawn 2008)<sup>3</sup>

D3107 Test Methods for Stretch Properties of Fabrics Woven from Stretch Yarns

D3775 Test Method for End (Warp) and Pick (Filling) Count of Woven Fabrics

D3776 Test Methods for Mass Per Unit Area (Weight) of Fabric

D7022 Terminology Relating to Apparel (Withdrawn 2022)<sup>3</sup>

2.2 AATCC Test Methods:<sup>4</sup>

TM8 Colorfastness to Crocking: AATCC Crockmeter

TM15 Colorfastness to Perspiration

TM16.3 Colorfastness to Light: Xenon-Arc

TM61 Colorfastness to Laundering: Accelerated

TM81 pH of the Water-Extraction from West Processed Textiles

TM109 Colorfastness to Ozone in the Atmosphere under Low Humidity's

TM116 Colorfastness to Crocking: Rotary Vertical Crockmeter

TM132 Colorfastness to Drycleaning

TM135 Dimensional Changes of Fabrics after Home Laundering

TM158 Dimensional Changes on Drycleaning in Perchloroethylene: Machine

TM172 Colorfastness to Powdered Non-Chlorine Bleach in Home Laundering

EP1 Gray Scale for Color Change

EP2 Gray Scale for Staining

EP8 AATCC 9-Step Chromatic Transference Scale

M11 A Glossary of AATCC Standard Terminology

2.3 Other Documents:<sup>5</sup>

16 CFR 1610 Standard for Flammability of Clothing Textiles

NOTE 1—Reference to test methods in this specification give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

## 3. Terminology

3.1 For all terminology related to Apparel see Terminology D7022.

3.1.1 The following terms are relevant to this standard: woven high stretch fabric.

<sup>4</sup> Available from American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27709, <http://www.aatcc.org>.

<sup>5</sup> Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel.

Current edition approved Jan. 1, 2023. Published August 2023. Originally approved in 2010. Last previous edition approved in 2014 as D7507-14. DOI: 10.1520/D7507-23.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

3.2 For definitions of all other textile terms, refer to Terminology **D123**.

3.3 For terms relating to chemical or colorfastness testing, refer to specific AATCC test methods, or the Glossary of AATCC Standard Terminology.

#### 4. Significance and Use

4.1 Upon mutual agreement between the purchaser and the supplier, woven high stretch fabrics used in apparel should meet all of the requirements listed in **Table 1** of this specification.

4.2 It is recognized that, for purposes of fashion or aesthetics, the ultimate consumer of articles made from these fabrics may find acceptable products that do not conform to all

of the requirements listed in **Table 1**. Therefore, one or more of the requirements in **Table 1** may be modified by mutual agreement between the purchaser and the supplier.

4.2.1 In such cases, any references to the specifications should specify that: “This product meets ASTM specifications XXXX except for the following characteristic(s).”

4.3 Where no pre-purchase agreement has been reached between the purchaser and supplier, and in case of controversy, the requirements listed in **Table 1** are intended to be used as a guide only. As noted in **4.2**, ultimate consumer demands dictate varying performance parameters for a particular product.

4.4 The uses and significance of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

**TABLE 1 Specification Requirements**

Characteristic	Requirements		Section
	One-Way Stretch	Two-Way Stretch	
Dimensional Change to Home Laundering 3 Cycles	±3 %	±5 %	7.1.1
Dimensional Change to Drycleaning 1 Cycle	±2 %		7.1.2
Colorfastness to Accelerated Laundering-General <sup>4</sup>			7.2.1
Color change	Grade 4		
Staining	Grade 3		
Colorfastness to Drycleaning			
Color Change	Grade 4		
Staining	Grade 3		
Colorfastness to Non-chlorine Bleach			
Color change	Grade 4		7.2.3
Colorfastness to Crocking <sup>4</sup>			7.2.4
Dry	Grade 4		
Wet	Grade 3		
Colorfastness to Crocking <sup>4</sup> —Raised Surfaces, Dark shades or Pigment			7.2.4
Dry	Grade 3		
Wet	Grade 2		
Colorfastness to Perspiration <sup>4</sup>			7.2.5
Color Change	Grade 4		
Staining	Grade 3		
Colorfastness to Light, 20 AFUs			7.2.6
Colorfastness to Ozone (one cycle) Bleached Denim and Indigo Fabrics Only			7.2.7
Stretch Properties			7.3
Stretch percentage	report actual		
Growth	5 % maximum		
Recovery	minimum 80 %		
Fabric Count	Report actual or ±5 % tolerance if a specific count is claimed		7.4
Fabric Weight	Record actual		7.5
pH			
Wool, nylon	4.5 – 7.0		7.6
White	5.5 – 6.5		
All Other	6.0 – 8.0		
Flammability	Class 1		7.7

<sup>4</sup>See **Note 3**.