



Designation: ~~D7507~~—14 D7507 – 23

## Standard Specification for Woven High Stretch Fabrics Used in Apparel<sup>1</sup>

This standard is issued under the fixed designation D7507; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers the performance requirements for woven high stretch fabrics used in apparel.

1.2 The following safety hazards caveat pertains only to the test methods described in this performance specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices, safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents (see **Note 1**)

#### 2.1 ASTM Standards:<sup>2</sup>

~~D123~~ Terminology Relating to Textiles

~~D2905~~ Practice for Statements on Number of Specimens for Textiles (Withdrawn 2008)<sup>3</sup>

~~D3107~~ Test Methods for Stretch Properties of Fabrics Woven from Stretch Yarns

~~D3775~~ Test Method for End (Warp) and Pick (Filling) Count of Woven Fabrics

~~D3776~~ Test Methods for Mass Per Unit Area (Weight) of Fabric

~~D7022~~ Terminology Relating to Apparel (Withdrawn 2022)<sup>3</sup>

#### 2.2 AATCC Test Methods:<sup>4</sup>

~~8TM8~~ Colorfastness to Crocking: AATCC Crockmeter Method

~~15TM15~~ Colorfastness to Perspiration

~~16TM16.3~~ Colorfastness to Light-Light: Xenon-Arc

~~61TM61~~ Colorfastness to Laundering, Home and Commercial: Laundering: Accelerated

~~81TM81~~ pH of the Water-Extraction from West Processed Textiles

~~109TM109~~ Colorfastness to Ozone in the Atmosphere Under Low Humidity's

~~116TM116~~ Colorfastness to Crocking: Rotary Vertical Crockmeter Method

~~132TM132~~ Colorfastness to Drycleaning

~~135TM135~~ Dimensional Changes of Fabrics after Home Laundering

~~158TM158~~ Dimensional Changes on Drycleaning in Perchloroethylene: Machine Method

~~172TM172~~ Colorfastness to Powdered Non-Chlorine Bleach in Home Laundering

~~EP1~~ Gray Scale for Color Change

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel. Current edition approved Feb. 1, 2014/Jan. 1, 2023. Published March 2014/August 2023. Originally approved in 2010. Last previous edition approved in 2014 as D7507-10. DOI: 10.1520/D7507-14-14. DOI: 10.1520/D7507-23.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>4</sup> Available from American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27709, http://www.aatcc.org.

[EP2 Gray Scale for Staining](#)

[EP8 AATCC 9-Step Chromatic Transference Scale](#)

[M11 A Glossary of AATCC Standard Terminology](#)

2.3 *Other Documents*:<sup>5</sup>

[16 CFR 1610 Standard for Flammability of Clothing Textiles](#)

NOTE 1—Reference to test methods in this specification give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

### 3. Terminology

3.1 *Definitions*: For definitions of textile terms used in this specification, refer to Terminology [D123](#) and the AATCC Glossary.

3.1.1 *woven high stretch fabric, n*—woven fabrics with greater than 15 % elastic fiber content.

3.1 For all terminology related to Apparel see Terminology [D7022](#).

3.1.1 The following terms are relevant to this standard: woven high stretch fabric.

3.2 For definitions of all other textile terms, refer to Terminology [D123](#).

3.3 For terms relating to chemical or colorfastness testing, refer to specific AATCC test methods, or the Glossary of AATCC Standard Terminology.

### 4. Significance and Use

4.1 Upon mutual agreement between the purchaser and the supplier, woven high stretch fabrics used in apparel should meet all of the requirements listed in [Table 1](#) of this specification.

4.2 It is recognized that, for purposes of fashion or aesthetics, the ultimate consumer of articles made from these fabrics may find acceptable products that do not conform to all of the requirements listed in [Table 1](#). Therefore, one or more of the requirements in [Table 1](#) may be modified by mutual agreement between the purchaser and the supplier.

4.2.1<sup>h</sup> In such cases, any references to the specifications should specify that: “This product meets ASTM specifications XXXX except for the following characteristic(s).”

4.3 Where no pre-purchase agreement has been reached between the purchaser and supplier, and in case of controversy, the requirements listed in [Table 1](#) are intended to be used as a guide only. As noted in [4.2](#), ultimate consumer demands dictate varying performance parameters for a particular product.

4.4 The uses and significance of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

### 5. Sampling

5.1 *Acceptance Testing Lot*—Unless agreed otherwise, consider as a lot for acceptance testing all material of a single item as a single shipment.

5.2 *Lot Samples and Laboratory Samples*—For acceptance testing, take lot samples and laboratory samples as directed by each of the applicable test methods.

5.3 *Specimens*—Take the number of specimens directed in each of the applicable test methods. Perform the tests on the finished fabrics representative of product as it reaches the consumer.

<sup>5</sup> Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

**TABLE 1 Specification Requirements**

Characteristic	Requirements		Section
	One-Way Stretch	Two-Way Stretch	
Dimensional Change to Home Laundering 3 Cycles	±3 %	±5 %	7.1.1
Dimensional Change to Drycleaning 1 Cycle	±2 %		7.1.2
Colorfastness to Accelerated Laundering-General <sup>4</sup> Color change Staining		Grade 4 Grade 3	7.2.1
Colorfastness to Drycleaning Color Change Staining		Grade 4 Grade 3	
Colorfastness to Non-chlorine Bleach Color change		Grade 4	7.2.3
Colorfastness to Crocking <sup>4</sup> Dry Wet		Grade 4 Grade 3	7.2.4
Colorfastness to Crocking <sup>4</sup> —Raised Surfaces, Dark shades or Pigment Dry Wet		Grade 3 Grade 2	7.2.4
Colorfastness to Perspiration <sup>4</sup> Color Change Staining		Grade 4 Grade 3	7.2.5
Colorfastness to Light, 20 AFU Colorfastness to Light, 20 AFUs		Grade 4 Grade 4	7.2.6 7.2.6
Colorfastness to Ozone (one cycle) Bleached Denim and Indigo Fabrics Only		Grade 4	7.2.7
Stretch Properties Stretch percentage Growth Recovery		report actual 5 % maximum minimum 80 %	7.3
Fabric Count	Report actual or ±5 % tolerance if a specific count is claimed		7.4
Fabric Weight		Record actual	7.5
pH Wool, nylon White All Other		4.5 – 7.0 5.5 – 6.5 6.0 – 8.0	7.6
Flammability		Class 1	7.7

<sup>4</sup>See Note 3.

5.3.1 If the applicable test method does not specify the number of specimens, use the procedures in Practice D2905 to determine the number of specimens per laboratory sample unit.

5.3.2 Use a reliable estimate of the variability of individual observations on similar materials in the user's laboratory, a 95 % probability level, and an allowable difference of 5 % of units and the average for the laboratory sampling unit.

5.3.3 The average for a laboratory sampling unit is the average that would be obtained by applying the test method to all of the potential specimens from the laboratory sampling unit.

## 6. Specification Requirements

6.1 The properties of high stretch fabrics used in apparel shall conform to the specification requirements of Table 1.