



Designation: ~~D1655—22a~~ D1655 – 23

## Standard Specification for Aviation Turbine Fuels<sup>1</sup>

This standard is issued under the fixed designation D1655; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This specification covers the use of purchasing agencies in formulating specifications for purchases of aviation turbine fuel under contract.

1.2 This specification defines the minimum property requirements for Jet A and Jet A-1 aviation turbine fuel and lists acceptable additives for use in civil and military operated engines and aircraft. Specification D1655 was developed initially for civil applications, but has also been adopted for military aircraft. Guidance information regarding the use of Jet A and Jet A-1 in specialized applications is available in the appendix.

1.3 This specification can be used as a standard in describing the quality of aviation turbine fuel from production to the aircraft. However, this specification does not define the quality assurance testing and procedures necessary to ensure that fuel in the distribution system continues to comply with this specification after batch certification. Such procedures are defined elsewhere, for example in ICAO 9977, EI/JIG Standard 1530, JIG 1, JIG 2, API 1543, API 1595, and ATA-103.

1.4 This specification does not include all fuels satisfactory for aviation turbine engines. Certain equipment or conditions of use may permit a wider, or require a narrower, range of characteristics than is shown by this specification.

1.5 Aviation turbine fuels defined by this specification may be used in other than turbine engines that are specifically designed and certified for this fuel.

1.6 This specification no longer includes wide-cut aviation turbine fuel (Jet B). FAA has issued a Special Airworthiness Information Bulletin which now approves the use of Specification **D6615** to replace Specification D1655 as the specification for Jet B and refers users to this standard for reference.

1.7 The values stated in SI units are to be regarded as standard. However, other units of measurement are included in this standard.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.9 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.J0.01 on Jet Fuel Specifications.

Current edition approved Oct. 1, 2022 July 1, 2023. Published November 2022 August 2023. Originally approved in 1959. Last previous edition approved in 2022 as ~~D1655—22; D1655 – 22a~~. DOI: ~~10.1520/D1655-22A~~; 10.1520/D1655-23.

\*A Summary of Changes section appears at the end of this standard

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- D56 Test Method for Flash Point by Tag Closed Cup Tester
- D86 Test Method for Distillation of Petroleum Products and Liquid Fuels at Atmospheric Pressure
- D93 Test Methods for Flash Point by Pensky-Martens Closed Cup Tester
- D130 Test Method for Corrosiveness to Copper from Petroleum Products by Copper Strip Test
- D381 Test Method for Gum Content in Fuels by Jet Evaporation
- D445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and Calculation of Dynamic Viscosity)
- D613 Test Method for Cetane Number of Diesel Fuel Oil
- D1266 Test Method for Sulfur in Petroleum Products (Lamp Method)
- D1298 Test Method for Density, Relative Density, or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method
- D1319 Test Method for Hydrocarbon Types in Liquid Petroleum Products by Fluorescent Indicator Adsorption
- D1322 Test Method for Smoke Point of Kerosene and Aviation Turbine Fuel
- D1660 Method of Test for Thermal Stability of Aviation Turbine Fuels (Withdrawn 1992)<sup>3</sup>
- D1840 Test Method for Naphthalene Hydrocarbons in Aviation Turbine Fuels by Ultraviolet Spectrophotometry
- D2276 Test Method for Particulate Contaminant in Aviation Fuel by Line Sampling
- D2386 Test Method for Freezing Point of Aviation Fuels
- D2622 Test Method for Sulfur in Petroleum Products by Wavelength Dispersive X-ray Fluorescence Spectrometry
- D2624 Test Methods for Electrical Conductivity of Aviation and Distillate Fuels
- D2887 Test Method for Boiling Range Distribution of Petroleum Fractions by Gas Chromatography
- D2892 Test Method for Distillation of Crude Petroleum (15-Theoretical Plate Column)
- D3227 Test Method for (Thiol Mercaptan) Sulfur in Gasoline, Kerosine, Aviation Turbine, and Distillate Fuels (Potentiometric Method)
- D3240 Test Method for Undissolved Water In Aviation Turbine Fuels
- D3241 Test Method for Thermal Oxidation Stability of Aviation Turbine Fuels
- D3242 Test Method for Acidity in Aviation Turbine Fuel
- D3338 Test Method for Estimation of Net Heat of Combustion of Aviation Fuels
- D3828 Test Methods for Flash Point by Small Scale Closed Cup Tester
- D3948 Test Method for Determining Water Separation Characteristics of Aviation Turbine Fuels by Portable Separometer
- D4052 Test Method for Density, Relative Density, and API Gravity of Liquids by Digital Density Meter
- D4054 Practice for Evaluation of New Aviation Turbine Fuels and Fuel Additives
- D4057 Practice for Manual Sampling of Petroleum and Petroleum Products
- D4171 Specification for Fuel System Icing Inhibitors
- D4175 Terminology Relating to Petroleum Products, Liquid Fuels, and Lubricants
- D4176 Test Method for Free Water and Particulate Contamination in Distillate Fuels (Visual Inspection Procedures)
- D4294 Test Method for Sulfur in Petroleum and Petroleum Products by Energy Dispersive X-ray Fluorescence Spectrometry
- D4306 Practice for Aviation Fuel Sample Containers for Tests Affected by Trace Contamination
- D4529 Test Method for Estimation of Net Heat of Combustion of Aviation Fuels
- D4625 Test Method for Middle Distillate Fuel Storage Stability at 43 °C (110 °F)
- D4737 Test Method for Calculated Cetane Index by Four Variable Equation
- D4809 Test Method for Heat of Combustion of Liquid Hydrocarbon Fuels by Bomb Calorimeter (Precision Method)
- D4865 Guide for Generation and Dissipation of Static Electricity in Petroleum Fuel Systems
- D4952 Test Method for Qualitative Analysis for Active Sulfur Species in Fuels and Solvents (Doctor Test)
- D5001 Test Method for Measurement of Lubricity of Aviation Turbine Fuels by the Ball-on-Cylinder Lubricity Evaluator (BOCLE)
- D5006 Test Method for Measurement of Fuel System Icing Inhibitors (Ether Type) in Aviation Fuels
- D5452 Test Method for Particulate Contamination in Aviation Fuels by Laboratory Filtration
- D5453 Test Method for Determination of Total Sulfur in Light Hydrocarbons, Spark Ignition Engine Fuel, Diesel Engine Fuel, and Engine Oil by Ultraviolet Fluorescence
- D5972 Test Method for Freezing Point of Aviation Fuels (Automatic Phase Transition Method)
- D6379 Test Method for Determination of Aromatic Hydrocarbon Types in Aviation Fuels and Petroleum Distillates—High Performance Liquid Chromatography Method with Refractive Index Detection

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

- D6469 Guide for Microbial Contamination in Fuels and Fuel Systems
- D6615 Specification for Jet B Wide-Cut Aviation Turbine Fuel
- D6751 Specification for Biodiesel Fuel Blendstock (B100) for Middle Distillate Fuels
- D6866 Test Methods for Determining the Biobased Content of Solid, Liquid, and Gaseous Samples Using Radiocarbon Analysis
- D6890 Test Method for Determination of Ignition Delay and Derived Cetane Number (DCN) of Diesel Fuel Oils by Combustion in a Constant Volume Chamber
- D7042 Test Method for Dynamic Viscosity and Density of Liquids by Stabinger Viscometer (and the Calculation of Kinematic Viscosity)
- D7153 Test Method for Freezing Point of Aviation Fuels (Automatic Laser Method)
- D7154 Test Method for Freezing Point of Aviation Fuels (Automatic Fiber Optical Method)
- D7170 Test Method for Determination of Derived Cetane Number (DCN) of Diesel Fuel Oils—Fixed Range Injection Period, Constant Volume Combustion Chamber Method (Withdrawn 2019)<sup>3</sup>
- D7224 Test Method for Determining Water Separation Characteristics of Kerosine-Type Aviation Turbine Fuels Containing Additives by Portable Separometer
- D7236 Test Method for Flash Point by Small Scale Closed Cup Tester (Ramp Method)
- D7344 Test Method for Distillation of Petroleum Products and Liquid Fuels at Atmospheric Pressure (Mini Method)
- D7345 Test Method for Distillation of Petroleum Products and Liquid Fuels at Atmospheric Pressure (Micro Distillation Method)
- D7524 Test Method for Determination of Static Dissipater Additives (SDA) in Aviation Turbine Fuel and Middle Distillate Fuels—High Performance Liquid Chromatograph (HPLC) Method
- D7566 Specification for Aviation Turbine Fuel Containing Synthesized Hydrocarbons
- D7619 Test Method for Sizing and Counting Particles in Light and Middle Distillate Fuels, by Automatic Particle Counter
- D7668 Test Method for Determination of Derived Cetane Number (DCN) of Diesel Fuel Oils—Ignition Delay and Combustion Delay Using a Constant Volume Combustion Chamber Method
- D7797 Test Method for Determination of the Fatty Acid Methyl Esters Content of Aviation Turbine Fuel Using Flow Analysis by Fourier Transform Infrared Spectroscopy—Rapid Screening Method
- D7872 Test Method for Determining the Concentration of Pipeline Drag Reducer Additive in Aviation Turbine Fuels
- D7945 Test Method for Determination of Dynamic Viscosity and Derived Kinematic Viscosity of Liquids by Constant Pressure Viscometer
- D7959 Test Method for Chloride Content Determination of Aviation Turbine Fuels using Chloride Test Strip
- D8073 Test Method for Determination of Water Separation Characteristics of Aviation Turbine Fuel by Small Scale Water Separation Instrument
- D8148 Test Method for Spectroscopic Determination of Haze in Fuels
- D8183 Test Method for Determination of Indicated Cetane Number (ICN) of Diesel Fuel Oils using a Constant Volume Combustion Chamber—Reference Fuels Calibration Method
- D8267 Test Method for Determination of Total Aromatic, Monoaromatic and Diaromatic Content of Aviation Turbine Fuels Using Gas Chromatography with Vacuum Ultraviolet Absorption Spectroscopy Detection (GC-VUV)
- D8305 Test Method for The Determination of Total Aromatic Hydrocarbons and Total Polynuclear Aromatic Hydrocarbons in Aviation Turbine Fuels and other Kerosene Range Fuels by Supercritical Fluid Chromatography
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- 2.2 *EI Standards:*<sup>4</sup>
- EI 1550 Handbook on equipment used for the maintenance and delivery of clean aviation fuel
- EI 1583 Laboratory tests and minimum performance levels for aviation fuel filter monitors
- EI/JIG 1530 Quality assurance requirements for the manufacture, storage and distribution of aviation fuels to airports
- IP 12 Determination of specific energy
- IP 16 Determination of freezing point of aviation fuels—Manual method
- IP 71 **Section 1** Petroleum products—Transparent and opaque liquids—Determination of kinematic viscosity and calculation of dynamic viscosity
- IP 123 Petroleum products—Determination of distillation characteristics at atmospheric pressure
- IP 154 Petroleum products—Corrosiveness to copper—Copper strip test
- IP 156 Petroleum products and related materials—Determination of hydrocarbon types—Fluorescent indicator adsorption method
- IP 160 Crude petroleum and liquid petroleum products—Laboratory determination of density—Hydrometer method
- IP 170 Determination of flash point—Abel closed-cup method
- IP 216 Particulate contaminant in aviation fuel
- IP 225 Copper content of aviation turbine fuel

<sup>4</sup> Available from Energy Institute, 61 New Cavendish St., London, WIG 7AR, U.K., <http://www.energyinst.org.uk>.

- IP 227 Silver corrosion of aviation turbine fuel
- IP 274 Determination of electrical conductivity of aviation and distillate fuels
- IP 323 Determination of thermal oxidation stability of gas turbine fuels
- IP 336 Petroleum products—Determination of sulfur content—Energy-dispersive X-ray fluorescence method
- IP 342 Petroleum products—Determination of thiol (mercaptan) sulfur in light and middle distillate fuels—Potentiometric method
- IP 354 Determination of the acid number of aviation fuels—Colour-indicator titration method
- IP 365 Crude petroleum and petroleum products—Determination of density—Oscillating U-tube method
- IP 406 Petroleum products—Determination of boiling range distribution by gas chromatography
- IP 423 Determination of particulate contamination in aviation turbine fuels by laboratory filtration
- IP 435 Determination of the freezing point of aviation turbine fuels by the automatic phase transition method
- IP 436 Determination of aromatic hydrocarbon types in aviation fuels and petroleum distillates—High performance liquid chromatography method with refractive index detection
- IP 523 Determination of flash point—Rapid equilibrium closed cup method
- IP 528 Determination for the freezing point of aviation turbine fuels—Automatic fibre optic method
- IP 529 Determination of the freezing point of aviation turbine fuels—Automatic laser method
- IP 534 Determination of flash point – Small scale closed cup ramp method
- IP 540 Determination of the existent gum content of aviation turbine fuel—Jet evaporation method
- IP 564 Determination of the level of cleanliness of aviation turbine fuel—Laboratory automatic particle counter method
- IP 565 Determination of the level of cleanliness of aviation turbine fuel—Portable automatic particle counter method
- IP 577 Determination of the level of cleanliness of aviation turbine fuel—Automatic particle counter method using light extinction
- IP 583 Determination of the fatty acid methyl esters content of aviation turbine fuel using flow analysis by Fourier transform infrared spectroscopy—Rapid screening method
- IP 585 Determination of fatty acid methyl esters (FAME), derived from bio-diesel fuel, in aviation turbine fuel—GC-MS with selective ion monitoring/scan detection method
- IP 590 Determination of fatty acid methyl esters (FAME) in aviation fuel—HPLC evaporative light scattering detector method
- IP 598 Petroleum products—Determination of the smoke point of kerosine, manual and automated method
- IP 599 Determination of fatty acid methyl esters (FAME) in aviation turbine fuel by gas chromatography using heart-cut and refocusing
- 2.3 *API Standards:*<sup>5</sup>
- API 1543 Documentation, Monitoring and Laboratory Testing of Aviation Fuel During Shipment from Refinery to Airport
- API 1595 Design, Construction, Operation, Maintenance, and Inspection of Aviation Pre-Airfield Storage Terminals
- 2.4 *Joint Inspection Group Standards:*<sup>6</sup>
- JIG 1 Aviation Fuel Quality Control & Operating Standards for Into-Plane Fuelling Services
- JIG 2 Aviation Fuel Quality Control & Operating Standards for Airport Depots & Hydrants
- 2.5 *ANSI Standard:*<sup>7</sup>
- ANSI 863 Report of Test Results
- 2.6 *Other Standards:*
- Defence Standard (Def Stan) 91-091 Turbine Fuel, Aviation Kerosine Type, Jet A-1<sup>8</sup>
- IATA Guidance Material on Microbiological Contamination in Aircraft Fuel Tanks Ref. No: 9680<sup>9</sup>
- IATA Guidelines for Sodium Chloride Contamination Troubleshooting and Decontamination of Airframe and Engine Fuel Systems, 2nd Ed., February 1998<sup>9</sup>
- EN14214 Automotive Fuels—Fatty Acid Methyl Esters (FAME) for Diesel Engines—Requirements and Test Methods<sup>10</sup>
- Bulletin Number 65 MSEP Protocol<sup>11</sup>
- ATA-103 Standard for Jet Fuel Quality Control at Airports<sup>12</sup>
- ICAO 9977 Manual on Civil Aviation Jet Fuel Supply<sup>13</sup>
- AFRL-RQ-WP-TR-2013-0271 Determination of the Minimum Use Level of Fuel System Icing Inhibitor (FSII) in JP-8 that will

<sup>5</sup> Available from American Petroleum Institute (API), 1220 L. St., NW, Washington, DC 20005-4070, <http://www.api.org>.

<sup>6</sup> Available from Joint Inspection Group (JIG), <http://www.jigonline.com>.

<sup>7</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

<sup>8</sup> Available from Procurement Executive DFS (Air), Ministry of Defence, St. Giles Court 1, St. Giles High St., London WC2H 8LD.

<sup>9</sup> Available from International Air Transport Association (IATA), (Head Office) 800 Place Victoria, PO Box 113, Montreal, H4Z 1M1, Quebec, Canada. [www.iata.org](http://www.iata.org)

<sup>10</sup> Available from European Committee for Standardization (CEN), 36 rue de Saussart, B-1050, Brussels, Belgium, <http://www.cenorm.be>.

<sup>11</sup> Available from Joint Inspection Group (JIG), <http://www.jigonline.com>.

<sup>12</sup> Available from Air Transport Association of America, Inc. (ATA) d/b/a Airlines for America, 1275 Pennsylvania Ave. NW, Suite 1300, Washington, D.C. 20004, <http://www.airlines.org>.

<sup>13</sup> Available from International Civil Aviation Organization (ICAO), 999 University St., Montreal, Quebec H3C 5H7, Canada, <http://www.icao.int>.

Provide Adequate Icing Inhibition and Biostatic Protection for Air Force Aircraft<sup>14</sup>

### 3. Terminology

3.1 For definitions of terms used in this specification, refer to Terminology **D4175**.

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *Certificate of Analysis (COA), n*—the quality document issued by independent inspectors and/or laboratories that contains the results of measurements made of Table 1 properties but does not necessarily contain or provide information regarding those identified as being required at point of manufacture.

##### 3.2.1.1 Discussion—

Typically, COAs are produced downstream of refineries in intermediate supply terminals or intermediate storage locations. A Certificate of Analysis is not considered equivalent to a Certificate of Quality.

3.2.2 *Certificate of Quality (COQ) (including Refinery Certificate of Quality, RCQ), n*—the quality document that is the definitive original document describing the quality of aviation fuel at the point of manufacture.

##### 3.2.2.1 Discussion—

A COQ contains the results of measurements, usually made by the product originator's laboratory, of all the properties listed in Table 1, the additive information as per Table 2, as well as those additional testing requirements detailed in **Annex A1** for fuels containing synthesized components and confirms conformance to the specification.

3.2.3 *co-hydroprocessed esters and fatty acids, n*—synthetic hydrocarbons derived from the hydroprocessing of bio-derived mono-, di-, and triglycerides, free fatty acids, and fatty acid esters with conventional hydrocarbons in accordance with the requirements of **A1.2.2.1**.

3.2.4 *co-hydroprocessed Fischer-Tropsch hydrocarbons, n*—synthetic hydrocarbons derived from the hydroprocessing of hydrocarbons derived from Fischer-Tropsch synthesis to paraffinic syncrude with conventional hydrocarbons in accordance with the requirements of **A1.2.2.2**.

3.2.5 *co-hydroprocessed synthesized kerosene, n*—hydrocarbons in the kerosene boiling range derived from non-petroleum sources such as coal, natural gas, biomass, fatty acid esters and fatty acids by processes such as gasification, Fischer-Tropsch synthesis, and hydroprocessing, that have been processed simultaneously with hydrocarbons from conventional sources.

3.2.6 *identified incidental materials, n*—chemicals and compositions that have defined upper content limits in an aviation fuel specification but are not approved additives.

3.2.7 *metrological method, n*—heater tube deposit rating methods employing an optically-based deposit thickness measurement and mapping technique described in the Test Method **D3241** annexes.

### 4. General

4.1 This specification, unless otherwise provided, prescribes the required properties of aviation turbine fuel at the time and place of delivery.

### 5. Classification

5.1 Two types of aviation turbine fuels are provided, as follows:

5.1.1 *Jet A and Jet A-1*—Relatively high flash point distillates of the kerosene type.

5.2 Jet A and Jet A-1 represent two grades of kerosene fuel that differ in freezing point. Other grades would be suitably identified.

5.3 This specification previously cited the requirements for Jet B. Requirements for Jet B fuel now appear in Specification **D6615**.

<sup>14</sup> Available from Defense Technical Information Center (DTIC), 8725 John J. Kingman Rd., Ft. Belvoir, VA 22060-6218, <http://www.dtic.mil/dtic>, accession number ADA595127.

## 6. Materials and Manufacture

6.1 Aviation turbine fuel is a complex mixture predominantly composed of hydrocarbons and varies depending on crude source and manufacturing process. Consequently, it is impossible to define the exact composition of Jet A/A-1. This specification has therefore evolved primarily as a performance specification rather than a compositional specification. It is acknowledged that this largely relies on accumulated experience; therefore the specification limits aviation turbine fuels to those made from conventional sources or by specifically approved processes.

6.1.1 Aviation turbine fuel, except as otherwise specified in this specification, shall consist predominantly of refined hydrocarbons (see **Note 1**) derived from conventional sources including crude oil, natural gas liquid condensates, heavy oil, shale oil, and oil sands. The use of jet fuel blends containing components from other sources is permitted only in accordance with **Annex A1**.

NOTE 1—Conventionally refined jet fuel contains trace levels of materials that are not hydrocarbons, including oxygenates, organosulfur, and nitrogenous compounds.

6.1.2 Fuels used in certified engines and aircraft are ultimately approved by the certifying authority subsequent to formal submission of evidence to the authority as part of the type certification program for that aircraft and engine model. Additives to be used as supplements to an approved fuel must also be similarly approved on an individual basis (see **X1.2.4** and **X1.15.1**).

6.2 *Additives*—Additives are used to improve the performance of the fuel or for fuel handling and maintenance purposes.

6.2.1 Only additives approved by the aviation industry (including the aircraft certifying authority) are permitted in the fuel on which an aircraft is operated. Practice **D4054** guides the practice used to evaluate additives intended for incorporation into Specification D1655. The additives included in Specification D1655 jet fuel are shown in **Table 2** and may be used within the concentration limits shown in the table subject to any restrictions described in the table footnotes.

6.2.2 Where it is necessary to dilute an additive for handling purposes, a refined hydrocarbon stream from a refinery, produced in accordance with Materials and Manufacture requirements of Specification D1655, or a reagent grade (or better) hydrocarbon or hydrocarbon mixture (excluding non-hydrocarbons) from a chemical supplier shall be used. Since not all additives and diluents are compatible (for example, an additive may drop-out if diluted with alkylate versus reformat), the additive manufacturer should be consulted regarding the preferred diluent. Reporting does not change when dilution is used; additive package content as received or active ingredient content as described in **Table 2** is the concentration to be reported.

**TABLE 1 Detailed Requirements of Aviation Turbine Fuels<sup>A</sup>**

| Property  | Test Methods <sup>B</sup> |                          |   |
|---|---------------------------|--------------------------|---|
|   | Jet A or Jet A-1          | Referee                  | Alternative   |
| <b>COMPOSITION</b>                              |                           |                          |   |
| Acidity, total mg KOH/g                         | max                       | 0.10                     | <b>D3242/IP 354</b>   |
| Aromatics                                       |                           |                          |   |
| (1) percent by volume, or                       | max                       | 25                       | <b>D1319</b>  |
| (2) percent by volume                           | max                       | 26.5                     | IP 156 <sup>C</sup> or <b>D8267</b> or <b>D8305<sup>D</sup></b><br><b>D6379/IP 436</b>  |
| Sulfur, mercaptan, <sup>E</sup> percent by mass | max                       | 0.003                    | <b>D3227/IP 342</b>   |
| Sulfur, total percent by mass                   | max                       | 0.30                     | <b>D1266, D2622, D4294, D5453,</b><br>or IP 336   |
| <b>VOLATILITY</b>                               |                           |                          |   |
| Distillation temperature, °C:                   |                           |                          | <b>D86<sup>F</sup></b>  |
| Distillation temperature, °C:                   |                           |                          | <b>D2887/IP 406,<sup>G</sup> D7344,<sup>H, I</sup> D7345,<sup>H</sup></b><br><b>IP 123<sup>F</sup></b>                                |
| 10 % recovered, temperature                     | max                       | 205                      |   |
| 50 % recovered, temperature                     |                           | report                   |   |
| 90 % recovered, temperature                     |                           | report                   |   |
| Final boiling point, temperature                | max                       | 300                      |   |
| Distillation residue, %                         | max                       | 1.5                      |   |
| Distillation loss, %                            | max                       | 1.5                      |   |
| Flash point, °C                                 | min                       | 38 <sup>J</sup>          | <b>D56</b>  |
| Density at 15 °C, kg/m <sup>3</sup>             |                           | 775 to 840               | <b>D93,<sup>K</sup> D3828,<sup>K</sup> D7236,<sup>K</sup> IP 170,<sup>K</sup></b><br><b>IP 523,<sup>K</sup> or IP 534<sup>K</sup></b> |
| Density at 15 °C, kg/m <sup>3</sup>             |                           | 775 to 840               | <b>D1298/IP 160 or D4052 or IP 365</b><br><b>D1298 or IP 160 or D4052 or IP 365</b>   |
| <b>FLUIDITY<sup>L</sup></b>                     |                           |                          |   |
| Freezing point, °C                              | max                       | -40 Jet A <sup>M,N</sup> | <b>D5972/IP 435, D7153/IP 529, or</b><br><b>D7154/IP 528</b>  |

**TABLE 1** *Continued*

| Property  |           | Test Methods <sup>B</sup>                 |  |   |
|---|-----------|---|--|---|
|   |           | Jet A or Jet A-1                          | Referee                                      | Alternative   |
| Freezing point, °C  | max       | -40 Jet A <sup>M,N</sup>                  | <u>D2386/IP 16</u>                           | <u>D5972/IP 435, D7153/IP 529, or D7154 or IP 528</u> |
|   |           | -47 Jet A-1 <sup>M,N</sup>                |  |   |
| Viscosity –20 °C, mm <sup>2</sup> /s <sup>O</sup>                             | max       | 8.0                                       | <u>D445/IP 71, Section 1</u>                 | <u>D7042<sup>P</sup> or D7945</u>                     |
| Viscosity –20 °C, mm <sup>2</sup> /s <sup>O</sup>                             | max       | 8.0                                       | <u>D445 or IP 71, Section 1</u>              | <u>D7042<sup>P</sup> or D7945</u>                     |
| <b>COMBUSTION</b>   |           |   |  |   |
| Net heat of combustion, MJ/kg   | min       | 42.8 <sup>O</sup>                         | <u>D4809</u>                                 | <u>D4529, D3338, or IP 12</u>                         |
| One of the following requirements shall be met:                               |           |   |  |   |
| (1) Smoke point, mm, or   | min       | 25.0                                      | <u>D1322/IP 598</u>                          |   |
| (2) Smoke point, mm, and  | min       | 18.0                                      | <u>D1322/IP 598</u>                          |   |
| Naphthalenes, percent by volume   | max       | 3.0                                       | <u>D1840</u>                                 | <u>D8305<sup>F</sup></u>                              |
| <b>CORROSION</b>  |           |   |  |   |
| Copper strip, 2 h at 100 °C   | max       | No. 1                                     | <u>D130/IP 154</u>                           |   |
| Copper strip, 2 h at 100 °C   | max       | No. 1                                     | <u>D130 or IP 154</u>                        |   |
| <b>THERMAL STABILITY<sup>L</sup></b>  |           |   |  |   |
| (2.5 h at control temperature of 260 °C min)                                  |           |   |  |   |
| Filter pressure drop, mm Hg   | max       | 25  | <u>D3241<sup>S</sup> /IP 323<sup>S</sup></u> |   |
| Tube rating: One of the following requirements shall be met: <sup>T</sup>     |           |   |  |   |
| (1) Annex A1 VTR, VTR Color Code  | Less than | 3 (no peacock or abnormal color deposits) |  |   |
| (2) Annex A2 ITR or Annex A3 ETR, nm average over area of 2.5 mm <sup>2</sup> | max       | 85  |  |   |
| <b>CONTAMINANTS</b>   |           |   |  |   |
| Existent gum, mg/100 mL   | max       | 7   | <u>D381</u>                                  | IP 540  |
| Microseparator, <sup>U</sup> Rating   |           |   | <u>D3948</u>                                 |   |
| Without electrical conductivity additive                                      | min       | 85  |  |   |
| With electrical conductivity additive   | min       | 70  |  |   |
| <b>ADDITIVES</b>  |           |   |  |   |
| Electrical conductivity, pS/m   |           | See 6.2                                   | <u>D2624/IP 274</u>                          |   |

<sup>A</sup> For compliance of test results against the requirements of Table 1, see 7.2.

<sup>B</sup> The test methods indicated in this table are referred to in Section 11. Where applicable, the referee test methods are identified in Table 1.

<sup>C</sup> In analyzing Aviation Turbine Fuel by Test Method D1319 or IP 156, users shall not report results obtained using any of the following lot numbers of Fluorescent Indicator Dyed Gel: 3000000975, 3000000976, 3000000977, 3000000978, 3000000979, and 3000000980.

<sup>D</sup> Results from Test Method D8305 shall be bias-corrected using the bias-correction equation for total aromatics in Section 13 (Precision and Bias) of Test Method D8305. The bias-corrected aromatics result shall also be used in Test Method D3338.

<sup>E</sup> The mercaptan sulfur determination may be waived if the fuel is considered sweet by the doctor test described in Test Method D4952.

<sup>F</sup> D86 and IP 123 distillation of jet fuel is run at Group 4 conditions, except Group 3 condenser temperature is used.

<sup>G</sup> D2887/IP or IP 406 results shall be converted to estimated D86 or IP 123 results by application of the correlation in Appendix X4 on Correlation for Jet and Diesel Fuel in Test Method D2887 or Annex G of IP 406. Distillation residue and loss limits provide control of the distillation process during the use of Test Method D86, and they do not apply to Test Method D2887/IP or IP 406. Distillation residue and loss shall be reported as “not applicable” (N/A) when reporting D2887 results.

<sup>H</sup> Results from Test Method D7344 and D7345 shall be corrected for relative bias as described in each of the test methods.

<sup>I</sup> Data supporting inclusion of the Test Method D7344 methodology is on file at ASTM International Headquarters and can be obtained by requesting Research Reports RR:D02-1621 and RR:D02-1855. Contact ASTM Customer Service at service@astm.org.

<sup>J</sup> A higher minimum flash point specification can be agreed upon between purchaser and supplier.

<sup>K</sup> Relative to D56, results obtained by Test Method: D93 can be up to 1.5 °C higher; IP 170, IP 534, and D7236 can be up to 0.5 °C higher; D3828 (IP 523) can be up to 0.5 °C lower (a research report is pending being filed at ASTM and is available at the Energy Institute as ILS2019\_MMS\_1).

<sup>L</sup> For Annex A1.2.2 co-processing the more stringent limits and test methods listed in Table A1.1 shall be applied at point of manufacture. Downstream from manufacture standard Table 1 limits and test methods apply.

<sup>M</sup> Other freezing points can be agreed upon between supplier and purchaser.

<sup>N</sup> During downstream distribution if the freezing point of the fuel is very low and cannot be determined within the ASTM D2386/IP 16 lowest achievable temperature of minus 65 °C, if no crystals appear during cooling of the fuel and when the thermometer indicates a temperature of minus 65 °C, the freezing point shall be recorded as below minus 65 °C. This limit does not apply if the freezing point is measured by D5972/IP 435, D7153/IP 529, or D7154/IP or IP 528.

<sup>O</sup> 1 mm<sup>2</sup>/s = 1 cSt.

<sup>P</sup> Test Method D7042 results shall be converted to bias-corrected kinematic viscosity results by the application of the correction described in Test Method D7042 for jet fuel at –20 °C (currently subsection 15.4.4).

<sup>Q</sup> For all grades use either Eq 1 or Table 1 in Test Method D4529 or Eq 2 in Test Method D3338. Calculate and report the net heat of combustion corrected for the sulfur content when using Test Method D4529 and D3338 empirical test methods. Test Method D4809 may be used as an alternative.

<sup>R</sup> Results from Test Method D8305 shall be bias-corrected using the bias-correction equation for total polynuclear aromatics in Section 13 (Precision and Bias) of Test Method D8305.

<sup>S</sup> D3241/IP 323 Thermal Stability is a critical aviation fuel test, the results of which are used to assess the suitability of jet fuel for aviation operational safety and regulatory compliance. The integrity of D3241/IP 323 testing requires that heater tubes (test coupons) meet the requirements of D3241 Table 2 and give equivalent D3241 results to the heater tubes supplied by the original equipment manufacturer (OEM). A test protocol to demonstrate equivalence of heater tubes from other suppliers is on file at ASTM International Headquarters and can be obtained by requesting Research Report RR:D02-1550. Heater tubes and filter kits, manufactured by the OEM (PAC, 8824 Fallbrook Drive, Houston, TX 77064) were used in the development of the D3241/IP 323 test method. Heater tube and filter kits, manufactured by Falex (Falex Corporation, 1020 Airpark Dr., Sugar Grove, IL, 60554-9585) were demonstrated to give equivalent results (see D3241 for research report references). These historical facts should not be construed as an endorsement or certification by ASTM International.

<sup>T</sup> Tube deposit ratings shall be measured by D3241 Annex A2 ITR or Annex A3 ETR, when available. If the Annex A2 ITR device reports “N/A” for a tube’s volume measurement, the test shall be a failure and the value reported as >85 nm. Visual rating of the heater tube by the method in D3241 Annex A1 is not required when Annex A2 ITR or Annex A3 ETR deposit thickness measurements are reported. In case of dispute between results from visual and metrological methods, the referee shall be considered the Annex A3 ETR method if available, otherwise Annex A2 ITR.

<sup>U</sup> At point of manufacture. See X1.13 for guidance concerning the application of microseparator results in fuel distribution.

<sup>v</sup> If electrical conductivity additive is used, the conductivity shall not exceed 600 pS/m at the point of use of the fuel. When electrical conductivity additive is specified by the purchaser, the conductivity shall be 50 to 600 pS/m under the conditions at point of delivery.

$$1 \text{ pS/m} = 1 \times 10^{-12} \Omega^{-1} \text{ m}^{-1}$$

**iTeh Standards**  
**(<https://standards.itih.ai>)**  
**Document Preview**

[ASTM D1655-23](#)

<https://standards.itih.ai/catalog/standards/sist/25def47c-c267-4700-b91c-cc9486be4987/astm-d1655-23>



**TABLE 2 Detailed Information for Additives for Aviation Turbine Fuels**

| Additive   | Dosage  |
|--|---|
| <b>Fuel Performance Enhancing Additives</b>  |   |
| Antioxidants <sup>A, B</sup><br><i>One of the following:</i><br>2,6 ditertiary-butyl phenol<br>2,6 ditertiary-butyl-4-methyl phenol<br>2,4 dimethyl-6-tertiary-butyl-phenol<br>75 % minimum, 2,6 ditertiary-butyl phenol plus<br>25 % maximum mixed tertiary and tritertiary butyl-phenols<br>55 % minimum 2,4 dimethyl-6-tertiary-butyl phenol plus<br>15 % minimum 2,6 ditertiary-butyl-4-methyl phenol,<br>remainder as monomethyl and dimethyl tertiary-butyl phenols<br>72 % minimum 2,4 dimethyl-6-tertiary-butyl phenol plus<br>28 % maximum monomethyl and dimethyl-tertiary-butyl-phenols | 24.0 mg/L max <sup>C</sup>                                  |
| Metal Deactivator (MDA) <sup>A</sup>   |   |
| N,N-disalicylidene-1,2-propane diamine<br>On initial blending<br>After field reblending cumulative concentration   | 2.0 mg/L max <sup>C, D</sup><br>5.7 mg/L max                |
| Fuel System Icing Inhibitor <sup>E, F, G, H</sup><br>Diethylene Glycol Monomethyl Ether (see Specification <b>D4171</b> Type III)  | 0.07 % by volume, min <sup>I</sup><br>0.15 % by volume, max |
| <b>Fuel Handling and Maintenance Additives</b>   |   |
| Electrical Conductivity Improver <sup>J</sup><br><br><i>One of the following:</i><br>AvGuard SDA <sup>K, L</sup><br>On initial blending<br>After field reblending, cumulative concentration  | <br><br>3 mg/L max<br>5 mg/L max                            |
| Stadis 450 <sup>L, M</sup><br>On initial blending<br>After field reblending, cumulative concentration  | 3 mg/L max<br>5 mg/L max                                    |
| If the additive concentrations are unknown at time of retreatment, additional concentration is restricted to 2 mg/L max  |   |
| Leak Detection Additive<br>Tracer A (LDTA-A) <sup>N</sup>  | 1 mg/kg max   |
| Biocidal Additives <sup>E, O, P</sup><br>Biobor JF <sup>Q</sup><br>Kathon FP1.5 <sup>R</sup>   |   |
| Corrosion Inhibitor/Lubricity Improvers <sup>S</sup><br><i>One of the following:</i><br>HITEC 580 <sup>T</sup><br>Innospec DCI-4A <sup>U</sup><br>Nalco 5403   | 23 mg/L max<br>23 mg/L max<br>23 mg/L max                   |
| Into-Plane Water Management<br>Kerojet Aquarius PRD 30568468 <sup>V</sup>  | 250 ppmv, max   |

<sup>A</sup> The active ingredient of the additive must meet the composition specified.

<sup>B</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D02-1125. Contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org).

<sup>C</sup> Active ingredient (not including weight of solvent).

<sup>D</sup> At the point of manufacture, Metal Deactivator Additive (MDA) may be added to improve thermal oxidative stability subject to the following limitations:

(1) No more than 5 % of the jet fuel batches produced in a 12 month period may be treated with MDA to meet **Table 1** thermal oxidative stability requirements (260 °C test temperature).

(2) The batch of fuel shall pass **Table 1** thermal oxidative stability requirements at a test temperature of 245 °C prior to any MDA addition.

(3) The fuel batch after MDA addition (2.0 mg/L maximum MDA) shall pass **Table 1** thermal oxidative stability requirements at a test temperature of 275 °C.

(4) The thermal oxidative stability test result at 245 °C prior to MDA addition, the original test result at 260 °C and the test result at 275 °C (post MDA addition) and the concentration of MDA added shall be reported on the Refinery Certificate of Quality.

Initial addition of more than 2.0 mg/L MDA to jet fuel that meets **Table 1** thermal oxidative stability requirements (260 °C test temperature) prior to MDA addition is permitted when fuel will be transported in supply chains where copper contamination can occur: the maximum cumulative addition in this table still applies.

MDA may be added to jet fuel in the distribution system to recover thermal oxidative stability performance lost during distribution (after refinery release). The Certificate of Quality shall show the initial thermal oxidative stability test result, the result after the addition of the MDA and the concentration of MDA added.

<sup>E</sup> The quantity shall be declared by the fuel supplier and agreed to by the purchaser.

<sup>F</sup> The lower FSII concentration limit allowable in Jet Fuel is based on research by the U.S. Air Force as documented in report AFRL-RQ-WP-TR-2013-0271. Some engines and aircraft as certified require higher minimum concentrations of icing inhibitor than the lower limit in this jet fuel specification. When fueling an aircraft, the fuel should be added to the concentration levels specified in the appropriate engine and aircraft manual.

<sup>G</sup> DiEGME content can be analyzed by Test Method **D5006**.

<sup>H</sup> DiEGME is not suitable for use in systems that will later use EI 1583 filter monitors, which are commonly used at the point of aircraft fueling. Additional guidance is provided in EI 1550 Chapter 9.

<sup>J</sup> Some aircraft require higher levels than 0.07 % by volume.

<sup>K</sup> If electrical conductivity improver is used, the conductivity shall not exceed 600 pS/m at the point of use of the fuel. When electrical conductivity additive is specified by the purchaser, the conductivity shall be 50 pS/m to 600 pS/m under the conditions at point of delivery.  $1 \text{ pS/m} = 1 \times 10^{-12} \Omega^{-1} \text{ m}^{-1}$

<sup>L</sup> AvGuard is a trademark of Afton Chemical Corporation, 500 Spring Street Richmond, VA 23219. Supporting documentation for this additive is found in RR:D02-1861.

<sup>M</sup> Electrical conductivity improver content can be analyzed by Test Method **D7524**.

<sup>N</sup> Stadis 450 is a registered trademark marketed by Innospec Inc., Innospec Manufacturing Park, Oil Sites Road, Ellesmere Port, Cheshire, CH65 4EY, UK.

<sup>O</sup> Tracer A (LDTA-A) is a registered trademark of Praxair Services, Inc., Tucson, AZ 85705.

<sup>P</sup> Biocidal additives are available for controlled usage. Where such an additive is used in the fuel, the approval status of the additive and associated conditions must be checked for the specific aircraft and engines to be operated.

<sup>Q</sup> Refer to the Aircraft Maintenance Manual (AMM) to determined if either biocide is approved for use and for their appropriate use and dosage.

<sup>R</sup> Biobor JF is a registered trademark of Hammonds Technical Services, Inc. 910 Rankin Rd., Houston, TX 77073; Fuel Additives, Inc. 6951 W. Little York, Houston, TX 77040.

<sup>S</sup> KATHON is a trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow, 2030 Dow Center, Midland, MI 48674.

<sup>T</sup> More information concerning minimum treat rates of corrosion inhibitor/lubricity improver additives is contained in **X1.10.2**.

<sup>U</sup> HITEC 580 is a trademark of Afton Chemical Corp., 500 Spring St., Richmond, VA 23219.

<sup>V</sup> Innospec DCI-4A is available from Innospec Inc., Innospec Manufacturing Park, Oil Sites Road, Ellesmere Port, Cheshire, CH65 4EY, UK.

<sup>W</sup> Kerojet Aquarius is available from BASF SE, Carl-Bosch-Strasse 38, D-67056 Ludwigshafen am Rhein, Germany. Any process or formulation change to Kerojet Aquarius Product Number (PRD) 30568468 that invalidates the data submitted in ASTM Research Report RR:D02-2001 will require a new and unique PRD. Note that given the unique function of Kerojet Aquarius and the need for careful management of use, the additive should only be used in compliance with the following controls: (1) Refer to the Aircraft Documentation (e.g., approved additives listed in the Type Certificate Data Sheet (TCDS), Aircraft Flight Manual (AFM), Aircraft Maintenance Manual (AMM), Consumable Materials List (CML), or other relevant documentation) for approved usage and dosage for the specific aircraft/engine/APU combination. (2) Additive to be injected after final filtration at the skin of the aircraft. For possible defueling of aircraft, do not allow additive to pass through EI 1581 and EI 1583 filters. (3) Dose only in compliance with Aircraft Documentation and recommended practice detailed in this specification. (4) Handling, usage, and injection equipment information is contained in the Kerojet Aquarius User Manual and RR:D02-2001.

**6.3 Identified Incidental Materials**—**Table 3** lists specific materials that have an agreed limit, known as Identified Incidental Materials. Specification D1655 does not require that each batch of fuel be analyzed for identified incidental materials where there is essentially no risk of contamination exceeding **Table 3** limits. Where a supplier risk assessment suggests that identified incidental materials could exceed **Table 3** limits, jet fuel should be confirmed to comply with **Table 3** limits prior to airport supply because airports generally are not equipped to mitigate identified incidental material content that exceeds specification limits. Further guidance concerning these materials is presented in **X1.16**.

**6.4** Guidance material is presented in **Appendix X2** concerning the need to control processing additives in jet fuel production.

## 7. Detailed Requirements

**7.1** The aviation turbine fuel shall conform to the requirements prescribed in **Table 1**.

**7.2** Test results shall not exceed the maximum or be less than the minimum values specified in **Table 1**. No allowance shall be made for the precision of the test methods. To determine conformance to the specification requirement, a test result may be rounded to the same number of significant figures as in **Table 1** using Practice **E29**. Where multiple determinations are made, the average result, rounded in accordance with Practice **E29**, shall be used.

**TABLE 3 Identified Incidental Materials**

| Material  | Permitted Level         | Test Methods <sup>A</sup> |                                      |
|---|-------------------------|---------------------------|--------------------------------------|
|   |                         | Referee                   | Alternative                          |
| Fatty Acid Methyl Ester (FAME), <sup>B</sup> max        | 50 mg/kg <sup>C,D</sup> | IP 585                    | <b>D7797</b> /IP 583, IP 590, IP 599 |
| Pipeline Drag Reducing Additive (DRA), <sup>E</sup> max | 72 µg/L <sup>F</sup>    | <b>D7872</b>              |                                      |

<sup>A</sup> Where applicable, the referee test methods are identified in **Table 3**.

<sup>B</sup> For the purpose of meeting this requirement FAME is defined as material meeting the limits of EN14214 or Specification **D6751**. Fatty acid methyl esters that fail to meet the biodiesel quality standards are not permitted in aviation turbine fuel.

<sup>C</sup> On an emergency basis, up to 100 mg/kg FAME is permitted in jet fuel when authorized by the airframe and engine manufacturers and managed in compliance with airframe and engine manufacturer requirements.

<sup>D</sup> Subcommittee J intends to evaluate field experience in December 2016 to determine if a ballot to increase the FAME content limit to 100 mg/kg is supported by the absence of significant FAME-related problems.

<sup>E</sup> Active polymer ingredient.

<sup>F</sup> DRA is not approved as an additive for jet fuel. This level is accepted by approval authorities as the functional definition of "nil addition."

## 8. Workmanship, Finish, and Appearance

8.1 The aviation turbine fuel specified in this specification shall be visually free of undissolved water, sediment, and suspended matter. The odor of the fuel shall not be nauseating or irritating. If the fuel has an odor similar to that of “rotten egg,” please refer to **X1.12.5** for further discussion. No substance of known dangerous toxicity under usual conditions of handling and use shall be present, except as permitted in this specification.

## 9. Sampling

9.1 Because of the importance of proper sampling procedures in establishing fuel quality, use the appropriate procedures in Practice **D4057** to obtain a representative sample from the batch of fuel for specification compliance testing. This requirement is met by producing fuel as a discrete batch then testing it for specification compliance. This requirement is not satisfied by averaging online analysis results.

9.2 A number of jet fuel properties, including thermal stability, water separation, electrical conductivity, and others, are very sensitive to trace contamination, which can originate from sample containers. For recommended sample containers, refer to Practice **D4306**.

## 10. Report

10.1 The type and number of reports to ensure conformance with the requirements of this specification shall be mutually agreed upon by the seller and the purchaser of the aviation turbine fuel.

10.2 When **Table 1** test results and **Table 2** additive additions are reported at the point of batch origination or at full certification in a form commonly known as a “Certificate of Quality” or “Certificate of Analysis,” at least the following should be included:

10.2.1 The designation of each test method used,

10.2.2 The limits from **Table 1**, **Table 2**, and specific Annex Table, for each item reported with units converted as appropriate to those measured and reported, and

10.2.3 The designation of the quality system used by the reporting test laboratory. If no quality system is used then this shall be reported as “None.”

10.3 For examples on reporting, see **Appendix X3** “Forms for Reporting Inspection Data on Aviation Turbine Fuels.”

## 11. Test Methods

NOTE 2—Where IP test methods are referenced in this specification as alternatives to ASTM test methods, the following nomenclature is used. Where test methods are officially jointed, this is denoted as Dxxxx/IP xxx. Where test methods are technically equivalent or related but not officially jointed, this is denoted as Dxxxx or IP xxx.

11.1 Determine the requirements enumerated in this specification in accordance with the following ASTM test methods. In case of dispute among measurements, the referee test methods are identified in **Table 1**, **Table 3**, and **Table A1.1**.

11.1.1 *Density*—Test Method **D1298**/~~IP~~ or **IP** 160 or **D4052** or **IP** 365.

11.1.2 *Distillation*—Test Method **D86** or **IP** 123. For Jet A and Jet A-1, Test Methods **D2887**/~~IP~~ or **IP** 406, **D7344**, and **D7345** may be used as an alternative. Results from Test Method **D2887** shall be reported as estimated **D86** results by application of the correlation in Appendix X4 on Correlation for Jet and Diesel Fuel in Test Method **D2887**/~~IP~~ or **IP** 406. Results from Test Method **D7344** and **D7345** shall be corrected for bias by applying the GRP4 corrections in each of the test method’s Precision and Bias section.

11.1.3 *Flash Point*—Test Method **D56**, **D93**, **D3828**, **D7236**, **IP** 170, **IP** 523, or **IP** 534.

11.1.4 *Freezing Point*—Test Method **D2386**/**IP** 16, **D5972**/**IP** 435, **D7153**/**IP** 529, or **D7154**/~~IP~~ or **IP** 528. Any of these test methods

can be used to certify and recertify jet fuel. An interlaboratory study (RR: D02–1572<sup>15</sup>) that evaluated the ability of freezing point methods to detect jet fuel contamination by diesel fuel determined that Test Methods **D5972/IP 435** and **D7153/IP 529** provided significantly more consistent detection of freezing point changes caused by contamination than Test Methods **D2386/IP 16** and **D7154/IP 528**. It is recommended to certify and recertify jet fuel using either Test Method **D5972/IP 435** or Test Method **D7153/IP 529**, or both, on the basis of the reproducibility and cross-contamination detection reported in RR:D02-1572.<sup>15</sup> The cause of freezing point results outside specification limits by automated methods should be investigated, but such results do not disqualify the fuel from aviation use if the results from the referee method are within the specification limit.

11.1.5 *Viscosity*—Test Method **D445/IP 71** or **IP 71** Section 1, **D7042**, or **D7945**. Results from Test Method **D7042** shall be reported as bias-corrected kinematic viscosity results by application of the correction in Test Method **D7042**, relative bias for jet fuel at –20 °C (currently subsection 15.4.4).

11.1.6 *Net Heat of Combustion*—Test Method **D4809**, **D4529**, **D3338**, or IP 12.

11.1.7 *Corrosion (Copper Strip)*—Test Method **D130/IP 154**, or IP 154.

11.1.8 *Total Acidity*—Test Method **D3242/IP 354**.

11.1.9 *Sulfur*—Test Method **D1266**, **D2622**, **D4294**, **D5453**, or IP 336.

11.1.10 *Mercaptan Sulfur*—Test Method **D3227/IP 342**.

11.1.11 *Water Separation*—Test Method **D3948**.

11.1.12 *Existent Gum*—Test Method **D381** or IP 540. Test Method **D381**, using steam jet operating conditions, shall be the referee test method.

11.1.13 *Thermal Stability*—Test Method **D3241/IP 323**.

11.1.14 *Aromatics*—Test Method **D1319**, IP 156, **D6379/IP 436**, **D8267**, or **D8305**.

11.1.14.1 In analyzing Aviation Turbine Fuel by Test Method **D1319** or IP 156, users shall not report results obtained using any of the following lot numbers of Fluorescent Indicator Dyed Gel: 3000000975, 3000000976, 3000000977, 3000000978, 3000000979, and 3000000980.

11.1.14.2 Results from Test Method **D8305** shall be bias-corrected using the bias-correction equation for total aromatics in Section 13 (Precision and Bias) of Test Method **D8305**.

11.1.15 *Smoke Point*—Test Method **D1322/IP 598**.

11.1.16 *Naphthalene Content*—Test Method **D1840** or **D8305**. Results from Test Method **D8305** shall be bias-corrected using the bias-correction equation for total polynuclear aromatics in Section 13 (Precision and Bias) of Test Method **D8305**.

11.1.17 *Electrical Conductivity*—Test Method **D2624/IP 274**.

## 12. Keywords

12.1 aviation turbine fuel; avtur; Jet A; Jet A-1; jet fuel; turbine fuel

<sup>15</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D02-1572. Contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org).