



Designation: D6742/D6742M – 23

Standard Practice for Filled-Hole Tension and Compression Testing of Polymer Matrix Composite Laminates¹

This standard is issued under the fixed designation D6742/D6742M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This practice provides instructions for modifying open-hole tension and compression test methods to determine filled-hole tensile and compressive strengths. The composite material forms are limited to continuous-fiber reinforced polymer matrix composites in which the laminate is both symmetric and balanced with respect to the test direction. The range of acceptable test laminates and thicknesses are described in 8.2.1.

1.2 This practice supplements Test Methods D5766/D5766M (for tension testing) and D6484/D6484M (for compression testing) with provisions for testing specimens that contain a close-tolerance fastener or pin installed in the hole. Several important test specimen parameters (for example, fastener selection, fastener installation method, and fastener hole tolerance) are not mandated by this practice; however, repeatable results require that these parameters be specified and reported.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3.1 Within the text the inch-pound units are shown in brackets.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This practice is under the jurisdiction of ASTM Committee D30 on Composite Materials, and is the direct responsibility of Subcommittee D30.05 on Structural Test Methods.

Current edition approved Sept. 1, 2023. Published September 2023. Originally approved in 2001. Last previous edition approved in 2017 as D6742/D6742M – 17. DOI: 10.1520/D6742_D6742M-23.

Developed in accordance with the principles of the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

- D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement
- D883 Terminology Relating to Plastics
- D3171 Test Methods for Constituent Content of Composite Materials
- D3878 Terminology for Composite Materials
- D5229/D5229M Test Method for Moisture Absorption Properties and Equilibrium Conditioning of Polymer Matrix Composite Materials
- D5766/D5766M Test Method for Open-Hole Tensile Strength of Polymer Matrix Composite Laminates
- D6484/D6484M Test Method for Open-Hole Compressive Strength of Polymer Matrix Composite Laminates
- D6507 Practice for Fiber Reinforcement Orientation Codes for Composite Materials
- D8509 Guide for Test Method Selection and Test Specimen Design for Bolted Joint Related Properties
- E6 Terminology Relating to Methods of Mechanical Testing
- E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods
- E456 Terminology Relating to Quality and Statistics

3. Terminology

3.1 *Definitions*—Terminology D3878 defines terms relating to high-modulus fibers and their composites. Terminology D883 defines terms relating to plastics. Terminology E6 defines terms relating to mechanical testing. Terminology E456 and Practice E177 define terms relating to statistics. In the event of a conflict between terms, Terminology D3878 shall have precedence over the other standards.

3.2 *Definitions of Terms Specific to This Standard*—Refer to Guide D8509.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.3 Symbols:

A = cross-sectional area of a specimen

d = fastener diameter

D = specimen hole diameter

d_{csk} = countersink depth

d_f = countersink flushness

f = distance, perpendicular to loading axis, from hole edge to closest side of specimen

F_x^{fbcu} = ultimate filled-hole compressive strength in the test direction

F_x^{fhtu} = ultimate filled-hole tensile strength in the test direction

g_1 = distance, parallel to loading axis, from hole edge to end of specimen

h = specimen thickness

P^{max} = maximum force carried by test specimen prior to failure

w = specimen width

4. Summary of Practice

4.1 *Filled-Hole Tensile Strength*—In accordance with Test Method **D5766/D5766M**, but with a close-tolerance fastener or pin installed in the hole, perform a uniaxial tension test of a balanced, symmetric laminate with a centrally located hole.

4.2 *Filled-Hole Compressive Strength*—In accordance with Test Method **D6484/D6484M**, but with a close-tolerance fastener or pin installed in the hole, perform a uniaxial compression test of a balanced, symmetric laminate with a centrally located hole.

NOTE 1—For both test methods, ultimate strength is calculated based on the gross cross-sectional area, disregarding the presence of the filled hole. While the filled hole causes a stress concentration and reduced net section, it is common aerospace practice to develop notched design allowable strengths based on gross section stress to account for various stress concentrations (fastener holes, free edges, flaws, damage, and so forth) not explicitly modeled in the stress analysis.

5. Significance and Use

5.1 Refer to Guide **D8509**.

6. Interferences

6.1 Refer to Guide **D8509**.

7. Apparatus

7.1 *General Apparatus*—General apparatus shall be in accordance with Test Methods **D5766/D5766M** (for tension tests) and **D6484/D6484M** (for compression tests), although with a fastener or pin installed in the specimen hole. The micrometer or gauge used shall be capable of determining the hole and fastener diameters to $\pm 8 \mu\text{m}$ [± 0.0003 in.].

7.2 *Fastener*—The fastener or pin type shall be specified as an initial test parameter and reported. The nominal fastener diameter shall be 6 mm [0.25 in.], unless a range of diameters is being investigated. Some fastener types (for example blind bolts) may not be available in this diameter; for these, it is recommended to use a fastener for which the diameter is as close as possible to 6 mm [0.25 in.]. The installation torque (if applicable) shall be specified as an initial test parameter and

reported. This value may be a measured torque or a specification torque for fasteners with lock-setting features. If washers are used, the washer type, number of washers, and washer location(s) shall be specified as initial test parameters and reported. Reuse of fasteners is not recommended because of potential differences in through-thickness clamp-up for a given torque level, caused by wear of the threads.

7.3 *Torque Wrench*—If using a torqued fastener, the torque wrench used to tighten the fastener shall be capable of determining the applied torque to within $\pm 10\%$ of the desired value.

8. Sampling and Test Specimens

8.1 *Sampling*—For tension tests, sampling shall be in accordance with Test Method **D5766/D5766M**. For compression tests, sampling shall be in accordance with Test Method **D6484/D6484M**.

8.2 Geometry:

8.2.1 *Stacking Sequence*—The standard laminates shall have multidirectional fiber orientations (fibers shall be oriented in a minimum of two directions) and balanced and symmetric stacking sequences. For tension specimens, nominal thickness shall be 2.5 mm [0.10 in.], with a permissible range of 2 mm to 4 mm [0.080 in. to 0.160 in.], inclusive. For compression specimens, nominal thickness shall be 4 mm [0.160 in.], with a permissible range of 3 mm to 5 mm [0.125 in. to 0.200 in.], inclusive. Fabric laminates containing satin-type weaves shall have symmetric warp surfaces, unless otherwise specified and noted in the report.

NOTE 2—Typically, a $[45/-45/0/90]_{ns}$ tape or $[45/0]_{ns}$ fabric laminate should be selected such that a minimum of 5% of the fibers lay in each of the four principal orientations. This laminate design has been found to yield the highest likelihood of acceptable failure modes. Consult Practice **D6507** for information on fiber orientation codes.

8.2.2 *Specimen Configuration*—For tension tests, the test specimen configuration shall be in accordance with Test Method **D5766/D5766M**. For compression tests, the test specimen configuration shall be in accordance with Test Method **D6484/D6484M**. The nominal hole diameter may vary from that specified in Test Methods **D5766/D5766M** and **D6484/D6484M** depending upon the type of fastener used.

8.3 *Specimen Preparation*—For tension tests, specimens shall be prepared in accordance with Test Method **D5766/D5766M**. For compression tests, specimens shall be prepared in accordance with Test Method **D6484/D6484M**. Use appropriate hole preparation procedures specified by the test requestor.

8.4 If specific gravity, density, reinforcement volume, or void volume are to be reported, then obtain these samples from the same panels being tested. Specific gravity and density may be evaluated by means of Test Method **D792**. Volume percent of the constituents may be evaluated by one of the matrix digestion procedures of Test Method **D3171**, or, for certain reinforcement materials such as glass and ceramics, by the matrix burn-off technique of Test Method **D3171**.

9. Calibration

9.1 The accuracy of all measuring equipment shall have certified calibrations that are current at the time of use of the equipment.

10. Conditioning

10.1 The recommended pre-test condition is effective moisture equilibrium at a specific relative humidity as established by Test Method **D5229/D5229M**; however, if the test requestor does not explicitly specify a pre-test conditioning environment, no conditioning is required and the test specimens may be tested as prepared.

10.2 The pre-test specimen conditioning process, to include specified environmental exposure levels and resulting moisture content, shall be reported with the test data.

NOTE 3—The term moisture, as used in Test Method **D5229/D5229M**, includes not only the vapor of a liquid and its condensate, but the liquid itself in large quantities, as for immersion.

10.3 If no explicit conditioning process is performed the specimen conditioning process shall be reported as “unconditioned” and the moisture content as “unknown.”

11. Procedure

11.1 Parameters to Be Specified Before Test:

11.1.1 The specimen sampling method, specimen type and geometry, fastener type and material, countersink angle and depth (if appropriate), fastener torque (if appropriate), use of washers (if appropriate), cleaning process, and conditioning travelers (if required).

11.1.2 All other parameters documented in Test Method **D5766/D5766M** for tension tests and Test Method **D6484/D6484M** for compression tests.

11.2 General Instructions:

11.2.1 Any deviations from these procedures, whether intentional or inadvertent, shall be reported.

11.2.2 Following final specimen preparation, but before conditioning and testing, measure the specimen width, and the specimen thickness, at three places in the gauge section in the vicinity of the hole. Report the averages of the thickness, h , and width, w , and use the average values as measured dimensions in subsequent calculations for ultimate strength and geometric ratios. The hole diameter, D , the fastener diameter, d , the countersink depth d_{csk} (if appropriate), the countersink flushness, d_f (if appropriate), distance from hole edge to closest specimen side, f , and distance from hole edge to specimen end,

g , shall also be measured. The accuracy of all measurements shall be within 1 % of the dimension, unless otherwise specified in this practice. Dimensions shall be recorded to three significant figures in units of millimetres [inches].

NOTE 4—The test requester may request that additional measurements be performed after the machined specimens have gone through any conditioning or environmental exposure.

11.2.3 *Cleaning*—The specimen hole, surrounding clamping area, and fastener shank shall be cleaned. If the fastener threads are required to be lubricated, the lubricant shall be applied to the nut threads instead of the fastener threads. Extreme care shall be taken not to accidentally transfer any of the lubricant to the fastener shank, the specimen hole, or to the clamping area during assembly and torquing. The cleaning method and lubricant used (if any) shall be recorded and reported.

11.2.4 *Specimen Assembly*—Assemble test specimen with fastener or pin (and washers if used), in accordance with the fastener installation procedures specified by the test requestor.

11.2.5 *Fastener Torquing*—If using a torqued fastener, the fastener shall be tightened to the required value using a calibrated torque wrench. The actual torque value shall be recorded and reported.

11.3 Condition the specimens as required. Specimens shall be stored in the conditioned environment until test time, if the test environment is different than the conditioning environment.

NOTE 5—The test requester may request that the hole be cleaned and the fastener installed after the specimens have gone through any conditioning or environmental exposure. Conditioning the specimen with the fastener installed is representative of the in-service environmental exposure of structural parts, but the additional weight may complicate the determination of the composite equilibrium moisture content. In such circumstances, the use of conditioning traveler specimens without fasteners is recommended for weight measurement.

11.4 Test Procedure:

NOTE 6—When testing a conditioned specimen at elevated temperature with no fluid exposure control, the percentage moisture loss of the specimen prior to test completion may be estimated by placing a conditioned traveler coupon of known weight within the test chamber at the same time the specimen is placed in the chamber. Upon completion of the test, the traveler coupon is removed from the chamber, weighed, and the percentage weight calculated and reported.

11.4.1 *Tension Test Method*—The tension test of the laminate specimen shall be performed in accordance with Test Method **D5766/D5766M**.

TABLE 1 Three-Place Failure Mode Codes

First Character		Second Character		Third Character	
Failure Type	Code	Failure Area	Code	Failure Location	Code
Angled	A	inside grip/tab	I	bottom	B
Edge delamination	D	at grip/tab	A	top	T
Grip/tab	G	<1 w from grip/tab	W	left	L
Lateral	L	gauge	G	right	R
Multimode	M(xyz)	multiple areas	M	middle, center of hole	M
Long, splitting	S	various	V	offset from center of hole	O
Explosive	X	unknown	U	offset of fastener edge	F
Other	O			various	V
				unknown	U