



SLOVENSKI STANDARD
SIST EN ISO 105-E04:1999

01-marec-1999

Tekstilije - Preskušanje barvne obstojnosti - Del E04: Barvna obstojnost proti znoju (ISO 105-E04:1994)

Textiles - Tests for colour fastness - Part E04: Colour fastness to perspiration (ISO 105-E04:1994)

Textilien - Farbechtheitsprüfungen - Teil E04: Farbechtheit gegen Schweiß (ISO 105-E04:1994)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Textiles - Essais de solidité des teintures - Partie E04: Solidité des teintures a la sueur (ISO 105-E04:1994)

[SIST EN ISO 105-E04:1999](https://standards.iteh.ai/catalog/standards/sist/34c6fe67-4f59-4d7f-9eb5-1c8151136cae/sist-en-iso-105-e04-1999)

[https://standards.iteh.ai/catalog/standards/sist/34c6fe67-4f59-4d7f-9eb5-](https://standards.iteh.ai/catalog/standards/sist/34c6fe67-4f59-4d7f-9eb5-1c8151136cae/sist-en-iso-105-e04-1999)

[1c8151136cae/sist-en-iso-105-e04-1999](https://standards.iteh.ai/catalog/standards/sist/34c6fe67-4f59-4d7f-9eb5-1c8151136cae/sist-en-iso-105-e04-1999)

Ta slovenski standard je istoveten z: EN ISO 105-E04:1996

ICS:

59.080.01 Tekstilije na splošno Textiles in general

SIST EN ISO 105-E04:1999 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 105-E04:1999](#)

<https://standards.iteh.ai/catalog/standards/sist/34c6fe67-4f59-4d7f-9eb5-1c8151136cae/sist-en-iso-105-e04-1999>

EUROPEAN STANDARD

EN ISO 105-E04

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 1996

ICS 59.080.10

Descriptors: See ISO document

English version

**Textiles - Tests for colour fastness - Part E04:
Colour fastness to perspiration
(ISO 105-E04:1994)**

Textiles - Essais de solidité des teintures -
Partie E04: Solidité des teintures à la sueur
(ISO 105-E04:1994)

Textilien - Farbechtheitsprüfungen - Teil E04:
Farbechtheit gegen Schweiß (ISO 105-E04:1994)

ITih STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 105-E04:1999

<https://standards.iteh.ai/catalog/standards/sist/34c6fe67-4f59-4d7f-9eb5-1c8151136cae/sist-en-iso-105-e04-1999>

This European Standard was approved by CEN on 1996-02-23. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN ISO 105-E04:1996

Foreword

The text of the International Standard from Technical Committee ISO/TC 38 "Textiles" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 248 "Textiles and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 1996, and conflicting national standards shall be withdrawn at the latest by December 1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 105-E04:1994 has been approved by CEN as a European Standard without any modification.

NOTE: Normative references to International Standards are listed in annex ZA (normative)

[SIST EN ISO 105-E04:1999](https://standards.iteh.ai/catalog/standards/sist/34c6fe67-4f59-4d7f-9eb5-1c8151136cae/sist-en-iso-105-e04-1999)

<https://standards.iteh.ai/catalog/standards/sist/34c6fe67-4f59-4d7f-9eb5-1c8151136cae/sist-en-iso-105-e04-1999>

Annex ZA(normative)
Normative references to international publications
with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative publications are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies(including amendments)

Publication	Year	Title	EN/HD	Year
ISO 105-A01	1994	Textiles - Tests for colour fastness Part A01 : General principles of testing	EN 20105-A01	1992
ISO 105-A02	1993	Textiles-Tests for colour fastness Part A02 Grey scale for assessing change in colour	EN 20105-A02	1994
ISO 105-A03	1993	Textiles-Tests for colour fastness Part A03 Grey scale for assessing staining	EN 20105-A03	1994

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 105-E04:1999](#)

<https://standards.iteh.ai/catalog/standards/sist/34c6fe67-4f59-4d7f-9eb5-1c8151136cae/sist-en-iso-105-e04-1999>

INTERNATIONAL
STANDARD

ISO
105-E04

Fourth edition
1994-09-15

Textiles — Tests for colour fastness —

Part E04:

Colour fastness to perspiration

iTeh STANDARD PREVIEW

(standards.iteh.ai)
Textiles — Essais de solidité des teintures —

Partie E04: Solidité des teintures à la sueur
SIST EN ISO 105-E04:1999

<https://standards.iteh.ai/catalog/standards/sist/34c6fe67-4f59-4d7f-9eb5-1c8151136cae/sist-en-iso-105-e04-1999>



Reference number
ISO 105-E04:1994(E)

ISO 105-E04:1994(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 105-E04 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

This fourth edition cancels and replaces the third edition (ISO 105-E04:1989), of which it constitutes a technical revision.

ISO 105 was previously published in 13 "parts", each designated by a letter (e.g. "Part A"), with publication dates between 1978 and 1985. Each part contained a series of "sections", each designated by the respective part letter and by a two-digit serial number (e.g. "Section A01"). These sections are now being republished as separate documents, themselves designated "parts" but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.

© ISO 1994

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Textiles — Tests for colour fastness —

Part E04:

Colour fastness to perspiration

1 Scope

This part of ISO 105 specifies a method for determining the resistance of the colour of textiles of all kinds and in all forms to the action of human perspiration.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 105. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 105 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 105-A01:1994, *Textiles — Tests for colour fastness — Part A01: General principles of testing.*

ISO 105-A02:1993, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour.*

ISO 105-A03:1993, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining.*

ISO 105-F:1985, *Textiles — Tests for colour fastness — Part F: Standard adjacent fabrics.*

ISO 105-F10:1989, *Textiles — Tests for colour fastness — Part F10: Specification for adjacent fabric: Multifibre.*

3 Principle

Specimens of the textile in contact with adjacent fabrics are treated in two different solutions containing histidine, drained and placed between two plates under a specified pressure in a test device. The specimens and the adjacent fabrics are dried separately. The change in colour of each specimen and the staining of the adjacent fabrics are assessed by comparison with the grey scales.

4 Apparatus and reagents

4.1 Test devices, each consisting of a frame of stainless steel into which a weight-piece of mass approximately 5 kg and base of 60 mm × 115 mm is closely fitted, so that a pressure of 12,5 kPa can be applied on test specimens measuring 40 mm × 100 mm placed between glass or acrylic-resin plates measuring approximately 60 mm × 115 mm × 1,5 mm. The test device shall be constructed so that, if the weight-piece is removed during the test, the pressure of 12,5 kPa remains unchanged.

If the dimensions of the composite specimen differ from the size of 40 mm × 100 mm, the weight-piece used shall be such that a pressure of 12,5 kPa is applied to the specimen.

NOTE 1 Other devices may be used provided that equivalent results are obtained.

4.2 Oven without an air-circulating fan, maintained at 37 °C ± 2 °C.