



SLOVENSKI STANDARD
SIST EN ISO 105-E06:1999

01-marec-1999

Tekstilije - Preskušanje barvne obstojnosti - Del E06: Barvna obstojnost proti kapljam: alkalije (ISO 10- E06:1989)

Textiles - Tests for colour fastness - Part E06: Colour fastness to spotting: Alkali (ISO 105-E06:1989)

Textilien - Farbechtheitsprüfungen - Teil E06: Farbechtheit gegen Flecken: Alkali (ISO 105-E06:1989)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Textiles - Essais de solidité des teintures - Partie E06: Solidité des teintures aux alcalis (ISO 105-E06:1989)

[SIST EN ISO 105-E06:1999](https://standards.iteh.ai/catalog/standards/sist/e20ef865-2409-4433-ae2b-8d897ea202aa/sist-en-iso-105-e06-1999)

[https://standards.iteh.ai/catalog/standards/sist/e20ef865-2409-4433-ae2b-](https://standards.iteh.ai/catalog/standards/sist/e20ef865-2409-4433-ae2b-8d897ea202aa/sist-en-iso-105-e06-1999)

[8d897ea202aa/sist-en-iso-105-e06-1999](https://standards.iteh.ai/catalog/standards/sist/e20ef865-2409-4433-ae2b-8d897ea202aa/sist-en-iso-105-e06-1999)

Ta slovenski standard je istoveten z: EN ISO 105-E06:1997

ICS:

59.080.01 Tekstilije na splošno Textiles in general

SIST EN ISO 105-E06:1999 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 105-E06:1999](#)

<https://standards.iteh.ai/catalog/standards/sist/e20ef865-2409-4433-ac2b-8d897ea202aa/sist-en-iso-105-e06-1999>

EUROPEAN STANDARD

EN ISO 105-E06

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 1997

ICS 59.080.01

Descriptors: see ISO document

English version

**Textiles - Tests for colour fastness - Part E06:
Colour fastness to spotting: Alkali
(ISO 105-E06:1989)**

Textiles - Essais de solidité des teintures -
Partie E06: Solidité des teintures aux alcalis
(ISO 105-E06:1989)

Textilien - Farbechtheitsprüfungen - Teil E06:
Farbechtheit gegen Flecken: Alkali
(ISO 105-E06:1989)

(standards.iteh.ai)

SIST EN ISO 105-E06:1999

<https://standards.iteh.ai/catalog/standards/sist/e20ef865-2409-4433-ac2b-8d897ea202aa/sist-en-iso-105-e06-1999>

This European Standard was approved by CEN on 1997-03-28. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN ISO 105-E06:1997

Foreword

The text of the International Standard from Technical Committee ISO/TC 38 "Textiles" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 248 "Textiles and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 1997, and conflicting national standards shall be withdrawn at the latest by October 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 105-E06:1989 has been approved by CEN as a European Standard without any modification.

NOTE: Normative references to International Standards are listed in annex ZA (normative).

[SIST EN ISO 105-E06:1999](https://standards.iteh.ai/catalog/standards/sist/e20ef865-2409-4433-ac2b-8d897ea202aa/sist-en-iso-105-e06-1999)

<https://standards.iteh.ai/catalog/standards/sist/e20ef865-2409-4433-ac2b-8d897ea202aa/sist-en-iso-105-e06-1999>



Annex ZA (normative)
Normative references to international publications
with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 105-A01	1994	Textiles - Test for colour fastness - Part A01: General principles of testing	EN ISO 105-A01	1995
ISO 105-A02	1993	Textiles - Test for colour fastness - Part A02: Grey scale for assessing change in colour	EN 20105-A02	1994

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 105-E06:1999

<https://standards.iteh.ai/catalog/standards/sist/e20ef865-2409-4433-ac2b-8d897ea202aa/sist-en-iso-105-e06-1999>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 105-E06:1999](#)

<https://standards.iteh.ai/catalog/standards/sist/e20ef865-2409-4433-ac2b-8d897ea202aa/sist-en-iso-105-e06-1999>

INTERNATIONAL STANDARD

ISO 105-E06

Third edition
1989-12-15

SIST EN ISO 105-E06:1999

Textiles — Tests for colour fastness —

Part E06 :

Colour fastness to spotting: Alkali

Textiles — Essais de solidité des teintures —

Partie E06 : Solidité des teintures aux alcalis



Reference number
ISO 105-E06:1989(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 105-E06 was prepared by Technical Committee ISO/TC 38, *Textiles*.

This third edition cancels and replaces the second edition (ISO 105-E06:1987), of which it constitutes a technical revision.

ISO 105 was previously published in 13 "parts", each designated by a letter (e.g. "Part A"), with publication dates between 1978 and 1985. Each part contained a series of "sections", each designated by the respective part letter and by a two-digit serial number (e.g. "Section A01"). These sections are now being republished as separate documents, themselves designated "parts" but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.

© ISO 1989

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Textiles — Tests for colour fastness —

Part E06 : Colour fastness to spotting: Alkali

1 Scope

This part of ISO 105 specifies a method for determining the resistance of the colour of textiles of all kinds and in all forms to the action of dilute alkaline solutions.

2 Normative references

The following standards contain provisions which through reference in this text, constitute provisions of this part of ISO 105. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 105 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 105-A01:1989, *Textiles — Tests for colour fastness — Part A01: General principles of testing*.

ISO 105-A02:1987, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*.

3 Principle

Drops of a solution of sodium carbonate are placed on the specimen, the surface of which is rubbed gently with a glass rod to ensure penetration. The change in colour of the textile is assessed with the grey scale.

4 Apparatus and reagents

4.1 Pipette or dropper.

4.2 Glass rod, with rounded end.

4.3 Grey scale for assessing change in colour, complying with ISO 105-A02.

4.4 Sodium carbonate, solution containing 100 g of anhydrous sodium carbonate per litre of water (4.5).

4.5 Grade 3 water (see ISO 105-A01:1989, sub-clause 8.2).

5 Test specimen

5.1 If the textile to be tested is fabric, use a specimen measuring 40 mm × 100 mm.

5.2 If the textile to be tested is yarn, knit it into fabric and use a specimen measuring 40 mm × 100 mm, or make a wick of parallel lengths 100 mm long and about 5 mm in diameter, tied near both ends.

5.3 If the textile to be tested is loose fibre, comb and compress enough of it to form a sheet measuring 40 mm × 100 mm.

6 Procedure

6.1 Spot the specimen at room temperature with the sodium carbonate solution (4.4) so that after working the solution into the specimen with the glass rod, a spot of diameter approximately 20 mm is formed. In the case of water-repellent fabrics, the amount of solution shall not exceed 0,5 ml.

6.2 Dry the specimen by hanging it in air at room temperature; brush it to remove sodium carbonate residues.