

Standard Specification for Copper Electrode Wire Used for Welding Seams of Steel Cans¹

This standard is issued under the fixed designation B1001; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope Scope*

1.1 This specification <u>establishescovers</u> the requirements for drawn, soft annealed round copper electrode wire used in welding machines for the purpose of seam welding of cans.

1.2 Units—The values stated in SI units are to be regarded as standard. The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and healthsafety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

<u>1.4 This international standard was developed in accordance with internationally recognized principles on standardization</u> established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

<u>ASTM B1001-23</u>

2.1 ASTM Standards: 2s. iteh.ai/catalog/standards/sist/609ca3f7-f2d1-4be9-b7ff-39a3f366ed61/astm-b1001-23

B49 Specification for Copper Rod for Electrical Purposes

B193 Test Method for Resistivity of Electrical Conductor Materials

B224 Classification of Coppers

B250/B250M Specification for General Requirements for Wrought Copper Alloy Wire

B258 Specification for Standard Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors

E8/E8M Test Methods for Tension Testing of Metallic Materials

E53 Test Method for Determination of Copper in Unalloyed Copper by Gravimetry (Withdrawn 2022)³

E2575 Test Method for Determination of Oxygen in Copper and Copper Alloys(Withdrawn 2017)⁴

F16 Test Methods for Measuring Diameter or Thickness of Wire and Ribbon for Electronic Devices and Lamps

2.2 *NIST Document:*³ NBS Handbook 100 Copper Wire Tables

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.02 on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved Jan. 1, 2017 Oct. 1, 2023. Published January 2017 October 2023. Originally approved in 2017. Last previous edition approved in 2017 as B1001 – 17. DOI: 10.1520/B1001-17. 10.1520/B1001-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, http://www.nist.gov.

3. General Requirements

- 3.1 The following sections of Specification B250/B250M, as applicable, constitute a part of this specification:
- 3.1.1 Terminology,
- 3.1.2 Materials and Manufacture,
- 3.1.3 Workmanship, Finish, and Appearance,
- 3.1.4 Sampling,
- 3.1.5 Number of Tests and Retests,
- 3.1.6 Test Methods,
- 3.1.7 Significance of Numerical Limits,
- 3.1.8 Inspection,
- 3.1.9 Rejection and Rehearing,
- 3.1.10 Certification,
- 3.1.11 Test Report, and
- 3.1.12 Packaging and Package Marking.
- 4. Ordering Information
- 4.1 Include the following specified choices when placing orders for product under this specification, as applicable:

4.1.1 ASTM designation and year of issue,

- 4.1.2 Copper [Alloy] UNS No. designation (see Classification Table 1B224), e9-b7ff-39a3/366ed61/astm-b1001-23
 - 4.1.3 Temper (Temper Section 7),
- 4.1.4 Form (wire) and size (diameter) (Dimensions and Permissible Variations Section <u>1110</u>),
- 4.1.5 How furnished: straight length or coils, coiled,
 - 4.1.6 Quantity; weight for each size and form,
 - 4.1.7 Intended application, and
- 4.1.8 Package type (stem, reel, bulk-or drum).
 - 4.1.9 The following options are available but may not be included unless specified at the time of placing the order, when required:
 - 4.1.9.1 Heat identification or traceability details,

TABLE 1 Chemical Composition		
UNS Number	C11000 ^A	C11020 ^A
Copper Type	ETP	FRHC
Copper incl silver, min	99.90 %	99.90 %
Oxygen	<650 ppm	<650 ppm

^A See Specification B49.

🕼 B1001 – 23

4.1.9.2 Electromagnetic (eddy current) examination,

4.1.9.3 Certification, and

4.1.9.4 Mill Test Report.

5. Materials and Manufacture

5.1 Materials:

5.1.1 The material of manufacture shall be drawn wire of the designated copper UNS number of such purity to be suitable for use prescribed herein.

5.2 Manufacture:

5.2.1 The product shall be manufactured by hot-working, cold-working, and annealing processes to produce a uniform structure in the finished product.

5.2.2 The product shall be hot- or cold-worked to the finished size and subsequently annealed to meet the temper properties specified.

6. Chemical Composition

6.1 The material shall conform to the chemical composition requirements in Table 1 for the copper UNS number designation specified in ordering information.

6.2 These composition limits do not preclude the presence of other elements. By agreement between the manufacturer and purchaser, limits may be established and analysis required for specific elements.

7. Temper

7.1 The standard temper for the product described in this specification include:

7.1.1 O60 Soft Annealed or Hard Temper H04. Annealed.

8. Physical Properties

8.1 Electrical resistivity in annealed condition at 20 °C: 0.15328 $\Omega \cdot g/m^2$ Maximum (100.00 % IACS Minimum). (See NBS Handbook 100.)

9. Mechanical Properties

9.1 Product furnished to this specification shall conform to the tensile requirements prescribed in Table 2.

9.1.1 Tensile requirements for product diameters not covered in Table 2 shall be agreed upon by the manufacturer and the supplier.

9.2 Acceptance or rejection based upon mechanical properties shall depend upon tensile strength and elongation.

9.2.1 Tensile tests performed on samples containing a rod joint (weld) shall provide a tensile strength of at least 95 % of the minimum requirement provided in 9.2.

10. Other Requirements

10.1 The surface of electrode wire shall be free of oxides visible to the eye.

10.2 The surface of electrode wire shall be free of flaws that may interfere with the welding or feeding process.