



Designation: **D5864—18** **D5864 – 23**

Standard Test Method for Determining Aerobic Aquatic Biodegradation of Lubricants or Their Components¹

This standard is issued under the fixed designation D5864; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the determination of the degree of aerobic aquatic biodegradation of fully formulated lubricants or their components on exposure to an inoculum under laboratory conditions.

1.2 This test method is intended to specifically address the difficulties associated with testing water insoluble materials and complex mixtures such as are found in many lubricants.

1.3 This test method is designed to be applicable to all lubricants that are not volatile and are not inhibitory at the test concentration to the organisms present in the inoculum.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Specific hazards are discussed in Section 10.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[D1193 Specification for Reagent Water](#)

[D1293 Test Methods for pH of Water](#)

[D4175 Terminology Relating to Petroleum Products, Liquid Fuels, and Lubricants](#)

[D4447 Guide for Disposal of Laboratory Chemicals and Samples](#)

[D5291 Test Methods for Instrumental Determination of Carbon, Hydrogen, and Nitrogen in Petroleum Products and Lubricants](#)

[E943 Terminology Relating to Biological Effects and Environmental Fate](#)

2.2 ISO Standard:³

[4259:1992\(E\) Petroleum Products—Determination and Application of Precision Data in Relation to Methods of Test](#)

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.12 on Environmental Standards for Lubricants.

Current edition approved June 1, 2018; November 1, 2023. Published June 2018. Originally approved in 1995. Last previous edition approved in 2017 as ~~D5864—17~~D5864 – 18. DOI: ~~10.1520/D5864-18~~10.1520/D5864-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard

2.3 APHA Standard.⁴

2540B Total Solids Dried at 103–105°C

9215 Heterotrophic Plate Count

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this test method, refer to Terminology [D4175](#).

3.1.2 Definitions of terms applicable to this test method that are not described herein appear in the *ASTM Online Dictionary of Engineering Science and Technology*⁵ or Terminology [E943](#).

3.1.3 *aerobic, adj*—(1) taking place in the presence of oxygen, (2) living or active in the presence of oxygen.

3.1.4 *biodegradation, n*—the process of chemical breakdown or transformation of a material caused by organisms or their enzymes.

3.1.4.1 Discussion—

Biodegradation is only one mechanism by which materials are transformed in the environment.

3.1.5 *biomass, n*—biological material including any material other than fossil fuels which is or was a living organism or component or product of a living organism.

3.1.5.1 Discussion—

In biology and environmental science, biomass is typically expressed as density of biological material per unit sample volume, area, or mass (g biomass / g (or / mL or / cm²) sample); when used for products derived from organisms biomass is typically expressed in terms of mass (kg, MT, etc.) or volume (L, m³, bbl, etc.).

3.1.5.2 Discussion—

Products of living organisms include those materials produced directly by living organisms as metabolites (for example, ethanol, various carbohydrates and fatty acids), materials manufactured by processing living organisms (for example: pellets manufactured by shredding and pelletizing plant material) and materials produced by processing living organisms, their components or metabolites (for example, transesterified oil; also called biodiesel).

3.1.6 *blank, n*—a flask containing the test medium and the inoculum with no additional carbon source added.

3.1.7 *inoculum, n*—the viable microorganisms used to contaminate a sample, device, or surface, often expressed as to number and type.

3.1.8 *lag phase, n*—the period of physiological activity and diminished cell division following the addition of microorganisms to a new culture medium.⁶

3.1.9 *log phase, n*—the period of growth of microorganisms during which cells divide at a constant rate.⁶

3.1.10 *mixed liquor, n*—the contents of an aeration tank including the activated sludge mixed with primary effluent or the raw wastewater and return sludge.

3.1.11 *pre-adaptation, n*—the pre-incubation of an inoculum in the presence of the test material under conditions similar to the test conditions.

3.1.11.1 Discussion—

The aim of pre-adaptation is to improve the precision of the test method by decreasing variability in the rate of biodegradation produced by the inoculum. Pre-adaptation may mimic the natural processes which cause changes in the microbial population of the inoculum leading to more rapid biodegradation of the test material but not to a change in the final degree of biodegradation.

⁴ From *Standard Methods for the Examination of Water and Wastewater*, latest edition. Available from the American Public Health Association, 1015 18th St., N.W., Washington, DC 20036.

⁵ *ASTM Online Dictionary of Engineering Science and Technology* (Stock#DEFONLINE) is available on the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org.

⁶ Adapted from *McGraw-Hill Dictionary of Scientific and Technical Terms*, 4th ed., 1989.

3.1.12 *supernatant, n*—the liquid above settled solids.

3.1.13 *theoretical CO₂, n*—the amount of CO₂ which could in theory be produced from the complete oxidation of all of the carbon in a material.

3.1.14 *ultimate biodegradation, n*—degradation achieved when a material is totally utilized by microorganisms resulting in the production of CO₂ (and possibly methane in the case of anaerobic biodegradation), water, inorganic compounds, and new microbial cellular constituents (biomass or secretions, or both).

4. Summary of Test Method

4.1 Biodegradation of a lubricant or the component(s) of a lubricant is measured by collecting and measuring the CO₂ produced when the lubricant or component is exposed to microorganisms under controlled aerobic aquatic conditions. This value is then compared to the theoretical amount of CO₂ which could be generated if all of the carbon in the test material were converted to CO₂. CO₂ is a product of aerobic microbial metabolism of carbon-containing substances and so is a direct measure of the test substance's ultimate biodegradation. CO₂ production is quantified by trapping it in a Ba(OH)₂ solution and titrating the solution to calculate the amount of CO₂ absorbed.

4.2 The carbon content of the test substance is determined by Test Method D5291 or an equivalent method and the theoretical CO₂ is calculated from that measurement. It is necessary to directly measure the carbon content of the test substance instead of calculating this number, because of the complexity of the mixture of compounds present in lubricants.

4.3 Biodegradability is expressed as a percentage of theoretical CO₂ production.

5. Significance and Use

5.1 Results from the test method suggest, within the confines of a controlled laboratory setting, the degree of aerobic aquatic biodegradation of a lubricant or components of a lubricant by measuring the evolved carbon dioxide upon exposure of the test material to an inoculum. The plateau level of CO₂ evolution in this test method will suggest the degree of biodegradability of the lubricant. Test substances that achieve a high degree of biodegradation in this test may be assumed to easily biodegrade in many aerobic aquatic environments.

5.2 Because of the stringency of this test, a low yield of CO₂ does not necessarily mean that the test substance is not biodegradable under environmental conditions, but indicates that further testing is necessary to establish biodegradability.

5.3 Information on toxicity to the inoculum of the test substance may be useful in the interpretation of low biodegradation results.

5.4 Activated sewage-sludge from a sewage-treatment plant that principally treats domestic waste is considered an acceptable active aerobic inoculum available over a wide geographical area in which to test a broad range of lubricants. An inoculum derived from soil or natural surface waters, or both, or any combination of the three sources, is also appropriate for this test method.

NOTE 1—Allowance for various and multiple inoculum sources provides access to a greater diversity of biochemical competency and potentially represents more accurately the capacity for biodegradation.

5.5 A reference or control substance known to biodegrade is necessary in order to verify the activity of the inoculum. The test must be regarded as invalid and should be repeated using a fresh inoculum if the reference does not demonstrate a biodegradation of >60 % of the theoretical CO₂ evolution within 28 days.

5.6 A total CO₂ evolution in the blank at the end of the test exceeding 75 mg CO₂ per 3 L of medium shall be considered as invalidating the test.

5.7 The water solubility or dispersibility of the lubricant or component may influence the results obtained and hence the procedure may be limited to comparing lubricants or components with similar solubilities.

5.8 The ratio of carbon incorporated into cellular material to carbon released as CO₂ will vary depending on the organic substrate, on the particular microorganisms carrying out the conversion, and on the environmental conditions under which the conversion takes place. In principle, this variability complicates the interpretation of the results from this test method.

6. Apparatus


6.1 Carbon Dioxide Scrubbing Apparatus—(see Fig. 1):

6.1.1 The following are required to produce a stream of CO₂-free air of sufficient volume to test up to three materials and the accompanying reference and blank controls in triplicate:

6.1.1.1 Five 1 L plastic bottles, containing 700 mL of 10 M sodium hydroxide (NaOH),

6.1.1.2 Two empty 1 L Erlenmeyer flasks, to prevent liquid carryover, and

6.1.1.3 One 1 L Erlenmeyer flask, containing 700 mL of 0.0125 M barium hydroxide [Ba(OH)₂] solution.



- A = NaOH
- B = Empty
- C = Blank
- S = Standard
- D = Ba(OH)₂
- 1 = Test substance 1
- 2 = Test substance 2
- 3 = Test substance 3

FIG. 1 Aerobic Aquatic Biodegradation Testing Schematic

6.1.2 Connect the bottles in series, as shown in **Fig. 1**, using vinyl, or other suitable non gas-permeable tubing, to a pressurized air system, and purge air through the scrubbing solution at a constant rate.

6.1.3 For each additional test substance to be tested, add one additional 1 L plastic bottle filled with 700 mL of 10 M sodium hydroxide.

6.1.4 The CO₂ scrubbing apparatus upstream of the Erlenmeyer flask containing the Ba(OH)₂ solution may be replaced by an alternative system which effectively and consistently produces CO₂ free air (that is, containing less than 1 ppm CO₂).

6.2 *Incubation/Biodegradation Apparatus*—Each test material, reference, or control requires the following:

6.2.1 *Three 4 L Erlenmeyer flasks,*

6.2.2 *Stoppers,* which are non-permeable to CO₂.

6.2.3 *Flexible Plastic Tubing,* which is non-permeable to CO₂.

6.2.4 *Agitators or Stirrers,* for each 4 L Erlenmeyer flask.

6.3 *Analytical Balance,* to weigh out test material or reference material before or as adding to the test flask,

6.4 *Trapping Apparatus for Measuring Production of CO₂*—For each incubation apparatus, the following are required:

6.4.1 *Several 200 mL Bottles,* fitted with gas bubblers and containing 100 mL 0.0125 M Ba(OH)₂ carbon dioxide scrubbing solution.

6.5 *Titration Apparatus for Measuring Production of CO₂:*

6.5.1 *100 mL burette.*

6.6 *Glass Wool,* for filtering the inoculum.

[ASTM D5864-23](https://standards.iteh.ai/catalog/standards/sist/dc509571-819d-4333-9878-6c3f878a6b93/astm-d5864-23)

<https://standards.iteh.ai/catalog/standards/sist/dc509571-819d-4333-9878-6c3f878a6b93/astm-d5864-23>

7. Reagents and Materials

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.⁷ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type II of Specification **D1193**.

7.3 Prepare the following stock solutions:

7.3.1 *Ammonium Sulfate Solution (40 g/L)*—Dissolve 40 g of ammonium sulfate ((NH₄)₂SO₄) in water and dilute to 1 L.

7.3.2 *Calcium Chloride Solution (27.5 g/L)*—Dissolve 27.5 g of calcium chloride (CaCl₂) in water and dilute to 1 L.

7.3.3 *Ferric Chloride Solution (0.25 g/L)*—Dissolve 0.25 g of ferric chloride hexahydrate (FeCl₃ 6H₂O) in water and dilute to 1 L.

⁷ *Reagent Chemicals, American Chemical Society Specifications, ACS Reagent Chemicals, Specifications and Procedures for Reagents and Standard-Grade Reference Materials*, American Chemical Society, Washington, DC. For ~~Suggestions~~ suggestions on the testing of reagents not listed by the American Chemical Society, see *Annual Analytical Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

7.3.4 *Magnesium Sulfate Solution (22.5 g/L)*—Dissolve 22.5 g of magnesium sulfate heptahydrate ($\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$) in water and dilute to 1 L.

7.3.5 *Phosphate Buffer*—Dissolve 8.5 g potassium dihydrogen phosphate (KH_2PO_4), 21.7 g potassium monohydrogen phosphate (K_2HPO_4), 33.4 g sodium monohydrogen phosphate dihydrate ($\text{Na}_2\text{HPO}_4 \cdot 2\text{H}_2\text{O}$), and 1.7 g ammonium chloride (NH_4Cl) in water and dilute to 1 L.

7.4 The test medium will contain the following reagents diluted to 1 L with water.

7.4.1 *Ammonium Sulfate Solution*, 1 mL,

7.4.2 *Calcium Chloride Solution*, 1 mL,

7.4.3 *Ferric Chloride Solution*, 4 mL,

7.4.4 *Magnesium Sulfate Solution*, 1 mL, and

7.4.5 *Phosphate Buffer Solution*, 10 mL.

7.5 *Barium Hydroxide Solution*, 0.0125 M, is prepared dissolving 4.0 g $\text{Ba}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$ per litre of distilled water. Filter free of solid material, confirm molarity by titration with standard acid, and store under nitrogen sealed as a clear solution to prevent absorption of CO_2 from the air. It is recommended that 5 L be prepared at a time when running a series of tests.

7.6 *Difco Vitamin-free Casamino Acids*.

7.7 *Yeast Extract*.

7.8 *Phenolphthalein*.

7.9 *Standardized Hydrochloric Acid (0.0480 M to 0.0520 M)*. [D5864-23](https://standards.iteh.ai/catalog/standards/sist/dc509571-819d-4333-9878-6c3f878a6b93/astm-d5864-23)

<https://standards.iteh.ai/catalog/standards/sist/dc509571-819d-4333-9878-6c3f878a6b93/astm-d5864-23>

8. Inoculum Test Organisms

8.1 *Sources of the Inoculum*—The following provides several options for where and how to obtain an appropriate inoculum:

8.1.1 *Inoculum from Activated Sludge*—Activated sludge freshly sampled (that is, less than 24 h old) from a well-operated domestic sewage treatment plant (that is, one with no recent upsets and operating within its design parameters) may be used. This sewage treatment plant should receive minimal or no effluent from industry.

8.1.1.1 Using CO_2 -free air, aerate sludge in the laboratory for 4 h. Remove and homogenize 500 mL of the mixed liquor for 2 min at medium speed in a blender or equivalent high speed mixer.

8.1.1.2 If using sludge supernatant as the inoculum, allow the homogenized sludge to settle for 30 min. If the supernatant still contains high levels of suspended solids at the end of 30 min, allow to settle for a further 30 min to 40 min or adapt laboratory conditions to obtain better settling. Once sufficient settling is achieved, decant sufficient volume of the supernatant to provide a 1 % (by volume) inoculum. Avoid carry-over of sludge solids which might cause inconsistencies in the measurement of CO_2 production. The supernatant inoculum is aerated immediately and continuously until use.

8.1.1.3 If using mixed liquor as the inoculum at 30 mg/L solids, determine the dry weight of sludge solids per unit volume in samples of well-mixed homogenized sludge using APHA Test Method 2540B. Calculate the volume of mixed liquor needed to achieve a final sludge dry-weight concentration in the test medium of 30 mg/L. Continue to aerate the mixed liquor until use.

NOTE 2—The use of mixed liquor at 30 mg/L solids without pre-adaptation (8.3) may result in exceedance of the CO_2 -production criterion in the blanks (75 mg CO_2 total). It is recommended that this inoculum type be used only if the inoculum will be pre-adapted.