



Designation: ~~A450/A450M – 21~~ A450/A450M – 23

Standard Specification for General Requirements for Carbon and Low Alloy Steel Tubes¹

This standard is issued under the fixed designation A450/A450M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification² covers a group of requirements which, with the exceptions of 6.3 and Sections 7, 8, 19, 20, 21, 22, 23, 24, and 25, are mandatory requirements to the following ASTM tubular product specifications:³

Title of Specification	ASTM Designation ^A
Electric-Resistance-Welded Carbon Steel and Carbon-Manganese Steel Boiler Tubes	A178/A178M
Seamless Cold-Drawn Low-Carbon Steel Heat-Exchanger and Condenser Tubes	A179/A179M
Seamless Carbon Steel Boiler Tubes for High-Pressure Service	A192/A192M
Seamless Medium-Carbon Steel Boiler and Superheater Tubes	A210/A210M
Electric-Resistance-Welded Carbon Steel Heat-Exchanger and Condenser Tubes	A214/A214M
Seamless and Electric-Welded Low-Alloy Steel Tubes	A423/A423M
Specification for Seamless and Welded Carbon Steel Heat-Exchanger Tubes with Integral Fins	A498/A498M
Seamless Cold-Drawn Carbon Steel Feedwater Heater Tubes	A556/A556M
Seamless, Cold-Drawn Carbon Steel Tubing for Hydraulic System Service	A822/A822M

^A These designations refer to the latest issue of the respective specifications.

1.2 One or more of Sections 6.3, 7, 8, 19, 20, 21, 22, 22.1, 24, and 25 apply when the product specification or purchase order has a requirement for the test or analysis described by these sections.

1.3 In case of conflict between a requirement of the product specification and a requirement of this general requirement specification only the requirement of the product specification need be satisfied.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved Nov. 1, 2021; Nov. 1, 2023. Published November 2021/November 2023. Originally approved in 1961. Last previous edition approved in 2018/2021 as A450/A450M – 18a/A450/A450M – 21. DOI: 10.1520/A0450-A0450M-21; 10.1520/A0450_A0450M-23.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-450 in Section II of that Code.

³ Annual Book of ASTM Standards, Vols 01.01 and 01.04.

***A Summary of Changes section appears at the end of this standard**

are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. The inch-pound units shall apply unless the “M” designation (SI) of the product specification is specified in the order.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:⁴

[A178/A178M Specification for Electric-Resistance-Welded Carbon Steel and Carbon-Manganese Steel Boiler and Superheater Tubes](#)

[A179/A179M Specification for Seamless Cold-Drawn Low-Carbon Steel Heat-Exchanger and Condenser Tubes](#)

[A192/A192M Specification for Seamless Carbon Steel Boiler Tubes for High-Pressure Service](#)

[A210/A210M Specification for Seamless Medium-Carbon Steel Boiler and Superheater Tubes](#)

[A214/A214M Specification for Electric-Resistance-Welded Carbon Steel Heat-Exchanger and Condenser Tubes](#)

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[A423/A423M Specification for Seamless and Electric-Welded Low-Alloy Steel Tubes](#)

[A498/A498M Specification for Seamless and Welded Carbon Steel Heat-Exchanger Tubes with Integral Fins](#)

[A530/A530M Specification for General Requirements for Specialized Carbon and Alloy Steel Pipe](#)

[A556/A556M Specification for Seamless Cold-Drawn Carbon Steel Feedwater Heater Tubes](#)

[A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment](#)

[A751 Test Methods and Practices for Chemical Analysis of Steel Products](#)

[A822/A822M Specification for Seamless Cold-Drawn Carbon Steel Tubing for Hydraulic System Service](#)

[A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys](#)

[A1047/A1047M Test Method for Pneumatic Leak Testing of Tubing](#)

[A1058 Test Methods for Mechanical Testing of Steel Products—Metric](#)

[D3951 Practice for Commercial Packaging](#)

[E92 Test Methods for Vickers Hardness and Knoop Hardness of Metallic Materials](#)

[E213 Practice for Ultrasonic Testing of Metal Pipe and Tubing](#)

[E273 Practice for Ultrasonic Testing of the Weld Zone of Welded Pipe and Tubing](#)

[E309 Practice for Eddy Current Examination of Steel Tubular Products Using Magnetic Saturation](#)

[E426 Practice for Electromagnetic \(Eddy Current\) Examination of Seamless and Welded Tubular Products, Titanium, Austenitic Stainless Steel and Similar Alloys](#)

[E570 Practice for Flux Leakage Examination of Ferromagnetic Steel Tubular Products](#)

2.2 SAE Aerospace Material Specifications:

[SAE-AMS2806 Identification Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys⁵](#)

2.3 Military Standards:

[MIL-STD-792 Identification Marking Requirements for Special Purpose Equipment⁶](#)

[NAVSEA T9074-AS-GIB-010/271 Requirements for Nondestructive Testing Methods⁷](#)

2.4 ASME Boiler and Pressure Vessel Code:

[Section IX⁸](#)

2.5 Steel Structures Painting Council:

[SSPC-SP 6 Surface Preparation Specification No. 6 Commercial Blast Cleaning⁹](#)

2.6 Other Document:

[SNT-TC-1A Recommended Practice for Nondestructive Personnel Qualification and Certification.](#)

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁵ Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096, <http://www.sae.org>.

⁶ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098.

⁷ Available from Naval Inventory Control Point, Code 1 Support Branch, 700 Robbins Ave., Philadelphia, PA 19111-5094.

⁸ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁹ Available from Society for Protective Coatings (SSPC), 40 24th St., 6th Floor, Pittsburgh, PA 15222-4656, <http://www.sspc.org>.

~~3.1.1 remelted heat~~—in secondary melting, all of the ingots remelted from a single primary heat.

~~3.1.2 thin-wall tube~~—a tube meeting the specified outside diameter and specified wall thickness set forth as follows:

Specified Outside Diameter	Specified Wall Thickness
2 in. [50.8 mm] or less	2 % or less of specified outside diameter
Greater than 2 in. [50.8 mm]	3 % or less of specified outside diameter
Any	0.020 in. [0.5 mm] or less

3.1 ~~Other defined terms~~—Definitions of Terms—The definitions in Test Methods and Definitions ~~A370~~, Test Methods, Practices, and Terminology ~~A751~~, and Terminology ~~A941~~ are applicable to this specification and to those listed in this standard that are not included in ~~1.3.2~~; refer to:

3.1.1 Terminology ~~A941~~ for general steel terminology,

3.1.2 Test Methods and Definitions ~~A370~~ or Test Methods ~~A1058~~ for mechanical testing of steel products terminology, and

3.1.3 Test Methods and Practices ~~A751~~ for chemical analysis of steel products terminology.

3.2 Definitions of Terms Specific to This Standard:

~~3.2.1 remelted heat~~—in secondary melting, all of the ingots remelted from a single primary heat.

~~3.2.2 thin-wall tube~~—a tube meeting the specified outside diameter and specified wall thickness set forth as follows:

Specified Outside Diameter	Specified Wall Thickness
2 in. [50.8 mm] or less	2 % or less of specified outside diameter
Greater than 2 in. [50.8 mm]	3 % or less of specified outside diameter
Any	0.020 in. [0.5 mm] or less

4. Ordering Information

4.1 It is the purchaser’s responsibility to specify in the purchase order all ordering information necessary to purchase the needed material. Examples of such information include, but are not limited to, the following:

4.1.1 Quantity (feet, metres, or number of lengths),

4.1.2 Specification number with grade or class, or both, as applicable and year date,

4.1.3 Manufacture (hot-finished or cold-finished),

4.1.4 Size (outside diameter and minimum wall thickness),

4.1.5 Length (specific or random),

4.1.6 Choice of testing track from the options listed in Test Methods ~~A1058~~ when material is ordered to an M suffix (SI units) product standard. If the choice of test track is not specified in the order, then the default ASTM test track shall be used as noted in Test Methods ~~A1058~~.

4.1.7 Supplementary Requirements, and

4.1.8 Additional requirements.

5. Process

5.1 The steel may be made by any process.

5.2 If a specific type of melting is required by the purchaser, it shall be as stated on the purchase order.

5.3 The primary melting may incorporate separate degassing or refining and may be followed by secondary melting, such as electroslag remelting or vacuum-arc remelting.

5.4 Steel may be cast in ingots or may be strand cast. When steel of different grades is sequentially strand cast, identification of the resultant transition material is required. The producer shall remove the transition material by an established procedure that positively separates the grades.

6. Chemical Composition

6.1 Samples for chemical analysis, and method of analysis shall be in accordance with Test ~~Methods, Practices, and Terminology~~ Methods and Practices A751.

6.2 *Heat Analysis*—If the heat analysis reported by the steel producer is not sufficiently complete for conformance with the heat analysis requirements of the applicable product specification to be fully assessed, the manufacturer may complete the assessment of conformance with such heat analysis requirements by using a product analysis for the specified elements that were not reported by the steel producer, provided that product analysis tolerances are not applied and the heat analysis is not altered.

6.3 *Product Analysis*—Product analysis requirements and options, if any, are contained in the product specification.

7. Tensile Properties

7.1 The material shall conform to the requirements as to tensile properties prescribed in the individual specification.

7.2 The yield strength corresponding to a permanent offset of 0.2 % of the gage length or to a total extension of 0.5 % of the gage length under load shall be determined.

7.3 If the percentage of elongation of any test specimen is less than that specified and any part of the fracture is more than ¾ in. [19.0 mm] from the center of the gage length, as indicated by scribe marks on the specimen before testing, a retest shall be allowed.

8. Standard Weights

8.1 The calculated weight per unit length, based upon a specified minimum wall thickness, shall be determined by the following equation:

$$W = C(D - t)t \quad (1)$$

where:

C = 10.69 [0.0246615],

W = weight, lb/ft [kg/m],

D = specified outside diameter, in. [mm], and

t = specified minimum wall thickness, in. [mm]

8.2 The permissible variations from the calculated weight per foot [kilogram per metre] shall be as prescribed in [Table 1](#).

9. Permissible Variations in Wall Thickness

9.1 Variations from the specified minimum wall thickness shall not exceed the amounts prescribed in [Table 2](#).

9.2 For tubes 2 in. [50.8 mm] and over in outside diameter and 0.220 in. [5.6 mm] and over in thickness, the variation in wall thickness in any one cross section of any one tube shall not exceed the following percentage of the actual mean wall at the section. The actual mean wall is defined as the average of the thickest and thinnest wall in that section.

Seamless tubes ±10 %

Welded tubes ±5 %



TABLE 1 Permissible Variations in Weight Per Unit Length^A

Method of Manufacture	Permissible Variation in Weight per Unit Length, %	
	Over	Under
Seamless, hot-finished	16	0
Seamless, cold-finished:		
1½ in. [38.1 mm] and under OD	12	0
Over 1½ in. [38.1 mm] OD	13	0
Welded	10	0

^A These permissible variations in weight apply to lots of 50 tubes or more in sizes 4 in. [101.6 mm] and under in outside diameter, and to lots of 20 tubes or more in sizes over 4 in. [101.6 mm] in outside diameter.

TABLE 2 Permissible Variations in Wall Thickness^A

Outside Diameter, in. [mm]	Wall Thickness, %							
	0.095 [2.4] and Under		Over 0.095 to 0.150 [2.4 to 3.8], incl		Over 0.150 to 0.180 [3.8 to 4.6], incl		Over 0.180, [4.6]	
	Over	Under	Over	Under	Over	Under	Over	Under
Seamless, Hot-Finished Tubes								
4 [101.6] and under	40	0	35	0	33	0	28	0
Over 4 [101.6]	35	0	33	0	28	0
Seamless, Cold-Finished Tubes								
1½ [38.1] and under	Over 20				Under 0			
Over 1½ [38.1]	22				0			
Welded Tubes								
All sizes	18				0			

^A These permissible variations in wall thickness apply only to tubes, except internal-upset tubes, as rolled or cold-finished, and before swaging, expanding, bending, polishing, or other fabricating operations.

ASTM A450/A450M-23

<https://standards.iteh.ai/catalog/standards/sist/c5a88bfe-92ec-4251-9653-bffc81160ed6/astm-a450-a450m-23>

9.3 When cold-finished tubes as ordered require wall thicknesses ¾ in. [19.1 mm] or over, or an inside diameter 60 % or less of the outside diameter, the permissible variations in wall thickness for hot-finished tubes shall apply.

10. Permissible Variations in Outside Diameter

10.1 Except as provided in 10.2, variations from the specified outside diameter shall not exceed the amounts prescribed in Table 3.

10.2 Thin-wall tubes usually develop significant ovality (out of roundness) during final annealing, or straightening, or both. The diameter tolerances of Table 3 are not sufficient to provide for additional ovality expected in thin-wall tubes, and, for such tubes, are applicable only to the *mean* of the extreme (maximum and minimum) outside diameter readings in any one cross section. However, for thin wall tubes the *difference* in extreme outside diameter readings (ovality) in any one cross section shall not exceed the following ovality allowances:

Outside Diameter	Ovality Allowance
1 in. [25.4 mm] and under	0.020 in. [0.5 mm]
Over 1 in. [25.4 mm]	2.0 % of specified outside diameter

11. Permissible Variations in Length

11.1 Variations from the specified length shall not exceed the amounts prescribed in Table 4.

TABLE 3 Permissible Variations in Outside Diameter^A

Outside Diameter, in. [mm]	Permissible Variations, in. [mm]	
	Over	Under
Hot-Finished Seamless Tubes		
4 [101.6] and under	1/64 [0.4]	1/32 [0.8]
Over 4 to 7 1/2 [101.6 to 190.5], incl	1/64 [0.4]	3/64 [1.2]
Over 7 1/2 to 9 [190.5 to 228.6], incl	1/64 [0.4]	1/16 [1.6]
Welded Tubes and Cold-Finished Seamless Tubes		
Under 1 [25.4]	0.004 [0.1]	0.004 [0.1]
1 to 1 1/2 [25.4 to 38.1], incl	0.006 [0.15]	0.006 [0.15]
Over 1 1/2 to 2 [38.1 to 50.8], excl	0.008 [0.2]	0.008 [0.2]
2 to 2 1/2 [50.8 to 63.5], excl	0.010 [0.25]	0.010 [0.25]
2 1/2 to 3 [63.5 to 76.2], excl	0.012 [0.3]	0.012 [0.3]
3 to 4 [76.2 to 101.6], incl	0.015 [0.38]	0.015 [0.38]
Over 4 to 7 1/2 [101.6 to 190.5], incl	0.015 [0.38]	0.025 [0.64]
Over 7 1/2 to 9 [190.5 to 228.6], incl	0.015 [0.38]	0.045 [1.14]

^A Except as provided in 10.2, these permissible variations include out-of-roundness. These permissible variations in outside diameter apply to hot-finished seamless, welded and cold-finished seamless tubes before other fabricating operations such as upsetting, swaging, expanding, bending, or polishing.

TABLE 4 Permissible Variations in Length^A

Method of Manufacture	Outside Diameter, in. [mm]	Cut Length, in. [mm]	
		Over	Under
Seamless, hot-finished	All sizes	3/16 [5]	0 [0]
Seamless, cold-	Under 2 [50.8]	1/8 [3]	0 [0]
finished	2 [50.8] and over	3/16 [5]	0 [0]
Welded	Under 2 [50.8]	1/8 [3]	0 [0]
	2 [50.8] and over	3/16 [5]	0 [0]

^A These permissible variations in length apply to tubes before bending. They apply to cut lengths up to and including 24 ft [7.3 m]. For lengths greater than 24 ft [7.3 m], the above over-tolerances shall be increased by 1/8 in. [3 mm] for each 10 ft [3 m] or fraction thereof over 24 ft or 1/2 in. [13 mm], whichever is the lesser.

12. Permissible Variations in Height of Flash on Electric-Resistance-Welded Tubes

12.1 For tubes manufactured to this specification, the weld flash on the outside of the tube shall be mechanically removed by cutting prior to any subsequent cold work or sizing.

12.2 For tubes over 2 in. [50.8 mm] in outside diameter, or over 0.135 in. [3.44 mm] in wall thickness, the flash on the inside of the tubes shall be mechanically removed by cutting to a maximum height of 0.010 in. [0.25 mm] at any point on the tube.

12.3 For tubes 2 in. [50.8 mm] and under in outside diameter and 0.135 in. [3.4 mm] and under in wall thickness, the flash on the inside of the tube shall be mechanically removed by cutting to a maximum height of 0.006 in. [0.15 mm] at any point on the tube.

13. Straightness and Finish

13.1 Finished tubes shall be reasonably straight and have smooth ends free of burrs. They shall have a workmanlike finish. Surface imperfections (see Note 1) may be removed by grinding, provided that a smooth curved surface is maintained, and the wall thickness is not decreased to less than that permitted by this or the product specification. The outside diameter at the point of grinding may be reduced by the amount so removed.

NOTE 1—An imperfection is any discontinuity or irregularity found in the tube.

14. Repair by Welding

14.1 Repair welding of base metal defects in tubing is permissible only with the approval of the purchaser and with the further understanding that the tube shall be marked “WR” and the composition of the deposited filler metal shall be suitable for the composition being welded. Defects shall be thoroughly chipped or ground out before welding and each repaired length shall be