



Designation: **C1064/C1064M—17** **C1064/C1064M – 23**

Standard Test Method for Temperature of Freshly Mixed Hydraulic-Cement Concrete¹

This standard is issued under the fixed designation C1064/C1064M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This test method covers the determination of temperature of freshly mixed hydraulic-cement concrete.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system ~~may not be exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other. Combining other, and values from the two systems may result in non-conformance with the standard; shall not be combined.~~

1.3 The text of this standard ~~refers to~~ refers to notes and footnotes that provide explanatory information. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. (Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²)*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

[C125 Terminology Relating to Concrete and Concrete Aggregates](#)

[C172/C172M Practice for Sampling Freshly Mixed Concrete](#)

[C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials](#)

3. Terminology

3.1 For definitions of the terms used in this test method, refer to Terminology [C125](#).

¹ This test method is under the jurisdiction of ASTM Committee [C09](#) on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee [C09.60](#) on Testing Fresh Concrete.

Current edition approved ~~Oct. 1, 2017~~ Dec. 1, 2023. Published ~~October 2017~~ December 2023. Originally approved in 1986. Last previous edition approved in ~~2012~~ 2017 as C1064/C1064M-12. DOI: 10.1520/C1064_C1064M-17-17. DOI: 10.1520/C1064_C1064M-23.

² Section on Safety Precautions, Manual of Aggregate and Concrete Testing, *Annual Book of ASTM Standards*, Vol 04.02.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

4. Significance and Use

4.1 This test method provides a means for measuring the temperature of freshly mixed concrete. The measured temperature represents the temperature at the time of testing and may not be an indication of the temperature of the freshly mixed concrete at a later time. It may be used to verify conformance to a specified requirement for temperature of concrete.

4.2 Concrete containing aggregate of a nominal maximum size greater than 75 mm [3 in.] may require up to 20 min for the transfer of heat from aggregate to mortar. (See ACI Committee 207.1R Report.⁴)

5. Apparatus

5.1 *Container*, shall be large enough to provide at least 75 mm [3 in.] of concrete in all directions around the sensor of the temperature measuring device; concrete cover must also be at least three times the nominal maximum size of the coarse aggregate.

5.2 *Temperature Measuring Device*, shall be capable of accurately measuring the temperature of the freshly mixed concrete to ± 0.5 °C [± 1 °F] throughout a range of 0° to 50 °C [30° to 120 °F]. The design of the temperature measuring device shall be such that it allows 75 mm [3 in.] or more immersion during operation.

5.3 Partial immersion liquid-in-glass thermometers (and possibly other types) shall have a permanent mark to which the device must be immersed without applying a correction factor.

5.4 *Reference Temperature Measuring Device*, shall be readable and accurate to ± 0.2 °C [0.5 °F] at the verification points in 6.1. A certificate or report that verifies the accuracy shall be available in the laboratory for review. Accuracy of liquid-in-glass reference temperature measuring devices shall be verified once. Verification of direct-reading resistance reference temperature measuring devices shall be performed at least every twelve (12) months. The certificate or report shall provide documentation that the reference standard used in the verification is traceable to the National Institute of Standards and Technology (NIST).

6. Verification of the Accuracy of Temperature Measuring Devices

6.1 The accuracy of each temperature measuring device used for determining the temperature of freshly mixed concrete shall be verified at least ~~annually, every twelve (12) months, or~~ whenever there is a question of accuracy. Verify the accuracy of the temperature measuring device by comparing the readings of the reference temperature measuring device to the temperature measuring device at two temperatures at least 15 °C [30 °F] apart.

6.2 Verification of the accuracy of the temperature measuring devices may be made in oil or other suitable bath liquids having uniform density if provision is made to:

6.2.1 Maintain the bath temperature constant within 0.2 °C [0.5 °F] during the verification process.

6.2.2 Continuously circulate the bath liquid to provide a uniform temperature throughout the bath.

6.2.3 Suspend the temperature measuring devices in such a manner that the devices are not contacting the sides or bottom of the bath container during verification.

6.3 Place both the temperature and reference temperature measuring devices in the bath for at least 5 min before reading temperatures at the test points specified in 6.1.

6.4 Prior to reading the temperature measuring devices, if the temperature in the bath has been reduced, slightly tap thermometers containing liquid to avoid adhesion of the liquid to the glass.

6.5 Read and record the temperature of both the reference temperature measuring device and the temperature measuring device. Reject the temperature measuring device if the difference in readings exceeds 0.5 °C [1 °F] at either test point. If the indicator of

⁴ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.