



Designation: ~~D16–23~~ **D16–24**

Standard Terminology for Paint, Related Coatings, Materials, and Applications¹

This standard is issued under the fixed designation D16; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This standard consists of technical terms used in standards under the jurisdiction of ASTM Committee D01 (on Paint and Related Coatings, Materials, and Applications), and of definitions suitable for use in these standards.

NOTE 1—When any definition in this standards is quoted or published out of the context of this standard, editorially insert the following delimiting statement “for paints and related coatings, materials, and applications” after the dash following the term (in the absence of an existing delimiting statement). This will limit the filed of application of the term and definition to that approved by this committee.

1.2 In this terminology standard, definitions used in other ASTM standards are indicated by following the definition with the designation of that standard. In some cases, a relevant D01 subcommittee is also listed. Definitions influenced by those used by other organizations are indicated by the acronym of the organization. Primary terms are given in bold, while narrower and unapproved terms are given in italics.

1.3 There are several specialized terminology standards under the jurisdiction of Committee D01, as follows: **D804**, **D1695**, **D6440**, **D6488**, and **D7188**. Few definitions from those standards are included in Terminology D16. Therefore, in searches for definitions of paints and coatings terms, these standards should be included where appropriate.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- D804 Terminology Relating to Pine Chemicals, Including Tall Oil and Related Products**
- D968 Test Methods for Abrasion Resistance of Organic Coatings by Falling Abrasive**
- D1475 Test Method for Density of Liquid Coatings, Inks, and Related Products**
- D1653 Test Methods for Water Vapor Transmission of Organic Coating Films**
- D1695 Terminology of Cellulose and Cellulose Derivatives**
- D1729 Practice for Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials**
- D1736 Test Method for Efflorescence of Interior Wall Paints (Withdrawn 1997)³**

¹ This terminology is under the jurisdiction of ASTM Committee **D01** on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee **D01.16** on Terminology.

Current edition approved ~~Aug. 1, 2023~~ **Jan. 1, 2024**. Published ~~September 2023~~ **January 2024**. Originally approved in 1911. Last previous edition approved in ~~2019~~ **2023** as ~~D16–19~~ **D16–23**. DOI: ~~10.1520/D0016-23~~ **10.1520/D0016-24**.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

- D1848 Classification for Reporting Paint Film Failures Characteristic of Exterior Latex Paints (Withdrawn 2003)³
- D2794 Test Method for Resistance of Organic Coatings to the Effects of Rapid Deformation (Impact)
- D3363 Test Method for Film Hardness by Pencil Test
- D3450 Test Method for Washability Properties of Interior Architectural Coatings
- D4062 Test Method for Leveling of Paints by Draw-Down Method
- D4209 Practice for Determining Volatile and Nonvolatile Content of Cellulosics, Emulsions, Resin Solutions, Shellac, and Varnishes
- D4366 Test Methods for Hardness of Organic Coatings by Pendulum Damping Tests
- D4958 Test Method for Comparison of the Brush Drag of Latex Paints
- D5146 Guide to Testing Solvent-Borne Architectural Coatings
- D5178 Test Method for Mar Resistance of Organic Coatings
- D6440 Terminology Relating to Hydrocarbon Resins
- D6488 Terminology Relating to Print Problems
- D7188 Terminology for Printing Inks, Materials, and Processes
- E284 Terminology of Appearance
- 2.2 EPA Documents:⁴
- 450/3-83-013R Glossary for Air Pollution Control of Industrial Coating Operations
- Method 24, 40 CFR Part 60, Appendix A Determination of Volatile Matter Content, Water Content, Density, Volume Solids, and Weight Solids of Surface Coatings

3. Terminology

3.1 For definitions of terms having to do with appearance, see Terminology E284.

3.2 Definitions:

abrasion resistance, *n*—(for coatings) the ability of a coating to resist being worn away and to maintain its original appearance and structure when subjected to rubbing, scraping, or wear. **D968, D01.23**

acid number, *n*—(for coatings) the number of milligrams of potassium hydroxide (KOH) required to neutralize the free acids in 1 g of an oil, resin, varnish, or other substance; generally reported on the nonvolatile content.

acid value—see **acid number**.

acrylic resin—under **resin, synthetic**, see *acrylic resin*.

additive, *n*—a substance added in small quantities to another substance, usually to improve specific properties (for example, a drier, mildewcide, etc.).

adhesion promoter, *n*—a material built into a binder or added to a paint to ~~form primary bonds to either~~ increase the number and/or strength of interactions to the substrate or the previously applied coating, with the specific aim of improving ~~the dry or wet adhesion, or both~~ adhesion. **D01.23 D01.23**

alkyd resin—under **resin, synthetic**, see *alkyd resin*.

architectural coating, *n*—organic coating intended for on-site application to interior or exterior surfaces of residential, commercial, institutional, or industrial buildings, in contrast to industrial coatings. **D5146, D01.42**

DISCUSSION—

They are protective and decorative finishes applied at ambient temperatures. Often called Trade Sales Coatings.

associative thickener, *n*—water-soluble polymers containing hydrophobic groups that are capable of nonspecific hydrophobic association similar to surfactants that elevate viscosity presumably by association between thickener particles or thickener and dispersed particles that may be present in the aqueous system such as latex particles rather than through high molecular weight or chain stiffness of the thickener molecules themselves.

⁴ Available from United States Environmental Protection Agency (EPA), William Jefferson Clinton Bldg., 1200 Pennsylvania Ave., NW, Washington, DC 20460, <http://www.epa.gov>.

autodeposition, *n*—a single-step immersion metal finishing process in which an organic coating is applied by means of unique surface chemical reactions carried out in an aqueous latex dispersion, also referred to as chemiphoresis. Components within the bath give rise to chemical reactions that slightly solubilize the metallic surface and lead to destabilization, deposition, and coalescence of the dispersed latex particles at that surface.

DISCUSSION—

The deposition rate of the latex is controlled by the rate of surface solubilization. The process does not require any pretreatments such as phosphating, needs no external energy input, and gives rise to deposition wherever the solution wets the substrate. Irregularly shaped parts can be uniformly coated.

baking finish, *n*—a paint or varnish that requires baking at temperatures above 150 °F (65 °C) for the development of desired properties.

baking temperature, *n*—a temperature above 150 °F (65 °C).

batch, *n*—the total quantity of a material produced in a single final mixing operation after all production processes are complete, or just prior to filling.

bituminous varnish—under **varnish**, see *bituminous varnish*.

bleeding, *n*—the diffusion of coloring matter through a coating from the substrate; also, the discoloration arising from such diffusion. In the case of printing ink, the spreading or running of a pigment color by the action of a solvent such as water or alcohol.

blister, *n*—a dome-shaped defect caused by the formation of a gas or liquid under a coating film which results in a localized loss of adhesion and lifting of the coating, that is, film, from the substrate.

blistering, *v*—the process of forming a blister.

blistering resistance, *n*—the ability of a coating to resist blistering.

blocking, *n*—*for coatings other than powder coatings*, the sticking of a coated surface to an adjacent surface when the two surfaces have been in contact for an extended period of time. **D01.42**

brush-drag, *n*—resistance encountered when applying a coating by brush, directly related to the high-shear viscosity of the coating. **D4958, D01.42**

bulking value, *n*—solid volume of a unit weight of material, usually expressed as gallons per pound. For practical purposes this is 0.120 divided by the specific gravity.

caulking compound, *n*—a soft, plastic material, consisting of pigment and vehicle, used for sealing joints in buildings and other structures where normal structural movement may occur.

DISCUSSION—

Caulking compound retains its plasticity for an extended period after application. It is available in forms suitable for application by gun and knife and in extruded preformed shapes.

cellulose lacquer—see **lacquer**.

chalking resistance, *n*—the ability of a pigmented coating to resist the formation of a friable powder on its surface caused by the disintegration of the binding medium by degradative weather factors.

checking resistance, *n*—the ability of a coating to resist slight breaks in the film that do not penetrate to the previously applied coating or to the substrate. The breaks should be called cracks if penetration extends to the previously applied coating or to the substrate. See **cracking resistance**.

chipping resistance, *n*—the ability of a coating or layers of coatings to resist removal, usually in small pieces, resulting from impact by hard objects or from wear during service.

coating, *n*—(1) a liquid, liquefiable, or mastic composition that is converted by evaporation, cross-linking, or cooling to a solid or semisolid protective, decorative, or functional adherent layer after application; (2) the solid or semisolid layer resulting from application of the composition above.

DISCUSSION—

Liquefiable can involve melting or suspending. Coatings include, but are not limited to, paints, varnishes, sealers, and stains.

color of an object, *n*—the aspect of the appearance of an object dependent upon the spectral composition of the incident light, the spectral reflectance or transmittance of the object, and the spectral response of the observer.

hue, *n*—the attribute of color perception by means of which a color is judged to be red, orange, yellow, green, blue, purple, or intermediate between adjacent pairs of these, considered in a close ring, red and purple being an adjacent pair. (White, gray and black colors possess no hue). **E284**

DISCUSSION—

The short end of the spectrum is violet, with purple by definition being a nonspectral combination of red and violet. The practice of replacing violet by purple in the roster of object colors is apparently a practical accommodation to color-order requirements, as described in the Munsell system. See Practice **D1729**.

lightness, *n*—(1) the attribute by which a perceived color is judged to be equivalent to a member of a series of grays ranging from black to white; (2) the attribute of color perception by which a non-self-luminous body is judged to reflect more or less light. **E284**

saturation—attribute of a visual sensation that permits a judgment to be made of the proportion of pure chromatic color in the total sensation. **E284**

contrast ratio, *n*—ratio of the reflectance of a dry paint film over a black substrate of 5 % or less reflectance, to the reflectance of the same paint, equivalently applied and dried, over a substrate of 80 % reflectance.

ASTM D16-24

coverage, coverage rate, covering power—ambiguous terms that are used in some instances to refer to hiding power and in others to mean spreading rate. The precise terms **hiding power** and **spreading rate** are preferred.

cracking resistance, *n*—the ability of a coating to resist breaks of the film where the breaks extend through to the surface painted and the previously applied coating or the substrate is visible. The use of a minimum magnification of 10 diameters is recommended in cases where it is difficult to differentiate between cracking and checking. See **checking resistance**.

crawling, *n*—defect in which the wet film recedes from localized areas of the substrate (usually caused by insufficient wetting) leaving those areas uncoated. **D1848, D01.42**

curtaining—see **sag or sagging**.

density, *n*—the mass per unit volume of a substrate at a specified temperature and pressure; usually expressed in g/mL, kg/L, g/cm³, g/L, kg/m³ or lb/gal. See **specific gravity**. **D01.23, D01.24**

DISCUSSION—

(1) g/mL = kg/L = g/cm³; g/L = kg/m³. (2) Density (lb/gal) = Density (g/mL) × 8.345405 ... (3) The temperature should be 25 °C for best conformance with Test Method **D1475**. For liquids and solids, which are the usual concerns of Committee D01, the pressure need not be specified. (4) Density of water at 25 °C = 0.997044 g/mL = 8.32 lb/gal.

dirt—(for coatings) see **soil**.

dirt resistance, *n*—(for coatings) the ability of a coating to resist soiling by foreign material, other than microorganisms, deposited on or embedded in the dried coating.

distinctness-of-image gloss, *n*—the sharpness with which image outlines are reflected by the surface of an object.

dope, *n*—a composition, usually a cellulosic lacquer, for application on textiles and leathers.

drier, *n*—an additive that accelerates the drying of an oil, paint, printing ink, or varnish.

DISCUSSION—

Driers are usually metallic compositions and are available in both solid and liquid forms.

drying oil, *n*—an oil that possesses to a marked degree the property of readily taking up oxygen from the air and changing to a relatively hard, tough, elastic substance when exposed in a thin film to the air.

du Noüy ring—platinum wire ring.

durability, *n*—a relative term indicating degree of permanency. It may be applied to individual protective, decorative, or functional properties, for example, “the durability of gloss,” but if used in a general way, for example, “the excellent durability of a paint,” implies the ability of the described coating to retain, to the indicated degree, all the properties required for the continued service of the coating.

edge-tracking, *n*—a residual, discernible pattern in a roller-applied coating, characterized by trails from either or both ends of the roller.

efflorescence, *n*—a condition that occurs when soluble salts in a dry coating or the substrate migrate to the surface due to the movement of water through the film; characterized by a (commonly) white, nonuniform powder or crystalline incrustation, not removable with neutral water but usually removed with dilute mineral acid. **D1736, D1848, D01.42**

DISCUSSION—

The previously water-soluble salts become insoluble at the surface of the film due to reaction with carbon dioxide of the air.

emulsion paint—under **paint**, see *emulsion paint*.

[ASTM D16-24](https://standards.iteh.ai/catalog/standards/astm/eb891508-08e5-4d1b-9b01-835ea377c9f3/astm-d16-24)

<https://standards.iteh.ai/catalog/standards/astm/eb891508-08e5-4d1b-9b01-835ea377c9f3/astm-d16-24>

enamel, *n*—a paint that is characterized by an ability to form an especially smooth film.

epoxy resins—under **resin, synthetic**, see *epoxy resins*.

erosion resistance, *n*—the ability of a coating to withstand being worn away by chalking or by the abrasive action of water or windborne particles of grit. The degree of resistance is measured by the amount of the coating retained. See **abrasion resistance**.

ester gum—under **resin, synthetic**, see *ester gum*.

extended pigments, *n*—organic pigments diluted with an extender (for example, alumina trihydrate, blanc fixe, or calcium carbonate).

facade paint, *n*—a decorative and protective coating for exterior masonry surfaces—usually for buildings and walls.

DISCUSSION—

This is a term more commonly used in Europe.

filiform corrosion resistance, *n*—the ability of a coating to resist that type of corrosion of metal substrates characterized by a definite thread-like structure and directional growth that occurs under coatings.

filler, *n*—a pigmented composition for filling pores or irregularities in a surface preparatory to application of other finishes.

finish, *n*—(1) final coat in a paint system; at the termination of cure or drying; (2) sometimes refers to the entire coating system: the texture, color, and smoothness of a surface, and other properties affecting appearance.

fire-retardant, *adj*—a descriptive term which implies that the described product, under accepted methods of test, will significantly: (a) reduce the rate of flame spread on the surface of a material to which it has been applied, or (b) resist ignition when exposed to high temperatures, or (c) insulate a substrate to which it has been applied and prolong the time required to reach its ignition, melting, or structural-weakening temperature.

fire-retardant coating, *n*—a coating that will do one or more of the following: (1) reduce the flame spread on the substrate over which the coating is applied, sometimes at the sacrifice of the coating (see *intumescent coating*); (2) resist ignition of the substrate when exposed to high temperature; or (3) insulate the substrate to which the coating is applied and thereby prolong the time required to reach its ignition, melting or structural-weakening temperature.

flaking resistance, *n*—the ability of a coating to resist the actual detachment of film fragments either from the previously applied coating or the substrate. Flaking is generally preceded by cracking, checking, or blistering and is the result of loss of adhesion. Also known as scaling resistance.

flattening agent, *n*—a material added to paints, varnishes, and other coating materials to reduce the gloss of the dried film.

forced drying temperature, *n*—a temperature between room temperature and 150 °F (65 °C).

fossil resin, *n*—under **resin, natural**, see *fossil resin*.

gallon, U. S., *n*—a volume equal to 231 in.³ For paint, varnish, lacquer, and related products this is measured at 77 °F (25 °C).

glaze, *n*—a very thin coating of a paint product usually a semi-transparent coating tinted with Van Dyke brown, burnt sienna, or a similar pigment, applied on a previously painted surface to produce a decorative effect.

glazing compound, *n*—a dough-like material consisting of pigment and vehicle, used for sealing window glass in frames. It differs from putty in that it retains its plasticity for an extended period.

gouge hardness, *n*—the hardest pencil lead that will leave the coating/film uncut for a stroke length of at least 3 mm (1/8 in.) (0.125 in.) – see *pencil hardness*. **D3363**

grain, *n*—an inch-pound unit of weight, equal to 0.002285 avoirdupois oz (0.0648 g).

CED

grinding japan—see **japan, grinding**.

grit, *n*—coarse foreign particles in paint materials and coatings, often of irregular shape, that are hard, abrasive, and resistant to disintegration.

hiding power, *n*—the ability of a paint, or paint material as used, to hide or obscure (see *opacity*) a surface to which it has been uniformly applied.

DISCUSSION—

When expressed numerically, it is generally in terms of the number of square feet over which a gallon of paint, or pound of pigment, as used, can be uniformly spread to produce a specified contrast ratio (see **contrast ratio**). The term **covering power** has no specific relationship to hiding power, and actually has no precise meaning.

hue—under **color of an object**, see *hue*.