
Sprijemna zapenjala - Ugotavljanje ukrivljenosti

Touch and close fasteners - Determination of curvature

Haftverschlüsse - Bestimmung der Bogigkeit

Fermetures auto-agrippantes - Détermination du cintrage

Ta slovenski standard je istoveten z: EN 1416:1996

[SIST EN 1416:1999](https://standards.iteh.ai/catalog/standards/sist/d9a1b92d-946d-4b2e-8479-79a1b299e723/sist-en-1416-1999)

<https://standards.iteh.ai/catalog/standards/sist/d9a1b92d-946d-4b2e-8479-79a1b299e723/sist-en-1416-1999>

ICS:

61.040	Pokrivala. Dodatki k oblačilom. Spenjanje oblačil	Headgear. Clothing accessories. Fastening of clothing
--------	--	---

SIST EN 1416:1999**en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1416:1999

<https://standards.iteh.ai/catalog/standards/sist/d9a1b92d-946d-4b2e-8479-79a1b299e723/sist-en-1416-1999>

EUROPEAN STANDARD

EN 1416

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 1996

ICS 61.040

Descriptors: haberdashery, tapes, touch and close fasteners, bend tests, measurements, bending

English version

**Touch and close fasteners - Determination of
curvature**Fermetures auto-agrippantes - Détermination du
cintrage

Haftverschlüsse - Bestimmung der Bogigkeit

ITEH STANDARD PREVIEW
(standards.iteh.ai)SIST EN 1416:1999<https://standards.iteh.ai/catalog/standards/sist/d9a1b92d-946d-4b2e-8479-79a1b299e723/sist-en-1416-1999>

This European Standard was approved by CEN on 1996-09-14. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CENEuropean Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
prEN 1416:1996

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 248 "Textiles and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 1997, and conflicting national standards shall be withdrawn at the latest by May 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1416:1999

<https://standards.iteh.ai/catalog/standards/sist/d9a1b92d-946d-4b2e-8479-79a1b299e723/sist-en-1416-1999>

1 Scope

This European Standard specifies a method for measuring the curvature of each of the male and female tapes making up a touch and close fastener.

2 Normative reference

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 20139 Textiles - Standard atmospheres for conditioning and testing (ISO 139 : 1973).

3 Definition

For the purposes of this standard, the following definition applies:

3.1 Curvature : The curved deformation of a tape lying flat.

[SIST EN 1416:1999](https://standards.iteh.ai/catalog/standards/sist/d9a1b92d-946d-4b2e-8479-79a1b299e723/sist-en-1416-1999)

<https://standards.iteh.ai/catalog/standards/sist/d9a1b92d-946d-4b2e-8479-79a1b299e723/sist-en-1416-1999>

4 Principle

The curvature of a male or female tape of a touch and close fastener is measured.

5 Apparatus

5.1 A test board measuring (1200^{+10}_0) mm x (200^{+5}_0) mm with its median longitudinal axis traced and incorporating locating pins (see figure 1).

5.2 A polycarbonate transparent plastic sheet measuring (1200^{+10}_0) mm x (200^{+5}_0) mm of thickness $(2 \pm 0,1)$ mm and of density $1,20 \text{ kg/m}^3$ with locating notches (see figure 2).

5.3 A rule of minimum length of 1000 mm, capable of measuring to within 1 mm.

5.4 A set square of dimensions (100 x 150) mm with a scale accurate to the nearest 1 mm on its long side (see figure 3).

6 Test specimens

Cut three test specimens approximately the length of the test board 1200 mm in length from a tape.

7 Conditioning

Condition the test specimens for at least 24 h in accordance with the standard atmosphere for testing as specified in EN 20139. The test shall be carried out in this atmosphere.

8 Procedure

Lay one test specimen on the test board approximately along the median longitudinal axis.

Take the sheet of transparent plastic by its ends and lay it on the test specimen using the pins and notches so that it is fitted initially to the middle of the test specimen.

Place the rule on the transparent plastic sheet and line up the 0 mm and 1000 mm graduations with the inside edge of the tape as shown in figure 3.

Place the set square on the rule and measure the maximum distance in millimetres between the inside edge of the test specimen and rule (see figure 4).

Repeat this process for the other two test specimens.

9 Expression of results

Indicate each individual value to the nearest millimetre

<https://standards.iteh.ai/catalog/standards/sist/d9a1b92d-946d-4b2e-8479-79a1b299e723/sist-en-1416-1999>

10 Test report

Report the following information :

- reference to this European Standard;
- identification of the touch and close fastener tapes;
- date of the test;
- each individual value;
- any deviation from this European Standard and any incident likely to have affected the result.

Dimensions in millimetres




Figure 1 : Test board

Dimensions in millimetres




Figure 2 : Transparent plastics sheet




Figure 3 : Measurement of curvature