



Designation: C404 – 24

Standard Specification for Aggregates for Masonry Grout¹

This standard is issued under the fixed designation C404; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers aggregate for use in grout for masonry.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The text of this standard references notes and footnotes, which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this standard.

1.4 The following precautionary caveat pertains only to the test methods portion, Section 9 of the standard. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C33/C33M Specification for Concrete Aggregates

C40/C40M Test Method for Organic Impurities in Fine Aggregates for Concrete

C87/C87M Test Method for Effect of Organic Impurities in Fine Aggregate on Strength of Mortar

¹ This specification is under the jurisdiction of ASTM Committee C12 on Mortars and Grouts for Unit Masonry and is the direct responsibility of Subcommittee C12.04 on Specifications for Aggregates for Mortars.

Current edition approved Jan. 15, 2024. Published January 2024. Originally approved in 1957. Last previous edition approved in 2018 as C404–18. DOI: 10.1520/C0404-24.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C88/C88M Test Method for Soundness of Aggregates by Use of Sodium Sulfate or Magnesium Sulfate
C117 Test Method for Materials Finer than 75- μ m (No. 200) Sieve in Mineral Aggregates by Washing
C123/C123M Test Method for Lightweight Particles in Aggregate
C127 Test Method for Relative Density (Specific Gravity) and Absorption of Coarse Aggregate (Withdrawn 2024)³
C128 Test Method for Relative Density (Specific Gravity) and Absorption of Fine Aggregate
C136/C136M Test Method for Sieve Analysis of Fine and Coarse Aggregates
C142/C142M Test Method for Clay Lumps and Friable Particles in Aggregates
C144 Specification for Aggregate for Masonry Mortar
C476 Specification for Grout for Masonry
C1180 Terminology of Mortar and Grout for Unit Masonry
D75/D75M Practice for Sampling Aggregates

3. Terminology

3.1 For definitions of terms used in this specification, refer to Terminology C1180.

4. General Characteristics

4.1 Aggregates shall consist of natural sand or manufactured sand, used alone or in combination with coarse aggregate as described in this specification. Manufactured sand is the product obtained by crushing stone, gravel, or air-cooled iron blast-furnace slag. Coarse aggregate shall consist of crushed stone, gravel, or air-cooled iron blast-furnace slag processed to assure suitable gradation.

NOTE 1—Care should be taken to ensure a suitable particle shape, since excessive quantities of flat and elongated particles have historically caused problems with workability.

5. Grading

5.1 Grading shall conform to the requirements in Table 1 or shall comply with the requirements of 5.2.

NOTE 2—Size No. 1 is that specified for concrete sand in Specification

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard