



## Designation: E785 – 81 (Reapproved 2024)

# Standard Specification for Crucibles, Ignition, Laboratory, Metal<sup>1</sup>

This standard is issued under the fixed designation E785; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This specification covers two types of metal ignition crucibles, nickel or platinum, complete with covers, for laboratory use.

1.2 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[B162 Specification for Nickel Plate, Sheet, and Strip](#)

2.2 *Federal Standards:*<sup>3</sup>

[Fed. Std. No. 123 Marking for Shipment \(Civil Agencies\)](#)

2.3 *Military Standards:*<sup>3</sup>

[MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes](#)

[MIL-STD-129 Marking for Shipment and Storage](#)

[MIL-STD-1188 Commercial Packaging of Supplies and Equipment](#)

## 3. Classification

3.1 *Types and Capacities*—The crucibles shall be furnished in one or more of the following types or capacities as specified (see S2.1).

3.1.1 *Type I*—Nickel.

Capacity: 100 mL  
250 mL

3.1.2 *Type II*—Platinum.

Capacity: 20 mL

## 4. Materials

4.1 *Type I*—Crucibles and covers shall be made from 99.4 % nickel, spun and hardened in conformance with Specification [B162](#).

4.2 *Type II*—Crucibles and covers shall be made from 99.9 % platinum plus iridium, with the iridium content of not more than 0.4 %.

## 5. Physical Requirements

5.1 *Crucibles* shall have a standard shape with a flat base to give a firm and stable resting surface. The side wall shall form a sloping and convex surface extending up to the brim. Crucibles shall be of one-piece construction.

5.2 *Covers* shall be flat, sunken in the center, and shall have an extension to serve as a handle. The sunken area in the center shall fit inside the crucible.

## 6. Dimensions, Mass, and Permissible Variations

6.1 *Type I* crucibles and covers shall conform to the requirements of [Table 1](#).

6.2 *Type II Crucibles and Covers:*

6.2.1 Type II crucibles shall conform to the requirements of [Table 2](#).

6.2.2 Type II covers shall conform to the requirements of [Table 3](#).

## 7. Workmanship

7.1 Crucibles and covers shall be free of defects (scratches, dents, discolorations) or contamination (grease, oil, foreign matter) that detract from their appearance or that impair their serviceability.

## 8. Keywords

8.1 crucibles; ignition; nickel; platinum

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee E41 on Laboratory Apparatus and is the direct responsibility of Subcommittee E41.01 on Laboratory Ware and Supplies.

Current edition approved Feb. 1, 2024. Published February 2024. Originally approved in 1981. Last previous edition approved in 2017 as E785 – 81 (2017). DOI: 10.1520/E0785-81R24.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.