



Standard Specification for Polyethylene of Raised Temperature (PE-RT) Systems for Non-Potable Water Applications¹

This standard is issued under the fixed designation F2623; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification establishes requirements for polyethylene of raised temperature (PE-RT) systems for non-potable water applications. System components include PE-RT SDR 9 tubing, manifolds, fittings, valves and other appurtenances, and mechanical and fusion joining. PE-RT tubing is pressure rated for water at 73 °F (23 °C) and 180 °F (82 °C), and optionally 140 °F (60 °C). Included are requirements for materials, workmanship, dimensions and tolerances, product tests, and markings, and an optional barrier layer. Fittings include mechanical insert fittings and fusion fittings.

1.2 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3.1 Values in parentheses are appropriately rounded for accuracy and precision and are not exact equivalents.

1.4 The tubing systems produced under this specification are intended for use in the transport of non-potable water such as hydronic and irrigation systems.

1.4.1 PE-RT tubing containing an outside surface or mid-wall gas barrier layer or both is acceptable.

1.4.2 PE-RT systems under this standard are not intended for use in the transport of potable water. See Specification F2769 for PE-RT potable water distribution systems.

1.5 The following safety hazards caveat pertains only to the test methods portion, Section 7, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and*

environmental practices and determine the applicability of regulatory limitations prior to use.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D618 Practice for Conditioning Plastics for Testing

D1435 Practice for Outdoor Weathering of Plastics

D1598 Test Method for Time-to-Failure of Plastic Pipe Under Constant Internal Pressure

D1599 Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings

D1600 Terminology for Abbreviated Terms Relating to Plastics (Withdrawn 2024)³

D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings

D2565 Practice for Xenon-Arc Exposure of Plastics Intended for Outdoor Applications

D2683 Specification for Socket-Type Polyethylene Fittings for Outside Diameter-Controlled Polyethylene Pipe and Tubing

D2837 Test Method for Obtaining Hydrostatic Design Basis for Thermoplastic Pipe Materials or Pressure Design Basis for Thermoplastic Pipe Products

D3261 Specification for Butt Heat Fusion Polyethylene (PE) Plastic Fittings for Polyethylene (PE) Plastic Pipe and Tubing

D3350 Specification for Polyethylene Plastics Pipe and Fittings Materials

D3895 Test Method for Oxidative-Induction Time of Polyolefins by Differential Scanning Calorimetry

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.26 on Olefin Based Pipe.

Current edition approved Feb. 1, 2024. Published February 2024. Originally approved in 2007. Last previous edition approved in 2023 as F2623–23. DOI: 10.1520/F2623-24.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

- F412** Terminology Relating to Plastic Piping Systems
- F1055** Specification for Electrofusion Type Polyethylene Fittings for Outside Diameter Controlled Polyethylene and Crosslinked Polyethylene (PEX) Pipe and Tubing
- F1281** Specification for Crosslinked Polyethylene/Aluminum/Crosslinked Polyethylene (PEX-AL-PEX) Pressure Pipe
- F1282** Specification for Polyethylene/Aluminum/Polyethylene (PE-AL-PE) Composite Pressure Pipe
- F1290** Practice for Electrofusion Joining Polyolefin Pipe and Fittings
- F1807** Specification for Metal Insert Fittings Utilizing a Copper Crimp Ring, or Alternate Stainless Steel Clamps, for SDR9 Cross-linked Polyethylene (PEX) Tubing and SDR9 Polyethylene of Raised Temperature (PE-RT) Tubing
- F2080** Specification for Cold-Expansion Fittings with Metal Compression-Sleeves for Crosslinked Polyethylene (PEX) Pipe and SDR9 Polyethylene of Raised Temperature (PE-RT) Pipe
- F2159** Specification for Plastic Insert Fittings Utilizing a Copper Crimp Ring, or Alternate Stainless Steel Clamps for SDR9 Crosslinked Polyethylene (PEX) Tubing and SDR9 Polyethylene of Raised Temperature (PE-RT) Tubing
- F2620** Practice for Heat Fusion Joining of Polyethylene Pipe and Fittings
- F2735** Specification for Plastic Insert Fittings For SDR9 Cross-linked Polyethylene (PEX) and Polyethylene of Raised Temperature (PE-RT) Tubing
- F2769** Specification for Polyethylene of Raised Temperature (PE-RT) Plastic Hot and Cold-Water Tubing and Distribution Systems
- G155** Practice for Operating Xenon Arc Lamp Apparatus for Exposure of Materials
- 2.2 *ANSI Standard:*
- B36.10** Standards Dimensions of Steel Pipe (NTS)⁴
- 2.3 *Federal Standard:*
- FED-STD-123** Marking for Shipment (Civil Agencies)⁵
- 2.4 *Military Standard:*
- MIL-STD-129** Marking for Shipment and Storage⁵
- 2.5 *PPI Standard:*⁶
- PPI TR-3** Policies and Procedures for Developing Hydrostatic Design Basis (HDB), Pressure Design Basis (PDB), Strength Design Basis (SDB), and Minimum Required Strength (MRS) Ratings for Thermoplastic Piping Materials or Pipe
- PPI TR-4** PPI Listing of Hydrostatic Design Basis (HDB), Strength Design Basis (SDB), Pressure Design Basis (PDB) and Minimum Required Strength (MRS) Ratings for Thermoplastic Piping Materials or Pipe

2.6 *ISO Standard:*⁷

- ISO 16871** Plastics piping and ducting systems—Plastics pipes and fittings—Method for exposure to direct (natural) weathering
- ISO 17455** - Plastics piping systems — Multilayer pipes — Determination of the oxygen permeability of the barrier pipe

3. Terminology

3.1 *Definitions*—Definitions are in accordance with Terminology **F412**, and abbreviations are in accordance with Terminology **D1600**, unless otherwise specified. The abbreviation for polyethylene of raised temperature is PE-RT. Plastic tubing denotes a particular diameter schedule of plastic pipe in which the outside diameter conforms to ANSI B36.10.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *barrier layer, n*—a very thin polymeric film within the tube wall or around the circumference of the tubing which provides a means for greatly reducing the transmission of oxygen from the atmosphere and into the fluid within the tube.

3.2.2 *fitting, n*—an appurtenance such as coupling, elbow or tee used to connect tubing or as an accessory to tubing.

3.2.3 *hydrostatic design stress (HDS)*—the estimated maximum tensile stress the material is capable of withstanding continuously with a high degree of certainty that failure of the tube will not occur. This stress is circumferential when internal hydrostatic water pressure is applied.

3.2.4 *manifold, n*—an appurtenance that has at least one inlet and multiple outlets.

3.2.5 *pressure rating (PR)*—the estimated maximum water pressure the tube is capable of withstanding continuously with a high degree of certainty that failure of the tube will not occur.

3.2.6 *relation between dimensions, hydrostatic design stress, and pressure rating*—the following expression, commonly known as the ISO equation,⁸ is used in this specification to relate dimensions, hydrostatic design stress, and pressure rating:

$$2S/P = (D_o/t) - 1 \quad (1)$$

or

$$2S/P = R - 1$$

where:

S = hydrostatic design stress, psi (or MPa) = Hydrostatic Design Basis \times 0.63,

P = pressure rating, psi (or MPa),

D_o = average outside diameter, in. (or mm),

t = wall thickness, in. (or mm), and

R = standard dimension ratio, SDR.

3.2.7 *standard dimension ratio (SDR)*—the ratio of outside diameter to wall thickness. For PE-RT-tubing, it is calculated by dividing the average outside diameter of the tubing in inches

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, <http://quicksearch.dla.mil>.

⁶ Available from Plastics Pipe Institute (PPI), 105 Decker Court, Suite 825, Irving, TX 75062, <http://www.plasticpipe.org>.

⁷ Available from International Organization for Standardization (ISO), ISO Central Secretariat, BIBC II, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, <http://www.iso.org>.

⁸ ISO 161-1.

or in millimeters by the minimum wall thickness in inches or millimeters. If the wall thickness calculated by this formula is less than 0.070 in. (1.78 mm) it shall be arbitrarily increased to 0.070 in. except for sizes NTS 1/8 and smaller. The SDR values shall be rounded to the nearest 0.5.

3.2.8 *standard thermoplastic material designated code*—the pipe material designation code shall consist of the abbreviation for the type of plastic (PE) followed by Arabic numerals which describe the short term properties in accordance with Specification **D3350**, the hydrostatic design stress for water at 73 °F (23 °C) in units of 100 psi with any decimal figures dropped. Where the hydrostatic design stress code contains less than two figures, a zero is used before the number.

3.2.9 *system components, n*—fittings and manifolds.

4. Classification

4.1 *Tubing*—This specification covers PE-RT tubing in one standard dimension ratio, 9.0, and nominal tubing sizes from NTS 1/8 through NTS 6 having pressure ratings based on water at 73 °F (23 °C) and 180 °F (82 °C) and optionally at 140 °F (60 °C), with a maximum continuous use temperature of 180 °F (82 °C). The pressure ratings decrease as the temperature is increased and is uniform for all nominal tubing sizes.

4.2 *System Components*—This specification covers system components, such as fittings and manifolds, for use in systems with PE-RT tubing on the basis of the requirements of this specification.

4.3 *Standard Thermoplastic Pipe Dimension Ratio (SDR)*—This specification covers PE-RT tubing in one standard dimension ratio (SDR 9) and nominal tubing sizes (NTS) from 1/8 in. through 6 in. with a maximum continuous use temperature that shall be 180 °F (82.2 °C). The pressure ratings are uniform for all nominal tubing sizes.

5. Materials and Manufacture

5.1 PE-RT Tubing:

5.1.1 The PE-RT compound used to make tubing shall have hydrostatic design basis (HDB) ratings at 73 °F (23 °C), 140 °F (60 °C) and 180 °F (82 °C) in accordance with **Table 1** that are determined in accordance PPI TR-3.

5.1.1.1 Ratings at 140 °F (60 °C) that are interpolated in accordance with PPI TR-3 shall be acceptable.

5.1.1.2 Polyethylene compound shall comply with *Requirements For Polyethylene (PE) Materials To Qualify For A Higher Design Factor* in PPI TR-3, and shall have a 73 °F (23 °C) hydrostatic design stress (HDS) rating of 800 psi (5.52 MPa).

5.1.1.3 Polyethylene compound shall comply with Specification **D3350** cell classification requirements in accordance with **Table 2**.

5.1.1.4 Polyethylene compound shall comply with Specification **D3350** requirements for thermal stability, brittleness temperature and tensile elongation at break.

5.1.2 *Barrier Layer*—It is optional and acceptable for PE-RT tubing to incorporate a gas barrier layer in the mid-wall or outer wall or both, of non-PE-RT material for the purpose of reducing gas transmission through the tubing wall. A barrier layer incorporating a material to bond between PE-RT material and gas barrier layer material shall be acceptable.

5.1.2.1 The material used for an optional oxygen barrier layer shall be ethylene-vinyl alcohol copolymer (EVOH).

NOTE 1—Gas barrier layer material and bonding material if used, do not contribute to the internal pressure capacity of PE-RT tubing.

5.1.2.2 The EVOH material selected shall result in multi-layer tubing that meets the adhesion and permeation requirements specified in **A1.3**.

5.2 *Rework Material*—Clean PE-RT material that complied with **5.1.1** through **5.1.1.4** when originally manufactured by the same manufacturer shall be acceptable as rework material when blended with new PE-RT compound that complies with **5.1.1** through **5.1.1.4**. Rework material shall not contain barrier layer materials.

5.2.1 PE-RT tubing containing rework material and system components containing rework material shall meet the requirements of this specification.

5.3 *Fittings*—Fitting materials shall meet the applicable material requirements of at least one of the Specifications **D2683**, **D3261**, **F1055**, **F1807**, **F2080**, **F2159**, or **F2735**. Polyethylene material used in fusion fittings shall meet the requirements of **5.1.1** through **5.1.1.4**.

6. Requirements

6.1 *Workmanship*—The tubing and fittings shall be homogeneous throughout and free of visible cracks, holes, foreign inclusions, or other defects. The tubing shall be as uniform as commercially practicable in color, opacity, density, and other physical properties. The walls of fittings and manifolds shall be free of cracks, holes, blisters, voids, foreign inclusions, or other defects that are visible to the naked eye and may affect fitting integrity. All sealing surfaces shall be smooth and free of foreign material.

6.2 Dimensions and Tolerances:

TABLE 1 Minimum Hydrostatic Design Basis at Different Temperatures

Rated Temperature		Hydrostatic Design Basis	
°F	(°C)	psi	(MPa)
73	(23)	1250	(8.62)
140	(60)	800	(5.52)
180	(82)	630	(4.34)

TABLE 2 Required Specification **D3350 Cell Classifications for PE-RT**

Physical Property	Required Cell Classification
Density	2, 3, or 4
Melt index	2, 3, 4, or 5
Flexural modulus	3 or 4
Tensile strength	2 or 3
Slow crack growth resistance	7
Hydrostatic design basis	3 or 4

6.2.1 *Outside Diameters of Tubing*—The outside diameters and tolerances shall be as shown in Table 3, when measured in accordance with 7.4 and 7.4.1. Optional barrier layer(s) shall not increase the outside diameter beyond the Table 3 maximum outside diameter.

6.2.2 *Wall Thickness of Tubing*—The total wall thickness and tolerances shall be as shown in Table 4, when measured in accordance with 7.4 and 7.4.2.

6.2.2.1 *Layers*—PE-RT tubing that incorporates an EVOH oxygen barrier layer for the purposes of reducing the transmission rate of oxygen through the PE-RT wall and into the fluid medium shall comply with the dimensional, performance and marking requirements in accordance with Annex A1.

6.2.3 *Dimensions of Fittings*—The dimensions and tolerances of fittings shall meet the specific requirements contained in Specifications D2683, D3261, F1055, F1807, F2080, F2159, F2735, or other recognized specification.

6.3 *Sustained Pressure*—The tubing and system components, assembled using the system component manufacturer’s instructions and tested as assemblies, shall not fail, balloon, burst, or weep as defined in Test Method D1598, at the test pressures given in Table 5 when tested in accordance with 7.5.

6.4 *Burst Pressure*—The tubing and system components, assembled using the system component manufacturer’s instructions and tested as assemblies, shall meet the minimum burst pressures as given in Table 6 without failure, when determined in accordance with 7.6.

6.4.1 *Manifolds*—If the manifold has more than one connection size, the test pressure selected from Table 6 shall be based on the largest nominal tubing connection.

6.5 *Oxidative Resistance*—PE-RT tubing shall have a minimum extrapolated time-to-failure of 50 years when tested and evaluated in accordance with 7.7.

6.6 *Bent Tube*—PE-RT tubing, nominal sizes, up to and including NTS 1, can be installed bent by the technique described in Appendix X3 provided the following requirements

TABLE 4 Wall Thickness and Tolerances for PE-RT SDR 9 Tubing^A

NTS, Nominal Tubing	Minimum Wall Thickness		Tolerance	
	in.	(mm)	in.	(mm)
1/8	0.047 ^B	(1.19) ^B	+0.007	(+0.18)
1/4	0.062 ^B	(1.57) ^B	+0.010	(+0.25)
5/16	0.064	(1.63)	+0.010	(+0.25)
3/8	0.070 ^B	(1.78) ^B	+0.010	(+0.25)
1/2	0.070 ^B	(1.78) ^B	+0.010	(+0.25)
5/8	0.083	(2.12)	+0.010	(+0.25)
3/4	0.097	(2.47)	+0.010	(+0.25)
1	0.125	(3.18)	+0.013	(+0.33)
1 1/4	0.153	(3.88)	+0.015	(+0.38)
1 1/2	0.181	(4.59)	+0.019	(+0.48)
2	0.236	(6.00)	+0.024	(+0.61)
2 1/2	0.292	(7.41)	+0.030	(+0.76)
3	0.347	(8.82)	+0.033	(+0.84)
3 1/2	0.403	(10.23)	+0.035	(+0.89)
4	0.458	(11.64)	+0.040	(+1.02)
4 1/2	0.514	(13.05)	+0.045	(+1.14)
5	0.569	(14.46)	+0.050	(+1.27)
6	0.681	(17.29)	+0.060	(+1.52)

^A The minimum is the lowest total wall thickness of PE-RT material in the tubing wall at any cross section. The maximum permitted wall thickness, at any cross section, is the minimum wall thickness plus the stated tolerance. All tolerances are on the plus side of the minimum requirement. The presence of optional barrier layer(s) shall not reduce the total thickness of PE-RT material in the tubing wall below the minimum, nor above the maximum (maximum = minimum + tolerance).
^B For tubing nominal sizes of 1/2 and below, wall thickness minimums are not functions of SDR.

are met. Bent tubing, with a radius of 6 times the outside diameter and consisting of a continuous bend length inducing not less than 90° angle, shall meet the 180 °F (82 °C) minimum hydrostatic sustained pressure strength requirements shown in Table 5 when tested in accordance with 7.8. The bend length and bend angle is kept throughout the testing period by rigid secures immediately outside the bend. The minimum test duration shall be 1000 h without failure.

NOTE 2—PE-RT tubing, nominal sizes larger than NTS 1, is typically installed as main distribution lines and is installed in straight runs. Fittings are used when a change in direction of 90° or greater and a bend radius of

TABLE 3 Outside Diameters and Tolerances for PE-RT Tubing

NTS, Nominal Tubing Size	Average Outside Diameter		Tolerances for Average Diameter		Out-of-Roundness ^A	
	in.	(mm)	in.	(mm)	in.	(mm)
1/8	0.250	(6.35)	±0.003	(±0.08)	0.008	(0.20)
1/4	0.375	(9.52)	±0.003	(±0.08)	0.008	(0.20)
5/16	0.430	(10.92)	±0.003	(±0.08)	0.008	(0.20)
3/8	0.500	(12.70)	±0.003	(±0.08)	0.012	(0.32)
1/2	0.625	(15.88)	±0.004	(±0.10)	0.016	(0.40)
5/8	0.750	(19.05)	±0.004	(±0.10)	0.016	(0.40)
3/4	0.875	(22.22)	±0.004	(±0.10)	0.016	(0.40)
1	1.125	(28.58)	±0.005	(±0.12)	0.020	(0.48)
1 1/4	1.375	(34.92)	±0.005	(±0.12)	0.020	(0.48)
1 1/2	1.625	(41.28)	±0.006	(±0.16)	0.024	(0.60)
2	2.125	(53.98)	±0.006	(±0.16)	0.030	(0.76)
2 1/2	2.625	(66.68)	±0.007	(±0.18)	0.038	(0.95)
3	3.125	(79.38)	±0.008	(±0.20)	0.045	(1.14)
3 1/2	3.625	(92.08)	±0.008	(±0.20)	0.046	(1.16)
4	4.125	(104.78)	±0.009	(±0.23)	0.052	(1.32)
4 1/2	4.625	(117.48)	±0.009	(±0.23)	0.059	(1.49)
5	5.125	(130.18)	±0.010	(±0.25)	0.065	(1.65)
6	6.125	(155.58)	±0.011	(±0.28)	0.072	(1.83)

^A The Out-of-Roundness specification applies only to tubing prior to coiling.

TABLE 5 Minimum Sustained Water Pressure Test Condition for PE-RT SDR 9 Tubing and Systems

NTS, Nominal Tubing Size	Pressure Required for Test, psig ^A (MPa)					
	73 °F (23 °C)	140 °F (60 °C) (optional)	180 °F (82 °C)	140 °F (60 °C) (optional)	180 °F (82 °C)	140 °F (60 °C) (optional)
1/8	600 (4.14)	405 (2.79)	300 (2.07)	405 (2.79)	300 (2.07)	405 (2.79)
1/4	515 (3.55)	350 (2.41)	260 (1.79)	350 (2.41)	260 (1.79)	350 (2.41)
5/16	455 (3.14)	310 (2.14)	230 (1.59)	310 (2.14)	230 (1.59)	310 (2.14)
3/8	425 (2.93)	285 (1.97)	215 (1.48)	285 (1.97)	215 (1.48)	285 (1.97)
1/2	330 (2.28)	220 (1.52)	165 (1.14)	220 (1.52)	165 (1.14)	220 (1.52)
5/8 and larger	325 (2.24)	220 (1.52)	165 (1.14)	220 (1.52)	165 (1.14)	220 (1.52)

^A The fiber stresses used to derive these test pressures are:
 at 73 °F (23 °C) 1300 psi (8.96 MPa)
 at 140 °F (60 °C) 880 psi (6.07 MPa)
 at 180 °F (82 °C) 650 psi (4.48 MPa)

TABLE 6 Burst Pressure Requirements for Water at Different Temperatures for PE-RT SDR 9 Tubing and Systems

NTS, Nominal Tubing Size	Minimum Burst Pressures at Different Temperatures, psig ^A (MPa)					
	73 °F (23 °C)	140 °F (60 °C) (optional)	180 °F (82 °C)	140 °F (60 °C) (optional)	180 °F (82 °C)	140 °F (60 °C) (optional)
1/8	880 (6.07)	575 (3.96)	335 (2.31)	575 (3.96)	335 (2.31)	575 (3.96)
1/4	755 (5.21)	490 (3.38)	285 (1.97)	490 (3.38)	285 (1.97)	490 (3.38)
5/16	665 (4.59)	435 (3.00)	250 (1.72)	435 (3.00)	250 (1.72)	435 (3.00)
3/8	620 (4.27)	405 (2.79)	235 (1.62)	405 (2.79)	235 (1.62)	405 (2.79)
1/2	480 (3.31)	315 (2.17)	180 (1.24)	315 (2.17)	180 (1.24)	315 (2.17)
5/8 and larger	475 (3.28)	310 (2.14)	180 (1.24)	310 (2.14)	180 (1.24)	310 (2.14)

^A The fiber stresses used to derive these test pressures are:
 at 73 °F (23 °C) 1900 psi (13.10 MPa)
 at 140 °F (60 °C) 1240 psi (8.55 MPa)
 at 180 °F (82 °C) 720 psi (4.96 MPa)

layer to the transported fluid may degrade barrier layer performance.

6.8.2 Electrofusion:

6.8.2.1 Electrofusion joints between tubing and Specification **F1055** fittings shall be made in accordance with Practice **F1290** and the fitting manufacturer's instructions.

6.8.2.2 Qualification of the fitting with PE-RT tubing shall be performed in accordance with **6.3**, **6.4**, and Specification **F1055**.

6.8.3 Socket Fusion:

6.8.3.1 Socket fusion joints between tubing and Specification **D2683** fittings shall be made in accordance with Practice **F2620** and the fitting manufacturer's instructions.

6.8.3.2 Qualification of socket fusion fittings with PE-RT shall be performed in accordance with **6.3**, **6.4** and the System Pressure Test requirements of Specification **D2683**.

6.8.4 Butt Fusion:

6.8.4.1 Butt fusion joints between tubing and Specification **D3261** fittings shall be made in accordance with Practice **F2620** and the fitting manufacturer's instructions.

6.8.4.2 Qualification of butt fusion fittings with PE-RT shall be performed in accordance with **6.3**, **6.4**, and the System Pressure Test requirements of Specification **D3261**.

6.9 Joints - Mechanical Insert:

6.9.1 Mechanical insert fittings shall be installed in accordance with the fitting manufacturer's installation instructions.

6.9.2 Qualification of mechanical insert fittings with PE-RT tubing shall be in accordance with **6.3**, **6.4**, and **6.9.3**.

6.9.3 *Thermo-cycling*—Tubing and mechanical insert joint system components, assembled using the system component manufacturer's instructions, shall not leak after completion of 1000 cycles between the temperatures of 60 °F (16 °C) and 180 °F (82 °C) when tested in accordance with **7.7**.

NOTE 4—Tests applicable to tubing and fittings assemblies are intended to be performance qualification tests of joints and not tests required of each fitting configuration.

7. Test Methods

7.1 *Conditioning*—Condition the specimens at 73 ± 4 °F (23 ± 2 °C) and 50 ± 10 % relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice **D618**, for those tests where conditioning is required. In cases of disagreement, the tolerances shall be ±2 °F (±1 °C) and ±5 % relative humidity.

7.2 *Test Conditions*—Conduct the test in the standard laboratory atmosphere of 73 ± 4 °F (23 ± 2 °C) and 50 ± 10 % relative humidity, unless otherwise specified in the test methods or in this specification. In cases of disagreement, the tolerances shall be ±2 °F (±1 °C) and ±5 % relative humidity.

7.3 *Sampling*—A sufficient quantity of tubing or systems components, as agreed upon by the purchaser and the seller, shall be selected and tested to determine conformance with this specification. In the case of no prior agreement, random samples selected by the testing laboratory shall be deemed adequate.

7.3.1 *Test Specimens*—Unless otherwise specified in this standard or as agreed upon by the purchaser and the seller, the quantity and size of the specimens to be tested shall be as specified by the test method referred to in this standard.

less than 6 times the outside diameter is needed. The test procedures in **6.6** are intended to evaluate PE-RT tubing installed in tight bend applications in accordance with the procedure in **Appendix X3**. This application applies to tubing up to and including nominal size 1 only.

6.7 *Adhesion Test*—Tubing that incorporates an optional middle or outer layer shall not show any delamination when tested in accordance with the adhesion test of Specification **F1282**.

6.8 *Joints - Fusion*—Tubing fusion joining using Specification **F1055** electrofusion fittings, Specification **D2683** socket fusion fittings or Specification **D3261** butt heat fusion fittings shall be acceptable. The tubing manufacturer shall indicate the recommended fitting types for use with their tubing as indicated in **9.2**.

6.8.1 *Fusion Joints*—Tubing with external barrier layers shall only be joined by fusion if recommended by the tubing manufacturer and where tubing is prepared so as to completely remove the barrier layer within the fusion zone per the tubing manufacturer's recommendations. Tubing with mid-wall barrier layers shall not be joined with fusion fittings.

NOTE 3—An external barrier layer will compromise electrofusion or socket fusion joining if not completely removed. A midwall barrier layer will compromise butt fusion joining. Exposure of the mid-wall barrier

Manifolds with integral shut-offs (valves) shall be in the full-open or unrestricted position.

7.4 Dimensions and Tolerances of tubing—Use any length of tubing to determine the dimensions. Measure in accordance with Test Method **D2122**.

7.4.1 Outside Diameter—Measure the outside diameter of the tubing in accordance with Test Method **D2122**. The referee method of measurement is to be by circumferential wrap tape. The tolerance for out-of-roundness shall apply only to tubing prior to shipment. Averaging micrometer or vernier caliper measurements, four (4) maximum and minimum diameter measurements at any cross section, may be used for quality control checks if desired.

7.4.2 Wall Thickness—Make micrometer measurements of the wall thickness in accordance with Test Method **D2122** to determine the maximum and minimum values. Measure the wall thickness at both ends of the tubing to the nearest 0.001 in. (0.025 mm).

7.4.3 Barrier Layer and Bonding/Tie Layer(s)—Make measurements of the layer or layers using either a video microscope, a microscope with graduations or optical comparator to determine the maximum and minimum values. Precision of layer measurements shall be at minimum 0.0005 in. (0.013 mm). Maximum and minimum barrier layer thicknesses inclusive of bonding/tie layer(s) shall be determined by 2 or more equally spaced samplings around the pipe circumference. For the purposes of this standard the minimum PE-RT wall shall be calculated as follows:

7.4.3.1 Minimum PE-RT wall thickness = Minimum total wall thickness per **7.4.2** minus the average of the measured barrier and bonding/tie layer thicknesses per **7.4.3**.

NOTE 5—It has been common practice to apply Merbromin (marketed as Mercurochrome trade name) or similar chemical die solution to the cut end of the pipe in order to add a color tint to the an otherwise clear EVOH layer.

7.5 Sustained Pressure Test—Select the test specimens at random. Test assemblies of at least six system component specimens and six tubing specimens, with at least six joints, per Test Method **D1598** in water at 73 °F (23 °C) and 180 °F (82 °C) as shown in **Table 5**. If the optional 140 °F (60 °C) rating is desired, perform an additional test at 140 °F (60 °C) in accordance with **Table 5**. Each specimen of tubing shall be at least five times the nominal diameter in length and not less than 12 in. (30 cm) or more than 3.0 ft (90 cm) between end closures. Maintain the specimens at the pressures indicated for the appropriate temperatures for a period of 1000 h. Failure of two of the six specimens tested at any temperature constitutes failure in the test. Failure of one of six specimens tested at any temperature is cause for retest of six additional specimens at that temperature. Failure of one of six specimens tested at any temperature in retest constitutes failure in the test. Failure of the tubing shall be defined in accordance with Test Method **D1598** and shall include leakage or separation at any of the joints. Delamination of the tubing shall constitute failure.

7.6 Burst Pressure—Determine the sample complies with the minimum burst pressure requirements by testing at least five assemblies of system component specimens and five

tubing specimens, with a minimum total of five joints, in accordance with Test Method **D1599** Method B. The pressure values are given in **Table 6**. If the optional 140 °F rating is desired, perform a test at 140 °F (60 °C) in accordance with **Table 5**. Each specimen of tubing shall be at least five times the nominal diameter in length and not less than 12 in. (2530 cm) or more than 3.0 ft (90 cm) between joints. Failure shall be defined in accordance with Test Method **D1599** and shall include leakage or separation at any of the joints.

7.7 Oxidative Resistance—The test shall be conducted and the extrapolated time-to-failure shall be determined in accordance with Test Method **F2023**. The test fluid shall be prepared in accordance with 9.1.1 of Test Method **F2023**. The extrapolated time-to-failure shall be calculated in accordance with 13.3 of Test Method **F2023**.

7.7.1 Significance—The test need only be performed once and only once for the original validation of a compound tested in the form of a tube. A compound is defined as the PE-RT resin and the stabilization system. It shall not be required to perform plant or extrusion line verification testing.

7.8 Bent Tube Test—Conduct the sustained pressure test on one bent tube sample in accordance with Test Method **D1598**. Test temperature shall be 180 °F (82 °C).

7.9 Thermo-cycling:

7.9.1 Summary of Test Method—This test method describes a pass-fail test for thermally cycling PE-RT tubing and mechanical fittings over a critical temperature range for a selected number of cycles while subjected to a nominal internal pressure. This test method provides a measure of resistance to failure due to the combined effects of differential thermal expansion and creep for PE-RT tubing and fittings intended for continuous use up to and including 180 °F (82 °C).

7.9.2 Apparatus—A nitrogen or air source capable of maintaining an internal pressure of 100 psig \pm 10 psig (0.69 MPa \pm 0.07 MPa) within the specimens is required. The immersion system shall consist of two water reservoirs controlled at 60 °F \pm 4 °F (16 °C \pm 2 °C) and 180 °F \pm 4 °F (82 °C \pm 2 °C). The specimen shall be cycled from one reservoir to the other or the hot and cold water shall be alternately cycled over the test specimens automatically and returned to the proper reservoirs.

NOTE 6—Automatic cycling may be accomplished by pumping from each reservoir, through a delivery system having timer-actuated valves, to a specimen water trough having synchronized, timer-actuated return drains. Any automatic apparatus shall provide for complete immersion of the test specimen in the trough.

7.9.3 Sampling and Specimen Preparation—Prepare assemblies with at least 6 joints from randomly selected tubing and system component specimens assembled per the system component manufacturer's instructions. Each specimen of tubing shall be at least five times the nominal diameter in length and not less than 12 in. (25 cm) or more than 3.0 ft (90 cm) between end closures. Close the specimen assembly with any suitable end closures that allow "free-end" mounting and will not leak under the thermo-cycling conditions, and connect the specimen assembly to the pressure source.

7.9.3.1 Manifolds with integral shut-offs (valves) shall be tested in the open or unrestricted position.