



Designation: ~~D6787/D6787M—02 (Reapproved 2023)~~ D6787/D6787M – 24

Standard Specification for Repositionable Note Pad¹

This standard is issued under the fixed designation D6787/D6787M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers pads of repositionable, colored, note paper. Each sheet has a strip of pressure-sensitive adhesive on the back side.

1.2 The values stated in either SI or inch-pound units are to be regarded separately as standard. The values stated in each system are not exact equivalents; therefore, each system must be used independently, without combining values in any way.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[D3715/D3715M Practice for Quality Assurance of Pressure-Sensitive Tapes](#)

[D3951 Practice for Commercial Packaging](#)

[D4332 Practice for Conditioning Containers, Packages, or Packaging Components for Testing](#)

2.2 TAPPI Test Methods:³

[T 410 Grammage of Paper and Paperboard \(Weight per Unit Area\)](#)

[T 411 Thickness \(caliper\) of Paper, Paper Board, and Combined Board](#)

2.3 Executive Orders:⁴

[Executive Order 13101 Greening the Government Through Waste Prevention, Recycling, and Federal Acquisition, September 16, 1998](#)

2.4 Federal Specification:⁵

[Code of Federal Regulations, 16 CFR Part 1500.3 Definitions of Toxic and Hazardous Materials](#)

~~[U.S. Government CID A-A-2546 Pad, Writing Paper \(Repositionable\)](#)~~

¹ This specification is under the jurisdiction of ASTM Committee [D10](#) on Packaging and is the direct responsibility of Subcommittee [D10.14](#) on Tape and Labels. Current edition approved ~~March 15, 2023~~ March 1, 2024. Published ~~March 2023~~ March 2024. Originally approved in 2002. Last previous edition approved in ~~2017~~ 2023 as D6787/D6787M – 02 (~~2017~~)(2023). DOI: ~~10.1520/D6787-D6787M-02R23~~ 10.1520/D6787_D6787M-24.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Technical Association of the Pulp and Paper Industry (TAPPI), 15 Technology Parkway South, Norcross, GA 30092, <http://www.tappi.org>.

⁴ Available from The White House Publications Office, New Executive Office Building, White House, Washington, DC 20500, Att: Publications.

⁵ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

2.5 ISO Standard:

ISO 9002 Quality Systems Model for Quality Assurance in Production and Installation⁶

2.6 Other Standards:

Coalition of Northeastern Governors (CONEG) Model Toxics Legislation⁷

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *flagging, v*—the lifting of an edge of a repositionable note from paper when the note and paper are wrapped around a cylinder.

3.1.2 *multiple lift, n*—the condition in which removal of the top sheet on a pad of notes causes the unintentional removal of a second sheet.

3.1.3 *postconsumer materials, n*—a material or finished product that has served its intended use and has been discarded for disposal or recovery, having completed its life as a consumer item. Postconsumer material is a part of the broader category of recovered material (see U.S. Executive Order 13101, section 203).

3.1.4 *recovered materials, n*—waste materials and by-products that have been recovered or diverted from solid waste, but such term does not include those materials and by-products generated from, and commonly reused within, an original manufacturing process (see U.S. Executive Order 13101, section 205).

4. Significance and Use

4.1 Repositionable note pads consist of individual sheets of paper with an adhesive strip on one edge. The adhesive will temporarily hold the note to another sheet of paper, a file, or other surface without damaging or otherwise modifying the surface of the sheet or file. The notes display a written message or reminder.

4.2 This specification is based on the U.S. Government CID A-A-2546, which was cancelled in 1999.

5. Apparatus

5.1 Roller, Hand-operated:

5.1.1 A steel roller 85 mm \pm 2.5 mm (3.25 in. \pm 0.1 in.) in diameter and 45 mm \pm 1.5 mm (1.75 in. \pm 0.005 in.) in width, covered with rubber approximately 6 mm (0.25 in.) in thickness, having a Shore scale A durometer hardness of 80 \pm 5. The surface shall be a true cylinder void of any convex or concave deviations. The mass of the roller shall be 2040 g \pm 45 g (4.5 lb \pm 0.1 lb).

5.1.2 No part of the apparatus shall increase the mass of the roller during use. The roller shall move either mechanically or by hand at the rate of 10 mm/s \pm 0.5 mm/s (24 in./min \pm 0.5 in./min).

5.2 Cylindrical Mandrel for Flagging Test:

5.2.1 The mandrel shall be a smooth cylinder, 51 mm (2 in.) in diameter and a minimum of 20 cm (8 in.) long. Suitable materials include wood, plastic, and aluminum. The mandrel may be a solid cylinder or a hollow tube.

6. Test Materials

6.1 *Multi-purpose Copy Paper*—Hammermill Fore DP, Multi-Function Paper, White #10326-7 or equivalent.

6.2 Double-coated pressure sensitive adhesive tape, with permanent adhesive on both sides of the tape.

⁶ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁷ Available from the Toxins in Packaging Clearinghouse, c/o the Council of State Governments, 2760 Research Park Drive, P.O. Box 11910, Lexington, KY 40578–1910.



7. Conditioning

7.1 Condition the pads of repositionable notes in the standard conditioning atmosphere as described in Practice D4332 for a period of not less than 24 h.

7.2 Conduct tests in an atmosphere of 50 % ± 2 % relative humidity and 23.0 °C ± 2.0 °C.

8. Classification

8.1 The size of the pads shall be as listed in Table 1. The adhesive stripe is located on the top of the horizontal dimension of the pad.

9. Ordering Information

9.1 The inquiry or order shall include the following:

9.1.1 ASTM designation and date of issue,

9.1.2 Type required (see 8.1),

9.1.3 Recycled paper content for government purchase (see purchase, 19.1);

9.1.4 When testing and inspection certification is required (see Section 21.20),

9.1.5 Packaging and marking (see 10.1), and

9.1.6 Color of paper and graphics, if any (see 11.1).

10. Packaging and Package Marking

10.1 Packaging and package marking shall be as specified in the contract or order.

11. Color and Graphics

11.1 The color and graphics of the repositionable note pads shall conform to those commercially available.

12. Materials and Manufacture

12.1 *Construction*—A minimum average of 100 sheets of paper shall be assembled in the form of a pad. No individual pad shall contain fewer than 97 sheets. The pad of paper and a backing sheet shall be securely fastened together by means of the repositionable, pressure-sensitive adhesive coating.

13. Physical Properties

13.1 *Paper*:

13.2 The paper used in the construction of the pad shall be of the color as specified in the ordering description, and shall conform to the requirements shown in Table 2.

TABLE 1 Dimensions of Notepads

Type	Horizontal Dimension	Vertical Dimension	Tolerance
1	127 mm (5 in.)	76 mm (3 in.)	±1.6 mm (±1/16 in.)
2	76 mm (3 in.)	76 mm (3 in.)	±1.6 mm (±1/16 in.)
3	51 mm (2 in.)	38 mm (1.5 in.)	±1.6 mm (±1/16 in.)
4	51 mm (2 in.)	76 mm (3 in.)	±1.6 mm (±1/16 in.)
5	101 mm (4 in.)	152 mm (6 in.)	±1.6 mm (±1/16 in.)
6	Custom	Custom	±1.6 mm (±1/16 in.)