



Designation: **D4042–93 (Reapproved 2019) D4042 – 24**

Standard Test Method for Sampling and Testing for Ash and Total Iron in Steel Mill Dispersions of Rolling Oils¹

This standard is issued under the fixed designation D4042; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. ~~Scope~~ Scope*

1.1 This test method describes a procedure for sampling and testing dispersions of rolling oils in water from operating steel rolling mills for determination of ash and total iron content. Its purpose is to provide a test method such that a representative sample may be taken and phenomenon such as iron separation, fat-emulsion separation, and so forth, do not contribute to analytical error in determination of ash and total iron.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* For specific warning statements, see Sections [67](#) and [78](#).

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D482 Test Method for Ash from Petroleum Products](#)

[D1068 Test Methods for Iron in Water](#)

[D1193 Specification for Reagent Water](#)

[D2795 Test Methods for Analysis of Coal and Coke Ash \(Withdrawn 2001\)](#)³

[D4175 Terminology Relating to Petroleum Products, Liquid Fuels, and Lubricants](#)

[E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials](#)

[E832 Specification for Laboratory Filter Papers](#)

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this test method, refer to Terminology [D4175](#).

¹ This test method is under the jurisdiction of ASTM Committee [D02](#) on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee [D02.L0.04](#) on Metal Deformation Fluids and Lubricants.

Current edition approved Dec. 1, 2019; March 1, 2024. Published December 2019; March 2024. Originally approved in 1981. Last previous edition approved in 2014 (2019) as D4042 – 93 (2014); (2019). DOI: [10.1520/D4042-93R19-10.1520/D4042-24](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on [www.astm.org](#).

*A Summary of Changes section appears at the end of this standard

4. Summary of Test Method

4.1 Polyethylene disposable sample bags in a suitable holding device are used to collect representative samples of nonhomogeneous dispersions of rolling mill oils in water from an operating mill coolant system.

4.2 The collected sample and disposable bag are analyzed as one for ash and total iron.

4.2.1 Ash content is determined gravimetrically by evaporating all water from the sample bag before heating the residue and bag in a muffle furnace to a constant weight (Test Method D482).

4.2.2 Total iron content is determined by digesting the iron in the ashed sample and bag in an acidified solution. The iron in the solution is reduced with stannous chloride and titrated with standardized potassium dichromate.

4.2.3 The ash and total iron contributed by a sample bag alone are determined separately and are subtracted from the values of bag and sample to obtain the values for the sample alone.

NOTE 1—There are a number of alternative methods available for determining total iron in an ashed solution such as Test Methods D2795 and D1068.

5. Significance and Use

5.1 The life cycle and cleanliness of a recirculating steel mill rolling oil dispersion is affected by the amount of iron present. This iron consists mainly of iron from acid pickling residues and iron from attrition of the steel sheet or rolls during cold rolling. In sampling rolling oils for total iron it is difficult to prevent adherence of iron containing sludge to the sample container. Thus, the accuracy of a total iron determination from an aliquot sample is suspect. This practice provides a means for ensuring that all iron contained in a sample is included in the analysis.

5.2 Although less significant, the ash content is still an essential part of the procedure for obtaining a total iron analysis. Generally, the ash will be mostly iron, and in many cases, could be used as a substitute for total iron in determining when to change the dispersion.

6. Sampling

6.1 Apparatus:

ASTM D4042-24

<https://standards.iteh.ai/catalog/standards/astm/flcf7flb-d943-4470-a89b-2c30d263b0c4/astm-d4042-24>

6.1.1 Disposable Plastic (Polyethylene) Sampling Bags⁴ 177 cm³ and 473 cm³ (6 oz and 16 oz) complete with closure wire.

6.1.2 Holding Fixture.




FIG. 1 Possible Holding Fixture and Assembly System

⁴ Sampling bags (with wires) can be found in most common laboratory supply catalogues.

NOTE 2—A plastic baby bottle holder with an open 177 cm³ (6 oz) sampling bag inserted makes a suitable holder.

6.1.3 Sampling Cup and Handle.

NOTE 3—A hockey stick or similar formed apparatus of steel, plastic, or wood with or without a separate cup can be used to hold the holding fixture or the fixture itself can be attached to the handle (see Fig. 1).

6.2 Sampling Procedure:

6.2.1 Weigh a number of identified sample bags on an analytical balance to the nearest 0.1 mg. Record the weight of each as W_{B1} .

6.2.2 Using a different, preweighed, identified plastic disposable sampling bag for each sample, remove samples from the mill only while the coolant is circulating and the mill running. Take samples from the same location between the second and third stand whenever possible. Fill the bag approximately two thirds full to allow for tying of the bag.

NOTE 4—Occasionally, due to mill configuration or other reasons, it may be advisable to obtain the sample from other points in the mill system. If so, record complete details on location and time of sampling.

6.2.3 Tie and seal each sample with the wire provided in another disposable plastic sampling bag 473 cm³ (16 oz) to prevent loss of material in transit. Individual rigid plastic bottles of suitable size are also satisfactory containers for shipment and can be substituted for the outer 473 cm³ (16 oz) plastic bag.

6.2.4 Take extreme care not to soil the exterior of the sampling bag with the dispersion or any foreign material.

7. Ash Content

7.1 Apparatus:

7.1.1 *Borosilicate-Glass Beaker*, 400 mL, or *Evaporating Dish*, 350 mL, designed for ashing in an electric furnace. Do not use platinum crucibles because of the tendency to alloy with metallic iron.

7.1.2 *Electric Muffle Furnace*, capable of maintaining a temperature of 775 °C ± 25 °C (1427 °F ± 45 °F), preferably having suitable apertures at the front and rear that allow a slow natural draft of air to pass through.

7.1.3 *Oven*, capable of maintaining a temperature of 105 °C ± 2 °C (221 °F ± 4 °F).

7.1.4 *Analytical Balance*, 200 g capacity, accurate to 0.1 mg.

7.1.5 *Top-Loading Balance*, 600 g minimum capacity, accurate to 0.01 g.

7.2 Procedure:

7.2.1 Heat the empty beaker or evaporating dish at 700 °C to 800 °C (1240 °F to 1470 °F) for 10 min or more. Cool at room temperature in a suitable container (NOTE 5) and weigh on an analytical balance to the nearest 0.1 mg.

NOTE 5—The container in which the beaker or evaporating dish is cooled should not contain a desiccating agent.

7.2.2 Remove the bagged sample from its carrier container and place it, still tied, in the dish. Remove the wire and weigh the bag with sample on a top loading balance to the nearest 0.01 g. Subtract the weight of the beaker or evaporating dish and record the weight in grams as W_{S1} .

7.2.3 Place the beaker or dish, sample, and bag in an oven at 105 °C (221 °F) overnight or until the moisture has been evaporated from the sample.

7.2.4 Cover the beaker or evaporating dish with ashless filter paper (NOTE 6) to prevent loss due to spatter. Add this filter paper to the sample prior to ashing.