



Designation: **A312/A312M—22a A312/A312M – 24**

Used in USDOE-NE standards

Standard Specification for Seamless, Welded, and Heavily Cold Worked Austenitic Stainless Steel Pipes¹

This standard is issued under the fixed designation A312/A312M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification² covers seamless, straight-seam welded, and heavily cold worked welded austenitic stainless steel pipe intended for high-temperature and general corrosive service.

1.2 Grades TP304H, TP309H, TP309HCb, TP310H, TP310HCb, TP316H, TP321H, TP347H, and TP348H are modifications of Grades TP304, TP309Cb, TP309S, TP310Cb, TP310S, TP316, TP321, TP347, and TP348, and are intended for service at temperatures where creep and stress rupture properties are important.

1.3 Optional supplementary requirements are provided for pipe where a greater degree of testing is desired. These supplementary requirements call for additional tests to be made and, when desired, it is permitted to specify in the order one or more of these supplementary requirements.

1.4 **Table X1.1** lists the standardized dimensions of welded and seamless stainless steel pipe as shown in ASME B36.19. These dimensions are also applicable to heavily cold worked pipe. Pipe having other dimensions is permitted to be ordered and furnished provided such pipe complies with all other requirements of this specification.⁴

1.5 Grades TP321 and TP321H have lower strength requirements for pipe manufactured by the seamless process in nominal wall thicknesses greater than $\frac{3}{8}$ in. [9.5 mm].

1.6 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved Nov. 1, 2022/March 1, 2024. Published December 2022/March 2024. Originally approved in 1948. Last previous edition approved in 2022 as A312/A312M—22/A312/A312M – 22a. DOI: 10.1520/A0312_A0312M-22A.10.1520/A0312_A0312M-24.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-312 in Section II of that Code.

*A Summary of Changes section appears at the end of this standard



2. Referenced Documents

2.1 ASTM Standards:³

A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

A999/A999M Specification for General Requirements for Alloy and Stainless Steel Pipe

A1016/A1016M Specification for General Requirements for Ferritic Alloy Steel, Austenitic Alloy Steel, and Stainless Steel Tubes

E112 Test Methods for Determining Average Grain Size

E381 Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 ASME Standards:

B1.20.1 Pipe Threads, General Purpose

B36.10M Welded and Seamless Wrought Steel Pipe

B36.19 Stainless Steel Pipe

ASME Boiler and Pressure Vessel Code : Section VIII⁴

2.3 AWS Standard:

A5.9 Corrosion-Resisting Chromium and Chromium-Nickel Steel Welding Rods and Electrodes⁵

2.4 Other Standard:

SAE J1086 Practice for Numbering Metals and Alloys (UNS)⁶

3. Terminology

3.1 Definitions:

3.1.1 The definitions in Specification A999/A999M and Terminology A941 are applicable to this specification.

4. Ordering Information

4.1 Orders for material to this specification shall conform to the requirements of the current edition of Specification A999/A999M.

5. General Requirements

5.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A999/A999M unless otherwise provided herein.

6. Materials and Manufacture

6.1 Manufacture:

6.1.1 The pipe shall be manufactured by one of the following processes:

6.1.2 *Seamless (SML) pipe* shall be made by a process that does not involve welding at any stage of production.

6.1.3 *Welded (WLD) pipe* shall be made using an automatic welding process with no addition of filler metal during the welding process.

6.1.4 *Heavily cold-worked (HCW) pipe* shall be made by applying cold working of not less than 35 % reduction in thickness of both wall and weld to a welded pipe prior to the final anneal. No filler shall be used in making the weld. Prior to cold working, the weld shall be 100 % radiographically inspected in accordance with the requirements of ASME Boiler and Pressure Vessel Code, Section VIII, Division 1, latest revision, Paragraph UW-51.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁵ Available from American Welding Society (AWS), 550 NW LeJeune Rd., Miami, FL 33126, <http://www.aws.org>.

⁶ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

TABLE 1 Chemical Requirements

| Grade | UNS Designation ^A | Composition, % ^B | | | | | | | | | | | | | | | | | |
|---------|------------------------------|-----------------------------|-----------|------------|--------|-----------|-----------|-----------|------------|----------|----------------------|---------------|-----------------------|-----------|----------|--------|-----------|-----------|-------|
| | | Carbon | Manganese | Phosphorus | Sulfur | Silicon | Chromium | Nickel | Molybdenum | Titanium | Niobium ^M | Tantalum, max | Nitrogen ^C | Vanadium | Copper | Cerium | Boron | Aluminum | Other |
| TP201 | S20100 | 0.15 | 5.5–7.5 | 0.060 | 0.030 | 1.00 | 16.0–18.0 | 3.5–5.5 | ... | ... | ... | ... | 0.25 | ... | ... | ... | ... | ... | ... |
| TP201LN | S20153 | 0.03 | 6.4–7.5 | 0.045 | 0.015 | 0.75 | 16.0–17.5 | 4.0–5.0 | ... | ... | ... | ... | 0.10–0.25 | ... | 1.00 | ... | ... | ... | ... |
| ... | S20400 | 0.030 | 7.0–9.0 | 0.045 | 0.030 | 1.00 | 15.0–17.0 | 1.50–3.00 | ... | ... | ... | ... | 0.15–0.30 | ... | ... | ... | ... | ... | ... |
| TPXM-19 | S20910 | 0.06 | 4.0–6.0 | 0.045 | 0.030 | 1.00 | 20.5–23.5 | 11.5–13.5 | 1.50–3.00 | ... | 0.10–0.30 | ... | 0.20–0.40 | 0.10–0.30 | ... | ... | ... | ... | ... |
| TPXM-10 | S21900 | 0.08 | 8.0–10.0 | 0.045 | 0.030 | 1.00 | 19.0–21.5 | 5.5–7.5 | ... | ... | ... | ... | 0.15–0.40 | ... | ... | ... | ... | ... | ... |
| TPXM-11 | S21904 | 0.04 | 8.0–10.0 | 0.045 | 0.030 | 1.00 | 19.0–21.5 | 5.5–7.5 | ... | ... | ... | ... | 0.15–0.40 | ... | ... | ... | ... | ... | ... |
| TPXM-29 | S24000 | 0.08 | 11.5–14.5 | 0.060 | 0.030 | 1.00 | 17.0–19.0 | 2.3–3.7 | ... | ... | ... | ... | 0.20–0.40 | ... | ... | ... | ... | ... | ... |
| TP304 | S30400 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 18.0–20.0 | 8.0–11.0 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| TP304L | S30403 | 0.035 ^D | 2.00 | 0.045 | 0.030 | 1.00 | 18.0–20.0 | 8.0–13.0 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| TP304H | S30409 | 0.04–0.10 | 2.00 | 0.045 | 0.030 | 1.00 | 18.0–20.0 | 8.0–11.0 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| ... | S30415 | 0.04–0.06 | 0.80 | 0.045 | 0.030 | 1.00 | 18.0–20.0 | 9.0–10.0 | ... | ... | ... | ... | 0.12–0.18 | ... | ... | ... | 0.03–0.08 | ... | ... |
| ... | S30416 | 0.030 | 2.00 | 0.045 | 0.015 | 1.00 | 17.5–2.00 | 9.0–11.0 | 0.40–0.80 | ... | ... | ... | 0.10 | ... | ... | ... | ... | ... | ... |
| TP304N | S30451 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 18.0–20.0 | 8.0–11.0 | ... | ... | ... | ... | 0.10–0.16 | ... | ... | ... | ... | ... | ... |
| TP304LN | S30453 | 0.035 | 2.00 | 0.045 | 0.030 | 1.00 | 18.0–20.0 | 8.0–12.0 | ... | ... | ... | ... | 0.10–0.16 | ... | ... | ... | ... | ... | ... |
| ... | S30600 | 0.018 | 2.00 | 0.02 | 0.02 | 3.7–4.3 | 17.0–18.5 | 14.0–15.5 | 0.20 | ... | ... | ... | ... | ... | 0.50 max | ... | ... | ... | ... |
| ... | S30601 | 0.015 | 0.50–0.80 | 0.030 | 0.013 | 5.0–5.6 | 17.0–18.0 | 17.0–18.0 | 0.20 | ... | ... | ... | 0.05 | ... | 0.35 | ... | ... | ... | ... |
| ... | S30615 | 0.16–0.24 | 2.00 | 0.030 | 0.03 | 3.2–4.0 | 17.0–19.5 | 13.5–16.0 | ... | ... | ... | ... | ... | ... | ... | ... | ... | 0.80–1.50 | ... |
| ... | S30815 | 0.05–0.10 | 0.80 | 0.040 | 0.030 | 1.40–2.00 | 20.0–22.0 | 10.0–12.0 | ... | ... | ... | ... | 0.14–0.20 | ... | ... | ... | 0.03–0.08 | ... | ... |
| TP309S | S30908 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 22.0–24.0 | 12.0–15.0 | 0.75 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| TP309H | S30909 | 0.04–0.10 | 2.00 | 0.045 | 0.030 | 1.00 | 22.0–24.0 | 12.0–15.0 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |

TABLE 1 Continued

| Grade | UNS Designation ^A | Composition, % ^B | | | | | | | | | | | | | | | | | |
|----------|------------------------------|-----------------------------|-----------|------------|--------|---------|-----------|-----------|------------|----------------|----------------------|---------------|-----------------------|-----------|-----------|--------|-------------|----------|-------------------------|
| | | Carbon | Manganese | Phosphorus | Sulfur | Silicon | Chromium | Nickel | Molybdenum | Titanium | Niobium ^M | Tantalum, max | Nitrogen ^C | Vanadium | Copper | Cerium | Boron | Aluminum | Other |
| TP309Cb | S30940 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 22.0–24.0 | 12.0–16.0 | 0.75 | ... | 10 × C min, 1.10 max | ... | ... | ... | ... | ... | ... | ... | ... |
| TP309HCb | S30941 | 0.04–0.10 | 2.00 | 0.045 | 0.030 | 1.00 | 22.0–24.0 | 12.0–16.0 | 0.75 | ... | 10 × C min, 1.10 max | ... | ... | ... | ... | ... | ... | ... | ... |
| | S31002 | 0.015 | 2.00 | 0.020 | 0.015 | 0.15 | 24.0–26.0 | 19.0–22.0 | 0.10 | ... | ... | ... | 0.10 | ... | ... | ... | ... | ... | ... |
| TP310S | S31008 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 24.0–26.0 | 19.0–22.0 | 0.75 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| TP310H | S31009 | 0.04–0.10 | 2.00 | 0.045 | 0.030 | 1.00 | 24.0–26.0 | 19.0–22.0 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| | S31035 | 0.04–0.10 | 0.60 | 0.025 | 0.015 | 0.40 | 21.5–23.5 | 23.5–26.5 | ... | ... | 0.40–0.60 | ... | 0.20–0.30 | ... | 2.5–3.5 | ... | 0.002–0.008 | ... | W 3.0–4.0 Co 1.0–2.0 |
| TP310Cb | S31040 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 24.0–26.0 | 19.0–22.0 | 0.75 | ... | 10 × C min, 1.10 max | ... | ... | ... | ... | ... | ... | ... | ... |
| TP310HCb | S31041 | 0.04–0.10 | 2.00 | 0.045 | 0.030 | 1.00 | 24.0–26.0 | 19.0–22.0 | 0.75 | ... | 10 × C min, 1.10 max | ... | ... | ... | ... | ... | ... | ... | ... |
| | S31050 | 0.025 | 2.00 | 0.020 | 0.015 | 0.4 | 24.0–26.0 | 20.5–23.5 | 1.6–2.6 | ... | ... | ... | 0.09–0.15 | ... | ... | ... | ... | ... | ... |
| ... | S31254 | 0.020 | 1.00 | 0.030 | 0.010 | 0.80 | 19.5–20.5 | 17.5–18.5 | 6.0–6.5 | ... | ... | ... | 0.18–0.25 | ... | 0.50–1.00 | ... | ... | ... | ... |
| ... | S31266 | 0.030 | 2.00–4.00 | 0.035 | 0.020 | 1.00 | 23.0–25.0 | 21.0–24.0 | 5.2–6.2 | ... | ... | ... | 0.35–0.60 | ... | 1.00–2.50 | ... | ... | ... | W 1.50–2.50 |
| S31272 | | | | | | | 0.08–0.12 | 1.5–2.00 | 0.030 | 0.015 | 0.25–0.75 | 14.0–16.0 | 14.0–16.0 | 1.00–1.40 | 0.30–0.60 | ... | ... | ... | ... |
| ... | S31277 | 0.020 | 3.00 | 0.030 | 0.010 | 0.50 | 20.5–23.0 | 26.0–28.0 | 6.5–8.0 | ... | ... | ... | 0.30–0.40 | ... | 0.50–1.50 | ... | ... | ... | ... |
| TP316 | S31600 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 16.0–18.0 | 10.0–14.0 | 2.00–3.00 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| TP316L | S31603 | 0.035 ^D | 2.00 | 0.045 | 0.030 | 1.00 | 16.0–18.0 | 10.0–14.0 | 2.00–3.00 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| TP316H | S31609 | 0.04–0.10 | 2.00 | 0.045 | 0.030 | 1.00 | 16.0–18.0 | 10.0–14.0 | 2.00–3.00 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| TP316Ti | S31635 | 0.08 | 2.00 | 0.045 | 0.030 | 0.75 | 16.0–18.0 | 10.0–14.0 | 2.00–3.00 | 5× (C+N) –0.70 | ... | ... | 0.10 | ... | ... | ... | ... | ... | ... |
| TP316N | S31651 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 16.0–18.0 | 10.0–14.0 | 2.00–3.00 | ... | ... | ... | 0.10–0.16 | ... | ... | ... | ... | ... | ... |
| TP316LN | S31653 | 0.035 | 2.00 | 0.045 | 0.030 | 1.00 | 16.0–18.0 | 10.0–14.0 | 2.00–3.00 | ... | ... | ... | 0.10–0.16 | ... | ... | ... | ... | ... | ... |



TABLE 1 Continued

| Grade | UNS Designation ^A | Composition, % ^B | | | | | | | | | | | | | | | | | |
|---------|------------------------------|-----------------------------|-----------|--------------------|--------|---------|-----------|-----------|------------|----------------------|------------------------|---------------|-----------------------|----------|-----------|--------|-------------|----------|-------|
| | | Carbon | Manganese | Phosphorus | Sulfur | Silicon | Chromium | Nickel | Molybdenum | Titanium | Niobium ^M | Tantalum, max | Nitrogen ^C | Vanadium | Copper | Cerium | Boron | Aluminum | Other |
| ... | S31655 | 0.030 | 2.00 | 0.045 | 0.015 | 1.00 | 19.5–21.5 | 8.0–9.5 | 0.50–1.50 | ... | ... | ... | 0.14–0.25 | ... | 1.00 | ... | ... | ... | ... |
| TP317 | S31700 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 18.0–20.0 | 11.0–15.0 | 3.0–4.0 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| TP317L | S31703 | 0.035 | 2.00 | 0.045 | 0.030 | 1.00 | 18.0–20.0 | 11.0–15.0 | 3.0–4.0 | ... | ... | ... | ... | ... | ... | ... | ... | ... | ... |
| ... | S31725 | 0.03 | 2.00 | 0.040 ^E | 0.030 | 1.00 | 18.0–20.0 | 13.5–17.5 | 4.0–5.0 | ... | ... | ... | 0.10 | ... | 0.75 | ... | ... | ... | ... |
| ... | S31726 | 0.03 | 2.00 | 0.040 ^E | 0.030 | 1.00 | 17.0–20.0 | 13.5–17.5 | 4.0–5.0 | ... | ... | ... | 0.10–0.20 | ... | 0.75 | ... | ... | ... | ... |
| ... | S31727 | 0.03 | 1.00 | 0.030 | 0.030 | 1.00 | 17.5–19.0 | 14.5–16.5 | 3.8–4.5 | ... | ... | ... | 0.15–0.21 | ... | 2.8–4.0 | ... | ... | ... | ... |
| ... | S31730 | 0.030 | 2.00 | 0.040 | 0.010 | 1.00 | 17.0–19.0 | 15.0–16.5 | 3.0–4.0 | ... | ... | ... | 0.045 | ... | 4.0–5.0 | ... | ... | ... | ... |
| ... | S31740 | 0.005–0.020 ^N | 2.00 | 0.045 | 0.030 | 1.00 | 17.0–19.0 | 11.0–15.0 | 3.0–4.5 | ... | 0.20–0.50 ^N | ... | 0.06–0.15 | ... | ... | ... | ... | ... | ... |
| ... | S32053 | 0.03 | 1.00 | 0.030 | 0.010 | 1.00 | 22.0–24.0 | 24.0–26.0 | 5.0–6.0 | ... | ... | ... | 0.17–0.22 | ... | ... | ... | ... | ... | ... |
| TP321 | S32100 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 17.0–19.0 | 9.0–12.0 | ... | ^F | ... | ... | 0.10 | ... | ... | ... | ... | ... | ... |
| TP321H | S32109 | 0.04–0.10 | 2.00 | 0.045 | 0.030 | 1.00 | 17.0–19.0 | 9.0–12.0 | ... | 4(C+N) min; 0.70 max | ... | ... | 0.10 | ... | ... | ... | ... | ... | ... |
| ... | S32615 | 0.07 | 2.00 | 0.045 | 0.030 | 4.8–6.0 | 16.5–19.5 | 19.0–22.0 | 0.30–1.50 | ... | ... | ... | ... | ... | 1.50–2.50 | ... | ... | ... | ... |
| ... | S32654 | 0.020 | 2.0–4.0 | 0.030 | 0.005 | 0.50 | 24.0–25.0 | 21.0–23.0 | 7.0–8.0 | ... | ... | ... | 0.45–0.55 | ... | 0.30–0.60 | ... | ... | ... | ... |
| ... | S33228 | 0.04–0.08 | 1.00 | 0.020 | 0.015 | 0.30 | 26.0–28.0 | 31.0–33.0 | ... | ... | 0.60–1.00 | ... | ... | ... | 0.05–0.10 | ... | 0.025 | ... | ... |
| ... | S34565 | 0.03 | 5.0–7.0 | 0.030 | 0.010 | 1.00 | 23.0–25.0 | 16.0–18.0 | 4.0–5.0 | ... | 0.10 | ... | 0.40–0.60 | ... | ... | ... | ... | ... | ... |
| TP347 | S34700 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 17.0–19.0 | 9.0–13.0 | ... | ... | ^G | ... | ... | ... | ... | ... | ... | ... | ... |
| TP347H | S34709 | 0.04–0.10 | 2.00 | 0.045 | 0.030 | 1.00 | 17.0–19.0 | 9.0–13.0 | ... | ... | ^H | ... | ... | ... | ... | ... | ... | ... | ... |
| TP347LN | S34751 | 0.005–0.020 | 2.00 | 0.045 | 0.030 | 1.00 | 17.0–19.0 | 9.0–13.0 | ... | ... | 0.20–0.50 ^I | ... | 0.06–0.10 | ... | ... | ... | ... | ... | ... |
| | S34752 | 0.005–0.020 | 2.00 | 0.035 | 0.010 | 0.60 | 17.0–19.0 | 10.0–13.0 | 0.20–1.20 | ... | 0.20–0.50 ^I | ... | 0.06–0.12 | ... | 2.50–3.50 | ... | 0.001–0.005 | ... | ... |
| TP348 | S34800 | 0.08 | 2.00 | 0.045 | 0.030 | 1.00 | 17.0–19.0 | 9.0–13.0 | ... | ... | ^G | 0.10 | ... | ... | ... | ... | ... | ... | ... |
| TP348H | S34809 | 0.04–0.10 | 2.00 | 0.045 | 0.030 | 1.00 | 17.0–19.0 | 9.0–13.0 | ... | ... | ^H | 0.10 | ... | ... | ... | ... | ... | ... | ... |

TABLE 1 Continued

| Grade | UNS Designation ^A | Composition, % ^B | | | | | | | | | | | | | | | | | |
|----------|------------------------------|-----------------------------|-----------|------------|--------|-----------|-----------|-----------|------------|------------------------|----------------------|---------------|-----------------------|-----------|-----------|--------|------------------------|------------------------------|-------|
| | | Carbon | Manganese | Phosphorus | Sulfur | Silicon | Chromium | Nickel | Molybdenum | Titanium | Niobium ^M | Tantalum, max | Nitrogen ^C | Vanadium | Copper | Cerium | Boron | Aluminum | Other |
| ... | S35045 | 0.06–0.10 | 1.50 | ... | 0.015 | 1.00 | 25.0–29.0 | 32.0–37.0 | ... | 0.15–0.60 | ... | ... | ... | 0.75 | ... | ... | 0.15–0.60 | | |
| ... | S35315 | 0.04–0.08 | 2.00 | 0.040 | 0.030 | 1.20–2.00 | 24.0–26.0 | 34.0–36.0 | ... | ... | ... | ... | 0.12–0.18 | ... | 0.03–0.08 | ... | ... | | |
| TPXM-15 | S38100 | 0.08 | 2.00 | 0.030 | 0.030 | 1.50–2.50 | 17.0–19.0 | 17.5–18.5 | ... | ... | ... | ... | ... | ... | ... | ... | ... | 0.30 | |
| ... | S38815 | 0.030 | 2.00 | 0.040 | 0.020 | 5.5–6.5 | 13.0–15.0 | 15.0–17.0 | 0.75–1.50 | ... | ... | ... | ... | 0.75–1.50 | ... | ... | ... | 0.30 | |
| ... | S35030 | 0.05–0.10 | 1.50 | 0.030 | 0.015 | 0.5–2.0 | 18.5–22.5 | 22.5–27.5 | ... | ... | 0.25–0.75 | ... | 0.05–0.15 | ... | 2.5–3.5 | ... | ... | ... | |
| Alloy 20 | N08020 | 0.07 | 2.00 | 0.045 | 0.035 | 1.00 | 19.0–21.0 | 32.0–38.0 | 2.0–3.0 | ... | L | L | ... | 3.0–4.0 | ... | ... | ... | | |
| | N08028 | 0.030 | 2.50 | 0.030 | 0.030 | 1.0 | 26.0–28.0 | 30.0–34.0 | 3.0–4.0 | ... | ... | ... | ... | 0.60–1.4 | ... | ... | ... | | |
| | N08029 | 0.020 | 2.0 | 0.025 | 0.015 | 0.6 | 26.0–28.0 | 30.0–34.0 | 4.0–5.0 | ... | ... | ... | ... | 0.6–1.4 | ... | ... | ... | | |
| ... | N08367 | 0.030 | 2.00 | 0.040 | 0.030 | 1.00 | 20.0–22.0 | 23.5–25.5 | 6.0–7.0 | ... | ... | ... | 0.18–0.25 | ... | 0.75 | ... | ... | ... | |
| 800 | N08800 | 0.10 | 1.50 | 0.045 | 0.015 | 1.00 | 19.0–23.0 | 30.0–35.0 | ... | ... | ... | ... | ... | 0.75 | ... | ... | 0.15–0.60 | Fe ^J 39.5 min. | |
| 800H | N08810 | 0.05–0.10 | 1.50 | 0.045 | 0.015 | 1.00 | 19.0–23.0 | 30.0–35.0 | ... | 0.15–0.60 | ... | ... | ... | 0.75 | ... | ... | 0.15–0.60 | Fe ^J 39.5 min. | |
| | N08811 | 0.06–0.10 | 1.50 | 0.045 | 0.015 | 1.00 | 19.0–23.0 | 30.0–35.0 | ... | 0.15–0.60 ^K | ... | ... | ... | 0.75 | ... | ... | 0.15–0.60 ^K | Fe ^J 39.5 min. | |
| ... | N08904 | 0.020 | 2.00 | 0.040 | 0.030 | 1.00 | 19.0–23.0 | 23.0–28.0 | 4.0–5.0 | ... | ... | ... | 0.10 | 1.00–2.00 | ... | ... | ... | | |
| ... | N08925 | 0.020 | 1.00 | 0.045 | 0.030 | 0.50 | 19.0–21.0 | 24.0–26.0 | 6.0–7.0 | ... | ... | ... | 0.10–0.20 | 0.80–1.50 | ... | ... | ... | | |
| ... | N08926 | 0.020 | 2.00 | 0.030 | 0.010 | 0.50 | 19.0–21.0 | 24.0–26.0 | 6.0–7.0 | ... | ... | ... | 0.15–0.25 | 0.50–1.50 | ... | ... | ... | | |

^A New designation established in accordance with Practice E527 and SAE J1086.

^B Maximum, unless otherwise indicated. Where ellipses (...) appear in this table, there is no requirement and analysis for the element need not be determined or reported.

^C The method of analysis for nitrogen shall be a matter of agreement between the purchaser and manufacturer.

^D For small diameter or thin walls or both, where many drawing passes are required, a carbon maximum of 0.040 % is necessary in grades TP304L and TP316L. Small outside diameter tubes are defined as those less than 0.500 in. [12.7 mm] in outside diameter and light wall tubes as those less than 0.049 in. [1.20 mm] in average wall thickness (0.044 in. [1.10 mm] in minimum wall thickness).

^E For welded pipe, the phosphorus maximum shall be 0.045 %.

^F Ti 5 × (C+N) min, 0.70 max.

^G The niobium content shall be not less than ten times the carbon content and not more than 1.00 %.

^H The niobium content shall be not less than eight times the carbon content and not more than 1.0 %.

^I Grade S34751 and Grade S34752 shall have a niobium content of not less than 15 times the carbon content.

^J Iron shall be determined arithmetically by difference of 100 minus the sum of the other specified elements.

^K Al + Ti shall be 0.85 % min; 1.20 % max.

^L Niobium (Nb) + Tantalum = 8 × Carbon min, 1.00 max.

^M The terms Niobium (Nb) and Columbium (Cb) are alternative names for the same element.

^N S31740 shall have a niobium (columbium) content of not less than 15 times the carbon content.