



Designation: **A369/A369M—23 A369/A369M – 24**

## Standard Specification for Carbon and Ferritic Alloy Steel Forged and Bored Pipe for High-Temperature Service<sup>1</sup>

This standard is issued under the fixed designation A369/A369M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This specification<sup>2</sup> covers heavy-wall carbon and alloy steel pipe (**Note 1**) made from turned and bored forgings and is intended for high-temperature service. Pipe ordered under this specification shall be suitable for bending and other forming operations and for fusion welding. Selection will depend on design, service conditions, mechanical properties and high-temperature characteristics.

NOTE 1—The use of the word “pipe” throughout the several sections of this specification is used in the broad sense and intended to mean pipe headers, or leads.

NOTE 2—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

1.2 Several grades of ferritic steels are covered. Their compositions are given in **Table 1**.

1.3 Supplementary requirements (S1 to S7) of an optional nature are provided. Supplementary requirements S1 to S5 call for additional tests to be made, and when desired shall be so stated in the order, together with the number of such tests required as applicable.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>3</sup>

**A999/A999M Specification for General Requirements for Alloy and Stainless Steel Pipe**

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved ~~May 1, 2023~~ March 1, 2024. Published ~~May 2023~~ March 2024. Originally approved in 1953. Last previous edition approved in ~~2018~~ 2023 as ~~A369/A369M—18~~ A369/A369M – 23. DOI: ~~10.1520/A0369\_A0369M-23.10.1520/A0369\_A0369M-24.~~

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SA-369 in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard



TABLE 1 Chemical Requirements

Grade	Composition, %				
	FPA	FPB	FP1		FP2
Carbon	0.25 max	0.30 max	0.10–0.20		0.10–0.20
Manganese	0.27–0.93	0.29–1.06	0.30–0.80		0.30–0.61
Phosphorus, max	0.035	0.035	0.025		0.025
Sulfur, max	0.035	0.035	0.025		0.025
Silicon	0.10 min	0.10 min	0.10–0.50		0.10–0.30
Chromium	...	...	...		0.50–0.81
Molybdenum	...	...	0.44–0.65		0.44–0.65
Grade	FP5	FP9	FP11		FP12
Carbon	0.15 max	0.15 max	0.05–0.15		0.05–0.15
Manganese	0.30–0.60	0.30–0.60	0.30–0.60		0.30–0.61
Phosphorus, max	0.025	0.030	0.025		0.025
Sulfur, max	0.025	0.030	0.025		0.025
Silicon	0.50 max	0.50–1.00	0.50–1.00		0.50 max
Chromium	4.00–6.00	8.00–10.00	1.00–1.50		0.80–1.25
Molybdenum	0.45–0.65	0.90–1.10	0.44–0.65		0.44–0.65
Grade	FP21	FP22	Type 1	Type 2	FP92
Carbon					0.07–0.13
Heat	0.05–0.15	0.05–0.15	0.08–0.12	0.08–0.12	
Product	...	...	...	0.07–0.13	
Manganese	0.30–0.60	0.30–0.60	0.30–0.60	0.30–0.50 <sup>A</sup>	0.30–0.60
Phosphorus, max	0.025	0.025	0.025	0.020 <sup>A</sup>	0.020
Sulfur, max	0.025	0.025	0.025	0.005 <sup>A</sup>	0.010
Silicon	0.50 max	0.50 max	0.20–0.50	0.20–0.40 <sup>A</sup>	0.50 max
Chromium	2.65–3.35	1.90–2.60	8.00–9.50	8.0–9.50 <sup>A</sup>	8.50–9.50
Molybdenum					0.30–0.60
Heat	0.80–1.06	0.87–1.13	0.85–1.05	0.85–1.05	
Product	...	...	...	0.80–1.05	
			Others:		W 1.50–2.00
			Ni 0.40 max	0.20 max <sup>A</sup>	V 0.15–0.25
				V	Nb <sup>C</sup> 0.04–0.09
			Heat 0.18–0.25	0.18–0.25	
			Product ...	0.16–0.27	
				Nb <sup>C</sup>	N 0.030–0.070
			Heat 0.06–0.10	0.06–0.10	
			Product ...	0.05–0.11	
			N 0.03–0.07	0.035–0.070 <sup>A</sup>	Ni 0.40 max
			Al 0.02 max	0.020 max <sup>A</sup>	Al 0.02 max
			Ti 0.01 max	0.01 max <sup>A</sup>	Ti 0.01 max
			Zr 0.01 max	0.01 max <sup>A</sup>	Zr 0.01 max
			Sn ... 4	0.010 max <sup>A</sup>	B 0.001–0.006
			Sb ...	0.003 max <sup>A</sup>	
			B ...	0.001 max <sup>A</sup>	
			Cu ...	0.10 max <sup>A</sup>	
			W ...	0.05 max <sup>A</sup>	
			As ...	0.010 max <sup>A</sup>	
			N/Al ...	≥ 4.0	
Grade	FP115 Heat	FP115 Product			
Carbon	0.08–0.13	0.07–0.14			
Manganese	0.20–0.50	0.20–0.50			
Phosphorus, max	0.020 max	0.020 max			
Sulfur, max	0.005 max	0.005 max			
Silicon	0.15–0.45	0.15–0.45			
Chromium	10.0–11.0	10.0–11.0			
Molybdenum	0.40–0.60	0.37–0.63			
	W 0.05 max	W 0.05 max			
	V 0.18–0.25	V 0.16–0.27			
	Nb <sup>C</sup> 0.02–0.06	Nb <sup>C</sup> 0.02–0.07			
	N 0.030–0.070	N 0.030–0.070			
	Ni 0.25 max	Ni 0.25 max			
	Al 0.02 max	Al 0.02 max			
	Ti 0.01 max	Ti 0.01 max			
	Zr 0.01 max	Zr 0.01 max			
	B 0.001 max	B 0.001 max			
	Cu 0.10 max	Cu 0.10 max			
	As 0.010 max	As 0.010 max			
	Sn 0.010 max	Sn 0.010 max			
	Sb 0.003 max	Sb 0.003 max			
	N/Al ratio 4.0 min				
	CNB <sup>B</sup> 10.5 max				

<sup>A</sup>Applies to both heat and product analyses.<sup>B</sup>Chromium-Nickel Balance is defined as CNB = (Cr + 6Si + 4Mo + 1.5W + 11V + 5Nb + 9Ti + 12Al) – (40C + 30N + 4Ni + 2Mn + 1Cu).



<sup>Ⓒ</sup>The terms Niobium (Nb) and Columbium (Cb) are alternate names for the same element.

- E290 Test Methods for Bend Testing of Material for Ductility
- E381 Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings
- 2.2 ASME Boiler and Pressure Vessel Code:<sup>4</sup>
  - Section IX
- 2.3 ASME Standard:<sup>4</sup>
  - B 46.1 Surface Texture
- 2.4 AWS Specifications:<sup>5</sup>
  - A5.5/A5.5M Specification for Low-Alloy Steel Electrodes for Shielded Metal Arc Welding
  - A5.23/A5.23M Specification for Low-Alloy Steel Electrodes and Fluxes for Submerged Arc Welding
  - A5.28/A5.28M Specification for Low-Alloy Steel Electrodes for Gas Shielded Arc Welding
  - A5.29/A5.29M Low-Alloy Steel Electrodes for Flux Cored Arc Welding

### 3. Ordering Information

- 3.1 Orders for material to this specification should include the following, as required, to describe the desired material adequately:
  - 3.1.1 Quantity (feet, centimetres, or number of lengths),
  - 3.1.2 Name of material (forged and bored pipe),
  - 3.1.3 Grade (Table 1),
  - 3.1.4 Size (inside diameter and minimum wall thickness),
  - 3.1.5 Length (Permissible Variations in Length Section of Specification A999/A999M),
  - 3.1.6 Verification of tensile and hardness properties at mid-thickness for Grade FP91 Type 1 and Type 2 (9.2),
  - 3.1.7 End finish (13),
  - 3.1.8 Optional requirements (Sections 8, Supplementary Requirements S1 to S7; 13.2),
  - 3.1.9 Test report required (Certification Section of Specification A999/A999M),
  - 3.1.10 Specification designation, and
  - 3.1.11 Special requirements or exceptions to this specification.

### 4. General Requirements

- 4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A999/A999M, unless otherwise provided herein.

### 5. Materials and Manufacture

#### 5.1 Discard:

- 5.1.1 A sufficient discard shall be made from each ingot to secure freedom from injurious defects. The steel shall have a homogeneous structure.

#### 5.2 Manufacture:

<sup>4</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

<sup>5</sup> Available from American Welding Society (AWS), 550 NW LeJeune Rd., Miami, FL 33126, <http://www.aws.org>.



5.2.1 Material for forging shall consist of ingots or of blooms, billets, or solid-rolled bars forged or rolled from an ingot, and cut to the required length by a process that will not produce injurious defects in the forging.

5.2.2 The material shall be forged (Note 3) by hammering or pressing, and shall be brought as nearly as practicable to the finished shape and size by hot working.

NOTE 3—The cross-sectional area of the solid forging shall have a reduction by forging or by rolling and forging from that of the ingot in the ratio of not less than 3 to 1.

5.2.3 Unless otherwise specified, the final forging operation shall be followed by a treatment suitable to the grade as specified in 5.4.

5.3 *Machining:*

5.3.1 All forgings shall have both the inner and outer surfaces machined.

5.3.2 After heat treatment, the pipe shall be machined to a finish with a roughness value no greater than 250- $\mu$ in. [6.4- $\mu$ m] arithmetical average deviation (AA), terms as defined in ANSI B 46.1-1962, unless otherwise specified.

5.4 *Heat Treatment:*

5.4.1 All pipe of the grades shown in Table 1 other than FPA, FPB, FP1, FP2, FP12, FP91 Type 1 and Type 2, FP92, and FP115 shall be reheated and furnished in the full-annealed or normalized and tempered condition. If furnished in the normalized and tempered condition (Note 4), the temperature for tempering shall be 1250 °F [680 °C] or higher for Grades FP5, FP9, FP21, and FP22, and 1200 °F [650 °C] or higher for Grades FP36 and FP11.

NOTE 4—It is recommended that the temperature for tempering should be at least 100 °F [50 °C] above the intended service temperature; consequently, the purchaser should advise the manufacturer if the service temperature is to be over 1100 °F [600 °C].

5.4.2 Pipe in Grades FPA and FPB as a final heat treatment shall be either normalized or shall be given a stress relieving treatment at 1200 to 1300 °F [650 to 705 °C]. Pipe in Grades FP1, FP2, and FP12, as a final heat treatment shall be given a stress-relieving treatment at 1200 to 1300 °F [650 to 705 °C].

NOTE 5—Certain of the ferritic steels covered by this specification tend to harden if cooled rapidly from above their critical temperature. Some will air harden, that is, become hardened to an undesirable degree when cooled in air from high temperatures. Therefore, operations involving heating such steels above their critical temperatures, such as welding, hot-bending and other forming operations, should be followed by suitable heat treatment.

5.4.3 Except when Supplementary Requirement S6 is specified by the purchaser, Grade FP91 Type 1 and Type 2 shall be normalized and tempered by reheating within the temperature range from 1900 to 1975 °F [1040 to 1080 °C], followed by air cooling and tempering in the temperature range of 1350 to 1470 °F [730 to 800 °C].

5.4.4 Except when Supplementary Requirement S6 is specified by the purchaser, Grade FP92 shall be normalized and tempered by reheating within the temperature range of 1900 to 1975 °F [1040 to 1080 °C], followed by air cooling and tempering in the temperature range of 1350 to 1470 °F [730 to 800 °C].

5.4.5 Grade FP115 shall be normalized and tempered by reheating within the temperature range of 1920 to 2010 °F [1050 to 1100 °C] and tempered in the range of 1380 to 1455 °F [750 to 790 °C]. The rate of cooling at mid thickness from 1650 to 900 °F [900 to 482 °C] shall be no slower than 9 °F/minute [5 °C/minute].

5.5 *Repair by Welding:*

5.5.1 Weld repair shall be permitted only subject to the approval of the purchaser and in accordance with Specification A999/A999M.

5.5.2 All repair welds in FP91 shall be made with one of the following welding processes and consumables: SMAW, A5.5/A5.5M