



Designation: D2065 – 24

Standard Test Method for Determination of Edge Performance of Composite Wood Products Under Surfactant Accelerated Moisture Stress¹

This standard is issued under the fixed designation D2065; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is intended to serve as a means for measurement of swelling and cracking of the coated or uncoated edge of a composite wood substrate that has been subjected to wetting by a test solution containing surface active agent.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D661 Test Method for Evaluating Degree of Cracking of Exterior Paints](#)

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.52 on Factory Coated Wood Products.

Current edition approved Feb. 1, 2024. Published March 2024. Originally approved in 1991. Last previous edition approved in 2017 as D2065 – 03 (2017). DOI: 10.1520/D2065-24.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1 *crack rating, n*—a numerical value on a scale from 1 to 10, with 10 representing no evidence of cracking of the edge (see Test Method [D661](#)).

3.1.2 *composite wood products, n*—boards or other structural or decorative materials manufactured from wood fibers, flakes or strands and various resin binders consolidated under heat, or pressure, or both.

4. Summary of Test Method

4.1 A surfactant solution is placed in a tray that contains a sponge. A preweighed and calipered panel with a coated edge is placed with the edge in contact with the surfactant saturated sponge for 2 h. The exposed panel is blotted dry, reweighed, recalipered, and inspected for edge cracking. Percentage weight and thickness changes are calculated and recorded. Edge cracking is rated in accordance with Test Method [D661](#) and recorded.

5. Significance and Use

5.1 This test method provides a measure of the dimensional stability and integrity of the coated edge of various composite wood products under accelerated moisture stress. It is widely used as an indicator or predictor of the anticipated performance of composite wood products during exterior exposure. It may be used for developmental evaluation of coatings, substrates, or both. It may also be useful for quality control or monitoring of the production of coated or uncoated composite wood products.

6. Apparatus

6.1 *Wide Flat Tray or Pan*, suitable to contain the required number of sponges and test boards. The sides must be high enough to safely contain at least 6 mm (¼ in.) of solution.

6.2 *Rack or Holder*, suitable to support the required number of test boards at the nominal 60° angle.

6.3 *Micrometer or Vernier Caliper*, of sufficient capacity for the board thickness to be measured and capable of 0.1 mm accuracy.

6.4 *Balance*, with sufficient capacity (typically 400 g) and 0.01 g accuracy.

6.5 *Suitable Saw*, for cutting of samples.