



Designation: ~~E2180~~—~~18~~ E2180 – 24

## Standard Test Method for Determining the Activity of Incorporated Antimicrobial Agent(s) In Polymeric or Hydrophobic Materials<sup>1</sup>

This standard is issued under the fixed designation E2180; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### INTRODUCTION

Polymeric materials such as vinyl pool liners, shower curtains, and various medical devices are treated frequently with incorporated or bound antimicrobial agents. Practice [G21](#) is used to determine the ability of polymer materials to resist microbial attack or staining (see also Practice [E1428](#)); however, none of the methods permit quantitative evaluations of incorporated antimicrobial activity.<sup>2</sup> These antimicrobials typically require contact with the microbial cell for maximal activity. When aqueous based bacterial inoculum suspensions are applied onto a preservative-treated plastic or other hydrophobic material, the surface tension of the polymer often causes the inocula suspension to dome. Bacteria within the drops of inoculum may not contact the treated surface if the challenged surface does not dry, or upon drying, cells may become layered. This test standard involves an agar slurry inoculum vehicle that provides a relatively uniform contact of the inocula with antimicrobial-treated hydrophobic surfaces.

<https://standards.iteh.ai>  
Document Preview

### 1. Scope

1.1 This test method is designed to evaluate (quantitatively) the antimicrobial effectiveness of agents incorporated or bound into or onto mainly flat (two dimensional) hydrophobic or polymeric surfaces. The method focuses primarily on assessing antibacterial activity; however, other microorganisms such as yeast and fungal conidia may be tested using this method.

1.2 The vehicle for the inoculum is an agar slurry which reduces the surface tension of the saline inoculum carrier and allows formation of a “pseudo-biofilm,” providing more even contact of the inoculum with the test surface.

NOTE 1—This test method facilitates the testing of hydrophobic surfaces by utilizing cells held in an agar slurry matrix. This test method, as written, is inappropriate to determine efficacy against biofilm cells, which are different both genetically and metabolically than planktonic cells used in this test.

1.3 This method can confirm the presence of antimicrobial activity in plastics or hydrophobic surfaces and allows determination of quantitative differences in antimicrobial activity between untreated plastics or polymers and those with bound or incorporated low water-soluble antimicrobial agents. Comparisons between the numbers of survivors on preservative-treated and control hydrophobic surfaces may also be made.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [E35](#) on Pesticides, Antimicrobials, and Alternative Control Agents and is the direct responsibility of Subcommittee [E35.15](#) on Antimicrobial Agents.

Current edition approved ~~May 1, 2018~~ April 1, 2024. Published ~~May 2018~~ April 2024. Originally approved in 2001. Last previous edition approved in 2018 as ~~E2180 – 07~~ [E2180 – 18](#) (2017). DOI: ~~10.1520/E2180-18~~ [10.1520/E2180-24](#).

<sup>2</sup> Price, D. L., Sawant, A. D., and Ahearn, D. G., “Assessment of the antimicrobial activity of an insoluble quaternary amine complex in plastics,” *J. Industr. Microbiol.*, Vol 8, No. 2, 1991, pp. 83–89.

1.4 The procedure also permits determination of “shelf-life” or long term durability of an antimicrobial treatment which may be achieved through testing both non-washed and washed samples over a time span.

1.5 Knowledge of microbiological techniques is required for these procedures.

1.6 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>3</sup>

[E1054 Practices for Evaluation of Inactivators of Antimicrobial Agents](#)

[E1428 Test Method for Evaluating the Performance of Antimicrobials in or on Polymeric Solids Against Staining by \*Streptomyces\* species \(A Pink Stain Organism\) \(Withdrawn 2024\)<sup>4</sup>](#)

[E2756 Terminology Relating to Antimicrobial and Antiviral Agents](#)

[G21 Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi](#)

## 3. Terminology

### 3.1 Definitions:

3.1.1 For definitions of terms used in this standard refer to Terminology [E2756](#).

3.1.2 *agar slurry, n*—a semi-gelatinous liquid formed when 3 g/L agar-agar is added to a 0.85 % saline solution.

3.1.3 *inoculum, n*—in microbiology, a specimen comprised of living spores, bacteria, single celled organisms, or other live materials, yeast or the multicellular filamentous fungi, or combination of two or more types of microorganisms, that are introduced into a test medium or onto a specimen to be tested in order to investigate the lability of the medium or specimen to support microbial growth or to investigate its antimicrobial properties.

3.1.4 *inoculum vehicle, n*—the carrier solution used to transport the ~~carrier solution used to transport the~~ inoculum to a given sample or object.

3.1.5 *neutralizing recovery broth, n*—liquid growth media used to inactivate the effects of the test antimicrobial agent.

## 4. Summary of Test Method

4.1 This method involves inoculation of a molten (45 °C) agar slurry with a standardized culture of bacterial cells.

4.2 A thin layer of the inoculated agar slurry (~~0.5-1.0 mL~~) (0.5 mL to 1.0 mL) is pipetted onto the test and untreated control material (triplicate samples minimum).

4.3 After the specified contact time (24 h commonly used), surviving microorganisms are recovered via elution of the agar slurry inoculum from the test substrate into neutralizing broth and extracted via methods that provide complete removal of the inoculum from the test article (examples include sonication, vortexing, and/or manual extraction, that is, stomacher).

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>4</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

4.4 Serial dilutions are made, then pour or spread plates are made of each dilution. Agar plates and dilution broths are incubated for  $48 \pm 2$ – $48 \text{ h} \pm 2 \text{ h}$  at a specified temperature dependent upon the optimal temperature for test organism.

4.5 Bacterial colonies from each dilution series are counted and recorded.

4.6 Calculation of percent reduction of bacteria from treated versus untreated samples is made.

## 5. Significance and Use

5.1 This method can be used to evaluate effectiveness of incorporated/bound antimicrobials in hydrophobic materials such as plastics, epoxy resins, as well as other hard surfaces.

5.2 The aqueous based bacterial inoculum remains in close, uniform contact in a “pseudo-biofilm” state with the treated material. The percent reduction in the surviving populations of challenge bacterial cells at 24 h versus those recovered from a non-treated control is determined.

5.3 The hydrophobic substrate may be repeatedly tested over time for assessment of persistent antimicrobial activity.

## 6. Apparatus

6.1 *Erlenmeyer Flask*, 250 mL.

6.2 *Petri Dishes*, ~~(15 ×)~~(15 mm by 100 mm), sterile.

6.3 *Colony Counter*.

6.4 *Specimen Cups*, (120 mL), sterile or equivalent sterile equipment for extraction.

6.5 *Pipetters*, (1000  $\mu\text{L}$ ) positive displacement.

6.6 *Pipette Tips*, sterile.

6.7 *Test Tubes*, ~~16 ×~~16 mm by 100 mm.

6.8 *Incubator*, set at required temperature ~~(25–35–)~~( $25 \text{ }^\circ\text{C}$  to  $35 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$ ).

6.9 *Autoclave*.

6.10 *Water Bath*, capable of maintaining water at ~~45~~ $45 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$ .

6.11 *Sterile Cotton Swabs*.

6.12 *Sonic Bath*, 47 Khz, cleaning non-cavitating.

6.13 *Vortex Mixer*.

6.14 *pH Meter*.

6.15 *Hot Plate*, with stirrer.

6.16 *Spectrophotometer*, set at 600 nm.