



Designation: C317/C317M – 24

Standard Specification for Gypsum Concrete¹

This standard is issued under the fixed designation C317/C317M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers mill-mixed gypsum concrete, consisting essentially of calcined gypsum and suitable aggregate, requiring the addition of water only at the job site. Gypsum concrete is intended for use in the construction of poured-in-place roof decks or slabs. Two classes, based on the compressive strength and density, are covered.

1.2 The values stated in either inch-pound units or SI units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

- 2.1 *ASTM Standards:*²
- [C11 Terminology Relating to Gypsum and Related Building Materials and Systems](#)
 - [C28/C28M Specification for Gypsum Plasters](#)
 - [C35 Specification for Inorganic Aggregates for Use in Gypsum Plaster](#)
 - [C472 Test Methods for Physical Testing of Gypsum, Gypsum Plasters, and Gypsum Concrete](#)

3. Terminology

3.1 Definitions of terms shall be in accordance with Terminology [C11](#).

¹ This specification is under the jurisdiction of ASTM Committee [C11](#) on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee [C11.01](#) on Specifications and Test Methods for Gypsum Products.

Current edition approved April 1, 2024. Published April 2024. Originally approved in 1953. Last previous edition approved in 2019 as C317/C317M – 00 (2019). DOI: 10.1520/C0317_C0317M-24.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Materials and Manufacture

4.1 Gypsum concrete shall consist of calcined gypsum to which is added aggregates, wood chips, or wood shavings in proportion to meet the applicable requirements of this specification.

4.2 *Calcined Gypsum*—Specification [C28/C28M](#).

4.3 *Aggregates*—Specification [C35](#).

4.4 *Wood Chips or Wood Shavings*, shall be dry wood, uniform and clean in appearance, passing a 1-in. [25 mm] sieve, and not more than 1/16 in. [1.5 mm] thick.

5. Physical Properties

5.1 Determine the physical properties of gypsum concrete in accordance with Test Methods [C472](#).

5.1.1 *Setting Time*—Gypsum concrete shall set in not less than 20 min and not more than 90 min determined by the Vicat method.

5.1.2 *Compressive Strength*—Gypsum concrete shall have the following compressive strength for the respective classes:

Class	Compressive Strength, psi [MPa]
A	500 [3.5] – 1000 [7.0]
B	>1000 [7.0]

5.1.3 *Density*—Gypsum concrete, Class A, shall have a density of not more than 60 lb/ft³ [960 kg/m³].

6. Sampling

6.1 Randomly select at least 1 % of the packages, but not less than five packages. Take samples from both the outer portion and the center of each package. Mix the samples so obtained to provide a composite sample of not less than 15 lb [6.5 kg]. Immediately place the sample in a clean, dry, airtight container for delivery to the laboratory.

7. Inspection

7.1 Inspection of the gypsum concrete shall be agreed upon between the purchaser and the supplier as part of the purchase agreement.

*A Summary of Changes section appears at the end of this standard

8. Rejection

8.1 Rejection of gypsum concrete that fails to conform to the requirements of this specification shall be reported to the producer or supplier promptly and in writing. The notice of rejection shall contain a statement documenting how the gypsum concrete has failed to conform to the requirements of this specification.

9. Certification

9.1 When specified in the purchase agreement, a producer's or supplier's report shall be furnished at the time of shipment certifying that the product is in compliance with this specification.

10. Packaging and Marking

10.1 Gypsum concrete shall be shipped dry and free of lumps.

10.2 When shipped for resale, the following information shall be legibly marked on each package or on a tag of suitable size attached thereto:

10.2.1 Name of the manufacturer or the seller,

10.2.2 Brand,

10.2.3 Description, and

10.2.4 Net and gross weight of the package.

11. Keywords

11.1 aggregates; calcined gypsum; gypsum; gypsum concrete

SUMMARY OF CHANGES

Committee C11 has identified the location of selected changes to this standard since the last issue (C317/C317M – 00 (2019)) that may impact the use of this standard. (Approved April 1, 2024.)

(1) Section 7 for Test Methods was combined with Section 5 and the range for Class A was clarified to be 500 psi to 1000 psi [3.5 MPa to 7.0 MPa].

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/