
Dc`ja Yfb]a Uhf]U]!`I [cHj `Ub`Y`hYbXYbW`na Yg]]b`dfc]nj cXcj `bUcgbcj]\ ca c!
]b`cdc`ja Yfcj `j]b]`cf]XU`XUdf]`dcj]yUb] `hYa dYfUi fU `gdfcy U`c``cfcj cX]`U]
Xfi [Y_]g`YdfcXi `hY!` ("XY.`DchYbW]ca Yf]`g_Ua YfcXUf]GC`% &!(.%- ' Ł

Plastics - Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures - Part 4: Potentiometric method (ISO 182-4:1993)

STANDARD PREVIEW

Kunststoffe - Bestimmung der Neigung von Formmassen und Erzeugnissen auf der Basis von Vinyl-chlorid-Homopolymeren und Copolymeren, bei erhöhten Temperaturen Chlorwasserstoff und andere saure Produkte abzugeben - Teil 4: Potentiometrisches Verfahren (ISO 182-4:1993)

<https://standards.itih.ai/catalog/standards/sist/cea4abe1-c495-468c-a7c4-0a320edb79c7/sist-en-iso-182-4-2001>

Plastiques - Détermination de la tendance des compositions a base d'homopolymères et copolymères du chlorure de vinyle a dégager du chlorure d'hydrogène et éventuellement d'autres produits acides a températures élevées - Partie 4: Méthode potentiométrique (ISO 182-4:1993)

Ta slovenski standard je istoveten z: EN ISO 182-4:2000

ICS:

83.080.20 Plastomeri Thermoplastic materials

SIST EN ISO 182-4:2001 en

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 182-4

September 2000

ICS 83.080

English version

Plastics - Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures - Part 4: Potentiometric method (ISO 182-4:1993)

Plastiques - Détermination de la tendance des compositions à base d'homopolymères et copolymères du chlorure de vinyle à dégager du chlorure d'hydrogène et éventuellement d'autres produits acides à températures élevées - Partie 4: Méthode potentiométrique (ISO 182-4:1993)

Kunststoffe - Bestimmung der Neigung von Formmassen und Erzeugnissen auf der Basis von Vinyl-chlorid-Homopolymeren und -Copolymeren, bei erhöhten Temperaturen Chlorwasserstoff und andere saure Produkte abzugeben - Teil 4: Potentiometrisches Verfahren (ISO 182-4:1993)

iTeh STANDARD PREVIEW

This European Standard was approved by CEN on 8 September 2000.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN ISO 182-4:2000

Foreword

The text of the International Standard from Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2001, and conflicting national standards shall be withdrawn at the latest by March 2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 182-4:1993 has been approved by CEN as a European Standard without any modification.

NOTE: Normative references to International Standards are listed in annex ZA (normative).

[SIST EN ISO 182-4:2001](https://standards.iteh.ai/catalog/standards/sist/cea4abe1-c495-468c-a7c4-0a320edb79c7/sist-en-iso-182-4-2001)

<https://standards.iteh.ai/catalog/standards/sist/cea4abe1-c495-468c-a7c4-0a320edb79c7/sist-en-iso-182-4-2001>

STANDARD PREVIEW
(standards.iteh.ai)

Annex ZA (normative)
Normative references to international publications
with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 182-2	1990	Plastics – Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures – Part 2 : ph method	EN ISO 182-2	1999
ISO 182-3	1993	Plastics – Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures – Part 3 : Conductometric method	EN ISO 182-3	2000

<https://standards.iteh.ai/catalog/standards/sist/cea4abe1-c495-468c-a7c4-0a320edb79c7/sist-en-iso-182-4-2001>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 182-4:2001

<https://standards.iteh.ai/catalog/standards/sist/cea4abe1-c495-468c-a7c4-0a320edb79c7/sist-en-iso-182-4-2001>

INTERNATIONAL
STANDARD**ISO**
182-4First edition
1993-04-01

**Plastics — Determination of the tendency
of compounds and products based on vinyl
chloride homopolymers and copolymers to
evolve hydrogen chloride and any other
acidic products at elevated
temperatures —****Part 4:** EN ISO 182-4:2001

<https://standards.iteh.ai/catalog/standards/sist/cea4abe1-c495-468c-a7c4-0a526cd679c7/sist-en-iso-182-4-2001>
Potentiometric method

*Plastiques — Détermination de la tendance des compositions à base
d'homopolymères et copolymères du chlorure de vinyle à dégager du
chlorure d'hydrogène et éventuellement d'autres produits acides à
températures élevées —*

Partie 4: Méthode potentiométrique

Reference number
ISO 182-4:1993(E)

ISO 182-4:1993(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 182-4 was prepared by Technical Committee ISO/TC 61, *Plastics*, Sub-Committee SC 6, *Ageing, chemical and environmental resistance*.

Together with the three other parts of ISO 182, it cancels and replaces ISO Recommendation R 182:1970, of which the four parts of ISO 182 constitute a technical revision.

ISO 182 consists of the following parts, under the general title *Plastics — Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures*:

- Part 1: Congo red method
- Part 2: pH method
- Part 3: Conductometric method
- Part 4: Potentiometric method

Annexes A and B of this part of ISO 182 are for information only.

© ISO 1993

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Plastics — Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures —

Part 4: Potentiometric method

iTeh STANDARD PREVIEW

WARNING — The use of this part of ISO 182 may involve hazardous materials, operations and equipment. This part of ISO 182 does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this part of ISO 182 to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

<https://standards.itih.ai/catalog/standards/sist/cea4abel-c495-468c-a7c4-0a320edb79c7/sist-en-iso-182-4-2001>

1 Scope

1.1 This part of ISO 182 specifies a method for the determination of the thermal stability at elevated temperature of compounds and products based on vinyl chloride homopolymers and copolymers (in the following text abbreviated as PVC) which undergo dehydrochlorination (the evolution of hydrogen chloride).

1.2 The method may be used as a quality control test during manufacture and conversion of PVC compounds. It may also be used for the characterization of PVC compounds and products, especially with regard to the effectiveness of their heat-stabilizing systems.

It is suitable for coloured PVC compounds and products for which a discolouration test under the action of heat may be unsatisfactory.

1.3 The method is recommended for compounded PVC materials and products only, although it can be used for polymers in powder form under appropriate conditions to be agreed upon between the interested

parties. The method is not recommended for PVC compounds in the form of dry blends, since such materials may not be sufficiently homogeneous.

1.4 PVC compounds and products may evolve other decomposition products in addition to hydrogen chloride at elevated temperatures. A limited number of these products, originating from the decomposition of certain comonomers (such as vinyl esters of organic acids) or of plasticizers, stabilizers and other additives, may effect the pH or the conductivity of an aqueous solution when they are absorbed. Consequently, the results obtained for different products by the methods described in Parts 2 and 3 of ISO 182 may not be comparable with those obtained using the method described in the present part of ISO 182.

1.5 This part of ISO 182 specifies a potentiometric method for the determination of chloride ion (Cl^-) concentration (expressed as pCl) in an absorbing solution, independent of the presence of other ions. The value pCl is defined as $-\lg c_{\text{Cl}}$, where c_{Cl} is the molar concentration of chloride ions. This method is, therefore, particularly recommended for plasticized PVC compounds and copolymers.

ISO 182-4:1993(E)

1.6 This method may also be applied to other plastics materials that can evolve hydrogen chloride when heated under the conditions prescribed by the relevant specifications, or as agreed upon between the interested parties.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 182. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 182 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 182-2:1990, *Plastics — Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures — Part 2: pH method.*

ISO 182-3:1993, *Plastics — Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures — Part 3: Conductometric method.*

ISO 565:1990, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings.*

ISO 4793:1980, *Laboratory sintered (fritted) filters — Porosity grading, classification and designation.*

ISO 5725:1986, *Precision of test methods — Determination of repeatability and reproducibility for a standard test method by inter-laboratory tests.*

ISO 6353-2:1983, *Reagents for chemical analysis — Part 2: Specifications — First series.*

3 Definition

For the purposes of this part of ISO 182, the following definition applies.

3.1 stability time, t_s : Time, measured by reference to a predetermined change in the pCl of an absorbing solution, required for a certain amount of hydrogen chloride to be evolved when a prescribed mass of PVC compound or product is maintained at an elevated temperature under the test conditions specified in this part of ISO 182.

4 Principle

A test portion of the PVC compound or product is maintained at an agreed temperature in a nitrogen gas stream and the hydrogen chloride evolved is absorbed in a given amount of an appropriate solution. The amount of hydrogen chloride evolved is determined potentiometrically in relation to the recorded change in pCl of the absorbing solution.

5 Reagents

During the test, use only reagents of recognized analytical grade in accordance with ISO 6353-2.

5.1 Pure nitrogen, containing less than 6 ppm oxygen and less than 0,1 ppm carbon dioxide by volume. The purity shall be such that when the gas is passed through the absorbing solution for 1 h at a rate of $7,2 \text{ l/h} \pm 0,1 \text{ l/h}$, the conductivity of the water remains unchanged.

The gas shall be dried by passing it through a suitable drying agent and the flow-rate through the dehydrochlorination cell adjusted by means of a needle valve and measured using a suitable flowmeter.

5.2 Hydrochloric acid, aqueous solution, $c(\text{HCl}) = 0,01 \text{ mol/l}$.

5.3 Distilled or demineralized water.

5.4 Potassium nitrate (KNO_3), potassium sulfate (K_2SO_4) or other salts, for the preparation of the absorbing solution (see 10.4).

6 Apparatus

The general arrangement of the apparatus, shown in figure 1, includes a re-usable dehydrochlorination cell A. This cell may be replaced by a disposable cell B.

6.1 Dehydrochlorination cells.

6.1.1 Cell A (re-usable), with shape and dimensions as shown in figure 2.


A recommended procedure for cleaning the cell is given in annex A.

6.1.2 Cell B (disposable), with shape and dimensions as shown in figure 3.

NOTE 1 Other types of cell may be employed if it has been proved that the results obtained are equivalent to those obtained with one of the cells described in 6.1.1 and 6.1.2.

6.2 Test portion holder, for use with cell A. The test portion is supported on a porous sintered-glass disc (grade P 100, see ISO 4793), 10 mm in diameter.

To prevent blocking of the porous disc, it is advisable to place a thin, soft layer of glass wool between it and the test portion.



- | | |
|---|---------------------------------------|
| 1 N ₂ cylinder | 9 Thermometer (scale division 0,1 °C) |
| 2 Purification train | 10 Silicone oil |
| 3 Ball flowmeter | 11 Magnetic stirrer |
| 4 Electronic temperature controller (scale division 0,1 °C) | 12 Absorbing solution |
| 5 Temperature sensor | 13 Measuring electrode(s) |
| 6 Heating bath | 14 Potentiometer |
| 7 PVC test portion | 15 Recorder |
| 8 Dehydrochlorination cell | |

Figure 1 — General arrangement of apparatus




Figure 2 — Cell A (re-usable) for dehydrochlorination of PVC samples

ITh STANDARD PREVIEW
(standards.iteh.ai)

SISTEN ISO 182-4:2001

<https://standards.iteh.ai/catalog/standards/sist/cea4abe1-c495-468c-a7c4-0a320ed1b79c7/sist-en-iso-182-4-2001>