
Dc`ja Yfb]a Uhf]U]!'Dc`jghfYbg_]fDGLa Uhf]U]nUcV]_cj Ub^]b`Y_gfi X]fUb^]!'%
XY.'G]ghYa `cnbU Yj Ub^]b`dcX`U] YnUgdYWZ_UW^fIGC`% &&!%% - (Ł

Plastics - Polystyrene (PS) moulding and extrusion materials - Part 1: Designation system and basis for specifications (ISO 1622-1:1994)

Kunststoffe - Polystyrol (PS)-Formmassen - Teil 1: Bezeichnungssystem und Basis für Spezifikationen (ISO 1622-1:1994)

Plastiques - Polystyrene (PS) pour moulage et extrusion - Partie 1: Systeme de désignation et base de spécification (ISO 1622-1:1994)

<https://standards.iteh.ai/catalog/standards/sist/f94872e-4862-4d60-84c1-3ef04bd15967/sist-en-iso-1622-1-2000>

Ta slovenski standard je istoveten z: EN ISO 1622-1:1999

ICS:

83.080.20 Plastomeri Thermoplastic materials

SIST EN ISO 1622-1:2000 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 1622-1:2000

<https://standards.iteh.ai/catalog/standards/sist/ff94872e-4862-4d60-84c1-3ef04bd15967/sist-en-iso-1622-1-2000>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 1622-1

May 1999

ICS 83.080.20

English version

**Plastics - Polystyrene (PS) moulding and extrusion materials -
Part 1: Designation system and basis for specifications (ISO
1622-1:1994)**

Plastiques - Polystyrène (PS) pour moulage et extrusion -
Partie 1: Système de désignation et base de spécification
(ISO 1622-1:1994)

Kunststoffe - Polystyrol (PS)-Formmassen - Teil 1:
Bezeichnungssystem und Basis für Spezifikationen (ISO
1622-1:1994)

This European Standard was approved by CEN on 16 April 1999.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of the International Standard from Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1999, and conflicting national standards shall be withdrawn at the latest by November 1999.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 1622-1:1994 has been approved by CEN as a European Standard without any modification.

NOTE: Normative references to International Standards are listed in annex ZA (normative).

<https://standards.iteh.ai/catalog/standards/sist/f94872e-4862-4d60-84c1-3ef04bd15967/sist-en-iso-1622-1-2000>



Annex ZA (normative)
Normative references to international publications
with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 306	1994	Plastics - Thermoplastic materials - Determination of Vicat softening temperature (VST)	EN ISO 306	1996
ISO 1043-1	1997	Plastics - Symbols and abbreviated terms - Part 1: Basic polymers and their special characteristics	EN ISO 1043-1	1999
ISO 1133	1997	Plastics - Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics	EN ISO 1133	1999
ISO 1622-2	1995	Plastics - Polystyrene (PS) moulding and extrusion materials - Part 2: Preparation of test specimens and determination of properties	EN ISO 1622-2	1999

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 1622-1:2000](https://standards.iteh.ai/catalog/standards/sist/ff94872e-4862-4d60-84c1-3ef04bd15967/sist-en-iso-1622-1-2000)

<https://standards.iteh.ai/catalog/standards/sist/ff94872e-4862-4d60-84c1-3ef04bd15967/sist-en-iso-1622-1-2000>

INTERNATIONAL STANDARD

ISO
1622-1

Second edition
1994-10-15

Plastics — Polystyrene (PS) moulding and extrusion materials —

Part 1:

Designation system and basis for
specifications

[SIST EN ISO 1622-1:2000](https://standards.iteh.ai/catalog/standards/sist/b94877e-4862-4d60-84c1-3ef04bd1596/sist-en-iso-1622-1-2000)

<https://standards.iteh.ai/catalog/standards/sist/b94877e-4862-4d60-84c1-3ef04bd1596/sist-en-iso-1622-1-2000>
*Plastiques — Polystyrène (PS) pour moulage et extrusion —
Partie 1: Système de désignation et base de spécification*



Reference number
ISO 1622-1:1994(E)

ISO 1622-1:1994(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 1622-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This second edition cancels and replaces the first edition (ISO 1622-1:1985), the text of which has been brought into accordance with the revised frame text for designation standards.

ISO 1622 consists of the following parts, under the general title *Plastics — Polystyrene (PS) moulding and extrusion materials*:

- Part 1: *Designation system and basis for specifications*
- Part 2: *Preparation of test specimens and determination of properties*

© ISO 1994

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Plastics — Polystyrene (PS) moulding and extrusion materials —

Part 1:

Designation system and basis for specifications

iTeh STANDARD PREVIEW (standards.iteh.ai)

1 Scope

1.1 This part of ISO 1622 establishes a system of designation for polystyrene thermoplastic material, which may be used as the basis for specifications.

1.2 The types of polystyrene plastics are differentiated from each other by a classification system based on appropriate levels of the designatory properties

a) Vicat softening temperature

b) melt mass-flow rate

and on information about the intended application and/or method of processing, important properties, additives and colorants.

1.3 This part of ISO 1622 is applicable to all amorphous polystyrene homopolymers.

It applies to materials ready for normal use, unmodified or modified by colorants, additives, fillers, etc.

This part of ISO 1622 does not apply to expanded polystyrene, styrene copolymers, homopolymers of substituted styrene and those modified with other polymers such as elastomers.

1.4 It is not intended to imply that materials having the same designation give necessarily the same performance. This part of ISO 1622 does not provide engineering data, performance data or data on processing conditions which may be required to specify a material for a particular application and/or method of processing.

If such additional properties are required, they shall be determined in accordance with the test methods specified in part 2 of this International Standard, if suitable.

1.5 In order to specify a thermoplastic material for a particular application or to ensure reproducible processing, additional requirements may be given in data block 5 (see clause 3, introductory paragraph).