

INTERNATIONAL ELECTROTECHNICAL COMMISSION  
COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

---

**IEC 60891**  
Edition 3.0 2021-10

**PHOTOVOLTAIC DEVICES – PROCEDURES  
FOR TEMPERATURE AND IRRADIANCE  
CORRECTIONS TO MEASURED I-V  
CHARACTERISTICS**

**IEC 60891**  
Édition 3.0 2021-10

**DISPOSITIFS PHOTOVOLTAÏQUES –  
PROCÉDURES POUR LES CORRECTIONS EN  
FONCTION DE LA TEMPÉRATURE ET DE  
L'ÉCLAIREMENT À APPLIQUER AUX  
CARACTÉRISTIQUES I-V MESURÉES**

## CORRIGENDUM 1

Corrections to the French version appear after the English text.

Les corrections à la version française sont données après le texte anglais.

*Replace the existing second item in the dashed list in 5.1 by the following:*

Relative temperature coefficients ( $\alpha_{rel}$ ,  $\beta_{rel}$  and  $\delta_{rel}$ ) expressed in percentage per unit temperature (%/K or %/°C) can be determined by dividing the calculated value of temperature coefficients  $\alpha$ ,  $\beta$ , and  $\delta$  by the values of short-circuit current, open-circuit voltage and maximum power respectively determined from the least squares fit at 25 °C corresponding to an irradiance of 1 000 W/m<sup>2</sup>. The relative coefficients so determined are valid at the irradiance and spectrum at which the measurements were made. For linear PV devices with respect to irradiance (typically the case for c-Si), the relative temperature coefficient  $\alpha_{rel}$  is valid over the entire range of irradiance for which the device is linear according to IEC 60904-10, whereas the relative temperature coefficient  $\beta_{rel}$  scales with  $f^2(G)$  (see Formula (7)).