



SLOVENSKI STANDARD
SIST EN ISO 120:2000

01-maj-2000

Plastice - Fenol-formaldehidne oblikovane delce - Določanje prostornine amonijaka in amonijevih spojin - Metodologija primerjalne kolorimetrije (ISO 120:1977)

Plastics - Phenol-formaldehyde mouldings - Determination of free ammonia and ammonium compounds - Colorimetric comparison method (ISO 120:1977)

Kunststoffe - Phenoplast-Formteile - Bestimmung von freiem Ammoniak und Ammoniumverbindungen - Colorimetrisches Vergleichsverfahren (ISO 120:1977)

Plastiques - Pièces moulées à base de phénoplastes - Dosage de l'ammoniac libre et des composés ammoniacaux - Méthode par comparaison colorimétrique (ISO 120:1977)

<https://standards.iteh.ai/catalog/standards/sist/6ee4d3e1-65d2-4a93-90b6-3c09a1d156ae/sist-en-iso-120-2000>

Ta slovenski standard je istoveten z: **EN ISO 120:1998**

ICS:

83.080.10 Duromeri

Thermosetting materials

SIST EN ISO 120:2000

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 120:2000

<https://standards.iteh.ai/catalog/standards/sist/6ee4d3e1-65d2-4a93-90b6-3c09a1d156ae/sist-en-iso-120-2000>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 120

July 1998

ICS 83.080.10

Descriptors: see ISO document

English version

Plastics - Phenol-formaldehyde mouldings - Determination of
free ammonia and ammonium compounds - Colorimetric
comparison method (ISO 120:1977)

Plastiques - Pièces moulées à base de phénoplastes -
Dosage de l'ammoniac libre et des composés
ammoniacaux - Méthode par comparaison colorimétrique
(ISO 120:1977)

Kunststoffe - Phenoplast-Formteile - Bestimmung von
freiem Ammoniak und Ammoniumverbindungen -
Colorimetrisches Vergleichsverfahren (ISO 120:1977)

This European Standard was approved by CEN on 12 June 1998.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

<https://standards.iteh.ai/catalog/standards/sist/6ee4d3e1-65d2-4a93-90b6->

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN ISO 120:1998

Foreword

The text of the International Standard from Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 1999, and conflicting national standards shall be withdrawn at the latest by January 1999.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 120:1977 has been approved by CEN as a European Standard without any modification.

(standards.iteh.ai)

SIST EN ISO 120:2000

<https://standards.iteh.ai/catalog/standards/sist/6ee4d3e1-65d2-4a93-90b6-3c09a1d156ae/sist-en-iso-120-2000>



ALIMBEVOJIS ANTIKURIS
SUDOLWES IN TEPHIS HE ENTERTSMM
.....
08A 000 000
.....
INTERNATIONAL UNION OF PURE AND APPLIED CHEMISTRY

INTERNATIONAL STANDARD**120**

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Plastics — Phenol-formaldehyde mouldings — Determination of free ammonia and ammonium compounds — Colorimetric comparison method

Plastiques — Pièces moulées à base de phénoplastiques — Dosage de l'ammoniac libre et des composés ammoniacaux — Méthode par comparaison colorimétrique

(standards.iteh.ai)

First edition — 1977-10-01

[SIST EN ISO 120:2000](https://standards.iteh.ai/catalog/standards/sist/6ee4d3e1-65d2-4a93-90b6-3c09a1d156ae/sist-en-iso-120-2000)

<https://standards.iteh.ai/catalog/standards/sist/6ee4d3e1-65d2-4a93-90b6-3c09a1d156ae/sist-en-iso-120-2000>

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 120 was developed by Technical Committee ISO/TC 61, *Plastics*, and was circulated to the member bodies in October 1975.

It has been approved by the member bodies of the following countries:

Australia	Iran	South Africa, Rep. of
Austria	Israel	Spain
Belgium	Italy	Sweden
Brazil	Japan	Switzerland
Czechoslovakia	Mexico	Turkey
Finland	Netherlands	United Kingdom
France	New Zealand	U.S.A.
Germany	Peru	U.S.S.R.
Hungary	Poland	Yugoslavia
India	Romania	

No member body expressed disapproval of the document.

This International Standard cancels and replaces ISO Recommendation R 120-1959, of which it constitutes a technical revision.

Plastics – Phenol-formaldehyde mouldings – Determination of free ammonia and ammonium compounds – Colorimetric comparison method

1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies a colorimetric comparison method for the semi-quantitative determination of the amount of ammonia in phenol-formaldehyde mouldings.

NOTE – This International Standard does not provide an absolute measure of the ammonia present.

The amount of ammonia in a moulded article is of importance when corrosion of metal inserts or contamination of foodstuffs in contact with the article has to be considered.

2 REFERENCES

ISO 565, *Test sieves – Woven metal wire cloth and perforated plate – Nominal sizes of apertures*.

ISO 648, *Laboratory glassware – One-mark pipettes*.

3 PRINCIPLE

Hot aqueous extraction of free ammonia from a powdered test portion. Distillation of the aqueous extract in the presence of potassium permanganate and sodium hydroxide solution. Coloration of the distillate by reaction with Nessler reagent and comparison of the colour with that obtained in each of a series of standard matching solutions.

4 REAGENTS

During the analysis, use only ammonia-free reagents of recognized analytical grade, and only ammonia-free distilled water or water of equivalent purity.

4.1 Potassium permanganate.

4.2 Sodium hydroxide, 2 % (m/m) solution.

4.3 Standard matching stock solution, containing 10 mg of NH₃ per litre.

Dissolve 31,5 mg of ammonium chloride in 1 000 ml of water.

4.4 Nessler reagent.

5 APPARATUS

Ordinary laboratory apparatus, and

5.1 Means for reducing the mouldings to a powder.

5.2 Sieve, with nominal apertures of 250 μm, conforming to ISO 565.

5.3 Balance, accurate to 0,01 g.

5.4 Glass-stoppered flask, 250 ml capacity.

5.5 Distillation apparatus, comprising a flask of 250 ml capacity, splash head and a condenser.

5.6 Filter funnel with hardened medium speed filter paper

5.7 Pipettes, capacities 2 and 10 ml, complying with the requirements of ISO 648.

5.8 Nessler cylinders, 50 ml capacity.

6 PREPARATION OF TEST SAMPLE

Reduce a fully representative sample of the mouldings to powder by filing, milling, grinding, turning or drilling, taking care that no undue heating of the material occurs. Sieve this powder, using the sieve (5.2), and use for the test that portion passing through the sieve. Keep the sample in a tightly stoppered flask until required.

The extraction with water (see 7.2) shall begin within 1 h of grinding the moulding.

NOTE – The method of reduction to powder can affect the results. In cases of dispute, or for referee purposes, the method should be agreed between the interested parties.

7 PROCEDURE

7.1 Test portion

Weigh, to the nearest 0,01 g, 5 ± 0,1 g of the sieved material (see clause 6).

ISO 120-1977 (E)

7.2 Preparation of the test solution

Place the test portion (7.1) in the flask (5.4) and cover it with ten times its mass of water at a temperature of 90 to 100 °C. Stopper the flask and shake it so that the powder is thoroughly wetted. Allow it to cool at room temperature, for 1 h, with occasional shaking. Then filter the contents of the flask, without suction, through the filter funnel (5.6). Transfer, with a pipette (5.7), 10 ml of the filtered extract, corresponding to 1 g of the powder, into the flask of the distillation apparatus (5.5).

NOTE — Before using the distillation apparatus, it is recommended that it should be freed from any ammonia which may be present by distilling a quantity of distilled water in it until the addition of 2 ml of Nessler reagent (4.4) to 50 ml of distillate does not give rise to any colour.

Add to the flask 0,1 g of potassium permanganate (4.1) and 10 ml of the sodium hydroxide solution (4.2). Slowly distil the mixture; collect the first 15 ml of the distillate in a Nessler cylinder (5.8) and dilute to 50 ml with water.

7.3 Determination

Transfer, with a pipette (5.7), 2 ml of the Nessler reagent (4.4) into the Nessler cylinder and determine the ammonia content by matching the colour of the test solution (7.2) with that of one of a series of standard matching solutions to which Nessler reagent has been added at the same time as to the test solution. To make the standard matching solutions transfer, with a pipette, 1, 2, 3, 4, 5 and 6 ml portions of standard matching stock solution (4.3) into each of a series of six Nessler cylinders (5.8) and dilute to 50 ml with water. These correspond to 0,01, 0,02, 0,03, 0,04, 0,05 and 0,06 mg of ammonia.

NOTE — If the 15 ml of distillate is found to contain more than 0,06 mg of ammonia, a 10 ml portion of the filtered extract shall be suitably diluted and a 10 ml portion of this diluted solution used in the distillation. An appropriate dilution factor should be used in the calculation.

8 EXPRESSION OF RESULTS

The amount of free ammonia and ammonium compounds, expressed as a percentage by mass of ammonia (NH₃), is given by the formula

$$\frac{m \times D}{10}$$

where

m is the mass, in milligrams, of ammonia contained in the appropriate standard matching solution from the series (see 7.3);

D is the dilution factor in the case where the filtrate is diluted before distillation :

$$D = \frac{V_2}{V_1}$$

where

V_1 is the volume in millilitres of the portion of the filtered extract before dilution ($V_1 = 10$ ml);

V_2 is the volume in millilitres of this 10 ml portion of the filtered extract after dilution.

9 TEST REPORT

The test report shall include the following particulars :

- reference to this International Standard;
- full details necessary for the identification of the sample;
- the method used for reducing the mouldings to powder;
- amount of free ammonia;
- date of the test.