



Designation: B 589 – 94 (Reapproved 1999)<sup>ε1</sup>

## Standard Specification for Refined Palladium<sup>1</sup>

This standard is issued under the fixed designation B 589; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—UNS number was added in June 1999.

### 1. Scope

1.1 This specification covers refined palladium as sponge, cast bar, and wrought forms (Note 1) in one grade as follows:

1.1.1 *Grade 99.95 (UNS P03995)*— Palladium having a purity of 99.95 %.

NOTE 1—Other forms of unfabricated palladium of commerce are not to be excluded under this specification.

NOTE 2—For the purposes of determining conformance with this specification, an observed value obtained from analysis shall be rounded to the nearest unit in the last right hand place of figures used in expressing the limiting value, in accordance with the rounding method of Practice E 29.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

### 2. Referenced Documents

2.1 *ASTM Standards:*

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications<sup>2</sup>

### 3. Materials and Manufacture

3.1 The metal may be produced by any refining process that yields a product capable of meeting the chemical requirements of this specification. The purchaser, upon request, shall be informed of the refining process used.

3.2 The surfaces of bars and wrought forms shall exhibit quality generally acceptable to the trade.

### 4. Chemical Composition

4.1 The refined palladium shall conform to the requirements as to the chemical composition prescribed in Table 1.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B-2 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.05 on Precious Metals.

Current edition approved Feb. 15, 1994. Published April 1994. Originally published as B 589 – 73. Last previous edition B 589 – 82 (1987).

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 14.02.

TABLE 1 Chemical Requirements

Element <sup>A</sup>	Composition, %
	Grade 99.95 (UNS P03995)
Palladium, min (by difference)	99.95
Platinum, max	...
Rhodium, max	...
Ruthenium, max	...
Iridium, max	...
Total platinum group metals other than palladium, max	0.03
Gold, max	0.01
Silver, max	0.01
Lead, max	0.005
Tin, max	0.005
Zinc, max	0.0025
Iron, max	0.005
Copper, max	0.005
Silicon, max	0.005
Magnesium, max	0.005
Calcium, max	0.005
Aluminum, max	0.005
Nickel, max	0.005
Chromium, max	0.001
Cobalt, max	0.001
Manganese, max	0.001
Antimony, max	0.002

<sup>A</sup> By agreement between manufacturer and purchaser analyses may be required and limits established for elements or compounds not specified in this table.

### 5. Sampling

5.1 The value of this material is such that special attention must be paid to sampling procedures. The purchaser and manufacturer shall agree upon the sampling procedures used.

5.2 *Lot Size*—Sampling lots shall consist of the following:

5.2.1 *Sponge*—A single refining lot, and

5.2.2 *Other Forms*— A single melt or primary consolidation.

### 6. Method of Analysis

6.1 Pending the development of standard ASTM methods of chemical or spectrographic analysis, or both, the methods to be used shall be a matter of agreement between the manufacturer and the purchaser.