



SLOVENSKI STANDARD

SIST EN 1842:1999

01-maj-1999

Polimerni materiali – Duromerni materiali za oblikovanje (SMC – BMC) – Določevanje skrčka pri oblikovanju s stiskanjem

Plastics - Thermoset moulding compounds (SMC - BMC) - Determination of compression moulding shrinkage

Kunststoffe - Wärmehärtende Formmassen (SMC - BMC) - Bestimmung der Verarbeitungsschwindung

Plastiques - Matières à mouler thermodurcissables (SMC - BMC) - Détermination du retrait au moulage par compression

[SIST EN 1842:1999](https://standards.iteh.ai/catalog/standards/sist/016ecc55-38da-42e7-8c62-c0ed1a43d8c9/sist-en-1842-1999)

[https://standards.iteh.ai/catalog/standards/sist/016ecc55-38da-42e7-8c62-](https://standards.iteh.ai/catalog/standards/sist/016ecc55-38da-42e7-8c62-c0ed1a43d8c9/sist-en-1842-1999)

[c0ed1a43d8c9/sist-en-1842-1999](https://standards.iteh.ai/catalog/standards/sist/016ecc55-38da-42e7-8c62-c0ed1a43d8c9/sist-en-1842-1999)

Ta slovenski standard je istoveten z: EN 1842:1997

ICS:

83.080.10 Duromeri

Thermosetting materials

SIST EN 1842:1999

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1842:1999

<https://standards.iteh.ai/catalog/standards/sist/016ecc55-38da-42e7-8c62-c0ed1a43d8c9/sist-en-1842-1999>

EUROPEAN STANDARD

EN 1842

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 1997

ICS 83.080.10

Descriptors: Plastics, thermosetting resins, plastic moulding, compression moulding, tests, determination, shrinkage

English version

**Plastics - Thermoset moulding compounds (SMC -
BMC) - Determination of compression moulding
shrinkage**

Plastiques - Matières à mouler thermodurcissables (SMC - BMC) - Détermination du retrait au moulage par compression

Kunststoffe - Wärmehärtende Formmassen (SMC - BMC) - Bestimmung der Verarbeitungsschwindung

STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1842:1999

<https://standards.iteh.ai/catalog/standards/sist/016ecc55-38da-42e7-8c62-c0ed1a43d8c9/sist-en-1842-1999>

This European Standard was approved by CEN on 1997-06-29. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Definitions	4
4 Apparatus.....	5
5 Sampling and conditioning of the moulding compound.....	5
6 Test specimens.....	5
7 Procedure.....	5
8 Expression of results	6
9 Test report.....	7
10 Precision	7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1842:1999

<https://standards.iteh.ai/catalog/standards/sist/016ecc55-38da-42e7-8c62-c0ed1a43d8c9/sist-en-1842-1999>

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 1998, and conflicting national standards shall be withdrawn at the latest by January 1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 1842:1999

<https://standards.iteh.ai/catalog/standards/sist/016ecc55-38da-42e7-8c62-c0ed1a43d8c9/sist-en-1842-1999>

1 Scope

This European Standard specifies a method to determine the moulding shrinkage of compression moulded test specimens of thermoset moulding compounds. It applies only to materials which exhibit no post-shrinkage after moulding such as polyester SMC (Sheet moulding compound) and BMC (Bulk moulding compound).

Knowledge of the shrinkage allows the construction of moulds to produce parts with accurate dimensions, as well as evaluation of the suitability of a moulding compound for this purpose.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

ISO 291	1977	Plastics - Standard atmospheres for conditioning and testing
ISO 472	1988	Plastics - Vocabulary
ISO 2577	1984	Plastics - Thermosetting moulding materials - Determination of shrinkage
EN ISO 12114		Fibre-reinforced plastics - Thermosetting moulding compounds and prepregs - Determination of cure characteristics (ISO 12114:1997)
prEN 12576		Plastics - Fibre reinforced composites - Preparation of compression moulded test plates of SMC, BMC and DMC.

3 Definitions

For the purposes of this Standard, the definitions of ISO 472:1988 and the following definition apply :

moulding shrinkage : The difference in dimensions between a moulding and the mould cavity in which it was moulded, both the mould and the moulding being at normal temperature when measured [ISO 2577:1984].

4 Apparatus

4.1 Mould and press suitable for moulding the test specimens specified in clause 6. Use a mould with a plane mould cavity not smaller than 200 cm². This mould shall be used with punch and die being able to maintain a positive pressure on the material. It can be rectangular, square or circular or as described in EN ISO 12114 or in prEN 12576. The mould can be designed with gauge marks engraved into mould cavity near opposite ends and with or without draft angles.

NOTE : Draft angles result in the opposite ends being not parallel which can cause difficulties in length measurement (see clause 7.4). In this case a reference plane at points 2 mm above the smaller surface can be used.

4.2 Equipment suitable for measuring the sizes of test specimens and the corresponding cavity of the mould with an accuracy of 0,01 mm.

4.3 Non metallic cooling rack to hold the test specimens vertically with a minimum spacing of 20 mm.

NOTE : To achieve symmetrical cooling both outer test specimens are protected by additional protective plates.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5 Sampling and conditioning of the moulding compound

Samples shall be taken from the moulding compound after maturation within the shelf-life given in the specification. They shall be placed inside an appropriate bag to avoid loss of volatile components and moisture absorption, kept under standard atmosphere (according to ISO 291:1997) until equilibrium is reached and then moulded into test specimens.

6 Test specimens

Test specimens are mouldings obtained by using mould and press (see 4.1). The thickness shall be between 3,5 mm and 5,5 mm.

7 Procedure

7.1 Measure the length of the mould cavity (see Note in 4.1), or the distance between the engraved gauge marks in the mould cavity to the nearest 0,01 mm at standard atmosphere as reference length L_0 .

Record this measurement for use in the calculation of shrinkage.

NOTE : Every year it is recommended to check mould dimensions for wear.

7.2 Mould three specimens.

Unless other conditions are specified or agreed between user and supplier the following conditions apply :

- mould temperature : 140 °C ± 1 % ;
- mould coverage : not less than 90 % for SMC. Moulding compounds like BMC shall be preformed to a homogeneous charge prior to moulding ;
- moulding pressure : 7 MPa ± 5 %.
- Pressing time : 40 seconds per millimetre of thickness of moulded test specimen or for whatever longer time is necessary to ensure full cure. The mould shall be closed within 15 s after charging.

On the moulded SMC test specimens, identify the production direction and/or unidirectional reinforcement direction if applicable.

7.3 After removal from the mould, allow the test specimens to cool down to room temperature by placing them in the cooling rack (see 4.3). Store them at standard atmosphere for a minimum of 16 h, or for a shorter time, providing it has been shown that it gives the same results.

(standards.iteh.ai)

7.4 For the determination of moulding shrinkage, measure at standard atmosphere, to the nearest 0,01 mm, the length of the test specimens between opposite ends as L_1 .

- With engraved gauge marks, measure the distance between the marks.
- With draft angles at the ends of the test specimens, measure the length of the reference plane (see Note in 4.1).
- Without draft angles, measure at any height the distance between opposite ends.

Carry out one measurement per test specimen.

8 Expression of results

The moulding shrinkage MS is given, as a percentage, by the formula :

$$MS = \frac{L_0 - L_1}{L_0} \times 100$$

where :

L_0 is the reference length of the mould, in millimetres, determined as in 7.1 ;

L_1 is the corresponding length of the test specimen in millimetres, according to 7.4.