



SLOVENSKI STANDARD
SIST EN ISO 10352:1999

01-maj-1999

**Z vlakni ojačeni polimerni materiali – Zmesi za oblikovanje in preimpregniranje -
Določevanje mase na enoto površine (ISO 10352:1997)**

Fibre-reinforced plastics - Moulding compounds and prepregs - Determination of mass per unit area (ISO 10352:1997)

Faserverstärkte Kunststoffe - Formmassen und Prepregs - Bestimmung des Flächengewichtes (ISO 10352:1997)

Plastiques renforcés - Préimprégnés - Détermination de la masse surfacique (ISO 10352:1997)

STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/f0bf846-0356-4855-a6e5-db87b4153ea8/sist-en-iso-10352-1999>

Ta slovenski standard je istoveten z: EN ISO 10352:1997

ICS:

83.120

Ojačani polimeri

Reinforced plastics

SIST EN ISO 10352:1999

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 10352:1999](#)

<https://standards.iteh.ai/catalog/standards/sist/f0bfe846-0356-4855-a6e5-db87b4153ea8/sist-en-iso-10352-1999>

EUROPEAN STANDARD

EN ISO 10352

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 1997

ICS 83.120

Descriptors: See ISO document

English version

**Fibre-reinforced plastics - Moulding compounds
and prepregs - Determination of mass per unit
area (ISO 10352:1997)**

Plastiques renforcés Préimprégnés Faserverstärkte Kunststoffe - Formmassen und
Détermination de la masse surfacique Prepregs - Bestimmung des Flächengewichtes
(ISO 10352:1997) (ISO 10352:1997)

(standards.iteh.ai)

[SIST EN ISO 10352:1999](https://standards.iteh.ai/catalog/standards/sist/f0bfe846-0356-4855-a6e5-db87b4153ea8/sist-en-iso-10352-1999)

[https://standards.iteh.ai/catalog/standards/sist/f0bfe846-0356-4855-a6e5-
db87b4153ea8/sist-en-iso-10352-1999](https://standards.iteh.ai/catalog/standards/sist/f0bfe846-0356-4855-a6e5-db87b4153ea8/sist-en-iso-10352-1999)

This European Standard was approved by CEN on 1997-05-21. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN ISO 10352:1997

Foreword

The text of the International Standard from Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1997, and conflicting national standards shall be withdrawn at the latest by November 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 10352:1997 has been approved by CEN as a European Standard without any modification.

(standards.iteh.ai)

[SIST EN ISO 10352:1999](https://standards.iteh.ai/catalog/standards/sist/f0bfe846-0356-4855-a6e5-db87b4153ea8/sist-en-iso-10352-1999)

<https://standards.iteh.ai/catalog/standards/sist/f0bfe846-0356-4855-a6e5-db87b4153ea8/sist-en-iso-10352-1999>

INTERNATIONAL
STANDARD

ISO
10352

Second edition
1997-01-15

**Fibre-reinforced plastics — Moulding
compounds and preregs — Determination
of mass per unit area**

iTeh STANDARD PREVIEW

(standards.iteh.ai)

*Plastiques renforcés — Préimprégnés — Détermination de la masse
surfacique*

[EN ISO 10352:1999](#)

[https://standards.iteh.ai/catalog/standards/sist/f0bfe846-0356-4855-a6e5-
db87b4153ea8/sist-en-iso-10352-1999](https://standards.iteh.ai/catalog/standards/sist/f0bfe846-0356-4855-a6e5-db87b4153ea8/sist-en-iso-10352-1999)



Reference number
ISO 10352:1997(E)

ISO 10352:1997(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10352 was prepared by Technical Committee ISO/TC 61, *Plastics*, subcommittee SC 13, *Composite and reinforced fibres*.

This second edition cancels and replaces the first edition (ISO 10352:1991), which has been technically revised.

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Fibre-reinforced plastics — Moulding compounds and prepregs — Determination of mass per unit area

1 Scope

This International Standard specifies a method for the determination of the mass per unit area of sheet moulding compounds and preimpregnated unidirectional sheet, tape, fabrics and mats.

Unless stated to the contrary in the relevant materials specification, this standard is applicable to prepregs irrespective of which type of reinforcement (aramid, carbon, glass, etc.) or which type of matrix (thermosetting or thermoplastic) is used.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 291:1977, *Plastics — Standard atmospheres for conditioning and testing*.

3 Principle

The mass of a test specimen of known area is determined after conditioning in a specified atmosphere. The result is expressed as the mass per unit area.

Alternative specimens sizes are given for

- Type I materials: sheet moulding compounds, preimpregnated mats and heavy preimpregnated fabrics;
- Type II materials: preimpregnated unidirectional lightweight fabrics (e.g. for aerospace use).

4 Apparatus

4.1 Balance, graduated in tenths of grams and accurate to 0,5 g for type I specimens, or graduated in milligrams and accurate to 5 mg for type II specimens.

4.2 Square template, with the dimensions given in table 1 for the material being tested, with tolerance of $\pm 0,1$ mm on the length of each side.

4.3 Ancillary items, such as a sharp cutting tool and tweezers.

5 Conditioning and testing

5.1 Conditioning

5.1.1 Conditioning of material stored at ambient temperature

For material which has been stored at ambient temperature, the laboratory sample, cut from an elementary unit (roll or packet of sheets), shall be conditioned in a standard atmosphere (see 5.2.1) for a minimum of 2 h, unless otherwise specified.

The laboratory sample shall be kept covered with its protective foils in a solvent-impermeable bag.

5.1.2 Conditioning of material stored below ambient temperature

For material which has been stored at temperatures lower than ambient temperature, the material (generally an elementary unit), suitably packed in an airtight, solvent-resistant bag to prevent moisture pick-up, shall be allowed to reach ambient temperature over a period of time determined by the mass of the package. This time shall not be less than 8 h and the actual time shall be recorded in the test report.

When the material has reached ambient temperature, the laboratory sample cut from the elementary unit shall be conditioned in a standard atmosphere (see 5.2.1) for a minimum of 2 h, unless otherwise specified.

The laboratory sample shall be kept covered with its protective foils in a solvent-impermeable bag.

5.2 Testing

5.2.1 Test atmosphere

The test shall be carried out in a standard atmosphere as specified in ISO 291.

5.2.2 Time interval between conditioning and testing

After conditioning, the test shall be carried out within 6 h unless otherwise specified, the laboratory sample being kept in the standard atmosphere until the test is carried out.

6 Test specimens

6.1 Shape and dimensions

The preferred test specimen is a square with the dimensions given in table 1, which depend on the type of material.

For special applications, rectangular, square or round specimens may be used, upon agreement between the interested parties. The surface area of these specimens should preferably be between 0,04 m² and 0,10 m² for type I materials, and between 0,01 m² and 0,04 m² for type II materials.

Table 1 — Preferred specimen sizes

| Specimen type | Type of material | Specimen size m |
|---------------|--|--------------------|
| I | Sheet moulding compounds, preimpregnated mats and heavy preimpregnated fabrics | 0,20 × 0,20 |
| II | Preimpregnated unidirectional lightweight fabrics | 0,10 × 0,10 |

6.2 Number

Unless otherwise required by a specification or by the person ordering the test, three specimens shall be taken from each elementary unit.

6.3 Preparation

Test specimens will usually be taken from the laboratory sample cut from an elementary unit comprising a roll or a packet of sheets. If necessary, taking into account the roll dimensions or the number of sheets per packet, an agreement between the interested parties shall define either the size of the laboratory sample to be taken from each elementary unit or other information such as the number of specimens and their location within the laboratory sample.

The specimens shall be taken uniformly across the roll or sheet and cut perpendicularly to the edges of the sheet.

The specimens shall be taken at least 50 mm away from the edges of the roll or sheet and from any folds or creases in the roll or sheet.

Typical cutting plans are shown in figures 1, 2 and 3. However, in practice, the product specification or the person ordering the test shall specify how specimens are to be taken.

7 Procedure

iTeh STANDARD PREVIEW
(standards.iteh.ai)

On completion of conditioning, cut the test specimens from each laboratory sample using the template (4.2) and a suitable cutting tool (see 4.3).

SIST EN ISO 10352:1999

To ensure consistency in the specimen dimensions, it is important to give the operator precise instructions as to how to carry out the cutting operation. <https://standards.iteh.ai/catalog/standards/sist/016846-0356-4955-26e5-db87b4153ea8/sist-en-iso-10352-1999>

Weigh each test specimen, with its protective foil(s), and record the mass (m_1) to the nearest 0,1 g for type I specimens or to the nearest 1 mg for type II specimens.

Remove, then weigh, the protective foil(s) and record the mass (m_2) to the nearest 0,1 g for type I specimens or to the nearest 1 mg for type II specimens. Ensure that the whole foil is removed before weighing.

IMPORTANT — Perform the weighings immediately after cutting out the test specimens, so that the result will not be influenced by loss of volatile matter due to a delay between this operation and the weighings.

If the protective sheets can be removed without taking any of the material with them, the specimens may be weighed directly without their sheets.

8 Expression of results

The mass per unit area ρ_A , expressed in grams per square metre, is given by the equation

$$\rho_A = \frac{m_1 - m_2}{A}$$

where