



SLOVENSKI STANDARD
SIST EN ISO 12115:1999

01-maj-1999

Z vlakni ojačeni polimerni materiali – Duromerne mase za oblikovanje in predimpregniranci – Določevanje pretočnosti, zorenja in časovne uporabnosti (ISO 12115:1997)

Fibre-reinforced plastics - Thermosetting moulding compounds and prepregs - Determination of flowability, maturation and shelf life (ISO 12115:1997)

Faserverstärkte Kunststoffe - Härtbare Formmassen und Prepregs - Bestimmung der Fließfähigkeit, Reifung und Gebrauchsdauer (ISO 12115:1997)

Plastiques renforcés de fibres - Compositions de moulage et préimprégnés - Détermination de la fluidité, de la maturation et de la durée de vie (ISO 12115:1997)

Ta slovenski standard je istoveten z: EN ISO 12115:1997

ICS:

83.120 Ojačani polimeri Reinforced plastics

SIST EN ISO 12115:1999 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 12115:1999

<https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999>

EUROPEAN STANDARD

EN ISO 12115

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 1997

ICS 83.120.00

Descriptors: see ISO document

English version

**Fibre-reinforced plastics - Thermosetting moulding
compounds and prepregs - Determination of
flowability, maturation and shelf life
(ISO 12115:1997)**

Plastics renforcés de fibres - Compositions de moulage et préimprégnés - Détermination de la fluidité, de la maturation et de la durée de vie (ISO 12115:1997)

Faserverstärkte Kunststoffstoffe - Härtbare Formmassen und Prepregs - Bestimmung der Fließfähigkeit, Reifung und Gebrauchsdauer (ISO 12115:1997)

(standards.iteh.ai)

[SIST EN ISO 12115:1999](https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999)

<https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999>

This European Standard was approved by CEN on 1997-05-10. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Corrected 1997-06-19

Foreword

The text of the International Standard ISO 12115:1997 has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1997, and conflicting national standards shall be withdrawn at the latest by November 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 12115:1997 was approved by CEN as a European Standard without any modification.

NOTE: Normative references to International Standards are listed in annex ZA (normative).

[SIST EN ISO 12115:1999](https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999)

<https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999>

Annex ZA (normative)**Normative references to international publications
with their relevant European publications**

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 12114	1997	Fibre-reinforced plastics - Thermosetting moulding and prepregs - Determination of curing behaviour	EN ISO 12114	1997

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 12115:1999](https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999)

<https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 12115:1999

<https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999>

INTERNATIONAL STANDARD

**ISO
12115**

First edition
1997-05-15

Fibre-reinforced plastics — Thermosetting moulding compounds and preregs — Determination of flowability, maturation and shelf life

*Plastiques renforcés de fibres — Compositions de moulage
thermodurcissables et préimprégnés — Détermination de la fluidité,
de la maturation et de la durée de vie*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 12115:1999

<https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999>



Reference number
ISO 12115:1997(E)

ISO 12115:1997(E)

Contents	Page
Introduction	iv
1 Scope	1
2 Normative references	1
3 Definitions	2
4 General	2
5 Apparatus	3
6 Sampling	4
7 Conditioning	5
8 Test specimens	5
9 Procedure	5
10 Expression of results	6
11 Precision	7
12 Test report	8

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
 Case postale 56 • CH-1211 Genève 20 • Switzerland
 Internet central@iso.ch
 X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

International Standard ISO 12115 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

[SIST EN ISO 12115:1999](https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999)

<https://standards.iteh.ai/catalog/standards/sist/59f49aab-caed-4eb8-ba4c-595da29e9251/sist-en-iso-12115-1999>

Introduction

The flowability of a moulding compound is a property which describes the ability of the compound to fill a mould cavity during the moulding operation.

The flowability varies with the age of the moulding compound due to the occurrence of a thickening process. This so-called maturation process is normally initiated by an additive, the aim being to prevent significant separation of the components of the moulding compound, and yet ensure sufficient flow for the moulding compound to be easy to handle and for it to spread out to fill the whole mould cavity when it is moulded.

When the flowability of a moulding compound has developed to a defined limit, the compound is said to have reached its matured state. This means it can be handled and moulded satisfactorily under given operating conditions.

The maturation and shelf life are determined from flowability measurements. The flowability is measured at several different points in time after production of the moulding compound, and the change in flowability plotted as a function of time. The shelf life of the moulding compound is determined by assessing the ease of handling and moulding behaviour as given by the flowability. Experience indicates that in some cases shelf life may also be dependent on the cure characteristics of the moulding compound (see ISO 12114).

Maturation and shelf life are not parameters in their own right. For a particular moulding compound, the shelf life, for instance, may even differ from one set of moulding conditions to another and from one application to the next.

Fibre-reinforced plastics — Thermosetting moulding compounds and preregs — Determination of flowability maturation and shelf life

1 Scope

This International Standard specifies two methods for the determination of the flowability of fibre-reinforced thermosetting moulding compounds and preregs. The methods apply to all fibre-reinforced thermosetting moulding compounds and differ in the test conditions and the apparatus required.

The methods may be used to assess the influence of individual components of the moulding compound on the moulding behaviour by determining the flowability of the compound. They are also suitable for quality control purposes, as well as the development of moulding compound formulations.

The major field of application is with moulding compounds based on unsaturated polyester (UP) resins.

Method I is a flowability test carried out at room temperature. Conducting the test at room temperature reduces the effect on the results of changes in the temperature of the moulding compound during the test.

Method II is a flowability test carried out under commonly used moulding conditions. In addition, the plate produced may be used for further testing.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 472:1988, *Plastics — Vocabulary*.

ISO 8605:1989, *Textile glass reinforced plastics — Sheet moulding compound (SMC) — Basis for a specification*.

ISO 8606:1990, *Plastics — Preregs — Bulk moulding compound (BMC) and dough moulding compound (DMC) — Basis for a specification*.

ISO 12114:1997, *Fibre-reinforced plastics — Thermosetting moulding compounds and preregs — Determination of curing behaviour*.