



SLOVENSKI STANDARD

SIST EN ISO 295:2004

01-oktober-2004

BUXca Yý U
SIST EN ISO 295:2000

Polimerni materiali - Stiskanje duromernih preskušancev (ISO 295:2004)

Plastics - Compression moulding of test specimens of thermosetting materials (ISO 295:2004)

Kunststoffe - Pressen von Probekörpern aus duroplastischen Werkstoffen (ISO 295:2004)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Plastiques - Moulage par compression des éprouvettes en matières thermodurcissables (ISO 295:2004)

[SIST EN ISO 295:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004>

Ta slovenski standard je istoveten z: EN ISO 295:2004

ICS:

83.080.10 Duromeri

Thermosetting materials

SIST EN ISO 295:2004

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 295:2004

<https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 295

February 2004

ICS 83.080.10

Supersedes EN ISO 295:1998

English version

Plastics - Compression moulding of test specimens of thermosetting materials (ISO 295:2004)

Plastiques - Moulage par compression des éprouvettes en
matières thermodurcissables (ISO 295:2004)

Kunststoffe - Pressen von Probekörpern aus
duroplastischen Werkstoffen (ISO 295:2004)

This European Standard was approved by CEN on 16 January 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

iTeh STANDARD PREVIEW

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 295:2004](https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004)

<https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

EN ISO 295:2004 (E)

CORRECTED 2004-03-10

Foreword

This document (EN ISO 295:2004) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2004, and conflicting national standards shall be withdrawn at the latest by August 2004.

This document supersedes EN ISO 295:1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh **Endorsement notice** STANDARD PREVIEW

The text of ISO 295:2004 has been approved by CEN as EN ISO 295:2004 without any modifications.

SIST EN ISO 295:2004

<https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004>

INTERNATIONAL STANDARD

ISO 295

Third edition
2004-02-01

Plastics — Compression moulding of test specimens of thermosetting materials

*Plastiques — Moulage par compression des éprouvettes en matières
thermodurcissables*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 295:2004](https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004)

<https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004>



Reference number
ISO 295:2004(E)

© ISO 2004

ISO 295:2004(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 295:2004](https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004)

<https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references	1
3 Terms and definitions.....	2
4 Apparatus.....	3
5 Conditioning of material prior to moulding.....	6
6 Preparation of the charge.....	6
7 Moulding conditions	7
7.1 General	7
7.2 Drying	8
7.3 High-frequency preheating	8
7.4 Pre-plastification	8
7.5 Release agents	8
7.6 Breathing.....	8
8 Procedure.....	8
9 Precision	9
10 Moulding report.....	9
Annex A (informative) Marking of test specimens.....	11
Bibliography	12

ISO 295:2004(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 295 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 12, *Thermosetting materials*.

This third edition cancels and replaces the second edition (ISO 295:1991), which has been technically revised.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 295:2004

<https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004>

Plastics — Compression moulding of test specimens of thermosetting materials

1 Scope

This International Standard

- establishes the general principles and lays down the procedure to prepare test specimens of heat- and pressure-moulded thermosetting material from different moulding compounds;
- specifies the details for test specimen preparation to be included with the test reports on properties;
- gives the general principles for the design of the mould intended for the preparation of the test specimens.

The conditions required for preparing, in a reproducible manner, test specimens which will give comparable results are discussed relative to the substance under consideration.

The method applies to phenolic resin, aminoplastic, melamine/phenol, epoxy and unsaturated-polyester based thermosetting powder moulding compounds (PMCs). Due to the nature of certain moulding compounds, their flow properties or other variable factors, it may be necessary to prepare the test specimens according to special methods. The latter are normally in an agreement between the interested parties and noted in the moulding report.

<https://standards.iteh.ai/catalog/standards/sist/9dac3381-c598-4340-a46e-3ed3839bd045/sist-en-iso-295-2004>

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472:1999, *Plastics — Vocabulary*

ISO 1183:1987, *Plastics — Methods for determining the density and relative density of non-cellular plastics*

ISO 3167:2002, *Plastics — Multipurpose test specimens*

ISO 4287, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Terms, definitions and surface texture parameters*

ISO 14526-1, *Plastics — Phenolic powder moulding compounds (PF-PMCs) — Part 1: Designation system and basis for specifications*

ISO 14526-2, *Plastics — Phenolic powder moulding compounds (PF-PMCs) — Part 2: Preparation of test specimens and determination of properties*

ISO 14526-3, *Plastics — Phenolic powder moulding compounds (PF-PMCs) — Part 3: Requirements for selected moulding compounds*

ISO 14527-1, *Plastics — Urea-formaldehyde and urea/melamine-formaldehyde powder moulding compounds (UF- and UF/MF-PMCs) — Part 1: Designation and basis for specifications*

ISO 295:2004(E)

ISO 14527-2, *Plastics — Urea-formaldehyde and urea/melamine-formaldehyde powder moulding compounds (UF- and UF/MF-PMCs) — Part 2: Preparation of test specimens and determination of properties*

ISO 14527-3, *Plastics — Urea-formaldehyde and urea/melamine-formaldehyde powder moulding compounds (UF- and UF/MF-PMCs) — Part 3: Requirements for selected moulding compounds*

ISO 14528-1, *Plastics — Melamine-formaldehyde powder moulding compounds (MF-PMCs) — Part 1: Designation system and basis for specifications*

ISO 14528-2, *Plastics — Melamine-formaldehyde powder moulding compounds (MF-PMCs) — Part 2: Preparation of test specimens and determination of properties*

ISO 14528-3, *Plastics — Melamine-formaldehyde powder moulding compounds (MF-PMCs) — Part 3: Requirements for selected moulding compounds*

ISO 14529-1, *Plastics — Melamine/phenolic powder moulding compounds (MP-PMCs) — Part 1: Designation system and basis for specifications*

ISO 14529-2, *Plastics — Melamine/phenolic powder moulding compounds (MP-PMCs) — Part 2: Preparation of test specimens and determination of properties*

ISO 14529-3, *Plastics — Melamine/phenolic powder moulding compounds (MP-PMCs) — Part 3: Requirements for selected moulding compounds*

ISO 14530-1, *Plastics — Unsaturated-polyester powder moulding compounds (UP-PMCs) — Part 1: Designation system and basis for specifications*

ISO 14530-2, *Plastics — Unsaturated-polyester powder moulding compounds (UP-PMCs) — Part 2: Preparation of test specimens and determination of properties*

ISO 14530-3, *Plastics — Unsaturated-polyester powder moulding compounds (UP-PMCs) — Part 3: Requirements for selected moulding compounds*

ISO 15252-1, *Plastics — Epoxy powder moulding compounds (EP-PMCs) — Part 1: Designation system and basis for specifications*

ISO 15252-2, *Plastics — Epoxy powder moulding compounds (EP-PMCs) — Part 2: Preparation of test specimens and determination of properties*

ISO 15252-3, *Plastics — Epoxy powder moulding compounds (EP-PMCs) — Part 3: Requirements for selected moulding compounds*

3 Terms and definitions

For the purposes of this document, the terms and definitions of ISO 472 and the following apply.

3.1 spatial temperature differences
differences in temperature existing simultaneously at various points inside the mould after the temperature adjustment device has been set at a given temperature and after a permanent thermal equilibrium has been reached

3.2 temporal temperature differences
differences in temperature that may occur at a single given point on the inside of the mould at various times after the temperature adjustment device has been set at a given temperature and after a permanent thermal equilibrium has been reached

3.3

crosslinking time or cure time

time interval between the end of the mould-closing operation and the beginning of the mould-opening operation

NOTE In practice, the cure time is generally counted as from the moment when the pressure reaches the specified value.

4 Apparatus

4.1 Compression mould, made of steel, able to withstand the prescribed moulding temperatures and pressures.

The mould shall be designed so that the compression force is transmitted to the moulding material with no appreciable loss. It may be a single-cavity or a multi-cavity type mould. Figure 1 shows an example of a single-cavity positive mould. The cavity of the mould may have the shape of the multi-purpose test specimen in accordance with ISO 3167. In some cases, e.g., for aminoplastic moulding materials, a semi-positive mould is more suitable, even though the pressure on the moulding material is not as well defined. In this case, the test-specimen thickness shall be adjusted using spacers on the mould parting line.

The mould cavity may have various forms, e.g., square plate, disc or multi-purpose specimen in accordance with ISO 3167.

For moulding powders, a "type E ISO 295" single-cavity mould with dimensions of 120 mm × 120 mm is recommended. In the moulding report, the plate is designated as "type E h ISO 295," where h is the thickness in millimetres (e.g., "type E4 ISO 295" for a plate with a thickness of 4 mm and dimensions of 120 mm × 120 mm).

The majority of the test methods require a thickness of 4 mm but, for a few, for instance the measurement of certain electrical properties, thinner plates may be required. When in doubt, the dimensions specified in the test procedure itself shall be used.

The use of a plate allows the required test specimens to be cut by machining. The test specimens shall not be taken from the edge of the plate. A margin of 10 mm is recommended.

The mould surface shall be free from superficial damage or contamination and have a roughness R_a between 0,4 μm and 0,8 μm , inclusive (see ISO 4287). Chrome plating is not always necessary, but it can prevent sticking.

The edge-taper angle, if any, shall not be greater than 3° (see Figure 1). Clearance between the vertical wall of the cavity and that of the punch shall not exceed 0,1 mm (see Figure 1). Dimension e' shall be calculated so that there is no risk of the punch damaging the die if there is no material present.

The mould shall have a cavity (see Figure 1) of sufficient volume to allow the introduction of the whole charge in one single operation. Bulk form moulding material occupies a volume two to ten times that of the object being moulded.