

**SLOVENSKI STANDARD  
SIST EN ISO 5659-2:2007****01-april-2007****BUXca Yý U  
SIST EN ISO 5659-2:2000**

Dc`ja Yfb]a Uhf]U]!'BUghUUb^YX]a U!'&^XY.'8c`c Ub^cdh] bY[ cgrchY'g  
dfYg\_i gca `j `Yb]dfYg\_i gb]\_ca cf]fGC`\*) - !&\$\$\* Ł

Plastics - Smoke generation - Part 2: Determination of optical density by a single-chamber test (ISO 5659-2:2006)

Kunststoffe - Rauchentwicklung - Teil 2: Bestimmung der optischen Dichte durch Einkammerprüfung (ISO 5659-2:2006)

Plastiques - Production de fumée - Partie 2: Détermination de la densité optique par un essai en enceinte unique (ISO 5659-2:2006)

**Ta slovenski standard je istoveten z: EN ISO 5659-2:2006**

**ICS:**

13.220.40	Sposobnost vžiga in obnašanje materialov in proizvodov pri gorenju	Ignitability and burning behaviour of materials and products
83.080.01	Polimerni materiali na splošno	Plastics in general

**SIST EN ISO 5659-2:2007****en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 5659-2:2007

<https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fc01eb8/sist-en-iso-5659-2-2007>

English Version

Plastics - Smoke generation - Part 2: Determination of optical density by a single-chamber test (ISO 5659-2:2006)

Plastiques - Production de fumée - Partie 2: Détermination de la densité optique par un essai en enceinte unique (ISO 5659-2:2006)

Kunststoffe - Rauchentwicklung - Teil 2: Bestimmung der optischen Dichte durch Einkammerprüfung (ISO 5659-2:2006)

This European Standard was approved by CEN on 30 November 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 5659-2:2007](https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fc01eb8/sist-en-iso-5659-2-2007)

<https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fc01eb8/sist-en-iso-5659-2-2007>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## Foreword

This document (EN ISO 5659-2:2006) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2007, and conflicting national standards shall be withdrawn at the latest by June 2007.

This document supersedes EN ISO 5659-2:1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

### Endorsement notice

The text of ISO 5659-2:2006 has been approved by CEN as EN ISO 5659-2:2006 without any modifications.

ITEH STANDARD PREVIEW  
(standards.iteh.ai)

[SIST EN ISO 5659-2:2007](https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fc01eb8/sist-en-iso-5659-2-2007)

<https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fc01eb8/sist-en-iso-5659-2-2007>

---

---

**Plastics — Smoke generation —**  
**Part 2:**  
**Determination of optical density**  
**by a single-chamber test**

*Plastiques — Production de fumée —*  
*Partie 2: Détermination de la densité optique par un essai en enceinte*  
*unique*

**STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 5659-2:2007](https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fc01eb8/sist-en-iso-5659-2-2007)

<https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fc01eb8/sist-en-iso-5659-2-2007>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 5659-2:2007](https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fe01eb8/sist-en-iso-5659-2-2007)

<https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fe01eb8/sist-en-iso-5659-2-2007>

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

Foreword.....	iv
Introduction .....	v
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions.....	2
4 Principles of the test.....	3
5 Suitability of a material for testing.....	3
6 Specimen construction and preparation.....	3
7 Apparatus and ancillary equipment.....	5
8 Test environment .....	17
9 Setting-up and calibration procedures.....	18
10 Test procedure .....	21
11 Expression of results .....	24
12 Precision.....	24
13 Test report .....	25
Annex A (normative) Calibration of heat flux meter .....	26
Annex B (informative) Variability in the specific optical density of smoke measured in the single-chamber test.....	27
Annex C (informative) Determination of mass optical density .....	29
Annex D (informative) Precision data from tests on intumescent materials .....	34
Bibliography .....	36

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 5659-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 4, *Burning behaviour*.

This second edition cancels and replaces the first edition (ISO 5659-2:1994), which has been technically revised.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 5659 consists of the following parts, under the general title *Plastics — Smoke generation*:

- *Part 1: Guidance on optical-density testing*  
<https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-19315fc01eb8/sist-en-iso-5659-2-2007>
- *Part 2: Determination of optical density by a single-chamber test*
- *Part 3: Determination of optical density by a dynamic-flow method* [Technical Report]



## Introduction

Fire is a complex phenomenon: its development and effects depend upon a number of interrelated factors. The behaviour of materials and products depends upon the characteristics of the fire, the method of use of the materials and the environment in which they are exposed (see also ISO/TR 3814 and ISO 13943).

A test such as is specified in this part of ISO 5659 deals only with a simple representation of a particular aspect of the potential fire situation, typified by a radiant heat source, and it cannot alone provide any direct guidance on behaviour or safety in fire. A test of this type may, however, be used for comparative purposes or to ensure the existence of a certain quality of performance (in this case, smoke production) considered to have a bearing on fire behaviour generally. It would be wrong to attach any other meaning to results from this test.

The term “smoke” is defined in ISO 13943 as the visible part of fire effluent. It is one of the first response characteristics to be manifested and should almost always be taken into account in any assessment of fire hazard as it represents one of the greatest threats to occupants of a building, and other enclosed spaces such as ships and trains, on fire.

The responsibility for the preparation of ISO 5659 was transferred during 1987 from ISO/TC 92 to ISO/TC 61 on the understanding that the scope and applicability of the standard for the testing of materials should not be restricted to plastics but should also be relevant to other materials where possible, including building materials.

ITEH STANDARD PREVIEW  
(standards.iteh.ai)

[SIST EN ISO 5659-2:2007](https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fc01eb8/sist-en-iso-5659-2-2007)

<https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fc01eb8/sist-en-iso-5659-2-2007>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 5659-2:2007

<https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fc01eb8/sist-en-iso-5659-2-2007>

# Plastics — Smoke generation —

## Part 2: Determination of optical density by a single-chamber test

### 1 Scope

**1.1** This part of ISO 5659 specifies a method of measuring smoke production from the exposed surface of specimens of essentially flat materials, composites or assemblies not exceeding 25 mm in thickness when placed in a horizontal orientation and subjected to specified levels of thermal irradiance in a closed cabinet with or without the application of a pilot flame. This method of test is applicable to all plastics and may also be used for the evaluation of other materials (e.g. rubbers, textile-coverings, painted surfaces, wood and other materials).

**1.2** It is intended that the values of optical density determined by this test be taken as specific to the specimen or assembly material in the form and thickness tested, and are not to be considered inherent, fundamental, properties.

**1.3** The test is intended primarily for use in research and development and in fire safety engineering of buildings, trains, ships, etc., and not as a basis for ratings for building codes or other purposes. No basis is provided for predicting the density of smoke that may be generated by the materials upon exposure to heat and flame under other (actual) exposure conditions, nor is any correlation established with measurements derived from other test methods. This test procedure excludes the effect of irritants on the eye.

**NOTE** This test procedure addresses the loss of visibility due to smoke density, which generally is not related to irritancy potency, as explained in Part 1 of this International Standard.

**1.4** It is emphasized that smoke production from a material varies according to the irradiance level to which the specimen is exposed. In making use of the results of this method, it should be borne in mind that the results are based on exposure to the specific irradiance levels of 25 kW/m<sup>2</sup> and 50 kW/m<sup>2</sup>.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 5659-1, *Plastics — Smoke generation — Part 1: Guidance on optical-density testing*

ISO 13943, *Fire safety — Vocabulary*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13943 and the following apply.

- 3.1 assembly**  
a fabrication of materials and/or composites
- EXAMPLE Sandwich panels.
- NOTE The assembly may include an air gap.
- 3.2 composite**  
a combination of materials which are generally recognized in building construction as discrete entities
- EXAMPLES Coated and laminated materials.
- 3.3 essentially flat surface**  
surface which does not deviate from a plane by more than 1 mm
- 3.4 exposed surface**  
that surface of the product subjected to the heating conditions of the test
- 3.5 irradiance**  
radiant flux incident on an infinitesimal element of the surface containing the point divided by the area of that element
- 3.6 material**  
basic single substance or uniformly dispersed mixture
- EXAMPLES Metal, stone, timber, concrete, mineral fibre and polymers.
- 3.7 mass optical density**  
**MOD**  
measure of the degree of opacity of smoke in terms of the mass loss of the material
- 3.8 optical density of smoke**  
*D*  
measure of the degree of opacity of smoke, taken as the negative common logarithm of the relative transmission of light
- 3.9 product**  
material, composite or assembly about which information is required
- 3.10 specific optical density**  
*D<sub>s</sub>*  
optical density multiplied by a factor which is calculated by dividing the volume of the test chamber by the product of the exposed area of the specimen and the path length of the light beam
- NOTE See 11.1.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[SIST EN ISO 5659-2:2007](https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fe01eb8/sist-en-iso-5659-2-2007)

<https://standards.iteh.ai/catalog/standards/sist/1b974da9-e593-4624-a68b-193f5fe01eb8/sist-en-iso-5659-2-2007>

**3.11****specimen**

representative piece of the product to be tested together with any substrate or surface coating

NOTE The specimen may include an air gap.

**3.12****intumescent material**

dimensionally unstable material, developing a carbonaceous expanded structure of thickness  $> 10$  mm during the test, with the cone heater 25 mm from the specimen

**4 Principles of the test**

Specimens of the product are mounted horizontally within a chamber and exposed to thermal radiation on their upper surfaces at selected levels of constant irradiance up to  $50 \text{ kW/m}^2$ .

The smoke evolved is collected in the chamber, which also contains photometric equipment. The attenuation of a light beam passing through the smoke is measured. The results are reported in terms of specific optical density.

**5 Suitability of a material for testing****5.1 Material geometry**

**5.1.1** The method is applicable to essentially flat materials, composites and assemblies not exceeding 25 mm in thickness.

**5.1.2** The method is sensitive to small variations in geometry, surface orientation, thickness (either overall or of the individual layers), mass and composition of the material, and so the results obtained by this method only apply to the thickness of the material as tested. It is not possible to calculate the specific optical density of one thickness of a material from the specific optical density of another thickness of the material.

**5.2 Physical characteristics**

Materials submitted for evaluation by this method could have faces which differ or could contain laminations of different materials arranged in a different order in relation to the two faces. If either of the faces is likely to be exposed to a fire condition when in use, then both faces shall be evaluated.

**6 Specimen construction and preparation****6.1 Number of specimens**

**6.1.1** The test sample shall comprise a minimum of twelve specimens if the test is to be carried out in all four modes (see 10.9.1): six specimens shall be tested at  $25 \text{ kW/m}^2$  (three specimens with a pilot flame and three specimens without a pilot flame) and six specimens shall be tested at  $50 \text{ kW/m}^2$  (three specimens with a pilot flame and three specimens without a pilot flame).

If the test is carried out in fewer than four modes, a minimum of three specimens shall be tested per mode.

**6.1.2** An additional number of specimens as specified in 6.1.1 shall be used for each face, in accordance with the requirements of 5.2.

**6.1.3** An additional twelve specimens (i.e. three specimens per test mode) shall be held in reserve if required by the modes specified in 10.9.2.