

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Specifications for particular types of winding wires –
Part 3: Polyester enamelled round copper wire, class 155

Spécifications pour types particuliers de fils de bobinage –
Partie 3: Fil de section circulaire en cuivre émaillé avec polyester, classe 155

<https://standards.iteh.ai/iec-60317-3-2004>



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2011 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue

Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 15 langues additionnelles. Egalelement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary

65 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

Recherche de publications IEC - www.iec.ch/searchpub

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.



IEC 60317-3

Edition 3.1 2011-02
CONSOLIDATED VERSION

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Specifications for particular types of winding wires –
Part 3: Polyester enamelled round copper wire, class 155

Spécifications pour types particuliers de fils de bobinage –
Partie 3: Fil de section circulaire en cuivre émaillé avec polyester, classe 155

<https://standards.iteh.ai/icc/15437bf1-3a12-44a7-b97e-81c233f76390/iec-60317-3-2004>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.060.10

ISBN 978-2-8891-2000-0

Warning! Make sure that you obtained this publication from an authorized distributor.

Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

| | |
|--|---|
| FOREWORD | 3 |
| INTRODUCTION | 5 |
| 1 Scope | 6 |
| 2 Normative references | 6 |
| 3 Definitions and general notes on methods of test and appearance | 6 |
| 3.1 Definitions and general notes on methods of test | 6 |
| 3.2 Appearance | 7 |
| 4 Dimensions | 7 |
| 5 Electrical resistance | 7 |
| 6 Elongation | 7 |
| 7 Springiness | 7 |
| 8 Flexibility and adherence | 7 |
| 9 Heat shock | 7 |
| 10 Cut-through | 7 |
| 11 Resistance to abrasion (nominal conductor diameters from 0,250 mm up to and including 2,500 mm) | 7 |
| 12 Resistance to solvents | 8 |
| 13 Breakdown voltage | 8 |
| 14 Continuity of insulation | 8 |
| 15 Temperature index | 8 |
| 16 Resistance to refrigerants | 9 |
| 17 Solderability | 9 |
| 18 Heat or solvent bonding | 9 |
| 19 Dielectric dissipation factor | 9 |
| 20 Resistance to transformer oil | 9 |
| 23 Pin hole test | 9 |
| 30 Packaging | 9 |
| Table 1 – Resistance to abrasion | 8 |

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**SPECIFICATIONS FOR PARTICULAR TYPES
OF WINDING WIRES –****Part 3: Polyester enamelled round copper wire,
class 155****FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 60317-3 edition 3.1 contains the third edition (2004) [documents 55/911/FDIS and 55/917/RVD] and its amendment 1 (2010) [documents 55/1117/CDV and 55/1152/RVC].

A vertical line in the margin shows where the base publication has been modified by amendment 1. Additions and deletions are displayed in red, with deletions being struck through.

International Standard IEC 60317-3 has been prepared by IEC technical committee 55: Winding wires.

The main changes with respect to the previous edition are listed below:

- new requirements for appearance, Subclause 3.2, added;
- the constant K, applied in calculating the number of revolutions for the peel test, Clause 8, increased from 130 mm to 150 mm;
- the test temperature for the cut-through test, Clause 10, increased from 240 °C to 270 °C;
- new pin hole test, Clause 23, added.

This International Standard is to be read in conjunction with IEC 60317-0-1.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of the base publication and its amendments will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The “colour inside” logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this publication using a colour printer.

<https://standards.iteh.ai/2004/05/standards/iec/15437bf1-3a12-44a7-b97e-81c233f76390/iec-60317-3-2004>

INTRODUCTION

This part of IEC 60317 is one of a series which deals with insulated wires used for windings in electrical equipment. The series has three groups describing

- 1) winding wires – Test methods (IEC 60851);
- 2) specifications for particular types of winding wires (IEC 60317);
- 3) packaging of winding wires (IEC 60264).



SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 3: Polyester enamelled round copper wire, class 155

1 Scope

This part of IEC 60317 specifies the requirements of enamelled round copper winding wire of class 155 with a sole coating based on polyester resin, which may be modified provided it retains the chemical identity of the original resin and meets all specified wire requirements.

NOTE A modified resin is a resin that has undergone a chemical change, or contains one or more additives to enhance certain performance or application characteristics.

Class 155 is a thermal class that requires a minimum temperature index of 155 and a heat shock temperature of at least 175 °C.

The temperature in degrees Celsius corresponding to the temperature index is not necessarily that at which it is recommended that the wire be operated and this will depend on many factors, including the type of equipment involved.

The range of nominal conductor diameters covered by this standard is as follows:

- grade 1: 0,020 mm up to and including 3,150 mm;
- grade 2: 0,020 mm up to and including 5,000 mm.

The nominal conductor diameters are specified in Clause 4 of IEC 60317-0-1.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60317-0-1:~~2008~~, *Specifications for particular types of winding wires – Part 0-1: General requirements – Enamelled round copper wire*

3 Definitions and general notes on methods of test and appearance

3.1 Definitions and general notes on methods of test

For definitions and general notes on methods of test, see ~~Clause 3 Subclauses 3.1 and 3.2~~ of IEC 60317-0-1.

In case of inconsistencies between IEC 60317-0-1 and this standard, IEC 60317-3 shall prevail.

3.2 Appearance

See ~~Clause 3~~ Subclause 3.3 of IEC 60317-0-1.

4 Dimensions

See Clause 4 of IEC 60317-0-1.

5 Electrical resistance

See Clause 5 of IEC 60317-0-1.

6 Elongation

See Clause 6 of IEC 60317-0-1.

7 Springiness

See Clause 7 of IEC 60317-0-1.

8 Flexibility and adherence

See Clause 8 of IEC 60317-0-1, where the constant K used for the calculation of the number of revolutions for the peel test shall be 150 mm.

9 Heat shock

See Clause 9 of IEC 60317-0-1, where the minimum heat shock temperature shall be 175 °C.

10 Cut-through

No failure shall occur within 2 min at a temperature of 270 °C.

11 Resistance to abrasion

(nominal conductor diameters from 0,250 mm up to and including 2,500 mm)

The wire shall meet the requirements given in Table 1.

Table 1 – Resistance to abrasion

| Nominal conductor diameter mm | Grade 1 | | Grade 2 | |
|----------------------------------|---------------------------------------|---|---------------------------------------|---|
| | Minimum average force to failure N | Minimum force to failure of each measurement N | Minimum average force to failure N | Minimum force to failure of each measurement N |
| 0,250 | 2,70 | 2,30 | 4,50 | 3,80 |
| 0,280 | 2,90 | 2,45 | 4,80 | 4,10 |
| 0,315 | 3,15 | 2,65 | 5,20 | 4,40 |
| 0,355 | 3,40 | 2,85 | 5,60 | 4,75 |
| 0,400 | 3,65 | 3,05 | 6,00 | 5,10 |
| 0,450 | 3,90 | 3,30 | 6,45 | 5,45 |
| 0,500 | 4,20 | 3,55 | 6,90 | 5,85 |
| 0,560 | 4,50 | 3,80 | 7,40 | 6,25 |
| 0,630 | 4,85 | 4,10 | 7,90 | 6,70 |
| 0,710 | 5,20 | 4,40 | 8,50 | 7,20 |
| 0,800 | 5,60 | 4,70 | 9,10 | 7,70 |
| 0,900 | 6,05 | 5,10 | 9,70 | 8,20 |
| 1,000 | 6,55 | 5,50 | 10,40 | 8,80 |
| 1,120 | 7,05 | 5,95 | 11,10 | 9,40 |
| 1,250 | 7,60 | 6,45 | 11,90 | 10,00 |
| 1,400 | 8,20 | 6,95 | 12,70 | 10,80 |
| 1,600 | 8,90 | 7,55 | 13,70 | 11,60 |
| 1,800 | 9,60 | 8,15 | 14,70 | 12,40 |
| 2,000 | 10,30 | 8,75 | 15,70 | 13,30 |
| 2,240 | 11,10 | 9,40 | 16,70 | 14,20 |
| 2,500 | 11,90 | 10,10 | 17,80 | 15,10 |

For intermediate nominal conductor diameters, the value of the next larger nominal conductor diameter shall be taken.

12 Resistance to solvents

See Clause 12 of IEC 60317-0-1.

13 Breakdown voltage

See Clause 13 of IEC 60317-0-1, where the elevated temperature shall be 155 °C.

14 Continuity of insulation

See Clause 14 of IEC 60317-0-1.

15 Temperature index

See Clause 15 of IEC 60317-0-1, where the minimum temperature index shall be 155.