



## Standard Specification for Aluminum-Alloy Investment Castings<sup>1</sup>

This standard is issued under the fixed designation B 618; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers aluminum-alloy investment castings designated as shown in Table 1.

1.2 Alloy and temper designations are in accordance with ANSI H35.1. The equivalent Unified Numbering System alloy designations are in accordance with Practice E 527.

1.3 For acceptance criteria for inclusion of new aluminum and aluminum alloys and their properties in this specification, see Annex A1 and Annex A2.

1.4 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

### 2. Referenced Documents

2.1 The following documents of the issue in effect on the date of purchase form a part of this specification to the extent referenced herein:

#### 2.2 ASTM Standards:

B 179 Specification for Aluminum Alloys in Ingot Form for Castings from all Casting Processes<sup>2</sup>

B 275 Practice for Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought<sup>2</sup>

B 557 Test Methods for Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products<sup>2</sup>

B 597 Practice for Heat Treatment of Aluminum Alloys<sup>2</sup>

B 660 Practices for Packaging/Packing of Aluminum and Magnesium Products<sup>2</sup>

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications<sup>3</sup>

E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys<sup>4</sup>

E 88 Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition<sup>4</sup>

E 94 Guide for Radiographic Testing<sup>5</sup>

E 155 Reference Radiographs for Inspection of Aluminum and Magnesium Castings<sup>5</sup>

E 165 Test Method for Liquid Penetrant Examination<sup>5</sup>

E 227 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique<sup>4</sup>

E 527 Practice for Numbering Metals and Alloys (UNS)<sup>6</sup>

E 607 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique, Nitrogen Atmosphere<sup>7</sup>

E 716 Practices for Sampling Aluminum and Aluminum Alloys for Spectrochemical Analysis<sup>7</sup>

E 1251 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Argon Atmosphere, Point-to-Plane, Unipolar Self-Initiating Capacitor Discharge<sup>7</sup>

IEEE/ASTM SI 10 Standard for Use of the International System of Units (SI): The Modern Metric System<sup>3</sup>

#### 2.3 ANSI Standard:

H35.1 Alloy and Temper Designation Systems for Aluminum<sup>2</sup>

H35.1M Alloy and Temper Designation System for Aluminum [Metric]<sup>2</sup>

#### 2.4 Military Standard:

MIL-STD-129 Marking for Shipment and Storage<sup>8</sup>

#### 2.5 Federal Standard:

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)<sup>8</sup>

### 3. Terminology

#### 3.1 Definition:

3.1.1 *investment casting*—a metal object produced by surrounding (investing) an expendable pattern (usually wax or plastic) with a refractory slurry that sets at room temperature, after which the pattern is removed through the use of heat, and then filling the resulting cavity with molten metal and allowing it to solidify.

### 4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 This specification designation (which includes the number, the year, and the revision letter, if applicable),

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.01 on Aluminum Alloy Ingots and Castings.

Current edition approved Apr. 10, 2001. Published May 2001. Originally published as B 618 – 77. Last previous edition B 618 – 99.

<sup>2</sup> Annual Book of ASTM Standards, Vol 02.02.

<sup>3</sup> Annual Book of ASTM Standards, Vol 14.02.

<sup>4</sup> Annual Book of ASTM Standards, Vol 03.05.

<sup>5</sup> Annual Book of ASTM Standards, Vol 03.03.

<sup>6</sup> Annual Book of ASTM Standards, Vol 01.01.

<sup>7</sup> Annual Book of ASTM Standards, Vol 03.06.

<sup>8</sup> Available from the Standardization Documents Order Desk, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094. Attn: NPODS.



**TABLE 1 Chemical Composition Requirements**

NOTE 1—When single units are shown, these indicate the maximum amounts permitted.

NOTE 2—Analysis shall be made for the elements for which limits are shown in this table.

NOTE 3—The following applies to all specified limits in this table: For purposes of acceptance and rejection, an observed value or a calculated value from analysis should be rounded off to the nearest unit in the last right-hand place of figures used in expressing the specified limit (Practice E 29).

| Alloy              |        | Composition, % |         |                  |           |                   |                |               |         |         |         |               |                                |                    |
|--------------------|--------|----------------|---------|------------------|-----------|-------------------|----------------|---------------|---------|---------|---------|---------------|--------------------------------|--------------------|
| ANSI <sup>A</sup>  | UNS    | Aluminum       | Silicon | Iron             | Copper    | Man-<br>ganese    | Mag-<br>nesium | Chro-<br>mium | Nickel  | Zinc    | Tin     | Titan-<br>ium | Other <sup>B</sup><br>Elements |                    |
|                    |        |                |         |                  |           |                   |                |               |         |         |         |               | Each                           | Total <sup>C</sup> |
| 201.0              | A02010 | remainder      | 0.10    | 0.15             | 4.0–5.2   | 0.20–0.50         | 0.15–0.55      | ...           | ...     | ...     | ...     | 0.15–0.35     | 0.05 <sup>D</sup>              | 0.10               |
| 204.0              | A02040 | remainder      | 0.20    | 0.35             | 4.2–5.0   | 0.10              | 0.15–0.35      | ...           | 0.05    | 0.10    | 0.05    | 0.15–0.30     | 0.05                           | 0.15               |
| 208.0              | A02080 | remainder      | 2.5–3.5 | 1.2              | 3.5–4.5   | 0.50              | 0.10           | ...           | 0.35    | 1.0     | ...     | 0.25          | ...                            | 0.50               |
| 222.0              | A02220 | remainder      | 2.0     | 1.5              | 9.2–10.7  | 0.50              | 0.15–0.35      | ...           | 0.50    | 0.8     | ...     | 0.25          | ...                            | 0.35               |
| 242.0              | A02420 | remainder      | 0.7     | 1.0              | 3.5–4.5   | 0.35              | 1.2–1.8        | 0.25          | 1.7–2.3 | 0.35    | ...     | 0.25          | 0.05                           | 0.15               |
| 295.0              | A02950 | remainder      | 0.7–1.5 | 1.0              | 4.0–5.0   | 0.35              | 0.03           | ...           | ...     | 0.35    | ...     | 0.25          | 0.05                           | 0.15               |
| 319.0              | A03190 | remainder      | 5.5–6.5 | 1.0              | 3.0–4.0   | 0.50              | 0.10           | ...           | 0.35    | 1.0     | ...     | 0.25          | ...                            | 0.50               |
| 328.0              | A03280 | remainder      | 7.5–8.5 | 1.0              | 1.0–2.0   | 0.20–0.6          | 0.20–0.6       | 0.35          | 0.25    | 1.5     | ...     | 0.25          | ...                            | 0.50               |
| 355.0              | A03550 | remainder      | 4.5–5.5 | 0.6 <sup>E</sup> | 1.0–1.5   | 0.50 <sup>E</sup> | 0.40–0.6       | 0.25          | ...     | 0.35    | ...     | 0.25          | 0.05                           | 0.15               |
| C355.0             | A33550 | remainder      | 4.5–5.5 | 0.20             | 1.0–1.5   | 0.10              | 0.40–0.6       | ...           | ...     | 0.10    | ...     | 0.20          | 0.05                           | 0.15               |
| 356.0              | A03560 | remainder      | 6.5–7.5 | 0.6 <sup>E</sup> | 0.25      | 0.35 <sup>E</sup> | 0.20–0.45      | ...           | ...     | 0.35    | ...     | 0.25          | 0.05                           | 0.15               |
| A356.0             | A13560 | remainder      | 6.5–7.6 | 0.20             | 0.20      | 0.10              | 0.25–0.45      | ...           | ...     | 0.10    | ...     | 0.20          | 0.05                           | 0.15               |
| 443.0              | A04430 | remainder      | 4.5–6.0 | 0.8              | 0.6       | 0.50              | 0.05           | 0.25          | ...     | 0.50    | ...     | 0.25          | ...                            | 0.35               |
| B443.0             | A24430 | remainder      | 4.5–6.0 | 0.8              | 0.15      | 0.35              | 0.05           | ...           | ...     | 0.35    | ...     | 0.25          | 0.05                           | 0.15               |
| 514.0              | A05140 | remainder      | 0.35    | 0.50             | 0.15      | 0.35              | 3.5–4.5        | ...           | ...     | 0.15    | ...     | 0.25          | 0.05                           | 0.15               |
| 520.0              | A05200 | remainder      | 0.25    | 0.30             | 0.25      | 0.15              | 9.5–10.6       | ...           | ...     | 0.15    | ...     | 0.25          | 0.05                           | 0.15               |
| 535.0              | A05350 | remainder      | 0.15    | 0.15             | 0.05      | 0.10–0.25         | 6.2–7.5        | ...           | ...     | ...     | ...     | 0.10–0.25     | 0.05 <sup>F</sup>              | 0.15               |
| 705.0              | A07050 | remainder      | 0.20    | 0.8              | 0.20      | 0.40–0.6          | 1.4–1.8        | 0.20–0.40     | ...     | 2.7–3.3 | ...     | 0.25          | 0.05                           | 0.15               |
| 707.0              | A07070 | remainder      | 0.20    | 0.8              | 0.20      | 0.40–0.6          | 1.8–2.4        | 0.20–0.40     | ...     | 4.0–4.5 | ...     | 0.25          | 0.05                           | 0.15               |
| 710.0 <sup>G</sup> | A07100 | remainder      | 0.15    | 0.50             | 0.35–0.65 | 0.05              | 0.6–0.8        | ...           | ...     | 6.0–7.0 | ...     | 0.25          | 0.05                           | 0.15               |
| 712.0 <sup>G</sup> | A07120 | remainder      | 0.30    | 0.50             | 0.25      | 0.10              | 0.50–0.65      | 0.40–0.6      | ...     | 5.0–6.5 | ...     | 0.15–0.25     | 0.05                           | 0.20               |
| 713.0              | A07130 | remainder      | 0.25    | 1.1              | 0.40–1.0  | 0.6               | 0.20–0.50      | 0.35          | 0.15    | 7.0–8.0 | ...     | 0.25          | 0.10                           | 0.25               |
| 771.0              | A07710 | remainder      | 0.15    | 0.15             | 0.10      | 0.10              | 0.8–1.0        | 0.06–0.20     | ...     | 6.5–7.5 | ...     | 0.10–0.20     | 0.05                           | 0.15               |
| 850.0              | A08500 | remainder      | 0.7     | 0.7              | 0.7–1.3   | 0.10              | 0.10           | ...           | 0.7–1.3 | ...     | 5.5–7.0 | 0.20          | ...                            | 0.30               |
| 851.0 <sup>G</sup> | A08510 | remainder      | 2.0–3.0 | 0.7              | 0.7–1.3   | 0.10              | 0.10           | ...           | 0.3–0.7 | ...     | 5.5–7.0 | 0.20          | ...                            | 0.30               |
| 852.0 <sup>G</sup> | A08520 | remainder      | 0.40    | 0.7              | 1.7–2.3   | 0.10              | 0.6–0.9        | ...           | 0.9–1.5 | ...     | 5.5–7.0 | 0.20          | ...                            | 0.30               |

<sup>A</sup> ASTM alloy designations are in Practice B 275.

<sup>B</sup> "Others" includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyze samples for trace elements not specified in the specification. However, such analysis is not required and may not cover all metallic "Others" elements. Should any analysis by the producer or the purchaser establish that an "Others" element exceeds the limit of "Each" or that the aggregate of several "Others" elements exceeds the limit of "Total," the material shall be considered nonconforming.

<sup>C</sup> Other Elements—Total shall be the sum of unspecified metallic elements 0.010 % or more, rounded to the second decimal before determining the sum.

<sup>D</sup> Contains silver 0.40–1.0 %.

<sup>E</sup> If iron exceeds 0.45 %, manganese content shall not be less than one half of the iron content.

<sup>F</sup> Contains beryllium 0.003–0.007 %, boron 0.002 % max.

<sup>G</sup> 710.0 formerly A712.0, 712.0 formerly D712.0, 851.0 formerly A850.0, 852.0 formerly B850.0.

- 4.1.2 Alloy (Section 7 and Table 1),
- 4.1.3 Temper (Section 10 and Table 2),
- 4.1.4 Applicable drawing or part number,
- 4.1.5 The quantity in either pieces or pounds.
- 4.2 Additionally, orders for material to this specification shall include the following information when required by the purchaser:
  - 4.2.1 Whether castings or test specimens or both may be supplied in the artificially aged—T5 temper for alloys 705.0, 707.0, D712.0, and 713.0 (see 10.2),
  - 4.2.2 Whether test specimens cut from castings are required in addition to or instead of separately cast specimens (see 10.3 and 11.2),
  - 4.2.3 Whether repairs are permissible (see 17.1),
  - 4.2.4 Whether inspection is required at the producer's works (see 18.1),
  - 4.2.5 Whether surface requirements shall be checked against observational standards where such standards are established (see 18.2),
  - 4.2.6 Whether liquid penetrant inspection is required (see 18.4),

- 4.2.7 Whether radiographic inspection is required (see 18.5),
- 4.2.8 Whether certification of chemical analysis and tensile properties is required (see 20.1),
- 4.2.9 Whether the material shall be packaged or marked, or both, in accordance with Practices B 660, MIL-STD-129, and Fed. Std. No. 123 (see 22.3).

## 5. Responsibility for Quality Assurance

5.1 *Responsibility for Inspection and Tests*—Unless otherwise specified in the contract or purchase order, the producer shall be responsible for the performance of all inspection and test requirements specified herein. Except as otherwise specified in the contract or order, the producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to confirm that material conforms to prescribed requirements.



**TABLE 2 Tensile Requirements<sup>A</sup>**

NOTE 1— For purposes of determining conformance with this specification, each value for tensile strength and yield strength shall be rounded to the nearest 0.1 ksi and each value for elongation shall be rounded to the nearest 0.5 %, both in accordance with the rounding method of Practice E 29.

| Alloy              |        | Temper <sup>B</sup>                 | Tensile Strength, min, ksi (MPa) <sup>C</sup> | Yield Strength (0.2 % offset) min, ksi (MPa) <sup>C</sup> | Elongation in 2 in. or 4× diameter, min, % | Typical Brinell Hardness, <sup>D</sup> 500 kgf, 10 mm |
|--------------------|--------|-------------------------------------|---|---|--|---|
| ANSI <sup>F</sup>  | UNS    |                                     |   |   |  |   |
| 201.0              | A02010 | T6                                  | 60.0 (414)                                    | 50.0 (345)  | 5.0  | ...   |
|                    |        | T7                                  | 60.0 (414)                                    | 50.0 (345)  | 3.0  | ...   |
| 204.0              | A02040 | T4                                  | 45.0 (310)                                    | 28.0 (193)  | 6.0  | ...   |
| 208.0              | A02080 | F                                   | 19.0 (131)                                    | 12.0 (83)   | 1.5  | 55  |
| 222.0              | A02220 | O <sup>F</sup>                      | 23.0 (159)                                    | <sup>G</sup>  | <sup>G</sup>                               | 80  |
|                    |        | T6                                  | 30.0 (207)                                    | <sup>G</sup>  | <sup>G</sup>                               | 115   |
| 242.0              | A02420 | O <sup>F</sup>                      | 23.0 (159)                                    | <sup>G</sup>  | <sup>G</sup>                               | 70  |
|                    |        | T61                                 | 32.0 (221)                                    | 20.0 (138)  | <sup>G</sup>                               | 105   |
| 295.0              | A02950 | T4                                  | 29.0 (200)                                    | 13.0 (90)   | 6.0  | 60  |
|                    |        | T6                                  | 32.0 (221)                                    | 20.0 (138)  | 3.0  | 75  |
|                    |        | T62                                 | 36.0 (248)                                    | 28.0 (193)  | <sup>B</sup>                               | 95  |
|                    |        | T7                                  | 29.0 (200)                                    | 16.0 (110)  | 3.0  | 70  |
| 319.0              | A03190 | F                                   | 23.0 (159)                                    | 13.0 (90)   | 1.5  | 70  |
|                    |        | T6                                  | 31.0 (214)                                    | 20.0 (138)  | 1.5  | 80  |
| 328.0              | A03280 | F                                   | 25.0 (172)                                    | 14.0 (97)   | 1.0  | 60  |
|                    |        | T6                                  | 34.0 (234)                                    | 21.0 (145)  | 1.0  | 80  |
| 355.0              | A03550 | T6                                  | 32.0 (221)                                    | 20.0 (138)  | 2.0  | 80  |
|                    |        | T51                                 | 25.0 (172)                                    | 18.0 (124)  | <sup>G</sup>                               | 65  |
|                    |        | T71                                 | 30.0 (207)                                    | 22.0 (152)  | <sup>G</sup>                               | 75  |
| C355.0             | A33550 | T6                                  | 36.0 (248)                                    | 25.0 (172)  | 2.5  | ...   |
| 356.0              | A03560 | F                                   | 19.0 (131)                                    | <sup>G</sup>  | 2.0  | 55  |
|                    |        | T6                                  | 30.0 (207)                                    | 20.0 (138)  | 3.0  | 70  |
|                    |        | T7                                  | 31.0 (214)                                    | <sup>G</sup>  | <sup>G</sup>                               | 75  |
|                    |        | T51                                 | 23.0 (159)                                    | 16.0 (110)  | <sup>G</sup>                               | 60  |
|                    |        | T71                                 | 25.0 (172)                                    | 18.0 (124)  | 3.0  | 60  |
|                    |        | T6                                  | 34.0 (234)                                    | 24.0 (166)  | 3.5  | 80  |
|                    |        | F                                   | 17.0 (117)                                    | 7.0 (48)  | 3.0  | 40  |
| B443.0             | A24430 | F                                   | 17.0 (117)                                    | 6.0 (41)  | 3.0  | 40  |
|                    |        | F                                   | 22.0 (152)                                    | 9.0 (62)  | 6.0  | 50  |
| 514.0              | A05140 | F                                   | 22.0 (152)                                    | 9.0 (62)  | 6.0  | 50  |
| 520.0              | A05200 | T4                                  | 42.0 (290)                                    | 22.0 (152)  | 12.0                                       | 75  |
| 535.0              | A05350 | F                                   | 35.0 (241)                                    | 18.0 (124)  | 9.0  | 70  |
| 705.0              | A07050 | T1 <sup>H</sup> and T5 <sup>I</sup> | 30.0 (207)                                    | 17.0 (117) <sup>J</sup>                                   | 5.0  | 65  |
| 707.0              | A07070 | T1 <sup>H</sup>                     | 33.0 (228)                                    | 22.0 (152) <sup>J</sup>                                   | 2.0  | 85  |
|                    |        | T7                                  | 37.0 (255)                                    | 30.0 (207) <sup>J</sup>                                   | 1.0  | 80  |
|                    |        | T1 <sup>H</sup>                     | 32.0 (221)                                    | 20.0 (138)  | 2.0  | 75  |
| 710.0 <sup>K</sup> | A07100 | T1 <sup>H</sup>                     | 32.0 (221)                                    | 20.0 (138)  | 2.0  | 75  |
| 712.0 <sup>K</sup> | A07120 | T1 <sup>H</sup> and T5 <sup>I</sup> | 34.0 (234)                                    | 25.0 (172) <sup>J</sup>                                   | 4.0  | 75  |
| 713.0              | A07130 | T1 <sup>H</sup> and T5 <sup>I</sup> | 32.0 (221)                                    | 22.0 (152)  | 3.0  | 75  |
| 771.0              | A07710 | T5                                  | 42.0 (290)                                    | 38.0 (262)  | 1.5  | 100   |
|                    |        | T51                                 | 32.0 (221)                                    | 27.0 (186)  | 3.0  | 85  |
|                    |        | T52                                 | 36.0 (248)                                    | 30.0 (207)  | 1.5  | 85  |
|                    |        | T6                                  | 42.0 (290)                                    | 35.0 (241)  | 5.0  | 90  |
|                    |        | T71                                 | 48.0 (331)                                    | 45.0 (310)  | 2.0  | 120   |
|                    |        | T5                                  | 16.0 (110)                                    | <sup>G</sup>  | 5.0  | 45  |
|                    |        | T5                                  | 17.0 (117)                                    | <sup>G</sup>  | 3.0  | 45  |
| 852.0 <sup>K</sup> | A08520 | T5                                  | 24.0 (166)                                    | 18.0 (124)  | <sup>G</sup>                               | 60  |

<sup>A</sup> If agreed upon by the producer and the purchaser, other mechanical properties may be obtained by other heat treatments such as annealing, aging, or stress relieving.

<sup>B</sup> Refer to ANSI H35.1 and/or H35.1M for description of tempers.

<sup>C</sup> SI units for information only. For explanation of the SI unit "MPa" see Appendix X2.

<sup>D</sup> For information only, not required for acceptance.

<sup>E</sup> ASTM alloy designations are in Practice B 275.

<sup>F</sup> Formerly designated 222.0-T2 and 242.0-T21.

<sup>G</sup> Not required.

<sup>H</sup> Aged 21 days at room temperature.

<sup>I</sup> Artificially aged in accordance with Practice B 597.

<sup>J</sup> Yield strength to be determined only when specified in the contract or purchase order.

<sup>K</sup> 710.0 formerly A712.0, 712.0 formerly D712.0, 851.0, formerly A850.0, 852.0 formerly B850.0.

## 6. Materials and Manufacture

6.1 The responsibility of furnishing castings that can be laid out and machined to the finished dimensions within the permissible variations specified, as shown on the blueprints or drawings, shall rest with the producer, except where pattern equipment is furnished by the purchaser.

6.1.1 Unless otherwise specified, only aluminum alloy conforming to the requirements of Specification B 179 or producer's foundry scrap (identified as being made from alloy conforming to Specification B 179) shall be used in the remelting furnace from which molten metal is taken for pouring directly into castings. Additions of small amounts of modifiers and grain refining elements or alloys are permitted.

6.1.2 Pure materials, recycled materials, and master alloys may be used to make alloys conforming to this specification, provided chemical analysis can be taken and adjusted to conform to Table 1 prior to pouring any castings.

## 7. Chemical Composition

7.1 The castings shall conform to the chemical composition limits prescribed in Table 1. Conformance shall be determined by the producer by analyzing samples taken at the time the castings are poured, or samples taken from castings or tension test specimens representative of castings. If the producer has determined the chemical composition of the material during the course of manufacture, he shall not be required to sample and analyze the finished product.

## 8. Sampling for Determination of Chemical Composition

8.1 A sample for the determination of chemical composition shall be taken to represent the following:

8.1.1 Not more than 500 lb (227 kg) of clean castings (gates and risers removed) or a single casting poured from one furnace and using only one melt charge.

8.1.2 Castings poured continuously from one furnace for not more than 8 consecutive hours from a single master heat. A master heat is defined as all the metal of a single furnace charge without subsequent additions after chemical composition has been determined.

8.2 Samples for determination of chemical composition shall be taken in accordance with one of the following methods.

8.2.1 *Samples for Chemical Analysis*— Samples for chemical analysis shall be taken by sawing, drilling, or milling the casting or test specimens in such a manner as to be representative of the material in accordance with Practice E 88. The weight of a prepared sample shall be not less than 75 g.

8.2.2 *Samples for Spectrochemical and Other Methods of Analysis*— Sampling for spectrochemical analysis shall be in accordance with Practices E 716. Samples for other methods of analysis shall be suitable for the form of material being analyzed and the type of analytical methods used.

## 9. Methods of Determination of Chemical Composition

9.1 The determination of chemical composition shall be made in accordance with suitable chemical (Test Methods E 34), or spectrochemical (Test Methods E 227, E 607 and E 1251) methods. Other methods may be used only when no published ASTM standard is available. In case of dispute, the methods of analysis shall be agreed upon between the producer and the purchaser.

## 10. Tensile Requirements

10.1 The separately cast tension test specimens representing the castings shall meet the mechanical properties prescribed in Table 2.

10.2 Although alloys 705.0, 707.0, D712.0, and 713.0 are most frequently used in the T1 naturally aged temper, by agreement of the producer and purchaser, the castings may be supplied in the T5 artificially aged temper. The producer and the purchaser may also agree to base the acceptance of castings on artificially aged test bars.

10.3 When specified, the tensile strength, yield strength, and elongation values of specimens cut from castings shall be not less than 75 % of the tensile and yield strength values and not less than 25 % of the elongation values specified in Table 2. The measurement of elongation is not required for test specimens cut from castings if 25 % of the specified minimum elongation value published in Table 2 is 0.5 % or less. If grade D quality castings as described in Table 3 are specified, no tensile tests shall be specified nor tensile requirements be met on specimens cut from castings.

## 11. Test Specimens

11.1 The tension test specimens shall be cast to size in

**TABLE 3 Discontinuity-Level Requirements for Aluminum Investment Castings (Reference Radiographs E 155)**

| Discontinuity                          | Radiograph | Grade A                |     | Grade B                         |     | Grade C |              | Grade D |              |
|--|------------|------------------------|-----|---------------------------------|-----|---------|--------------|---------|--------------|
|  |            | Section Thickness, in. |     |                                 |     |         |              |         |              |
|  |            | 1/4                    | 3/4 | 1/4                             | 3/4 | 1/4     | 3/4          | 1/4     | 3/4          |
| Gas holes                              | 1.1        | none                   |     | 1                               | 1   | 2       | 2            | 5       | 5            |
| Gas porosity (round)                   | 1.21       | none                   |     | 1                               | 1   | 3       | 3            | 7       | 7            |
| Gas porosity (elongated)               | 1.22       | none                   |     | 1                               | 1   | 3       | 4            | 5       | 5            |
| Shrinkage cavity                       | 2.1        | none                   |     | 1                               | 1   | 2       | <sup>A</sup> | 3       | <sup>A</sup> |
| Shrinkage porosity or sponge           | 2.2        | none                   |     | 1                               | 1   | 2       | 2            | 4       | 3            |
| Foreign material (less dense material) | 3.11       | none                   |     | 1                               | 1   | 2       | 2            | 4       | 4            |
| Foreign material (more dense material) | 3.12       | none                   |     | 1                               | 1   | 2       | 1            | 4       | 3            |
| Segregation                            | 3.2        | none                   |     | none                            |     | none    |              | none    |              |
| Cracks                                 | ...        | none                   |     | none                            |     | none    |              | none    |              |
| Cold shuts                             | ...        | none                   |     | none                            |     | none    |              | none    |              |
| Surface irregularity                   | ...        |                        |     | not to exceed drawing tolerance |     |         |              |         |              |
| Core shift                             | ...        |                        |     | not to exceed drawing tolerance |     |         |              |         |              |

<sup>A</sup> Not available.