

SLOVENSKI STANDARD
SIST EN 61249-2-12:2001**01-marec-2001**

**Materials for printed boards and other interconnecting structures - Part 2-12:
Sectional specification set for reinforced base materials, clad and unclad -
Epoxyde non-woven aramid laminate of defined flammability, copper-clad**

Materials for printed boards and other interconnecting structures -- Part 2-12: Sectional specification set for reinforced base materials, clad and unclad - Epoxyde non-woven aramid laminate of defined flammability, copper-clad

iTeh STANDARD PREVIEW

Materialien für Leiterplatten und andere Verbindungsstrukturen -- Teil 2-12:
Rahmenspezifikation für verstärkte, kaschierte und unkaschierte Basismaterialien -
Aramidwirrfaser-verstärktes Epoxidharz-Laminat mit definierter Brennbarkeit,
kupferkaschiert

[SIST EN 61249-2-12:2001](https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-49d33e1115a3/sist-en-61249-2-12-2001)

<https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-49d33e1115a3/sist-en-61249-2-12-2001>

Matériaux pour circuits imprimés et autres structures d'interconnexion -- Partie 2-12:
Collection de spécifications intermédiaires pour les matériaux de base renforcés,
recouverts ou non de feuille conductrice - Stratifié à base d'aramide non tissé collé avec
de la résine époxyde, recouvert de cuivre, d'inflammabilité définie

Ta slovenski standard je istoveten z: EN 61249-2-12:1999

ICS:

31.180 Vā \ aē aē^: lā \ Q \ Dē \ ā \ aē^ Printed circuits and boards
] || z ^

SIST EN 61249-2-12:2001**en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 61249-2-12:2001](#)

<https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-49d33e1115a3/sist-en-61249-2-12-2001>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 61249-2-12

April 1999

ICS 31.180

English version

**Materials for printed boards and other interconnecting structures
Part 2-12: Sectional specification set for reinforced base materials,
clad and unclad - Epoxide non-woven aramid laminate of defined
flammability, copper-clad
(IEC 61249-2-12:1999)**

Matériaux pour circuits imprimés et autres structures d'interconnexion
Partie 2-12: Collection de spécifications intermédiaires pour les matériaux de base renforcés, recouverts ou non de feuille conductrice - Stratifié à base d'aramide non tissé collé avec de la résine epoxyde, recouvert de cuivre, d'inflammabilité définie
(CEI 61249-2-12:1999)

Materialien für Leiterplatten und andere Verbindungsstrukturen
Teil 2-12: Rahmenspezifikation für verstärkte, kaschierte und unkaschierte Basismaterialien Aramidwirrfaser-verstärktes Epoxidharz-Laminat mit definierter Brennbarkeit, kupferkaschiert
(IEC 61249-2-12:1999)

This European Standard was approved by CENELEC on 1999-04-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

The text of document 52/772/FDIS, future edition 1 of IEC 61249-2-12, prepared by IEC TC 52, Printed circuits, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 61249-2-12 on 1999-04-01.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2000-01-01
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2002-01-01

Annexes designated "normative" are part of the body of the standard.
Annexes designated "informative" are given for information only.
In this standard, annex ZA is normative and annex A is informative.
Annex ZA has been added by CENELEC.

Endorsement notice

The text of the International Standard IEC 61249-2-12:1999 was approved by CENELEC as a European Standard without any modification.

(standards.iteh.ai)

SIST EN 61249-2-12:2001

<https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-49d33e1115a3/sist-en-61249-2-12-2001>



Annex ZA (normative)

Normative references to international publications
with their corresponding European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

NOTE: When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 61189-2	1997	Test methods for electrical materials, printed boards and other interconnection structures and assemblies Part 2: Test methods for materials for interconnection structures	EN 61189-2 + corr. August	1997 1997
IEC 61249-5-1	1995	Materials for interconnection structures Part 5: Sectional specification set for conductive foils and films with and without coatings Section 1: Copper foils (for the manufacture of copper-clad base materials)	EN 61249-5-1	1996

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 61249-2-12:2001](https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-49d33e1115a3/sist-en-61249-2-12-2001)

<https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-49d33e1115a3/sist-en-61249-2-12-2001>

**NORME
INTERNATIONALE
INTERNATIONAL
STANDARD**

**CEI
IEC**

61249-2-12

Première édition
First edition
1999-01

**Matériaux pour circuits imprimés et autres
structures d'interconnexion –**

Partie 2-12:

**Collection de spécifications intermédiaires
pour les matériaux de base renforcés,
recouverts ou non de feuille conductrice –
Stratifié à base d'aramide non tissé collé avec
de la résine époxyde, recouvert de cuivre,
d'inflammabilité définie**

[SIST EN 61249-2-12:2001](https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-415c11557/sist/61249-2-12:2001)

[https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-](https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-415c11557/sist/61249-2-12:2001)

**Materials for printed boards and
other interconnecting structures –**

Part 2-12:

**Sectional specification set for
reinforced base materials, clad and unclad –
Epoxyde non-woven aramid laminate of
defined flammability, copper-clad**

© IEC 2001 Droits de reproduction réservés — Copyright - all rights reserved

Aucune partie de cette publication ne peut être reproduite ni
utilisée sous quelque forme que ce soit et par aucun procédé,
électronique ou mécanique, y compris la photocopie et les
microfilms, sans l'accord écrit de l'éditeur.

No part of this publication may be reproduced or utilized in
any form or by any means, electronic or mechanical,
including photocopying and microfilm, without permission in
writing from the publisher.

International Electrotechnical Commission
Telefax: +41 22 919 0300

e-mail: inmail@iec.ch

3, rue de Varembe Geneva, Switzerland
IEC web site <http://www.iec.ch>



Commission Electrotechnique Internationale
International Electrotechnical Commission
Международная Электротехническая Комиссия

CODE PRIX
PRICE CODE

P

*Pour prix, voir catalogue en vigueur
For price, see current catalogue*

CONTENTS

FOREWORD	5
1 Scope	7
2 Normative references	7
3 Materials and construction	7
4 Internal marking	7
5 Electrical properties	9
6 Non-electrical properties of the copper-clad laminate	9
7 Non-electrical properties of the base material after complete removal of the copper foil	19
8 Packaging and marking	23
9 Acceptance testing	23
Annex A (informative) Conversion table for test method numbers	25
Table 1 – Electrical properties	9
Table 2 – Types, sizes and permitted number of imperfections	11
Table 3 – Nominal thickness and tolerances of metal-clad laminate	13
Table 4 – Pull-off and peel strength	15
Table 5 – Dimensional stability	15
Table 6 – Size tolerances for cut panels	17
Table 7 – Rectangularity of cut panels	17
Table 8 – Flexural strength	19
Table 9 – Flammability	19
Table 10 – Water absorption	21
Table 11 – Glass transition temperature and cure factor	21
Table 12 – Thermal coefficient of expansion	21
Table 13 – Recommended acceptance tests	23

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**MATERIALS FOR PRINTED BOARDS AND OTHER
INTERCONNECTING STRUCTURES –****Part 2-12: Sectional specification set for reinforced
base materials, clad and unclad –
Epoxide non-woven aramid laminate of
defined flammability, copper-clad**

FOREWORD

- 1) The IEC (International Electrotechnical Commission) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of the IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, the IEC publishes International Standards. Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. The IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of the IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested National Committees.
- 3) The documents produced have the form of recommendations for international use and are published in the form of standards, technical specifications, technical reports or guides and they are accepted by the National Committees in that sense.
- 4) In order to promote international unification, IEC National Committees undertake to apply IEC International Standards transparently to the maximum extent possible in their national and regional standards. Any divergence between the IEC Standard and the corresponding national or regional standard shall be clearly indicated in the latter. <https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d->
- 5) The IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with one of its standards.
- 6) Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. The IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61249-2-12 has been prepared by IEC technical committee 52: Printed circuits.

This bilingual version (2001-05) replaces the English version.

The text of this standard is based on the following documents:

FDIS	Report on voting
52/772/FDIS	52/797/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 3.

Annex A is for information only.

The committee has decided that the contents of this publication will remain unchanged until 2005. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

MATERIALS FOR PRINTED BOARDS AND OTHER INTERCONNECTING STRUCTURES –

Part 2-12: Sectional specification set for reinforced base materials, clad and unclad – Epoxide non-woven aramid laminate of defined flammability, copper-clad

1 Scope

This part of IEC 61249 gives requirements for properties of epoxide non-woven aramid copper-clad laminate of defined flammability, in thicknesses of 0,05 mm up to 6,4 mm.

NOTE To designate this material, the reference: 61249-2-12-FV1-IEC-EP-AP-Cu may be used; if there is no risk of confusion, the type designation may be abbreviated to read IEC-61249-2-12-FV1.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of IEC 61249. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of IEC 61249 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of IEC and ISO maintain registers of currently valid International Standards.

IEC 61189-2:1997, *Test methods for electrical materials, interconnection structures and assemblies – Part 2: Test methods for materials for interconnection structures*

<https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-161311111111/iec-61189-2-1997>

IEC 61249-5-1:1995, *Materials for printed boards and other interconnecting structures – Part 5: Sectional specification set for conductive foils and films with or without coatings – Section 1: Copper foils (for the manufacture of copper-clad base materials)*

3 Materials and construction

The material consists of an insulating base with metal foil bonded to one side or both.

3.1 Insulating base

Epoxide resin bonded non-woven aramid laminate. Its flame resistance is defined in terms of the flammability requirements of 7.3.

3.2 Metal foil

Copper as specified in IEC 61249-5-1. The preferred foils are type E1 (standard electro-deposited copper) of standard ductility.

4 Internal marking

Not specified.

5 Electrical properties

Table 1 – Electrical properties

Property	Test method (IEC 61189-2)	Requirements
Resistance of foil	2E12	As specified in IEC 61249-5-1
Surface resistance after damp heat while in the humidity chamber (optional)	2E03	1 000 M Ω min.
Surface resistance after damp heat and recovery	2E03	10 000 M Ω min.
Volume resistivity after damp heat while in the humidity chamber (optional)	2E04	1 000 M Ω m min.
Volume resistivity after damp heat and recovery	2E04	10 000 M Ω m min.
Surface corrosion	2E08	No visible corrosion products in the gap
Corrosion at the edge	2E13	Positive pole: not worse than A/B Negative pole: not worse than 1,4
Relative permittivity after damp heat and recovery	2E10	The average value shall not exceed 4,5
Dielectric dissipation factor after damp heat and recovery	2E10	The average value shall not exceed 0,03
Electrical strength (optional) material thickness not greater than 0,8 mm	2E11	30 kV/mm min.
Surface resistance at 200 °C	2E07	1 000 M Ω min.
Volume resistivity at 200 °C	2E07	10 M Ω m min.

[https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-](https://standards.iteh.ai/catalog/standards/sist/b5b113f8-ef0b-468d-8c5d-49d33e1115a3/sist-en-61249-2-12-2001)

6 Non-electrical properties of the copper-clad laminate

6.1 Appearance of the copper-clad face

6.1.1 Normal surface appearance

The copper-clad face shall be substantially free from blisters, wrinkles, pin-holes, deep scratches, pits and resin. Any discoloration or contamination shall be readily removable with a hydrochloric acid solution of density 1,02 g/cm² or with a suitable organic solvent.

6.1.2 Qualified surface appearance (optional)

If a surface of high quality is essential for precious metal plating or fine line etching and is ordered by the purchaser, the following requirements shall apply in addition to those of 6.1.1 when inspected in accordance with 2M18 of IEC 61189-2.

The surface appearance of the copper-clad face shall be such as not to conceal imperfections.

The surface of the copper foil shall be free from scratches of depth greater than 10 μ m or 1/5 of the nominal thickness of the copper foil, whichever is lower.