

SLOVENSKI STANDARD SIST EN 1993-1-3:2007

01-marec-2007

9jfc_cX''.`Dfc^Y_hjfUb^Y`Y_`Ybj\`_cbglfi_Wj^!`%' "XY`.`Gd`cýbU'dfUj j`U'!`8cXUhbU dfUj]`U'nU'\`UXbc`cV`]_cjUbY`dfcZj`Y`]b`d`c Yj]bc

Eurocode 3 - Design of steel structures - Part 1-3: General rules - Supplementary rules for cold-formed members and sheeting

Bemessung und Konstruktion von Stahlbauten - Teil 1-3: Allgemeine Regeln -Ergänzende Regeln für kaltgeformte dünnwandige Bauteile und Bleche

Eurocode 3 - Calcul des structures en acier - Partie 1-3: Regles générales - Regles supplémentaires pour les profilés et plagues formés a froid

https://standards.iteh.ai/catalog/standards/sist/1d96a7d7-1050-4931-a1b9-

Ta slovenski standard je istoveten Z: EN 1993-1-3:2006

ICS:

V^@2,ã}ã4çãããããã 91.010.30 91.080.10 Kovinske konstrukcije

Technical aspects Metal structures

SIST EN 1993-1-3:2007

en

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 1993-1-3:2007</u> https://standards.iteh.ai/catalog/standards/sist/1d96a7d7-1050-4931-a1b9-8e6ba930e5a2/sist-en-1993-1-3-2007

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 1993-1-3

October 2006

ICS 91.010.30

Supersedes ENV 1993-1-3:1996

English Version

Eurocode 3 - Design of steel structures - Part 1-3: General rules - Supplementary rules for cold-formed members and sheeting

Eurocode 3 - Calcul des structures en acier - Partie 1-3: Règles générales - Règles supplémentarires pour les profilés et plaques à parois minces formés à froid Eurocode 3 - Bemessung und Konstruktion von Stahlbauten - Teil 1-3: Allgemeine Regeln - Ergänzende Regeln für kaltgeformte dünnwandige Bauteile und Bleche

This European Standard was approved by CEN on 16 January 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austra, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom. <u>SIST EN 1993-1-3:2007</u>

https://standards.iteh.ai/catalog/standards/sist/1d96a7d7-1050-4931-a1b9-8e6ba930e5a2/sist-en-1993-1-3-2007



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

© 2006 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN 1993-1-3:2006: E

Content

1	Introduction	5
	1.1 Scope	5
	1.2 Normative references	5
	1.3 Terms and definitions	6
	1.4 Symbols1.5 Terminology and conventions for dimensions	7 8
2	Basis of design	o 11
3	Materials	12
	3.1 General	12
	3.2 Structural steel3.3 Connecting devices	15 17
4		
	Durability	17
5	Structural analysis	18
	5.1 Influence of rounded corners	18
	5.2 Geometrical proportions	20 22
	5.3 Structural modelling for analysis5.4 Flange curling	22
	5.5 Local and distortional buckling	23
	5.6 Plate buckling between fasteners	41
6	Ultimate limit states iTeh STANDARD PREVIEW	41
	6.1 Resistance of cross-sections (standards.iteh.ai)	41
	0.2 Buckning resistance	56
_	6.3 Bending and axial tension SIST EN 1993-1-3:2007	60
7	Serviceability limit states and ards.iteh.ai/catalog/standards/sist/1d96a7d7-1050-4931-a1b9- 8e6ba930e5a2/sist-en-1993-1-3-2007	60
	 7.1 General 7.2 Plastic deformation 	60 60
	7.2 Plastic deformation 7.3 Deflections	60 60
8	Design of joints	61
Ū	8.1 General	61
	8.2 Splices and end connections of members subject to compression	61
	8.3 Connections with mechanical fasteners	61
	8.4 Spot welds	68
	8.5 Lap welds	69
9	Design assisted by testing	73
10	Special considerations for purlins, liner trays and sheetings	74
	10.1 Beams restrained by sheeting	74
	10.2 Liner trays restrained by sheeting	92
	10.3 Stressed skin design	95 99
	10.4 Perforated sheeting	
Aı	nnex A [normative] – Testing procedures	100
	A.1 General	100
	A.2 Tests on profiled sheets and liner traysA.3 Tests on cold-formed members	100 105
	A.4 Tests on structures and portions of structures	103
	A.5 Tests on torsionally restrained beams	110
	A.6 Evaluation of test results	114

Annex B [informative] – Durability of fasteners		
Annex C [informative] – Cross section constants for thin-walled cross sections	121	
C.1 Open cross sections	121	
C.2 Cross section constants for open cross section with branches	123	
C.3 Torsion constant and shear centre of cross section with closed part	124	
Annex D [informative] – Mixed effective width/effective thickness method for outstand elements	125	
Annex E [Informative] – Simplified design for purlins	127	

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 1993-1-3:2007</u> https://standards.iteh.ai/catalog/standards/sist/1d96a7d7-1050-4931-a1b9-8e6ba930e5a2/sist-en-1993-1-3-2007

Foreword

This European Standard EN 1993-1-3, Eurocode 3: Design of steel structures: Part 1-3 General rules – Supplementary rules for cold formed members and sheeting, has been prepared by Technical Committee CEN/TC250 « Structural Eurocodes », the Secretariat of which is held by BSI. CEN/TC250 is responsible for all Structural Eurocodes.

This European Standard shall be given the status of a National Standard, either by publication of an identical text or by endorsement, at the latest by April 2007, and conflicting National Standards shall be withdrawn at latest by March 2010.

This Eurocode supersedes ENV 1993-1-3.

According to the CEN-CENELEC Internal Regulations, the National Standard Organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

National annex for EN 1993-1-3

This standard gives alternative procedures, values and recommendations for classes with notes indicating where national choices may have to be made. Therefore the National Standard implementing EN 1993-1-3 should have a National Annex containing all Nationally Determined Parameters to be used for the design of steel structures to be constructed in the relevant country.

National choice is allowed in EN 1993 1 3 through clauses:) PREVIEW -2(3)P(standards.iteh.ai) - 2(5) SIST EN 1993-1-3:2007 - 3.1(3) Note 1 and Noter2ps://standards.iteh.ai/catalog/standards/sist/1d96a7d7-1050-4931-a1b9-8e6ba930e5a2/sist-en-1993-1-3-2007 -3.2.4(1)-5.3(4)-8.3(5)- 8.3(13), Table 8.1 - 8.3(13), Table 8.2 - 8.3(13), Table 8.3 - 8.3(13), Table 8.4 -8.4(5)- 8.5.1(4) - 9(2) -10.1.1(1)- 10.1.4.2(1) - A.1(1), NOTE 2 - A.1(1), NOTE 3 - A.6.4(4)- E(1)

1 Introduction

1.1 Scope

(1) EN 1993-1-3 gives design requirements for cold-formed thin gauge members and sheeting. It applies to cold-formed steel products made from coated or uncoated thin gauge hot or cold rolled sheet or strip, that have been cold-formed by such processes as cold-rolled forming or press-braking. It may also be used for the design of profiled steel sheeting for composite steel and concrete slabs at the construction stage, see EN 1994. The execution of steel structures made of cold-formed thin gauge members and sheeting is covered in EN 1090.

NOTE: The rules in this part complement the rules in other parts of EN 1993-1.

(2) Methods are also given for stressed-skin design using steel sheeting as a structural diaphragm.

(3) This part does not apply to cold-formed circular and rectangular structural hollow sections supplied to EN 10219, for which reference should be made to EN 1993-1-1 and EN 1993-1-8.

(4) EN 1993-1-3 gives methods for design by calculation and for design assisted by testing. The methods for design by calculation apply only within stated ranges of material properties and geometrical proportions for which sufficient experience and test evidence is available. These limitations do not apply to design assisted by testing.

(5) EN 1993-1-3 does not cover load arrangement for testing for loads during execution and maintenance.

(6) The calculation rules given in this standard are only valid if the tolerances of the cold formed members comply with EN 1090-2

1.2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this European Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply.

However, parties to agreements based on this European Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below 1For undated references, the latest edition of the normative document referred to applies 1993-1-3-2007

EN 1993 Eurocode 3 – Design of steel structures

Part 1-1 to part 1-12

EN 10002	Metallic materials - Tensile testing:				
Part 1:	Method of test (at ambient temperature);				
EN 10025-1	Hot-rolled products of structural steels - Part 1: General delivery conditions;				
EN 10025-2	Hot-rolled products of structural steels - Part 2: Technical delivery conditions for non-alloy structural steels;				
EN 10025-3	Hot-rolled products of structural steels - Part 3: Technical delivery conditions for normalized / normalized rolled weldable fine grain structural steels;				
EN 10025-4	Hot-rolled products of structural steels - Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels;				
EN 10025-5	Hot-rolled products of structural steels - Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance;				
EN 10143	Continuously hot-dip metal coated steel sheet and strip - Tolerances on dimensions and shape;				
EN 10149	Hot rolled flat products made of high yield strength steels for cold-forming:				
Part 2:	Delivery conditions for normalized/normalized rolled steels;				
Part 3:	Delivery conditions for thermomechanical rolled steels;				
EN 10204	Metallic products. Types of inspection documents (includes amendment A 1:1995);				
EN 10268	Cold-rolled flat products made of high yield strength micro-alloyed steels for cold forming - General delivery conditions;				

EN 1993-1-3: 2006 (E)

- EN 10292 Continuously hot-dip coated strip and sheet of steels with higher yield strength for cold forming Technical delivery conditions;
- EN 10326 *Continuously hot-dip coated strip and sheet of structural steels Technical delivery conditions;*
- EN 10327 Continuously hot-dip coated strip and sheet of low carbon steels for cold forming Technical delivery conditions;
- EN-ISO 12944-2 Paints and vanishes. Corrosion protection of steel structures by protective paint systems. Part 2: Classification of environments (ISO 12944-2:1998);
- EN 1090-2 *Execution of steel structures and aluminium structures Part 2: Technical requirements for steel structures:*
- EN 1994 *Eurocode 4: Design of composite steel and concrete structures;*
- EN ISO 1478 Tapping screws thread;
- EN ISO 1479 Hexagon head tapping screws;
- EN ISO 2702 Heat-treated steel tapping screws Mechanical properties;
- EN ISO 7049 Cross recessed pan head tapping screws;
- EN ISO 10684 Fasteners hot deep galvanized coatings
- ISO 4997 *Cold reduced steel sheet of structural quality;*
- EN 508-1 *Roofing products from metal sheet Specification for self-supporting products of steel, aluminium or stainless steel sheet Part 1: Steel;*
- FEM 10.2.02 Federation Europeenne de la manutention, Secion X, Equipment et proceedes de stockage, FEM 10.2.02. The design of static steel pallet racking, Racking design code, April 2001 Version 1.02.

(standards.iteh.ai)

1.3 Terms and definitions

Supplementary to EN 1993-1-1, for the purposes of 9this 3Part 1-3 of EN 1993, the following terms and definitions apply: https://standards.iteh.ai/catalog/standards/sist/1d96a7d7-1050-4931-a1b9-8e6ba930e5a2/sist-en-1993-1-3-2007

1.3.1

basic material

The flat sheet steel material out of which cold-formed sections and profiled sheets are made by cold-forming.

1.3.2

basic yield strength

The tensile yield strength of the basic material.

1.3.3

diaphragm action

Structural behaviour involving in-plane shear in the sheeting.

1.3.4

liner tray

Profiled sheet with large lipped edge stiffeners, suitable for interlocking with adjacent liner trays to form a plane of ribbed sheeting that is capable of supporting a parallel plane of profiled sheeting spanning perpendicular to the span of the liner trays.

1.3.5

partial restraint

Restriction of the lateral or rotational movement, or the torsional or warping deformation, of a member or element, that increases its buckling resistance in a similar way to a spring support, but to a lesser extent than a rigid support.

1.3.6

relative slenderness

A normalized non-dimensional slenderness ratio.

1.3.7

restraint

Restriction of the lateral or rotational movement, or the torsional or warping deformation, of a member or element, that increases its buckling resistance to the same extent as a rigid support.

1.3.8

stressed-skin design

A design method that allows for the contribution made by diaphragm action in the sheeting to the stiffness and strength of a structure.

1.3.9

support

A location at which a member is able to transfer forces or moments to a foundation, or to another member or other structural component.

1.3.10

nominal thickness

A target average thickness inclusive zinc and other metallic coating layers when present rolled and defined by the steel supplier (t_{nom} not including organic coatings).

1.3.11

steel core thickness iTeh STANDARD PREVIEW

A nominal thickness minus zinc and other metallic coating layers (t_{cor}) .

1.3.12

SIST EN 1993-1-3:2007

the steel core thickness used in design by calculation according to 1.5.3(6) and 3.2.4.

1.4 Symbols

design thickness

(1) In addition to those given in EN 1993-1-1, the following main symbols are used:

- $f_{\rm y}$ yield strength
- f_{ya} average yield strength
- f_{yb} basic yield strength
- t design core thickness of steel material before cold forming, exclusive of metal and organic coating
- $t_{\rm nom}$ nominal sheet thickness after cold forming inclusive of zinc and other metallic coating not including organic coating
- $t_{\rm cor}$ the nominal thickness minus zinc and other metallic coating
- *K* spring stiffness for displacement
- *C* spring stiffness for rotation
- (2) Additional symbols are defined where they first occur.
- (3) A symbol may have several meanings in this part.

1.5 Terminology and conventions for dimensions


1.5.1 Form of sections

(1) Cold-formed members and profiled sheets have within the permitted tolerances a constant nominal thickness over their entire length and may have either a uniform cross section or a tapering cross section along their length.

(2) The cross-sections of cold-formed members and profiled sheets essentially comprise a number of plane elements joined by curved elements.

(3) Typical forms of sections for cold-formed members are shown in figure 1.1.

NOTE: The calculation methods of this Part 1-3 of EN 1993 does not cover all the cases shown in figures 1.1-1.2.




c) Closed built-up sections


Figure 1.1: Typical forms of sections for cold-formed members

(4) Examples of cross-sections for cold-formed members and sheets are illustrated in figure 1.2.

NOTE: All rules in this Part 1-3 of EN 1993 relate to the main axis properties, which are defined by the main axes y - y and z - z for symmetrical sections and u - u and v - v for unsymmetrical sections as e.g. angles and Zed-sections. In some cases the bending axis is imposed by connected structural elements whether the cross-section is symmetric or not.



a) Compression members and tension members



c) Profiled sheets and liner trays

Figure 1.2: Examples of cold-formed members and profiled sheets

(5) Cross-sections of cold-formed members and sheets may either be unstiffened or incorporate longitudinal stiffeners in their webs or flanges, or in both.

1.5.2 Form of stiffeners

(1) Typical forms of stiffeners for cold-formed members and sheets are shown in figure 1.3.






Figure 1.3: Typical forms of stiffeners for cold-formed members and sheeting

- (2) Longitudinal flange stiffeners may be either edge stiffeners or intermediate stiffeners.
- (3) Typical edge stiffeners are shown in figure 1.4.





1.5.3 Cross-section dimensions

(1) Overall dimensions of cold-formed members and sheeting, including overall width b, overall height h, internal bend radius r and other external dimensions denoted by symbols without subscripts, such as a, c or d, are measured to the face of the material, unless stated otherwise, as illustrated in figure 1.6.




Figure 1.6: Dimensions of typical cross-section

(2) Unless stated otherwise, the other cross-sectional dimensions of cold-formed members and sheeting, denoted by symbols with subscripts, such as b_d , h_w or s_w , are measured either to the midline of the material or the midpoint of the corner.

(3) In the case of sloping elements, such as webs of trapezoidal profiled sheets, the slant height s is measured parallel to the slope. The slope is straight line between intersection points of flanges and web.

(4) The developed height of a web is measured along its midline, including any web stiffeners.

(5) The developed width of a flange is measured along its midline, including any intermediate stiffeners.

(6) The thickness t is a steel design thickness (the steel core thickness extracted minus tolerance if needed as specified in clause 3.2.4), if not otherwise stated. (standards.iteh.ai)

1.5.4 Convention for member axes

(1) In general the conventions for members is as used in Part 1-1 of EN 1993, see Figure 1.7.




Figure 1.7: Axis convention

- (2) For profiled sheets and liner trays the following axis convention is used:
 - y y axis parallel to the plane of sheeting;
 - z z axis perpendicular to the plane of sheeting.

2 Basis of design

(1) The design of cold formed members and sheeting should be in accordance with the general rules given in EN 1990 and EN 1993-1-1. For a general approach with FE-methods (or others) see EN 1993-1-5, Annex C.

(2)P Appropriate partial factors shall be adopted for ultimate limit states and serviceability limit states.

(3)P For verifications by calculation at ultimate limit states the partial factor γ_M shall be taken as follows:

- resistance of cross-sections to excessive yielding including local and distortional buckling: γ_{M0}

- resistance of members and sheeting where failure is caused by global buckling: χ_{M1}

- resistance of net sections at fastener holes: γ_{M2}

NOTE: Numerical values for γ_{Mi} may be defined in the National Annex. The following numerical values are recommended for the use in buildings:

 $\gamma_{M0} = 1,00;$

γ_{M1} = 1,00;

 $\gamma_{M2} = 1,25.$

(4) For values of γ_{M} for resistance of connections, see Section 8.

(5) For verifications at serviceability limit states the partial factor $\chi_{M,ser}$ should be used.

NOTE: Numerical value for $\gamma_{M,ser}$ may be defined in the National Annex. The following numerical value is recommended for the use in buildings:

 $\gamma_{M,ser} = 1,00$.

(6) For the design of structures made of cold formed members and sheeting a distinction should be made between "structural classes" associated with failure consequences according to EN 1990 – Annex B defined as follows:

Structural Class I: Construction where cold-formed members and sheeting are designed to contribute to the overall strength and stability of a structure;

Structural Class II: Construction where cold-formed members and sheeting are designed to contribute to the strength and stability of individual structural elements;

Structural Class III: Construction where cold-formed sheeting is used as an element that only transfers loads to the structure.

NOTE 1: During different construction stages different structural classes/may be considered. **NOTE 2:** For requirements for execution of sheeting see EN 1090.3-1-3-2007

3 Materials

3.1 General

(1) All steels used for cold-formed members and profiled sheets should be suitable for cold-forming and welding, if needed. Steels used for members and sheets to be galvanized should also be suitable for galvanizing.

(2) The nominal values of material properties given in this Section should be adopted as characteristic values in design calculations.

(3) This part of EN 1993 covers the design of cold formed members and profiles sheets fabricated from steel material conforming to the steel grades listed in table 3.1a.

Type of steel	Standard	Grade	$f_{\rm yb} {\rm N/mm^2}$	$f_{\rm u}$ N/mm ²
Hot rolled products of non-alloy structural steels. Part 2: Technical delivery conditions for non alloy structural steels	EN 10025: Part 2	S 235	235	360
		S 275	275	430
		S 355	355	510
Hot-rolled products of structural steels. Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels	EN 10025: Part 3	S 275 N	275	370
		S 355 N	355	470
		S 420 N	420	520
		S 460 N	460	550
		S 275 NL	275	370
		S 355 NL	355	470
		S 420 NL	420	520
		S 460 NL	460	550
Hot-rolled products of structural steels. Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels	EN 10025: Part 4	S 275 M	275	360
		S 355 M	355	450
		S 420 M	420	500
		S 460 M	460	530
		S 275 ML	275	360
		S 355 ML	355	450
		S 420 ML	420	500
		S 460 ML	460	530

Table 3.1a: Nominal values of basic yield strength f_{yb} and ultimate tensile strength f_u

TTeh STANDARD PREVIEW

NOTE 1: For steel strip less than 3 mm thick conforming to EN 10025, if the width of the original strip is greater than or equal to 600 mm, the characteristic values may be given in the National Annex. Values equal to 0,9 times those given in Table 3.1a are recommended.

NOTE 2: For other steel materials and products see the National Annex. Examples for steel grades that may conform to the requirements of this standard are given in Table 3.10. Seeba930e5a2/sist-en-1993-1-3-2007