

Transformed.

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

**ISO RECOMMENDATION
R 818**

FIBRE BUILDING BOARDS

DEFINITION – CLASSIFICATION

1st EDITION
September 1968

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

BRIEF HISTORY

The ISO Recommendation R 818, *Fibre building boards – Definition – Classification*, was drawn up by Technical Committee ISO/TC 89, *Boards made from wood or other ligno-cellulosic fibrous materials*, the Secretariat of which is held by the Deutscher Normenausschuss (DNA).

Work on this question by the Technical Committee began in 1959 and led, in 1964, to the adoption of a Draft ISO Recommendation.

In May 1966, this Draft ISO Recommendation (No. 956) was circulated to all the ISO Member Bodies for enquiry. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

Austria	Israel	Sweden
Belgium	Korea, Rep. of	Switzerland
Canada	Netherlands	U.A.R.
Chile	New Zealand	United Kingdom
Colombia	Norway	U.S.S.R.
Czechoslovakia	Poland	Yugoslavia
Finland	Portugal	
France	Romania	
Germany	South Africa,	
India	Rep. of	
Ireland	Spain	

No Member Body opposed the approval of the Draft.

The Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided, in September 1968, to accept it as an ISO RECOMMENDATION.

FIBRE BUILDING BOARDS

DEFINITION – CLASSIFICATION

1. SCOPE

This ISO Recommendation gives a definition and establishes a classification of fibre building boards.

2. DEFINITION

2.1 **Fibre building board.** Sheet material generally exceeding 1.5 mm in thickness, manufactured from ligno-cellulosic fibres with the primary bond deriving from the felting of the fibres and their inherent adhesive properties. Bonding materials and/or additives may be added.

2.2 There are also fibre building boards for special purposes.

These are

- either fibre building boards incorporating additives in order to modify one or more of their properties (this may have the effect of altering the density),
- or fibre building boards, treated, and/or processed (for example, machined, coated).

These special fibre building boards will be defined in detail later if needed.

3. CLASSIFICATION

The fibre building boards as defined in clause 2.1 should be classified according to their density as follows :

Type of board	Density g/cm ³
soft	≤ 0.35
medium	> 0.35 ≤ 0.80
hard	> 0.80