

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Insulating materials based on mica –
Part 3: Specifications for individual materials –
Sheet 5: Glass-backed mica paper with an epoxy resin binder
for post-impregnation (VPI)**

[IEC 60371-3-5:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/6ff0cd72-e490-4274-98bf-91c83709/iec-60371-3-5-2005>

**Matériaux isolants à base de mica –
Partie 3: Spécifications pour matériaux particuliers -
Feuille 5: Papier de mica renforcé de verre avec un agglomérant en résine
époxyde pour post-imprégnation (VPI)**



THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2005 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 14 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

More than 55 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue

Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Recherche de publications IEC - www.iec.ch/searchpub

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 14 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary

Plus de 55 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Insulating materials based on mica –
Part 3: Specifications for individual materials –
Sheet 5: Glass-backed mica paper with an epoxy resin binder
for post-impregnation (VPI)**

[IEC 60371-3-5:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/6ff0cd72-e490-4274-98bf-3911-28b09/iec-60371-3-5-2005>

**Matériaux isolants à base de mica –
Partie 3: Spécifications pour matériaux particuliers -
Feuille 5: Papier de mica renforcé de verre avec un agglomérant en résine
époxyde pour post-imprégnation (VPI)**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX



ICS 29.035.10; 29.035.50

ISBN 978-2-8322-1595-1

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Designation	6
4 Requirements: raw materials	8
4.1 Mica paper	8
4.2 Glass fabric	8
4.3 Epoxy resin	8
5 Requirements: composition and tolerances.....	8
6 Requirements for material (as received)	9
6.1 General	9
6.2 Width	9
6.3 Thickness.....	9
6.4 Length.....	9
6.5 Cores	9
6.6 Joins	10
6.7 Tensile strength in the warp direction	10
6.8 Stiffness.....	10
6.9 Air porosity.....	10
7 Packing	10
<p style="color: red; font-size: small;">IEC 60371-3-5:2005</p> <p style="color: red; font-size: small;">https://standards.iteh.ai/catalog/standards/sist/6ff0cd72-e490-4274-98bf-53917ce18b09/iec-60371-3-5-2005</p>	
Table 1 – Composition low bond, with a resin content in the range (8 ± 3) %	7
Table 2 – Composition medium bond, with a resin content in the range of (16 ± 3) %	8
Table 3 – Tolerance on width.....	9
Table 4 – Air porosity.....	10

iTech STANDARD PREVIEW
(standards.iteh.ai)

INTERNATIONAL ELECTROTECHNICAL COMMISSION

INSULATING MATERIALS BASED ON MICA –**Part 3: Specifications for individual materials –
Sheet 5: Glass-backed mica paper with an epoxy resin binder
for post-impregnation (VPI)**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60371-3-5 has been prepared by IEC technical committee 15: Standards on specifications for electrical insulating materials.

This bilingual version (2014-05) corresponds to the English version, published in 2005-11.

This second edition cancels and replaces the first edition, published in 1992, and constitutes a technical revision.

The main changes with regard to the previous edition include adjustments needed to align this standard with changes included in the latest edition of IEC 60371-2.

The text of this standard is based on the following documents:

FDIS	Report on voting
15/228/FDIS	15/246/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

The French version of this standard has not been voted upon.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[IEC 60371-3-5:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/6ff0cd72-e490-4274-98bf-53917ce18b09/iec-60371-3-5-2005>

INTRODUCTION

This part of IEC 60371 forms part of a series which deals with insulating materials built up from mica splittings or mica paper with or without reinforcement, and with mica paper in its pure state for use in electrical equipment..

IEC 60371 consists of three parts under the main title *Specification for insulating materials based on mica*:

- Part 1: Definitions and general requirements
- Part 2: Methods of test
- Part 3: Specifications for individual materials

This standard contains one of the sheets comprising part 3, as follows:

Sheet 5: Glass-backed mica paper with an epoxy resin binder for post-impregnation (VPI – *vacuum pressure impregnation*)

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60371-3-5:2005](https://standards.iteh.ai/catalog/standards/sist/6ff0cd72-e490-4274-98bf-53917ce18b09/iec-60371-3-5-2005)

<https://standards.iteh.ai/catalog/standards/sist/6ff0cd72-e490-4274-98bf-53917ce18b09/iec-60371-3-5-2005>

The descriptive code quoted in Tables 1 and 2, for example G23/M80/R08 for type 5.1.01, Table 1, is derived from:

- glass content (G) 23 g/m²
- muscovite mica content (M) 80 g/m²
- resin content (R) 8 ± 3 %.

NOTE For phlogopite mica paper the letter "M" is replaced by the letter "P".

Table 1 – Composition low bond, with a resin content in the range (8 ± 3) %

Type	Descriptive code	Glass content g/m ²		Mica content g/m ²		Mass/ unit area g/m ²		Permissible thickness range mm		Volatile content max. %
		Nom.	Tol. ±	Nom.	Tol. ±	Nom.	Tol. ±	Mean	Individual	
5.1.01	G23/M80/R08	23	2	80	7	112	12	0,08-0,12	0,07-0,13	0,5
5.1.02	G23/P80/R08	23	2	80	7	112	12	0,08-0,12	0,07-0,13	0,5
5.1.03	G23/M120/R08	23	2	120	10	155	15	0,09-0,13	0,08-0,14	0,5
5.1.04	G23/P120/R08	23	2	120	10	155	15	0,09-0,13	0,08-0,14	0,5
5.1.05	G32/M120/R08	32	3	120	10	165	17	0,10-0,14	0,09-0,15	0,5
5.1.06	G32/P120/R08	32	3	120	10	165	17	0,10-0,14	0,09-0,15	0,5
5.1.07	G23/M160/R08	23	2	160	13	199	20	0,11-0,16	0,10-0,17	0,5
5.1.08	G23/P160/R08	23	2	160	13	199	20	0,11-0,16	0,10-0,17	0,5
5.1.09	G32/M160/R08	32	3	160	13	209	21	0,12-0,17	0,11-0,18	0,5
5.1.10	G32/P160/R08	32	3	160	13	209	21	0,12-0,17	0,11-0,18	0,5
5.1.11	G23/M180/R08	23	2	180	14	220	22	0,13-0,18	0,12-0,19	0,5
5.1.12	G23/P180/R08	23	2	180	14	220	22	0,13-0,18	0,12-0,19	0,5
5.1.13	G32/M180/R08	32	3	180	14	231	23	0,14-0,19	0,13-0,20	0,5
5.1.14	G32/P180/R08	32	3	180	14	231	23	0,14-0,19	0,13-0,20	0,5
5.1.15	G23/M250/R08	23	2	250	20	297	30	0,16-0,21	0,15-0,22	0,5
5.1.16	G23/P250/R08	23	2	250	20	297	30	0,16-0,21	0,15-0,22	0,5
5.1.17	G32/M250/R08	32	3	250	20	307	31	0,17-0,22	0,16-0,23	0,5
5.1.18	G32/P250/R08	32	3	250	20	307	31	0,17-0,22	0,16-0,23	0,5

Table 2 – Composition medium bond, with a resin content in the range of (16 ± 3) %

Type	Descriptive code	Glass content g/m ²		Mica content g/m ²		Mass/ unit area g/m ²		Permissible thickness range mm		Volatile content max. %
		Nom.	Tol. ±	Nom.	Tol. ±	Nom.	Tol. ±	Mean	Individual	
5.2.01	G23/M120/R16	23	2	120	10	170	17	0,10-0,14	0,09-0,15	0,5
5.2.02	G23/P120/R16	23	2	120	10	170	17	0,10-0,14	0,09-0,15	0,5
5.2.03	G32/M120/R16	32	3	120	10	181	18	0,12-0,16	0,11-0,17	0,5
5.2.04	G32/P120/R16	32	3	120	10	181	18	0,12-0,16	0,11-0,17	0,5
5.2.05	G23/M160/R16	23	2	160	13	218	22	0,12-0,17	0,11-0,18	0,5
5.2.06	G23/P160/R16	23	2	160	13	218	22	0,12-0,17	0,11-0,18	0,5
5.2.07	G32/M160/R16	32	3	160	13	229	23	0,14-0,19	0,13-0,20	0,5
5.2.08	G32/P160/R16	32	3	160	13	229	23	0,14-0,19	0,13-0,20	0,5
5.2.09	G23/M180/R16	23	2	180	14	242	24	0,14-0,19	0,13-0,20	0,5
5.2.10	G23/P180/R16	23	2	180	14	242	24	0,14-0,19	0,13-0,20	0,5
5.2.11	G32/M180/R16	32	3	180	14	253	26	0,16-0,21	0,15-0,22	0,5
5.2.12	G32/P180/R16	32	3	180	14	253	26	0,16-0,21	0,15-0,22	0,5
5.2.13	G23/M250/R16	23	2	250	20	325	33	0,17-0,22	0,16-0,23	0,5
5.2.14	G23/P250/R16	23	2	250	20	325	33	0,17-0,22	0,16-0,23	0,5
5.2.15	G32/M250/R16	32	3	250	20	336	34	0,19-0,24	0,18-0,25	0,5
5.2.16	G32/P250/R16	32	3	250	20	336	34	0,19-0,24	0,18-0,25	0,5

IEC 60371-3-5:2005

[https://standards.iteh.ai/catalog/standards/sist/6ff0cd72-e490-4274-98bf-](https://standards.iteh.ai/catalog/standards/sist/6ff0cd72-e490-4274-98bf-53917ce18b09/iec-60371-3-5-2005)

4 Requirements: raw materials

4.1 Mica paper

Mica paper referred to in this specification shall comply with the requirements of IEC 60371-3-2.

4.2 Glass fabric

Normally the glass fabric shall be continuous filament glass fibre made from E glass. Unless otherwise agreed to between purchaser and seller, the glass fibre shall be in the loom state and have a size content not greater than 3 % by weight.

For some applications a special type of size may be necessary and any requirements shall be subject to the purchase contract.

4.3 Epoxy resin

Any epoxy resin system may be used which enables the material to meet the requirements of this specification.

5 Requirements: composition and tolerances

When tested by the method of Clause 7 of IEC 60371-2 the composition of the products shall lie within the limits of Tables 1 and 2 for the appropriate grade of mica paper.

6 Requirements for material (as received)

6.1 General

All materials in any one consignment shall have the same properties, within the limits of this specification, throughout the length of each roll.

The surfaces shall be uniform and free from defects such as bubbles, pin-holes, creases and flaws.

Material supplied in rolls shall be capable of being unrolled continuously without damage, and the force required to unroll the material shall be substantially uniform. The material shall be supplied non-interleaved.

Unless otherwise specified in the purchase contract the material shall be rolled with the mica surface on the outside.

6.2 Width

This specification contains no requirement for width of tape. However, the following widths are preferred: 10, 12, 15, 20, 25, 30, 40 and 50 mm.

The maximum trimmed width of full width material and sheet normally available is 1 000 mm.

The tolerance on the width of the material shall be as in Table 3.

Table 3 – Tolerance on width

Nominal width mm	Tolerance mm
≤ 20	±0,5
> 20 ≤ 500	±1,0
> 500	±5,0

6.3 Thickness

Measure the thickness in accordance with Clause 4 of IEC 60371-2, using the apparatus given in 4.1.1 of that standard, making 10 measurements on one thickness of material. The measured values shall be in accordance with the requirements of Tables 1 and 2.

6.4 Length

There is no requirement in this specification for roll length, and this shall therefore be subject to the purchase contract.

For sheet material, the tolerance on length shall be the same as for width.

6.5 Cores

The tape shall be supplied compactly wound on cores of 25 mm, 40 mm, 55 mm, or 76 mm inside diameter which shall be free from sharp edges.

The width of the cores in relation to that of the tape shall be subject to the purchase contract.

Full width material and material wider than 100 mm shall be supplied on 55 mm or 76 mm cores.