



**SLOVENSKI STANDARD**  
**SIST EN 12811-2:2004**

**01-maj-2004**

---

ČdfYa UnUnU UgbY[ fUXb^Y'È &rXY. :bZcfa UW^Uc`a UHf]U\]

Temporary works equipment - Part 2: Information on materials

Temporäre Konstruktionen für Bauwerke - Teil 2: Informationen zu den Werkstoffen

Équipements temporaires de chantiers - Partie 2: Informations concernant les matériaux

**Ta slovenski standard je istoveten z: EN 12811-2:2004**

SIST EN 12811-2:2004  
<https://standards.iteh.ai/catalog/standards/sist/928b43d5-7566-4f0b-9821-c81740a595c1/sist-en-12811-2-2004>

---

**ICS:**

91.220

Gradbena oprema

Construction equipment

**SIST EN 12811-2:2004**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 12811-2:2004

<https://standards.iteh.ai/catalog/standards/sist/928b43d5-75b6-4f0b-9821-c81740a595c1/sist-en-12811-2-2004>

ICS 91.220

English version

## Temporary works equipment - Part 2: Information on materials

Equipements temporaires de chantiers - Partie 2:  
Information concernant les matériaux

Temporäre Konstruktionen für Bauwerke - Teil 2:  
Informationen zu den Werkstoffen

This European Standard was approved by CEN on 17 December 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

**STANDARD PREVIEW**  
(standards.iteh.ai)

SIST EN 12811-2:2004  
<https://standards.iteh.ai/catalog/standards/sist/928b43d5-75b6-4f0b-9821-c81740a595c1/sist-en-12811-2-2004>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

**Contents**

page

1	Scope .....	5
2	Normative references .....	5
3	General.....	6
3.1	Selection of materials.....	6
3.2	Characteristic values.....	6
3.3	Inspection documents.....	6
3.4	Effects of fabrication .....	6
4	Steel.....	6
4.1	General.....	6
4.2	Dimensions, mass and tolerance.....	6
4.3	Fracture toughness .....	7
4.4	Steel grades in EN 10142 .....	7
5	Cast iron.....	7
5.1	General.....	7
5.2	Prototype testing .....	7
5.3	Inspection document.....	7
6	Aluminium alloys .....	8
6.1	General.....	8
6.2	Dimensions, mass and tolerance.....	8
6.3	Heat affected zones .....	8
6.4	Inspection document.....	8
7	Timber and timber based materials .....	8
7.1	General.....	8
7.2	Solid timber and glued laminated timber .....	9
7.2.1	General.....	9
7.2.2	Characteristic values.....	9
7.2.3	Dimensions, mass and tolerance.....	9
7.3	Wood-based materials (plywood, particleboard, fibreboard).....	9
7.3.1	General.....	9
8	Protection against corrosion and deterioration .....	9
8.1	Ferrous metal products.....	9
8.2	Aluminium alloys .....	10
8.3	Plywood for scaffold decks .....	10
9	Welding .....	10
Annex A (informative) Information taken from other material and design standards.....		11
Bibliography .....		17

**iTeh STANDARD PREVIEW**  
 (standards.iteh.ai)

SIST EN 12811-2:2004  
<https://standards.iteh.ai/catalog/standards/sist/928b43d5-75b6-4f0b-9821-c81740a955c1/sist-en-12811-2-2004>

## Foreword

This document (EN 12811-2:2004) has been prepared by Technical Committee CEN/TC 53 "Temporäre Baukonstruktionen", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2004, and conflicting national standards shall be withdrawn at the latest by August 2004.

This European Standard EN 12811 consists of the following parts under the general title: Temporary works equipment:

- Part 1: Scaffolds - Performance requirements and general design
- Part 2: Information on materials
- Part 3: Load testing

Annex A is informative.

This document includes a Bibliography.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

FOR STANDARD PREVIEW

(standards.iteh.ai)

SIST EN 12811-2:2004

<https://standards.iteh.ai/catalog/standards/sist/928b43d5-75b6-4f0b-9821-c81740a595c1/sist-en-12811-2-2004>

## Introduction

This European Standard represents a supporting standard for product standards produced by CEN/TC 53.

It takes into account the material-related comments on the following drafts obtained in the CEN-enquiry:

prEN 12810-1:1997, *Façade scaffolds made of prefabricated components — Part 1: Product specifications.*

prEN 12810-2, *Façade scaffolds made of prefabricated components - Part 2: Particular methods of structural design*

prEN 12811:1997, *Scaffolds — Performance requirements and general design.*

prEN 12812:1997, *Falsework — Performance requirements and general design.*

prEN 12813:1997, *Load bearing towers made of prefabricated elements — Methods of particular design and assessment.*

prEN 13331-1:1998, *Trench lining systems — Part 1: Product specifications.*

prEN 13331-2:1998, *Trench lining systems — Part 2: Assessment by calculation or test.*

prEN 13377:1998, *Prefabricated timber formwork beams — Requirements, classification and assessment.*

This standard is limited to the selection of types and grades of material from standards, which are either international or European standards. However, in the field of temporary works equipment the use of other materials can be indicated or even imperative.

The use of non standardised (new) materials can give advantage for particular components. But this use prevents the marking of the product conforming in other respects to the product standard with the number of the respective product standard.

The components of temporary works equipment are used for many years. There are components in the stores of the users and on building sites which are made of materials corresponding to former national standards.

This standard does not intend to prevent neither the use of non standardised (new) materials nor the use of components made of old materials.

It is beyond the scope and the competence of CEN/TC 53 to formulate regulations for non standardized new materials and for old materials former standardized nationally.

In the absence of a European product directive for temporary works equipment, such regulations and their mutual acknowledgement are reserved to the single European country.

For closing the gap until a European regulation is available, the following recommendations are given:

1. The single country could add a national foreword to this standard, which regulates the further use of components, made of old materials for its jurisdiction.
2. The Working Groups of CEN/TC 53 could include a requirement in their product standards that also products made partially of materials not covered by ISO or EN standards may have the number of the product standard, if they are marked with an asterisk additionally and if the fact is recorded in the product manual.

## 1 Scope

This European Standard provides guidance on where to find information on materials often used in temporary works. It draws attention to a number of points that a designer should take into account.

The information given is limited to commonly used steel, aluminium alloys, cast iron, timber and timber based materials.

Requirements are also given for welding, for limiting corrosion and other deterioration.

It is limited to the selection of types and grades of material from standards, which are either international or European Standards.

## 2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 301, *Adhesives, phenolic and aminoplastic, for load-bearing timber structures - Classification and performance requirements.*

EN 336, *Structural timber — Sizes, permitted deviations.*

EN 338, *Structural timber — Strength classes.*

EN 390, *Glued laminated timber — Sizes — Permissible deviations.*

EN 729-1, *Quality requirements for welding — Fusion welding of metallic materials — Part 1: Guidelines for selection and use.*

EN 1562, *Founding — Malleable cast irons.*

EN 1563, *Founding — Spheroidal graphite cast irons.*

EN 10142, *Continuously hot-dip zinc coated low carbon steels strip and sheet for cold forming — Technical delivery conditions.*

EN 10204, *Metallic products — Types of inspection documents.*

ENV 1993-1-1, *Eurocode 3: Design of steel structures — Part 1-1: General rules and rules for buildings.*

ENV 1993-1-3, *Eurocode 3: Design of steel structures — Part 1-3: General rules - Supplementary rules for cold formed thin gauge members and sheeting.*

ENV 1995-1-1, *Eurocode 5: Design of timber structures — Part 1-1: General rules and rules for buildings.*

ENV 1999-1-1:1998, *Eurocode 9: Design of aluminium structures — Part 1-1: General rules - General rules and rules for buildings.*

EN ISO 1461; *Hot dip galvanized coatings on fabricated iron and steel articles - Specifications and test methods (ISO 1461:1999).*

EN ISO 12944 – Parts 1 to 8, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems.*

### 3 General

#### 3.1 Selection of materials

Material used shall be sufficiently robust and durable to withstand normal working conditions.

Materials shall be free from any impurities and defects, which may affect their satisfactory use.

Materials shall be selected from European or International Standards.

NOTE Commonly used materials are listed in annex A.

#### 3.2 Characteristic values

The minimum values for yield stress or proof stress and for the tensile strength specified in material standards shall be used as characteristic values in design calculations.

#### 3.3 Inspection documents

Materials for components, which affect the load bearing behaviour and/or health and safety aspects, shall be delivered with an inspection document in accordance with EN 10204. The minimum level shall be 2.2.

#### 3.4 Effects of fabrication

Account shall be taken of forming or other fabrication techniques such as welding which can affect the material properties. For example, for steel the yield stress could be raised and the ductility could be reduced by these operations.

iTeH STANDARD PREVIEW  
(standards.iteh.ai)  
SIST EN 12811-2:2004  
<https://standards.iteh.ai/catalog/standards/sist/928b43d5-75b6-4f0b-9821-c81740a595c1/sist-en-12811-2-2004>

### 4 Steel

#### 4.1 General

The commonly used materials are listed in Table A.1 and Table A.2. In addition, requirements are given in ENV 1993-1-1 and ENV 1993-1-3.

Some material values are given in Table 1.

Table 1 — Material values for steel

Modulus of elasticity, <i>E</i>	Shear modulus, <i>G</i>	Coefficient of linear thermal expansion $\alpha$	Density
MPa	MPa	$\frac{1}{K}$	$\frac{kg}{m^3}$
210000	81000	$1,2 \times 10^{-5}$	7850
1 MPa = 1 N/mm <sup>2</sup>			

#### 4.2 Dimensions, mass and tolerance

Dimensions, mass and tolerances shall be in accordance with the material standard specified.



### 4.3 Fracture toughness

When structures are used at temperatures below  $-20\text{ }^{\circ}\text{C}$ , impact resistant material shall be used. For advice and for reference temperature related to maximum thickness see ENV 1993-1-1.

### 4.4 Steel grades in EN 10142

For design purposes, the steel grades in EN 10142 shall be considered to have a yield stress of  $140\text{ N/mm}^2$  and a tensile strength of  $270\text{ N/mm}^2$ .

## 5 Cast iron

### 5.1 General

Malleable cast iron in accordance with EN 1562 or spheroidal graphite cast iron in accordance with EN 1563 shall be used.

When welding whiteheart malleable cast iron EN-GJMW-360-12 should be used.

Due to ductility requirements the elongation for spheroidal graphite cast iron shall be limited to  $A_5 \geq 12\%$ , for malleable cast iron to  $A_{3,4} \geq 7\%$ .

Some material values are given in Table 2.

iTech STANDARD PREVIEW  
(standards.iteh.ai)

Table 2 — Material values for cast iron

Cast iron	Modulus of elasticity, $E$ MPa	Poisson's ratio	Coefficient of linear thermal expansion $\alpha$ $\frac{1}{K}$	Density $\frac{\text{kg}}{\text{m}^3}$
Spheroidal graphite	169000	0,275	$1,25 \times 10^{-5}$	7100
malleable	180000	0,275	$1,1 \times 10^{-5}$	7400
1 MPa = $1\text{ N/mm}^2$				

### 5.2 Prototype testing

If the load bearing capacity and/or stiffness is determined by testing of a component made partially or totally of cast iron, a metallographic record (macrographs and micrographs) of the component being tested shall be obtained for reference purpose.

### 5.3 Inspection document

Cast irons shall be subjected to specific inspection and testing and issued with an inspection document type 3.1 B in accordance with EN 10204.

## 6 Aluminium alloys

### 6.1 General

The commonly used aluminium alloys are given in Table A.3 and Table A.4. In addition, requirements are given in ENV 1999-1-1.

Some material values are given in Table 3.

**Table 3 — Material values for aluminium alloys**

Modulus of elasticity, <i>E</i>	Shear modulus, <i>G</i>	Coefficient of linear thermal expansion $\alpha$	Density
MPa	MPa	$\frac{1}{K}$	$\frac{kg}{m^3}$
70000	27000	$2,3 \times 10^{-5}$	2700
1 MPa = 1 N/mm <sup>2</sup>			

### 6.2 Dimensions, mass and tolerance

Dimensions, mass and tolerances of structural extruded products, sheet and plate products, drawn tube, electrically welded tube, wire and forging, shall conform with the European Standards listed in ENV 1999-1-1.

### 6.3 Heat affected zones

SIST EN 12811-2:2004

<https://standards.iteh.ai/catalog/standards/sist/928b43d5-75b6-4f0b-9821->

The values given in annex A are only valid for unaffected material. Welding affects a reduction of the strength properties of the material in the vicinity of the welds. The reduction affects the 0,2 % proof stress of the material more severely than the ultimate tensile strength. For design purposes it is assumed that throughout the heat affected zone (HAZ) the strength properties are reduced by a constant factor  $\rho_{\text{haz}}$ .

NOTE  $\rho_{\text{haz}}$  can be chosen following ENV 1999-1-1.

### 6.4 Inspection document

The performance of aluminium alloys not listed in ENV 1999-1-1 shall be subjected to specific inspection and testing and issued with an inspection document 3.1.B in accordance with EN 10204.

## 7 Timber and timber based materials

### 7.1 General

Materials specified in ENV 1995-1-1 shall be used. Service class 2 is the most appropriate.

## 7.2 Solid timber and glued laminated timber

### 7.2.1 General

For solid timber coniferous or poplar wood with a minimum strength class C16 in accordance to EN 338 shall be used. The glue used for glued laminated timber and timber based materials shall meet the requirements of Type I of EN 301.

### 7.2.2 Characteristic values

For the structural design of components of solid timber and glued laminated timber the characteristic values of the respective strength class in accordance with EN 338 shall be used, see also Table A.5 and Table A.6.

### 7.2.3 Dimensions, mass and tolerance

The effective cross-section and geometrical properties shall be calculated from the target size provided that the following tolerance classes are used:

Solid timber:

- Tolerance class 1 to EN 336 target size relates to a timber moisture of 20 %.

Glued laminated timber:

- Tolerances to EN 390 target size related to a timber moisture of 12 %.

## 7.3 Wood-based materials (plywood, particleboard, fibreboard)

### 7.3.1 General

SIST EN 12811-2:2004

[https://standards.iteh.ai/catalog/standards/sist/928b43d5-75b6-4f0b-9821-](https://standards.iteh.ai/catalog/standards/sist/928b43d5-75b6-4f0b-9821-81749e595e1/sist-en-12811-2:2004)

Wood based materials shall be produced so that it maintains its integrity and strength in the assigned service class throughout the expected life of the structure. Plywood used for platforms shall also meet the following requirements:

- Construction of platforms: The top layer shall have a minimum thickness of 0,8 mm, the intermediate ones may have 2,0 mm maximum thickness, measured in final condition. The top layer in uncoated condition shall be free of defects like loose knots, fissures and splits.
- Surface conditions: The platforms used as scaffold decks shall have a slip resistant and abrasion resistant coating.

## 8 Protection against corrosion and deterioration

### 8.1 Ferrous metal products

Corrosion protection for ferrous metal products shall conform to the classes given below:

Class    Corrosion protection

C1        Protective paint in accordance with EN ISO 12944 part 1 to 8.