
Hidroizolacijski trakovi - Ojačeni bitumenski trakovi za tesnjenje streh - Definicije in lastnosti

Flexible sheets for waterproofing - Reinforced bitumen sheets for roof waterproofing - Definitions and characteristics

Abdichtungsbahnen - Bitumenbahnen mit Trägereinlage für Dachabdichtungen - Definitionen und Eigenschaften

Feuilles souples d'étanchéité - Feuilles bitumineuses armée pour l'étanchéité de toiture - Définitions et caractéristiques

[SIST EN 13707:2005](https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005)

[https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-](https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005)

[b45937237b77/sist-en-13707-2005](https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005)

Ta slovenski standard je istoveten z: EN 13707:2004

ICS:

01.040.91	Gradbeni materiali in gradnja (Slovarji)	Construction materials and building (Vocabularies)
91.060.20	Strehe	Roofs
91.100.50	Veziva. Tesnilni materiali	Binders. Sealing materials

SIST EN 13707:2005

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13707:2005

<https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005>

EUROPEAN STANDARD

EN 13707

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2004

ICS 01.040.91; 91.100.50

English version

Flexible sheets for waterproofing - Reinforced bitumen sheets for roof waterproofing - Definitions and characteristics

Feuilles souples d'étanchéité - Feuilles bitumineuses
armée pour l'étanchéité de toiture - Définitions et
caractéristiques

Abdichtungsbahnen - Bitumenbahnen mit Trägereinlage für
Dachabdichtungen - Definitionen und Eigenschaften

This European Standard was approved by CEN on 30 July 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 13707:2005](https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005)

<https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	6
4 System-related characteristics.....	8
5 Product characteristics	8
5.1 General.....	8
5.2 Characteristics	8
5.2.1 Visible defects.....	8
5.2.2 Dimensions, tolerances and mass per unit area	8
5.2.3 Watertightness	8
5.2.4 Effects of water	9
5.2.5 Fire performance.....	9
5.2.6 Resistance to hail	9
5.2.7 Watertightness after stretching at low temperature	9
5.2.8 Joint strength	9
5.2.9 Water vapour properties	10
5.2.10 Tensile properties	10
5.2.11 Resistance to impact	10
5.2.12 Resistance to static loading	10
5.2.13 Resistance to tearing (nail shank)	10
5.2.14 Resistance to root penetration.....	10
5.2.15 Dimensional stability.....	10
5.2.16 Form stability under cyclic temperature change.....	10
5.2.17 Flexibility at low temperature (pliability)	11
5.2.18 Flow resistance at elevated temperature	11
5.2.19 Artificial ageing behaviour.....	11
5.2.20 Adhesion of granules	11
5.3 Dangerous substances	12
6 Evaluation of conformity.....	12
6.1 General.....	12
6.2 Initial type testing	12
6.2.1 General.....	12
6.2.2 Sampling.....	12
6.3 Factory production control (FPC)	12
6.3.1 General.....	12
6.3.2 Frequency of testing	13
7 Product data sheet.....	13
8 Marking, labelling and packaging	13
Annex A (normative) Applicability of characteristics	14
Annex B (normative) Frequencies of testing for factory production control	15
Annex C (informative) Information about chemical resistance	17
Annex D (informative) Example of a product data sheet.....	20
D.1 General information.....	20

Annex ZA (informative) Clauses of this European Standard addressing essential requirements or other provisions of EU Directives	22
ZA.1 Scope and relevant characteristics	22
ZA.2 Procedure for attestation of conformity	24
ZA.2.1 Systems of attestation of conformity	24
ZA.2.2 EC Certificate and declaration of conformity	26
ZA.3 CE marking and labelling	26
Bibliography	29

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 13707:2005](https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005)

<https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005>

Foreword

This document (EN 13707:2004) has been prepared by Technical Committee CEN/TC 254 “Flexible sheets for waterproofing”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2005, and conflicting national standards shall be withdrawn at the latest by July 2007.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 13707:2005](https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005)

<https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005>

1 Scope

This document specifies definitions and characteristics for flexible reinforced bitumen sheets for which the intended use is roofing. This covers sheets used as top layers, intermediate layers and underlayers. It does not cover reinforced bitumen sheets for waterproofing used as underlays for discontinuous roofing.

It does not cover waterproofing sheets which are intended to be used fully bonded under bituminous products (e.g. asphalt) directly applied at high temperature, specified by prEN 14695.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1107-1, *Flexible sheets for waterproofing — Part 1: Bitumen sheets for roof waterproofing — Determination of dimensional stability.*

EN 1108, *Flexible sheets for waterproofing — Bitumen sheets for roof waterproofing — Determination of form stability under cyclical temperature changes.*

EN 1109, *Flexible sheets for waterproofing — Bitumen sheets for roof waterproofing — Determination of flexibility at low temperature.*

EN 1110, *Flexible sheets for waterproofing — Bitumen sheets for roof waterproofing — Determination of flow resistance at elevated temperature.*

EN 1296, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roofing — Method of artificial ageing by long term exposure to elevated temperature.*

EN 1297, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Method of artificial ageing by long term exposure to the combination of UV radiation, elevated temperature and water.*

EN 1848-1, *Flexible sheets for waterproofing — Determination of length, width and straightness — Part 1: Bitumen sheets for roof waterproofing.*

EN 1849-1, *Flexible sheets for waterproofing — Determination of thickness and mass per unit area — Part 1: Bitumen sheets for roof waterproofing.*

EN 1850-1, *Flexible sheets for waterproofing — Determination of visible defects — Part 1: Bitumen sheets for roof waterproofing.*

EN 1928:2000, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of watertightness.*

EN 1931, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of water vapour transmission properties.*

EN 12039, *Flexible sheets for waterproofing — Bitumen sheets for roof waterproofing — Determination of adhesion of granules.*

EN 12310-1, *Flexible sheets for waterproofing — Part 1: Bitumen sheets for waterproofing — Determination of resistance to tearing (nail shank).*

EN 13707:2004 (E)

EN 12311-1, *Flexible sheets for waterproofing — Part 1: Bitumen sheets for roof waterproofing — Determination of tensile properties.*

EN 12316-1, *Flexible sheets for waterproofing — Part 1: Bitumen sheets for roof waterproofing — Determination of peel resistance of joints.*

EN 12317-1, *Flexible sheets for waterproofing — Part 1: Bitumen sheets for roof waterproofing — Determination of shear resistance of joints.*

EN 12691, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of resistance to impact.*

EN 12730:2001, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of resistance to static loading.*

EN 13416:2001, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Rules for sampling.*

EN 13501-1:2002, *Fire classification of construction products and building elements — Part 1: Classification using test data from reaction to fire tests.*

prEN 13501-5, *Fire classification of construction products and building elements — Part 5: Classification using test data from external fire exposure to roof tests.*

EN 13897, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of watertightness after stretching at low temperature.*

prEN 13948, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of resistance to root penetration.*

EN ISO 11925-2, *Reaction to fire tests — Ignitability of building products subjected to direct impingement of flame — Part 2: Single-flame source test (ISO 11925-2:2002).*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13416:2001 and the following apply.

3.1**waterproofing**

action to prevent the passage of water from one plane to another

3.2**waterproofing system**

assembly of one or more layers of roofing sheet in its applied and jointed form, which has certain performance characteristics, to be assessed as a whole

NOTE 1 Where only one layer is used this is usually referred to as a single layer system.

NOTE 2 A bituminous roofing system is formed on site by connecting and sealing one or more superimposed layers of bitumen sheets to form a single composite waterproof layer for use over flat, pitched or vertical surfaces according to building application requirements.

3.3**roofing**

waterproofing used in the roof of a building including roofs used for parking of vehicles and for roof gardens

NOTE Waterproofing sheets which are intended to be fully bonded and bituminous products directly applied at high temperature are specified by the European Standard on flexible reinforced bitumen sheets for concrete bridge decks and other concrete surfaces trafficable by vehicles (see prEN 14695 ([6])).

3.4

roofing sheet

factory made flexible sheet including any carriers, facings, surface texture and/or backing

3.5

carrier

material incorporated into or onto the factory-made roofing sheet to ensure its stability and/or mechanical resistance

3.6

backing

material incorporated onto the factory-made roofing sheet without a permanent mechanical function

3.7

surfacing

material applied on one or both sides of roofing sheets, either as a permanent light surface protection against weathering on the upper surface or as an anti-sticking substance of the roofing sheets

3.8

batch

amount of product manufactured to the same specification within a maximum period of 24 h

3.9

manufacturer's limiting value (MLV)

value stated by the manufacturer to be met during testing. The manufacturer's limiting value can be a minimum or a maximum value according to statements made under product characteristics of this document

[SIST EN 13707:2005](https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-937237b77/sist-en-13707-2005)

3.10

manufacturer's declared value (MDV)

value declared by the manufacturer accompanied by a declared tolerance

3.11

reinforced bitumen sheet

factory made flexible layer of bitumen with internal or external incorporation of one or more carriers, supplied in roll form ready for use

3.12

oxidized bitumen

straight run petroleum bitumen or a fluxed bitumen which has been hardened and rendered less temperature susceptible by blowing with air at high temperature with or without the use of a catalyst

3.13

elastomeric bitumen

petroleum bitumen and/or oxidized bitumen modified by the addition of thermo-plastic rubbers

3.14

plastomeric bitumen

petroleum bitumen and/or oxidized bitumen modified by the addition of polyolefin or polyolefin copolymer compound

3.15

sampling

procedure used to select or constitute a sample

EN 13707:2004 (E)**3.16****sample**

sheet from which a test piece is taken

3.17**test piece**

part of the sample from which test specimens are taken

3.18**test specimen**

piece of precise dimensions taken from the test piece

4 System-related characteristics

System-related characteristics with respect to multilayer systems, sheets for single layer application, mechanically fastened systems and roof gardens or under heavy protection are given in Annex A.

5 Product characteristics**5.1 General**

5.1.1 Where a tolerance is limited by this standard it does not have to be declared by the manufacturer.

5.1.2 When tested for purposes other than initial type testing or factory production control, the tests to determine product characteristics indicated in this standard shall be started within 1 month of delivery from the manufacturer.

5.2 Characteristics

<https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005>

5.2.1 Visible defects

The product shall be free of visible defects, as determined in accordance with EN 1850-1.

5.2.2 Dimensions, tolerances and mass per unit area

The length, width and straightness of the sheet shall be determined in accordance with EN 1848-1. The length and width shall not be shorter than the manufacturer's limiting value. The maximum deviation from straightness shall not exceed 20 mm per 10 m length or in proportion for other lengths (e.g. 10 mm per 5 m length).

Where a product is specified by mass per unit area, it shall be measured in accordance with EN 1849-1, except that the sample shall be 100 mm × 100 mm, and the results shall lie within the declared tolerance of the manufacturer's declared value.

Where a product is specified by thickness, it shall be measured in accordance with EN 1849-1 and the results shall lie within the declared tolerance of the manufacturer's declared value.

Where sheets with incorporated mineral protection are specified by thickness, the measurement of thickness may be carried out on the granule-free selvedge. This shall be declared in the report.

5.2.3 Watertightness

The watertightness shall be determined in accordance with EN 1928:2000 using method A or B at an applied water pressure of 10 kPa (0,1 bar) and shall give a pass result.

5.2.4 Effects of water

Not specified.

NOTE Experience has shown that water has little or no effect upon the in-service performance of reinforced bitumen sheets. See also Annex C.

5.2.5 Fire performance

5.2.5.1 External fire performance

Where the manufacturer wishes to declare external fire performance (e.g. when subject to regulatory requirements), the product shall be tested and classified in accordance with prEN 13501-5. Where the defined system meets the deemed to satisfy criteria¹ no testing is required.

NOTE Compliance with this requirement is not possible until a version of prEN 13501-5 later than 2002 becomes available. The text is written like this to avoid the need for the standard to be changed after FV/UAP.

5.2.5.2 Reaction to fire

Where required, the product shall be tested and classified in accordance with EN 13501-1:2002, Table 1. When tested according to EN ISO 11925-2, the products shall be tested under conditions of surface flame attack.

NOTE It is currently considered that the Euroclasses Classification system at Classes D and above requires investigation to determine its appropriateness to the products covered by this document (the SBI test may be inappropriate for products covered by the standard). Pending results of such an investigation and discussions in the Fire Regulators Group, products covered by this document are tested to EN ISO 11925-2. If and when a new fire test scenario and test method are developed for the products, this document will be amended to refer to them.

[SIST EN 13707:2005](http://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005)

5.2.6 Resistance to hail

Not specified.

NOTE Experience has shown that hail has little or no effect upon the in-service performance of reinforced bitumen sheets.

5.2.7 Watertightness after stretching at low temperature

Where required, the watertightness after stretching at low temperature shall only be determined for mechanically fastened single layer applications in accordance with EN 13897 and the results shall be greater than or equal to the manufacturer's limiting value.

5.2.8 Joint strength

5.2.8.1 The peel resistance of joints shall only be determined for mechanically fastened single layer applications in accordance with EN 12316-1 and the results shall lie within the declared tolerance of the manufacturer's declared value.

5.2.8.2 The shear resistance of joints shall be determined for all single layer applications in accordance with EN 12317-1 and the results shall lie within the declared tolerance of the manufacturer's declared value.

¹ See Commission Decision 2000/553/EC [5]

EN 13707:2004 (E)**5.2.9 Water vapour properties**

If necessary, the moisture resistance factor μ of reinforced bitumen sheets may be determined in accordance with EN 1931. If the factor μ is not determined, a value of 20 000 may be used for calculation purposes.

5.2.10 Tensile properties

The tensile properties shall be determined in accordance with EN 12311-1 and the results (for the longitudinal and transverse directions) shall lie within the declared tolerance of the manufacturer's declared value.

5.2.11 Resistance to impact

The resistance to impact shall be determined in accordance with EN 12691 and shall be expressed as the smallest diameter it will resist, which shall be less than or equal to the manufacturer's limiting value.

5.2.12 Resistance to static loading

The resistance to static loading shall be determined in accordance with EN 12730:2001, method A and shall be greater than or equal to the manufacturer's limiting value.

5.2.13 Resistance to tearing (nail shank)

The resistance to tearing (nail shank) shall be determined in accordance with EN 12310-1 and the results shall lie within the declared tolerance of the manufacturer's declared value.

5.2.14 Resistance to root penetration

The resistance to root penetration shall be determined only for products used as root barriers in roof gardens in accordance with prEN 13948 and shall give a **pass result**.

5.2.15 Dimensional stability

The dimensional stability shall be determined in accordance with EN 1107-1 and shall be less than or equal to the manufacturer's limiting value. This test shall only be carried out on sheets containing organic fibres or synthetic fibres (e.g. jute, hessian, polyester, polyolefines).

5.2.16 Form stability under cyclic temperature change

The form stability under cyclic temperature change shall be determined only for sheets with metal foil surfacing in accordance with EN 1108 and shall be less than or equal to the manufacturer's limiting value.

iteh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/0f7b277b-8539-4b3f-a89d-b45937237b77/sist-en-13707-2005>