



SLOVENSKI STANDARD

SIST EN 13967:2005

01-maj-2005

Hidroizolacijski trakovi - Polimerni in elastomerni tesnilni trakovi za temelje - Definicije in lastnosti

Flexible sheets for waterproofing - Plastic and rubber damp proof sheets including plastic and rubber basement tanking sheet - Definitions and characteristics

Abdichtungsbahnen - Kunststoff- und Elastomerbahnen für die Bauwerksabdichtung gegen Bodenfeuchte und Wasser - Definitionen und Eigenschaften

Feuilles souples d'étanchéité - Feuilles plastiques et élastomères empêchant les remontées capillaires du sol - Définitions et caractéristiques

<https://standards.iteh.ai/catalog/standards/sist/a2e4d085-0b47-4835-a450-22cc9e1a5ddf/sist-en-13967-2005>

Ta slovenski standard je istoveten z: EN 13967:2004

ICS:

01.040.91	Gradbeni materiali in gradnja (Slovarji)	Construction materials and building (Vocabularies)
91.100.50	Veziva. Tesnilni materiali	Binders. Sealing materials

SIST EN 13967:2005

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13967:2005

<https://standards.iteh.ai/catalog/standards/sist/a2e4d085-0b47-4835-a450-22cc9e1a5ddf/sist-en-13967-2005>

ICS 01.040.91; 91.100.50

English version

Flexible sheets for waterproofing - Plastic and rubber damp proof sheets including plastic and rubber basement tanking sheet - Definitions and characteristics

Feuilles souples d'étanchéité - Feuilles plastiques et élastomères empêchant les remontées capillaires du sol - Définitions et caractéristiques

Abdichtungsbahnen - Kunststoff- und Elastomerbahnen für die Bauwerksabdichtung gegen Bodenfeuchte und Wasser - Definitionen und Eigenschaften

This European Standard was approved by CEN on 20 October 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/a2e4d085-0b47-4835-a450-22cc9e1a5ddf/sist-en-13967-2005>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Product designation	6
5 Product characteristics	6
6 Evaluation of conformity.....	9
7 Product data sheet and designation.....	12
8 Marking, labelling and packaging	12
Annex A (informative) Product designation, typical materials and structure of sheets	13
Annex B (normative) Method of measuring the resistance of ventilating and draining damp-proof sheets to deformation under load	14
Annex C (normative) Method of testing for the accelerated ageing of damp-proof sheets in an alkaline environment	18
Annex D (informative) Example of product data sheet.....	20
Bibliography	29

Foreword

This document (EN 13967:2004) has been prepared by Technical Committee CEN/TC 254 "Flexible sheets for waterproofing", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2005, and conflicting national standards shall be withdrawn at the latest by September 2006.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

The European Standard is a general product standard for flexible sheets of plastics intended for damp proof sheets, including plastics basement tanking sheets, for use in buildings. This standard is one of a series of product standards for factory made flexible sheets for use in buildings.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

(standards.iteh.ai)
SIST EN 13967:2005
<https://standards.iteh.ai/catalog/standards/sist/a2e4d085-0b47-4835-a450-22cc9e1a5ddf/sist-en-13967-2005>

1 Scope

This document specifies definitions and characteristics of flexible plastic and rubber sheets for which the intended use is as damp proofing for buildings, including basement tanking. It specifies the requirements and test methods and provides for the evaluation of conformity of the products with the requirements of this standard.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1296, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roofing — Method of artificial ageing by long term exposure to elevated temperature*

prEN 1548:2000, *Flexible sheets for waterproofing — Method for exposure to bitumen — Plastic and rubber sheets for waterproofing*

EN 1847, *Flexible sheets for waterproofing — Plastic and rubber sheets for roof waterproofing — Methods for exposure to liquid chemicals, including water*

EN 1848-2, *Flexible sheets for waterproofing — Determination of length, width, straightness and flatness — Part 2: Plastic and rubber sheets for roof waterproofing*

EN 1849-2, *Flexible sheets for waterproofing — Determination of thickness and mass per unit area — Part 2: Plastic and rubber sheets for roof waterproofing*

EN 1850-2, *Flexible sheets for waterproofing — Determination of visible defects — Part 2: Plastic and rubber sheets for roof waterproofing*

EN 1928, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of watertightness*

EN 1931, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of water vapour transmission properties*

EN 12310-1, *Flexible sheets for waterproofing — Part 1: Bitumen sheets for roof waterproofing — Determination of resistance to tearing (nail shank)*

EN 12311-2, *Flexible sheets for waterproofing — Determination of tensile properties — Part 2: Plastic and rubber sheets for roof waterproofing*

EN 12317-2, *Flexible sheets for waterproofing — Determination of the shear resistance of joints — Part 2: Plastic and rubber sheets for roof waterproofing*

EN 12691, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of resistance to impact*

EN 12730:2001, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of resistance to static loading*

EN 13416:2001, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Rules for sampling*

EN 13501-1:2002, *Fire classification of construction products and building elements — Part 1: Classification using test data from reaction to fire tests*

EN 13859-1:2000, *Flexible sheets for waterproofing — Definitions and characteristics of underlays — Part 1: Underlays for discontinuous roofing*

EN ISO 11925-2, *Reaction to fire tests — Ignitability of building products subjected to direct impingement of flame — Part 2: Single-flame source test (ISO 11925-2:2002)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13416:2001 and the following apply.

3.1

sheet for damp proofing

plastic or rubber sheet used on or under floors or ground slabs to prevent liquid water not under hydrostatic pressure passing from the ground into the internal environment. This can also include use in walls

3.2

ventilating or draining damp proof sheet

sheet conforming to the definition in 3.1 and with the ability to provide a continuous void or structure to allow free movement of water vapour or liquid water between the sheet and any further construction

3.3

tanking sheet

sheet conforming to the definition in 3.1 used in wall construction, or on or under floors or ground slabs to prevent liquid water under hydrostatic pressure passing from the ground into the internal environment or from one section of the structure to another

3.4

manufacturer's limiting value, MLV

value stated by the manufacturer to be met during testing. The manufacturer's limiting value can be a minimum or a maximum value according to statements made under product characteristics of this standard

3.5

manufacturer's declared value, MDV

value declared by the manufacturer accompanied by a declared tolerance

3.6

plastic sheet

factory made flexible sheet made from a plastic polymeric material and which may include composites with other materials

3.7

rubber sheet

factory made flexible sheet made from an elastomeric polymeric material and which may include composites with other materials

3.8

sampling

procedure used to select or constitute a sample

3.9

sample

sheet from which a test piece is taken

3.10

test piece

part of the sample from which test specimens are taken

3.11

test specimen

piece of precise dimensions taken from the test piece

4 Product designation

The types of damp proof sheets covered by this document are designated as follows:

TYPE A damp proof sheet;

TYPE V damp proof ventilating or draining sheet;

TYPE T tanking sheet.

5 Product characteristics

5.1 General

5.1.1 Where a tolerance is limited by this document it does not have to be declared by the manufacturer.

5.1.2 When tested for purposes other than initial type testing or factory production control, the tests to determine product characteristics indicated in this document shall be started within 1 month of delivery from the manufacturer.

[SIST EN 13967:2005](https://standards.iteh.ai/catalog/standards/sist/a2e4d085-0b47-4835-a450-12110155ddf/sist-en-13967-2005)

[https://standards.iteh.ai/catalog/standards/sist/a2e4d085-0b47-4835-a450-](https://standards.iteh.ai/catalog/standards/sist/a2e4d085-0b47-4835-a450-12110155ddf/sist-en-13967-2005)

[12110155ddf/sist-en-13967-2005](https://standards.iteh.ai/catalog/standards/sist/a2e4d085-0b47-4835-a450-12110155ddf/sist-en-13967-2005)

5.2 Deviation from test sample dimensions

Where the contours of the product make it impossible to obtain a test sample of the required dimensions, or otherwise render the test impracticable, testing may be carried out either on samples of different dimensions or if still impracticable on the equivalent flat sheet of the same thickness as the finished product. Any such deviations from the test method shall be recorded on the test report and the product data sheet.

5.3 Visible defects

The product shall be free of visible defects as determined in accordance with EN 1850-2.

5.4 Dimensions and tolerances

The length, width and straightness shall be determined in accordance with EN 1848-2. The length and width shall lie within the declared tolerance of the manufacturer's declared value (MDV). The maximum deviation from straightness shall not exceed 75 mm per 10 m length or in proportion for other lengths (e.g. 37,5 mm per 5 m length).

5.5 Thickness and mass per unit area

The thickness and mass per unit area shall be determined in accordance with EN 1849-2.

Where a product is specified by mass per unit area, the mass shall lie within the declared tolerance of the manufacturer's declared value. Where the dimensions of any profile are comparable to the area to be measured, a larger sample area shall be used and the deviation from the test method noted.

Where a product is specified by thickness, the thickness shall lie within the declared tolerance of the manufacturer's declared value. No single measurement shall lie outside the declared tolerance the manufacturer's declared value.

5.6 Water tightness

The product shall be watertight as determined by Method A or B of EN 1928:2000 with a pressure of 2 kPa for Types A and V damp proof sheets and a pressure of 60 kPa for Type T damp proof sheets.

5.7 Resistance to impact

Where required, the resistance to impact shall be determined in accordance with EN 12691 but with a drop height of 300 mm \pm 5 mm. The smallest diameter it will resist shall be less than or equal to the manufacturer's limiting value. The expression of the manufacturer's limiting value in millimetres shall be accompanied by the drop height $h = 300$ mm.

5.8 Durability

5.8.1 Against ageing/degradation

In order to verify the artificial ageing behaviour of the product, watertightness shall be determined after exposure in accordance with EN 1296 for a period of 12 weeks. The watertightness shall be determined in accordance with EN 1928:2000 Method A or B. Type A and V damp proof sheets shall be tested at a pressure of 2 kPa and Type T tanking sheets at a pressure of 60 kPa, and shall give a pass result.

5.8.2 Against chemicals

In order to verify the durability of the products the sheet shall be tested before and after exposure to chemicals in accordance with EN 1847. The sheet shall be watertight as determined in accordance EN 1928:2000 Method A or B, with a pressure of 2 kPa for Types A and V damp proof sheets and a pressure of 60 kPa for Type T damp proof sheets both before and after long term exposure to dilute alkali in accordance with EN 1847.

Where required, damp proof sheets shall be tested in accordance with the method given in Annex C. The product passes if the elongation after 24 weeks is not less than 50 % of the initial value.

5.9 Compatibility with bitumen

Where required, the product shall be exposed to bitumen for 28 days at 70 °C using the method given in prEN 1548:2000, but with a sample size large enough to provide a 200 mm diameter circular sample after exposure. It shall be watertight when subsequently tested in accordance with Method A of EN 1928:2000. Type A and V damp proof sheets shall be tested at a pressure of 2 kPa and Type T tanking sheets at a pressure of 60 kPa.

5.10 Resistance to tearing (nail shank)

For unreinforced sheets the tear resistance (nail shank) shall be determined in accordance with EN 12310-1 and shall be greater than or equal to the manufacturer's limiting value.

For reinforced sheets the tear resistance (nail shank) shall be determined in accordance with Annex B of prEN 13859-1:2000 and shall be greater than or equal to the manufacturer's limiting value.

5.11 Joint strength

Where required, the joint strength shall be determined in accordance with EN 12317-2 and shall be greater than or equal to the manufacturer's limiting value.

5.12 Water vapour transmission properties

Where required, the water vapour resistance shall be determined in accordance with EN 1931 and shall lie within the declared tolerance of the manufacturer's declared value.

5.13 Resistance to static loading

The resistance to static loading shall be determined in accordance with Method B of EN 12730:2001 and shall be greater than or equal to the manufacturer's limiting value.

5.14 Tensile properties

The tensile properties of unreinforced sheets shall be determined in accordance with EN 12311-2 and shall be greater than or equal to the manufacturer's limiting value for the longitudinal and transverse directions of the sheet.

The tensile properties of reinforced sheets shall be determined in accordance with Annex A of prEN 13859-1:2000 and shall be greater than or equal to the manufacturer's limiting value for the longitudinal and transverse directions of the sheet.

5.15 Resistance to deformation under load

The resistance of ventilating or draining damp proof sheets to deformation under load shall be determined in accordance with Annex B and the results shall be less than or equal to the manufacturer's limiting value of deformation at the defined load and the defined time.

5.16 Reaction to fire

Where required, the product shall be tested and classified in accordance with EN 13501-1:2002, Table 1. When tested according to EN ISO 11925-2, the products shall be tested under conditions of surface flame attack.

NOTE It is currently considered that the Euroclasses Classification system at Classes D and above requires investigation to determine its appropriateness to the products covered by this document (the SBI test may be inappropriate for products covered by the standard). Pending results of such an investigation and discussions in the Fire Regulators Group, products covered by this document are tested to EN ISO 11925-2.

If and when a new fire test scenario and test method are developed for the products, this document will be amended to refer to them.

5.17 Dangerous substances

For products placed on the market within the European Economic Area see ZA.1. Outside the EEA products shall conform to any applicable provisions related to dangerous substances valid in the place of use.

The manufacturer shall disclose on the product wrapper and in the health and safety data sheets the use of any additive or constituent considered hazardous.

6 Evaluation of conformity

6.1 General

The compliance of a plastic or rubber damp proofing sheet with the requirements of this document and with the stated values (including classes) shall be demonstrated by:

- initial type testing;
- factory production control by the manufacturer, including product assessment.

For the purposes of testing, products may be grouped into families, where it is considered that the selected property is common to all products within that family.

6.2 Type testing

6.2.1 General

Initial type testing shall be performed to show conformity with this document. Tests previously performed in accordance with the provisions of this standard (same product, same characteristic(s), test method, sampling procedure, system of attestation of conformity, etc.) may be taken into account. In addition, initial type testing shall be performed at the beginning of the production of a new product type (unless a member of the same family) or at the beginning of a new method of production (where this may affect the stated properties).

All characteristics in Clause 5 shall be subject to initial type testing, where required.

Whenever a change occurs in the product design, the raw material or supplier of the components, or the production process (subject to the definition of a family), which would change significantly one or more of the characteristics, the type tests shall be repeated for the appropriate characteristic(s).

6.2.2 Sampling

Samples shall be taken according to EN 13416. The minimum number of tests to show compliance for initial and further type testing shall be one for all characteristics.

6.3 Factory production control (FPC)

6.3.1 General

The manufacturer shall establish, document and maintain an FPC system to ensure that the products placed on the market conform to the stated performance characteristics. The FPC system shall consist of procedures, regular inspections and tests and/or assessments and the use of the results to control raw and other incoming materials or components, equipment, the production process and the product.

If a manufacturer claims compliance with FPC requirements by operating an EN ISO 9001 system, EN ISO 9001 shall be applied in full and shall be made specific to the requirements of this document.

The results of inspections, tests or assessments requiring action shall be recorded, as shall any action taken. The action to be taken when control values or criteria are not met shall be recorded.

6.3.2 Frequency of testing

The characteristics to be controlled within the framework of factory production control are those for which the manufacturer claims a performance. Control of the product is required, either by direct testing or by indirect control. The frequency of testing shall be given in the manufacturer's FPC system.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 13967:2005](https://standards.iteh.ai/catalog/standards/sist/a2e4d085-0b47-4835-a450-22cc9e1a5ddf/sist-en-13967-2005)

<https://standards.iteh.ai/catalog/standards/sist/a2e4d085-0b47-4835-a450-22cc9e1a5ddf/sist-en-13967-2005>