
Železniške aplikacije - Radsätze und Drehgestelle - Vollräder - Technische Zulassungsverfahren - Teil 1: Geschmiedete und gewalzte Räder

Railway applications - Wheelsets and bogies - Monobloc wheels - Technical approval procedure - Part 1: Forged and rolled wheels

Bahnanwendungen - Radsätze und Drehgestelle - Vollräder - Technische Zulassungsverfahren - Teil 1: Geschmiedete und gewalzte Räder

Applications ferroviaires - Essieux montés et bogies - Roues monobloc - Procédure d'homologation technique - Partie 1: Roues forgées et laminées

<https://standards.iteh.ai/catalog/standards/sist/26d77491-c71d-4066-8618-51f533ac01c4/sist-en-13979-1-2004>

Ta slovenski standard je istoveten z: **EN 13979-1:2003**

ICS:

45.040	Materiali in deli za železniško tehniko	Materials and components for railway engineering
--------	---	--

SIST EN 13979-1:2004

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 13979-1:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/26d77491-c71d-4066-8618-51f533ac01c4/sist-en-13979-1-2004>

EUROPEAN STANDARD

EN 13979-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2003

ICS 45.040

English version

Railway applications - Wheelsets and bogies - Monobloc wheels - Technical approval procedure - Part 1: Forged and rolled wheels

Applications ferroviaires - Essieux montés et bogies -
Roues monobloc - Procédure d'homologation technique -
Partie 1: Roues forgées et laminées

Bahnanwendungen - Radsätze und Drehgestelle - Vollräder
- Technische Zulassungsverfahren - Teil 1: Geschmiedete
und gewalzte Räder

This European Standard was approved by CEN on 3 November 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/26d77491-c71d-4066-8618-51f533ac01c4/sist-en-13979-1-2004>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	4
Introduction.....	5
1 Scope.....	6
2 Normative references.....	6
3 Parameters for the definition of the application covered.....	6
3.1 Parameters for geometrical interchangeability.....	6
3.1.1 Functional requirements.....	6
3.1.2 Assembly requirements.....	7
3.1.3 Maintenance requirements.....	7
3.2 Parameters for thermomechanical assessment.....	7
3.3 Parameters for mechanical assessment.....	7
3.4 Parameters for acoustic assessment.....	8
4 Description of the wheel to be approved.....	8
5 Assessment of the geometrical interchangeability.....	8
6 Assessment of the thermomechanical behaviour.....	8
6.1 General procedure.....	8
6.2 First stage – Braking bench test.....	9
6.2.1 Test procedure.....	9
6.2.2 Decision criteria.....	9
6.3 Second stage – Wheel fracture bench test.....	10
6.3.1 General.....	10
6.3.2 Test procedure.....	10
6.3.3 Decision criterion.....	10
6.4 Third stage – Field braking test.....	10
6.4.1 General.....	10
6.4.2 Test procedure.....	10
6.4.3 Decision criteria.....	10
7 Assessment of the mechanical behaviour.....	11
7.1 General procedure.....	11
7.2 First stage - Calculation.....	11
7.2.1 Applied forces.....	11
7.2.2 Calculation procedure.....	12
7.2.3 Decision criteria.....	13
7.3 Second stage – Bench test.....	13
7.3.1 General.....	13
7.3.2 Definition of bench loading and of the test procedure.....	13
7.3.3 Decision criteria.....	13
8 Assessment of the acoustical behaviour.....	13
8.1 General procedure.....	13
8.2 Calculation procedure.....	14
8.3 Field measurements.....	14
8.4 Decision criteria.....	14
9 Technical approval documents.....	15
Annex A (normative) Assessment of the thermomechanical behaviour.....	17
A.1 Assessment organigram.....	17
A.2 Braking bench test procedure.....	18

A.2.1	Principle of the test	18
A.2.2	Definition of braking	18
A.2.3	Method of measuring the decision criteria	18
A.2.4	Tests and measurements	20
A.2.5	Anomalies	21
A.3	Wheel fracture bench test procedure	21
A.3.1	Principle of the test	21
A.3.2	Definition of drag braking	21
A.3.3	Pre-cracking of the rim	22
A.3.4	Special measurement methods required for this test	22
A.3.5	Tests and measurements	22
A.3.6	Anomalies	23
A.4	Field braking test procedure	23
A.4.1	Principle of the test	23
A.4.2	Definition of braking	23
A.4.3	Method of measurement of the decision criteria	24
A.4.4	Standard test run	24
A.4.5	Tests and measurements	25
A.4.6	Anomalies	26
Annex B (normative) Organigram of the mechanical behaviour assessment		27
Annex C (informative) Mechanical behaviour – Finite element code assessment		28
Annex D (informative) Mechanical behaviour – Bench loading and test procedure		29
D.1	Principle of bench loading and test procedure	29
D.2	Definition of loading	29
D.2.1	General	29
D.2.2	Measurement of the stresses during field tests	30
D.3	Fatigue bench test	30
D.3.1	Method 1 – Random fatigue test	30
D.3.2	Method 2 – Single-stage fatigue test	31
Annex E (informative) Assessment of the acoustical behaviour		34
E.1	Assessment organigram	34
E.2	Calculation procedure	35
E.2.1	Preliminary comment	35
E.2.2	Calculation of the wheel modal basis	35
E.2.3	Selection of the reference track model	35
E.2.4	Definition of the calculation parameters	35
E.2.5	Power calculation	35
E.2.6	Insertion	36
E.2.7	Calculations of the decision criteria for acoustical technical approval of the wheel	37
E.2.8	Optional calculations	37
E.3	Field measurement procedure	37
E.3.1	Objective and preliminary remark	37
E.3.2	Recommendations for the operating conditions	38
E.3.3	Measurement procedure	41
E.3.4	Analysis of results	43
Bibliography		46

EN 13979-1:2003 (E)**Foreword**

This document EN 13979-1:2003 has been prepared by Technical Committee CEN/TC 256 "Railway applications", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2004, and conflicting national standards shall be withdrawn at the latest by June 2004.

Annexes A and B are normative.

Annexes C, D and E are informative.

This document contains a bibliography.

This European Standard is part of a series of two EN 13979 standards, Part 2 of which is:

Part 2: Other procedures.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

SIST EN 13979-1:2004

<https://standards.itech.ai/catalog/standards/sist/26d77491-c71d-4066-8618-51f533ac01c4/sist-en-13979-1-2004>

Introduction

To date, UIC regulations specified that for a wheel to be used in Europe:

- its design had to be standardized;
- it had to conform to the quality requirements of UIC leaflet 812-3.

In order to be able to adapt to new railway working conditions, on the one hand, and to facilitate the introduction of new technical solutions, on the other, it has been necessary to replace the concept of standardization with the definition of specifications that a wheel design shall meet to be accepted on a European network.

The standard covers these specifications and describes precisely how to assess the wheel design.

To be able to apply these specifications, it is essential to define the use of the wheel; this standard also states how to define this use.

At least four aspects are described with different purposes:

- a geometrical aspect: to allow interchangeability of different solutions for the same application;
- a thermomechanical aspect: to manage wheel deformations and to ensure that braking will not cause wheels to break;
- a mechanical aspect: to ensure that no fatigue cracks occur in the web;
- an acoustical aspect: to ensure that the solution chosen is as good as the reference wheel, for the use in question.

For each of these three latter aspects, the rules proposed tend to limit the procedure, the easier the objectives are to attain by the wheel under study.

This standard does not cover assessment of the hub nor of the static mechanical dimensioning of the wheel.

EN 13979-1:2003 (E)**1 Scope**

The aim of this European Standard is to define the requirements that a monobloc wheel of a freight or passenger railway vehicle non-powered axle shall meet in order to be able to be used on a European network.

For wheels of powered axles or wheels with noise dampers, the requirements may be amended or supplemented.

For light vehicles and tramways, other standards or documents accepted by the customer and supplier may be used.

This European Standard only applies to wheels of new design.

These requirements are intended to assess the validity of the design choice for the proposed use.

The assessment of these requirements is the technical approval procedure.

This European Standard is applicable to forged and rolled wheels for which the quality requirements are defined in prEN 13262.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 12668-3, *Non-destructive testing - Characterization and verification of ultrasonic examination equipment - Part 3: Combined equipment.*

EN 13103, *Railway applications - Wheelsets and bogies - Non-powered axles – Design method.*

prEN 13262, *Railway applications - Wheelsets and bogies – Wheels - Product requirement.*

3 Parameters for the definition of the application covered

The application for which the wheel is to be approved shall be defined by the following parameters.

If the application parameters are changed for an approved wheel, the customer and supplier shall review the assessments.

3.1 Parameters for geometrical interchangeability

The application shall be defined by geometrical interchangeability parameters divided into three categories according to whether they are linked to functional, assembly or maintenance requirements.

3.1.1 Functional requirements

- the nominal tread diameter that influences the buffer height and the loading gauge;
- the maximum rim width linked to the points and crossing and the track brakes;

- the tread profile outside the conical part of the tread;
- the position of the rim internal surface relative to the corresponding surface of the hub;
- the conicity of the hub bore;
- the space required for disc brakes mounted on the wheel;
- the space needed on the bogie frame, braking equipment and suspension equipment.

3.1.2 Assembly requirements

- the bore diameter;
- the hub length to ensure overhanging of the hub on the wheelseat.

3.1.3 Maintenance requirements

- the wear limit diameter or the last reprofiling diameter;
- the wear groove shape;
- the geometry of the area for wheel clamping on reprofiling machines;
- the position and shape of the hole and groove for displacement under oil pressure;
- the general rim shape to allow ultrasonic measurement of residual stresses in wheels braked by shoes.

3.2 Parameters for thermomechanical assessment

The application shall be defined by:

- the maximum braking energy created by the friction of the brake shoes on the rail surface. This energy may be defined by a power P_a , a time t_a and a train speed V_a during drag braking. If it is defined by other parameters (for braking to a stop, for example), these parameters are defined by agreement between the customer and the supplier;
- the type of brake shoes applied to the wheel (nature, dimensions and number).

3.3 Parameters for mechanical assessment

The application shall be defined by:

- the maximum vertical static force per wheelset;
- the type of service to be provided by the vehicles that will be fitted with the wheels to be approved:
 - description of the lines: geometric quality of the tracks, curve parameters, maximum speeds ... ;
 - running times on these lines;
- the calculated service life of the wheel, in kilometres.

EN 13979-1:2003 (E)**3.4 Parameters for acoustic assessment**

The application shall be defined by all the parameters influencing the noise emitted by the wheel and not directly involved in the design of the wheel to be approved, such as:

- the reference track on which the wheel is to run;
- the reference wheel to which the design will be compared;
- the reference rolling stock and one or more reference speeds;
- one or two surface roughness spectra representative of the range of operational values of the wheel under test.

4 Description of the wheel to be approved

The designer of the wheel to be approved shall supply documentation comprising:

- the description of the fabrication process (forging, rolling, heat treatment,...);
- the definition of the wheel geometry (drawing);
- the following fabrication parameters, if they differ from those defined in prEN 13262:
 - geometrical tolerances;
 - surface finishes;
 - steel grade;
- the parameters for defining the application for which the approval is requested.

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 13979-1:2004](https://standards.iteh.ai/catalog/standards/sist/26d77491-c71d-4066-8618-51f533ac01c4/sist-en-13979-1-2004)

<https://standards.iteh.ai/catalog/standards/sist/26d77491-c71d-4066-8618-51f533ac01c4/sist-en-13979-1-2004>

At the end of this technical approval procedure and before being put into service, a wheel shall be subjected to the product qualification procedure defined in prEN 13262.

5 Assessment of the geometrical interchangeability

The wheel design shall conform to the requirements of 3.1.

6 Assessment of the thermomechanical behaviour**6.1 General procedure**

This assessment may comprise three stages. The transition from one stage to the next depends on the results obtained.

The flowchart for this assessment is shown in normative annexe A.

For each of the three stages, the test shall be carried out on a new rim (nominal tread diameter) and a worn rim (wear limit tread diameter).

In each case, new rim and worn rim, the web geometry of the tested wheels shall be the least favourable for thermomechanical behaviour within the geometrical tolerance ranges. The wheel designer shall prove, by numerical simulation, that the tested wheels give the worst results. If that is not the case, the numerical simulation shall allow the results that would be obtained on wheels not in the most unfavourable geometrical conditions to be corrected.

In order to allow measurement of residual stress, the wheels to be tested shall not have either a wear limit groove or a bevel.

NOTE For the moment, the calculation codes and thermomechanical parameters are too imprecise and not well known enough to be used as assessment parameters in a standard. In future, if this situation develops, a thermomechanical calculation should be made as the first stage of the assessment.

6.2 First stage – Braking bench test

6.2.1 Test procedure

The test method and the measurements to be made are given in normative annex A.

The power to be applied during this test shall be equal to $1,2 P_a$ (P_a is defined in 3.2). The duration of each drag braking period and the train speed are those defined in 3.2 (t_a and V_a).

6.2.2 Decision criteria

Three criteria shall be met simultaneously for the wheel with the new rim and the wheel with the worn rim.

Wheel with new rim:

- maximum lateral displacement of the rim during braking :+ 3 / -1 mm;
- level of residual stress in the rim after cooling:
 - $\sigma_{rn} \leq + \Sigma_r$ N/mm² as the average of three measurements;
 - $\sigma_{in} \leq + (\Sigma_r + 50)$ N/mm² for each measurement;
- maximum lateral displacement of the rim after cooling: + 1,5 / - 0,5mm.

Wheel with worn rim:

- maximum lateral displacement of the rim during braking :+ 3 / -1 mm;
- level of residual stress in the rim after cooling:
 - $\sigma_{rw} \leq + (\Sigma_r + 75)$ N/mm² as the average of three measurements;
 - $\sigma_{iw} \leq + (\Sigma_r + 100)$ N/mm² for each measurement;
- maximum lateral displacement of the rim after cooling: + 1,5 / - 0,5mm.

The value of Σ_r shall be defined according to the criteria of the wheel rim steel grade. For grades ER6 and ER7 of prEN 13262, $\Sigma_r = 200$ N/mm².

The lateral displacement is positive if the distance between the two inner faces of the wheel of the wheelset increases.

EN 13979-1:2003 (E)

For domestic traffic, if the track tolerances differ from general tolerances used in Europe, other values of lateral displacement may be agreed between the parties concerned

6.3 Second stage – Wheel fracture bench test**6.3.1 General**

This second stage shall only be proceeded with if the residual stress levels measured during the first stage exceed the decision criteria.

6.3.2 Test procedure

The test procedure is given in normative annex A.

6.3.3 Decision criterion

The tested wheels shall not fracture.

6.4 Third stage – Field braking test**6.4.1 General**

This third stage shall be proceeded with if one of the results of the first stage does not meet the decision criteria and the wheel is not rejected after the second stage.

6.4.2 Test procedure

The test method and the measurements to be taken are given in normative annex A.

The power to be taken into account for this test is $1,2 P_a$ (P_a is defined in 3.2). The duration of each drag braking and the running speed of the train are those defined in 3.2 (t_a et V_a).

6.4.3 Decision criteria

Three criteria shall be met simultaneously for the wheel with the new rim and the wheel with the worn rim.

Wheel with new rim:

- maximum lateral displacement of the rim during braking :+ 3 / -1 mm;
- level of residual stress in the rim after the tests and after cooling:
 - $\sigma_{rm} \leq + (\Sigma_r - 50) \text{ N/mm}^2$ as the average of the three measurements
 - $\sigma_{in} \leq + \Sigma_r \text{ N/mm}^2$ for each of the measurements
- maximum lateral displacement of the rim after cooling: + 1,5 /- 0,5 mm.

Wheel with worn rim:

- maximum lateral displacement of the rim during braking :+ 3 /-1 mm;
- level of residual stress in the rim after the tests and after cooling:

- $\sigma_{rw} \leq + \Sigma_r$ N/mm² as the average of the three measurements;
- $\sigma_{iw} \leq + (\Sigma_r + 50)$ N/mm² for each of the measurements;
- maximum lateral displacement of the rim after cooling: + 1,5 /- 0,5 mm

The value of Σ_r shall be defined according to the criteria of the wheel rim steel grade. For grades ER6 and ER7 of prEN 13262, $\Sigma_r = 200$ N/mm².

The lateral displacement is positive if the distance between the two inner faces of the wheel of the wheelset increases.

For domestic traffic, if the track tolerances differ from the general tolerances used in Europe, other values of lateral displacement may be agreed between the parties concerned

7 Assessment of the mechanical behaviour

7.1 General procedure

This assessment may comprise two stages. The second stage is carried out depending on the results of the first stage. The purpose of this assessment is to ensure that there will be no risk of fatigue cracking either in the wheel web or in its connections with the hub or the rim during the service life of the wheel.

Both for the calculation and the test, the wheel geometry shall be the least favourable with regard to the mechanical behaviour. If that is not the case for the test, the test parameters shall be corrected by the calculation.

The flowchart for this assessment is shown in normative annex B.
<https://standards.iteh.ai/catalog/standards/sist/26d77491-c71d-4066-8618-51f533ac01c4/sist-en-13979-1-2004>

7.2 First stage - Calculation

7.2.1 Applied forces

Conventional forces shall be used. They are calculated on the basis of the value of load P . Load P is defined in EN 13103. It is half the vertical force per wheelset on the rail.

On the basis of the parameters necessary for the mechanical assessment defined in 3.3, additional forces shall be used if these parameters generate greater forces (for example, tilting trains, curve parameters, frozen track, etc...).

Three load cases shall be considered (see Figure 1):

- Case 1: straight track (centred wheelset)

$$F_z = 1,25 P$$

$$F_{y1} = 0$$

- Case 2: curve (flange pressed against the rail)

$$F_z = 1,25 P$$

$$F_{y2} = 0,6 P \text{ for non-guiding wheelsets}$$