

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Optical fibre cables –
Part 3-11: Outdoor cables – Detailed specification for duct and directly buried
single-mode optical fibre telecommunication cables**

**Câbles à fibres optiques –
Partie 3-11: Câbles extérieurs – Spécification particulière pour les câbles de
télécommunication à fibres optiques unimodales destinés à être installés
dans des conduites ou à être directement enterrés**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2007 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch
Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch
Tél.: +41 22 919 02 11
Fax: +41 22 919 03 00

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Optical fibre cables –
Part 3-11: Outdoor cables – Detailed specification for duct and directly buried
single-mode optical fibre telecommunication cables**

**Câbles à fibres optiques –
Partie 3-11: Câbles extérieurs – Spécification particulière pour les câbles de
télécommunication à fibres optiques unimodales destinés à être installés
dans des conduites ou à être directement enterrés**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

U

CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	7
4 Symbols	7
5 General information	8
5.1 Overview	8
5.2 General cable description.....	8
5.2.1 Characteristics of optical fibre	8
5.2.2 Characteristics of optical fibre cable elements	8
5.2.3 Characteristics of optical fibre cables	8
5.2.4 Environmental and product safety requirements	9
5.3 Optical fibre spliceability	9
5.4 Testing.....	9
6 Requirements for cabled single-mode optical fibres.....	10
6.1 Fibre materials	10
6.2 Optical requirements	10
6.2.1 Attenuation coefficient.....	10
6.2.2 Attenuation discontinuities	11
6.2.3 Cable cut-off wavelength	12
6.2.4 Polarization mode dispersion (PMD).....	12
6.2.5 Group index.....	12
7 Requirements for cable elements.....	12
7.1 Element design	12
7.1.1 Modularity	13
7.1.2 Fibre and element identification.....	13
7.2 Element characteristics	14
7.2.1 Ribbon.....	14
7.2.2 Tube kinking.....	14
8 Requirements for optical cables.....	14
8.1 Cable construction	14
8.1.1 Cable core.....	15
8.1.2 Anti-buckling and strength element splicing	15
8.1.3 Cable element stranding.....	15
8.1.4 Spliced fibres	15
8.1.5 Spare fibres.....	15
8.1.6 Cable sheath removal.....	15
8.1.7 Armouring.....	15
8.2 Marking.....	16
8.2.1 Sheath marking	16
8.2.2 Identification marking	16
8.2.3 Cable length marking.....	16
8.3 Cable core materials	17
8.3.1 Tube filling compound material (if required).....	17
8.3.2 Water-blocking material.....	17

8.3.3	Cable material compatibility.....	17
8.3.4	Tube material	17
8.4	Cable sheath	17
8.4.1	Sheath material	17
8.4.2	Sheath thickness	17
8.4.3	Outer cable diameter	18
8.4.4	Moisture barrier	18
8.4.5	Rodent resistant barrier	18
8.5	Mechanical requirements.....	18
8.5.1	Cable bend.....	18
8.5.2	Impact	19
8.5.3	Crush	19
8.5.4	Tensile performance.....	20
8.5.5	Torsion	21
8.5.6	Repeated bending	21
8.6	Environmental requirements.....	22
8.6.1	Temperature cycling	22
8.6.2	Stripping force stability of cabled optical fibres.....	23
8.6.3	Water penetration.....	23
8.6.4	Environmental impact.....	23
8.7	Electrical protection.....	23
8.7.1	Continuity of metallic members.....	23
8.7.2	Lightning damage susceptibility.....	23
9	Quality assurance.....	23
Annex A (informative)	Guidance for ITU-T and IEC cabled fibre and fibre references.....	24
Annex B (informative)	Fibres.....	26
Bibliography.....		28
Figure 1 –	Definition of the different temperatures	22
Table 1 –	Attenuation coefficient.....	11
Table 2 –	Colour for individual fibres or units (listed alphabetically)	13
Table A.1 –	IEC and ITU cross-reference.....	25
Table B.1 –	Dimensional attributes and measurement methods	26
Table B.2 –	Mechanical attributes and test methods	27
Table B.3 –	Transmission attributes and measurement methods	27
Table B.4 –	Environmental exposure tests	27
Table B.5 –	Attributes measured.....	27

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRE CABLES

**Part 3-11: Outdoor cables –
Detailed specification for duct and directly buried
single-mode optical fibre telecommunication cables**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60794-3-11 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

The text of this standard is based on the following documents:

FDIS	Report on voting
86A/1147/FDIS	86A/1165/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with ISO/IEC Directives, Part 2.

A list of all parts of the IEC 60794 series, published under the general title *Optical fibre cables*, can be found on the IEC website.

This standard shall be used in conjunction with IEC 60794-3 and IEC 60794-3-10.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

Withdrawing

iTech Standards
(<https://standards.itih.ai>)
Document Preview

<https://standards.itih.ai/standards/iec/db835ed9-4163-46f5-be15-21337bb4eedb/iec-60794-3-11-2007>

OPTICAL FIBRE CABLES

Part 3-11: Outdoor cables – Detailed specification for duct and directly buried single-mode optical fibre telecommunication cables

1 Scope

This part of IEC 60794 sets forth technical requirements and characteristics of single-mode optical fibre cables for duct and direct buried installation.

This specification includes functional mechanical, environmental and optical requirements, recommended features and test methods for assessing the product against the stated requirements.

The specified test methods, where applicable, are those referenced in IEC 60794-1-1 and described in detail in IEC 60794-1-2.

The requirements of this specification are used in conjunction with IEC 60794-3 and IEC 60794-3-10.

Multimode fibre requirements are not addressed in this document; see IEC 60794-3-12¹⁾.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC Guide 104, *The preparation of safety publications and the use of basic safety publications and group safety publications*

IEC 60304, *Standard colours for insulation for low-frequency cables and wires*

IEC 60708, *Low-frequency cables with polyolefin insulation and moisture barrier polyolefin sheath*

IEC 60793-1-22, *Optical fibres – Part 1-22: Measurement methods and test procedures – Length measurement*

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

1) IEC 60794-3-12, *Optical fibre cables - Part 3-12: Outdoor cables - Detailed specification for duct and directly buried optical telecommunication cables for use in premises cabling*

IEC 60793-1-44, *Optical fibres – Part 1-44: Measurement methods and test procedures – Cut-off wavelength*

IEC 60793-1-48, *Optical fibres – Part 1-48: Measurement methods and test procedures – Polarization mode dispersion*

IEC 60793-2-50, *Optical fibres – Part 2-50: Product specifications – Sectional specification for single-mode class B fibres*

IEC 60794 (all parts), *Optical fibre cables*

IEC 60794-1-1, *Optical fibre cables – Part 1-1: Generic specification – General*

IEC 60794-1-2, *Optical fibre cables – Part 1-2: Generic specification – Basic optical cable test procedures*

IEC 60794-3, *Optical fibre cables – Part 3: Sectional specification – Outdoor cables*

IEC 60794-3-10, *Optical fibre cables – Part 3-10: Outdoor cables – Family specification for duct and directly buried optical telecommunication cables*

IEC 60811-1-1, *Common test methods for insulating and sheathing materials of electric cables and optical cables – Part 1-1: Methods for general application – Measurement of thickness and overall dimensions – Tests for determining the mechanical properties*

IEC 62305 (all parts), *Protection against lightning*

IEC/TR 61931, *Fibre optic – Terminology*

IEC/TR 62000, *Single-mode fibre compatibility guidelines*

ITU-T G.652, *Characteristics of a single-mode optical fibre and cable*

3 Terms and definitions

For the purposes of this document, unless otherwise specified, the terms and definitions given in IEC/TR 61931 apply.

4 Symbols

The following symbols are used in this document.

λ_{cc} cable cut-off wavelength

d outer cable diameter

SZ technique in which the lay reverses direction periodically

5 General information

5.1 Overview

Single-mode optical fibres are widely used for telecommunication purposes and are cabled to satisfy the functional requirements of the installation environment. Further, cables placed into ducts and sub-ducts may be installed using solely, or a combination of, pushing, pulling, and air-assisted installation techniques. For duct installations, the environment and infrastructure can be varied and may also involve the use of single and multiple sub-ducts. Directly buried cables may be installed by a variety of methods such as ploughing and trenching with different environments and infrastructure. This may require specific cable design solutions based on multiple layers of armours and sheaths. It is recognised that certain designs of cable for direct buried applications involving such solutions may also be suitable for duct installation. The functional requirements and test methods featured in this specification are based upon adherence to established and recognised installation techniques such as those highlighted in Annex A (Guide to the installation of optical fibre cable) of IEC 60794-1-1.

5.2 General cable description

5.2.1 Characteristics of optical fibre

Single-mode optical fibres are classified according to their operational wavelength and dispersion characteristics. The fibres covered by this specification are categorised as type B and described in IEC 60793-2-50. The fibre types featured in this specification include dispersion unshifted (B1.1, B1.3), dispersion shifted (B2), cut-off shifted (B1.2), non-zero dispersion (B4), and anticipated fibre category for wide-band non-zero dispersion-shifted (B5). (See Annex A for ITU-T cabled optical fibre references). While cut-off shifted B1.2 fibre can be used in terrestrial applications, it is mainly used in submarine applications.

5.2.2 Characteristics of optical fibre cable elements

Optical fibre cable elements such as loose buffer tubes, slotted core, fibre ribbons, fibre bundles and central/core tubes shall be suitably designed to provide adequate means of fibre location, identification, modularity, protection during cable manufacture, installation and termination. The structure of these elements and the materials used in their manufacture shall not have any long-term detrimental effects on fibre performance during the service life of the cable, splice enclosure and/or cabinet. To satisfy these functional requirements, the different elements shall comply with the requirements of IEC 60794-3 as well as those outlined in Clause 7 of this standard.

5.2.3 Characteristics of optical fibre cables

Optical fibre cables, for the intent of this document, are completed cable products as shipped by the manufacturer typically on disposable reels. Such products do not require additional assembly, or the use of additional materials or protection to meet the requirements contained herein. Some assembly or added protection is usually required only where the cables are terminated to other cables or equipment, and typically involve the use of an optical fibre closure or other hardware to protect cable splice or connectorization points. The required levels of protection for the fibre can be achieved by laying up or assembling the cable elements in association with suitable strength and/or anti buckling members. These can be either metallic in nature or non-metallic and positioned at the centre of the cable core or as peripheral members in or underneath the outer cable sheath. The cable may also contain moisture barrier tapes, metallic or non-metallic tapes, and water blocking or swellable materials.

5.2.4 Environmental and product safety requirements

IEC Guide 104 should be taken into account as far as possible. The materials of the cables in contact with the environment shall not be hazardous to the environment and personnel.

It should be noted that the cable types specified by this standard are rarely accessible once installed. Therefore, the risk of exposure to hazardous materials, if any, is mostly a concern in the handling of the cable during manufacturing and installation. Additionally, the type of outer sheath specified herein is generally considered to be non-toxic, therefore the risk to the environment or personnel is minimal once properly installed.

This standard does not address the use of all types of cable materials that may be utilized in various cable designs to support meeting the requirements unique to a specific type of special application (e.g., very high temperatures or resistance to specific chemical attack). In such cases, it is incumbent on the customer and supplier to agree on the requirements applicable to such materials and cable designs, and to determine any special handling precautions or instructions needed as a result of their use.

5.3 Optical fibre spliceability

All of the single-mode fibre types covered in this specification can readily achieve very low splice loss levels using a range of commercially available techniques.

Typical bi-directional splice losses at 1 550 nm should be below 0,1 dB, with an average of 0,05 dB for fusion splices between fibres of the same category (B1-B1, or B2-B2, etc.) performed by skilled operators according to the current best practices. Additional fibre compatibility guidelines are provided in IEC/TR 62000.

NOTE 1 Higher maximum splice losses may occur without affecting the link transmission capability.

NOTE 2 Splices of fibres of the same category but different manufacturers and/or different production processes do generally not exceed the above values.

NOTE 3 If fibres of different categories (B1-B2, B1-B4, etc.) are spliced, typically the splice loss is slightly higher than with splices between fibres of the same category.

5.4 Testing

For all test procedures, the test conditions shall be the standard atmospheric conditions ($23^{\circ}\text{C} \pm 5^{\circ}\text{C}$, and 20 % - 70 % relative humidity), unless otherwise specified. All measured and computed values are to be rounded to the number of decimal places given in the corresponding acceptance criteria for each requirement.

The parameters specified in this standard may be affected by measurement uncertainty arising either from measurement errors or calibration errors due to a lack of suitable standards. Acceptance criteria shall be interpreted with respect to this consideration. The total uncertainty of measurement for this standard shall be less than or equal to 0,05 dB for attenuation or 0,05 dB/km for attenuation coefficient. Any measured value within this range, either positive or negative, shall be considered as “no change in attenuation”.

Some of the mechanical and environmental tests in 8.5 and 8.6 can be performed on a short sample length of cable, which is still an integral part of a longer length. Thus it becomes possible to detect permanent changes in attenuation.

6 Requirements for cabled single-mode optical fibres

6.1 Fibre materials

Use optical fibre as specified in IEC 60793-2-50.

The coating surface shall be cleaned (e.g. from cable filling compounds) with only those cleaning agents recommended by the fibre manufacturer. In any case, chlorine-based cleaning agents shall not be used because of the health hazards involved.

6.2 Optical requirements

All optical fibre transmission attributes shall comply with the “transmission requirements” in IEC 60793-2-50. Attributes of the cabled fibre (attenuation, point defects, polarization mode dispersion, cable cut-off wavelength and group index) are specified in the following subclauses. Other fibre attributes in IEC 60793-2-50 are summarized in Annex B.

6.2.1 Attenuation coefficient

The cabled fibre attenuation coefficients for the fibre types covered by this specification shall meet the following requirements in Table 1, or as otherwise agreed upon between customer and supplier.

Table 1 – Attenuation coefficient

Fibre type (maximum attenuation in dB/km)						
Wavelength	B1.1	B1.2	B1.3	B2	B4	B5
1 310 nm	0,40	Not applicable	0,40	0,50	See Note 1	Not applicable
1 383 nm	Not applicable	Not applicable	0,40 (Note 2)	Not applicable	Not applicable	Not applicable
1 550 nm	0,35	0,30	0,30	0,35	0,35	0,35
1 625 nm	0,40	0,40	0,40	0,40	0,40	0,40
	See Note 3	See Note 3	See Note 3	See Note 3	See Note 3	See Note 3

NOTE 1 1 310 nm is not specified unless agreed otherwise between customer and supplier.

NOTE 2 1 383 nm attenuation is specified after hydrogen ageing as per IEC 60793-2-50.

NOTE 3 1 625 nm attenuation values are optionally specified by the customer.

Fibre type definitions are provided in IEC 60793-2-50 for single-mode fibre. For informative purposes, they are described below:

B1.1: Single-mode fibre with a zero dispersion between 1 300 nm to 1 324 nm, which is optimised for use in the 1 310 nm region and is compatible in the 1 550 nm region.

B1.2: Dispersion unshifted single-mode fibre that is optimised for 1 550 nm transmission with a cable cut-off wavelength <1 530 nm.

B1.3: Single-mode fibre similar to B1.1 but has a low loss at 1 383 nm to provide additional compatibility between 1 360 nm to 1 460 nm.

B2: Dispersion shifted single-mode fibre with a zero dispersion in the 1 525 nm to 1 575 nm region.

B4: A non-zero dispersion shifted single-mode fibre (NZDSF) that is optimised for 1 550 nm transmission with the zero dispersion outside the 1 530 nm to 1 565 nm region.

B5: A non-zero dispersion shifted single-mode fibre (NZDSF) that is optimised for 1 460 nm to 1 625 nm transmission with the zero dispersion region below 1 460 nm.

Test procedure:

Measurements shall be made in accordance with IEC 60793-1-40 at room temperature (23 °C ± 5 °C).

6.2.2 Attenuation discontinuities

Point discontinuities / local variations representing non-reflective events shall be: ≤ 0,10 dB.

Test procedure:

Measurements shall be made in accordance with IEC 60793-1-40, method C (back scattering technique).

Measurement variables:

Wavelength: 1 310 nm and/or 1 550 nm.

6.2.3 Cable cut-off wavelength

Cable cut-off wavelength λ_{cc} shall be:

$$\lambda_{cc} \leq 1\,260 \text{ nm for fibre types B1.1 and B1.3}$$

$$\lambda_{cc} \leq 1\,260 \text{ nm for fibre type B2}$$

$$\lambda_{cc} \leq 1\,450 \text{ nm for fibre type B4 and B5}$$

$$\lambda_{cc} \leq 1\,530 \text{ nm for fibre type B1.2}$$

Test procedure:

Cut-off wavelength measurements shall be made in accordance with IEC 60793-1-44.

6.2.4 Polarization mode dispersion (PMD)

Polarization mode dispersion (PMD) is usually described in terms of a differential group delay (DGD), which is the propagation time difference between the principal states of polarization of an optical signal. PMD in cabled fibres and optical components causes an optical pulse to spread in the time domain, which may impair the performance of a long length and high bit rate (e.g. 10 Gbit/s transport over 400 km) optical fibre system. For these systems, only the following evaluation may be useful.

Concerning the statistical nature of PMD in installed cable links, reference is made to Annex A of IEC 60794-3.

The appropriate test method shall be selected from IEC 60793-1-48, which also describes the statistical nature of PMD (see introduction):

- For links > 400 km, the link design value (PMD_Q) shall be less than or equal to $0,20 \text{ ps/km}^{0,5}$. Note, from ITU-T Recommendation G.652 Table I.2/, this maximum link design value should allow the possibility of 3 000 km links at 10 Gbit/s and 80 km (to 200 km) at 40 Gbit/s.
- For links ≤ 400 km, the link design value (PMD_Q) shall be less than or equal to $0,50 \text{ ps/km}^{0,5}$. Note from ITU-T Recommendation G.652 Table I.2 /, this maximum link design value should allow the possibility of 400 km links at 10 Gbit/s.

6.2.5 Group index

This parameter is used to determine the fibre length within cables or cable lengths (taking construction into account) using IEC 60793-1-22, method B. The group index shall be given at 1 310 nm for B1.1, B1.3, and B2 fibres and at 1 550 nm for all fibres. The group index shall be given at 1 625 nm for any cable specified for operation at 1 625 nm.

7 Requirements for cable elements

7.1 Element design

An optical fibre cable element is an assembly of optical fibres arranged in such a way to maintain its structure both inside the cable and once the sheath is removed.

The design intent of a fibre optic cable element is to organize fibres so as to facilitate fibre identification and to improve handling.