

INTERNATIONAL STANDARD

IEC
62329-2

First edition
2006-07

Heat-shrinkable moulded shapes –

**Part 2:
Methods of test**

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 62329-2:2006](#)

<https://standards.iteh.ai/catalog/standards/iec/992c9ab6-7746-4cfd-b304-41080503cabf/iec-62329-2-2006>



Reference number
IEC 62329-2:2006(E)

Publication numbering

As from 1 January 1997 all IEC publications are issued with a designation in the 60000 series. For example, IEC 34-1 is now referred to as IEC 60034-1.

Consolidated editions

The IEC is now publishing consolidated versions of its publications. For example, edition numbers 1.0, 1.1 and 1.2 refer, respectively, to the base publication, the base publication incorporating amendment 1 and the base publication incorporating amendments 1 and 2.

Further information on IEC publications

The technical content of IEC publications is kept under constant review by the IEC, thus ensuring that the content reflects current technology. Information relating to this publication, including its validity, is available in the IEC Catalogue of publications (see below) in addition to new editions, amendments and corrigenda. Information on the subjects under consideration and work in progress undertaken by the technical committee which has prepared this publication, as well as the list of publications issued, is also available from the following:

- **IEC Web Site** (www.iec.ch)

- **Catalogue of IEC publications**

The on-line catalogue on the IEC web site (www.iec.ch/searchpub) enables you to search by a variety of criteria including text searches, technical committees and date of publication. On-line information is also available on recently issued publications, withdrawn and replaced publications, as well as corrigenda.

- **IEC Just Published**

This summary of recently issued publications (www.iec.ch/online_news/justpub) is also available by email. Please contact the Customer Service Centre (see below) for further information.

- **Customer Service Centre**

If you have any questions regarding this publication or need further assistance, please contact the Customer Service Centre:

Email: custserv@iec.ch
Tel: +41 22 919 02 11
Fax: +41 22 919 03 00

INTERNATIONAL STANDARD

IEC 62329-2

First edition
2006-07

Heat-shrinkable moulded shapes –

Part 2: Methods of test

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 62329-2:2006](https://standards.iteh.ai/catalog/standards/iec/992c9ab6-7746-4cfd-b304-41080503cabf/iec-62329-2-2006)

<https://standards.iteh.ai/catalog/standards/iec/992c9ab6-7746-4cfd-b304-41080503cabf/iec-62329-2-2006>

© IEC 2006 — Copyright - all rights reserved

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Electrotechnical Commission, 3, rue de Varembé, PO Box 131, CH-1211 Geneva 20, Switzerland
Telephone: +41 22 919 02 11 Telefax: +41 22 919 03 00 E-mail: inmail@iec.ch Web: www.iec.ch



Commission Electrotechnique Internationale
International Electrotechnical Commission
Международная Электротехническая Комиссия

PRICE CODE

X

For price, see current catalogue

CONTENTS

FOREWORD.....	6
INTRODUCTION.....	8
1 Scope.....	9
2 Normative references.....	9
3 Test conditions.....	10
4 Standard test specimens.....	11
4.1 Moulded shape material specimens.....	11
4.2 Moulded shape compatibility specimens.....	11
5 Dimensions.....	11
5.1 Number of test specimens.....	11
5.2 Procedure.....	11
5.3 Result.....	11
6 Density.....	11
6.1 Number of test specimens.....	11
6.2 Procedure.....	11
6.3 Report.....	11
6.4 Result.....	11
7 Heat shock.....	12
7.1 Number of test specimens.....	12
7.2 Form of test specimens.....	12
7.3 Procedure.....	12
7.4 Report.....	12
7.5 Result.....	12
8 Bending at low temperature.....	12
8.1 Number and form of test specimens.....	12
8.2 Procedure.....	12
8.3 Result.....	12
9 Dimensional stability on storage.....	12
9.1 Number of test specimens.....	12
9.2 Procedure.....	13
9.3 Result.....	13
10 Tensile strength and elongation at break.....	13
10.1 Number and form of test specimens.....	13
10.2 Conditioning.....	13
10.3 Test temperature.....	13
10.4 Procedure.....	13
10.5 Calculations.....	14
10.6 14	
10.7 Result.....	14
11 Secant modulus at 2 % elongation.....	14
11.1 Number and form of test specimens.....	14
11.2 Procedure.....	14
11.3 Calculation.....	15
11.4 Report.....	15
11.5 Result.....	15

<https://standards.iteh.ai/> IEC 62329-2:2006 <https://standards.iteh.ai/catalog/standards/iec/62329-2-2006>

12	Electric strength	15
12.1	Number and form of test specimens	15
12.2	Conditioning	15
12.3	Electrodes	15
12.4	Procedure	15
12.5	Result	15
12.6	Result	16
13	Volume resistivity after damp heat	16
13.1	Number and form of test specimens	16
13.2	Electrodes	16
13.3	Procedure	16
13.4	Result	16
14	Permittivity and dissipation factor	16
14.1	Number and form of test specimens	16
14.2	Electrodes	16
14.3	Procedure	16
14.4	Calculation	16
14.5	Result	16
15	Resistance to tracking	17
15.1	Report	17
15.2	Result	17
16	Flammability	17
16.1	Number and form of test specimens	17
16.2	Procedure	17
16.3	Result	17
17	Oxygen index	17
17.1	Oxygen index at ambient temperature	17
17.2	Oxygen index at elevated temperature	17
18	Copper corrosion (presence of corrosive volatiles)	17
18.1	Principle	17
18.2	Apparatus	18
18.3	Number and form of test specimens	18
18.4	Procedure	18
18.5	Report	18
18.6	Result	18
19	Colour fastness to light	19
19.1	Principle	19
19.2	Test specimen	19
19.3	Procedure	19
19.4	Result	19
20	Resistance to selected fluids	19
20.1	Principle	19
20.2	Choice of fluid	19
20.3	Methods of assessment	19
20.4	Number and form of test specimens	20
20.5	Procedure	20
20.6	Result	20

21	Long term heat ageing (3000 h).....	20
21.1	Number and form of test specimens	20
21.2	Procedure	20
21.3	Report	21
21.4	Result	21
22	Mass	21
22.1	Number of test specimens	21
22.2	Procedure	21
22.3	Result	21
23	Heat ageing.....	21
23.1	Number and form of test specimens	21
23.2	Procedure	21
24	Water absorption	21
25	Colour stability to heat.....	21
25.1	Number of test specimens	21
25.2	Form of test specimens	21
25.3	Procedure	22
25.4	Report	22
25.5	Result	22
26	Smoke index.....	22
26.1	Definitions	22
26.2	Principle	22
26.3	Apparatus.....	22
26.4	Number and form of test specimen	23
26.5	Conditioning	23
26.6	Mounting of test pieces	23
26.7	Safety of operations	23
26.8	Procedure	23
26.9	Calculation of results	24
27	Toxicity index	26
27.1	Definition.....	26
27.2	Principle	27
27.3	Apparatus.....	27
27.4	Conditioning	28
27.5	Safety of operations	28
27.6	Test procedure	28
27.7	Calculation of toxicity index	30
27.8	Toxic constituents	30
27.9	Values for C_f	31
27.10	Result and report.....	31
28	Halogen content	31
28.1	Method for the determination of low levels of chlorine and/or bromine and/or iodine	31
28.2	Determination of low levels of fluorine	32
29	Acid gas generation.....	33
30	Resistance to mould growth.....	33

iTeh Standards

(<https://standards.itih.ai>)

Document Preview

IEC 62329-2:2006

<https://standards.itih.ai/standards/iec/992c9ab0-7740-4c1d-b304-41080505cab/iec-62329-2-2006>

31 Compatibility	34
31.1 Dynamic shear at room temperature	34
31.2 Static load	34
31.3 Fluid resistance	35
31.4 Thermal ageing	36
31.5 Peel adhesion	36
31.6 Altitude immersion	37
 Bibliography	 47
 Figure 1 – Dumb-bell specimen for tensile strength test	 39
Figure 2 – Schematic details of burner for smoke index test	40
Figure 3 – Compatibility test specimen	41
Figure 4 – Aluminium test adaptor	42
Figure 5 – Tensile test fixture for adaptor	42
Figure 6 – Test arrangement for dynamic shear	43
Figure 7 – Test arrangement for static load	44
Figure 8 – Test assembly for peel adhesion	44
Figure 9 – Test arrangement for heatshrink sleeved cable to moulded shape	45
Figure 10 – Test arrangement for aluminium adaptor to moulded shape	46

<https://standards.iteh.ai>
Document Preview

[IEC 62329-2:2006](https://standards.iteh.ai/catalog/standards/iec/992c9ab6-7746-4cfd-b304-41080503cabf/iec-62329-2-2006)

<https://standards.iteh.ai/catalog/standards/iec/992c9ab6-7746-4cfd-b304-41080503cabf/iec-62329-2-2006>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

HEAT-SHRINKABLE MOULDED SHAPES –

Part 2: Methods of test

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62329-2 has been prepared by IEC technical committee 15: Standards on specifications for electrical insulating materials.

The text of this standard is based on the following documents:

FDIS	Report on voting
15/316/FDIS	15/338/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 62329-2:2006](#)

<https://standards.iteh.ai/catalog/standards/iec/992c9ab6-7746-4cfd-b304-41080503cabf/iec-62329-2-2006>

INTRODUCTION

This International Standard is one of a series which deals with heat-shrinkable moulded shapes. The series consists of the following parts:

- Part 1: Definitions and general requirements (IEC 62329-1)
- Part 2: Methods of test (IEC 62329-2)
- Part 3: Specification requirements for shape dimensions, material requirements and compatibility performance (IEC 62329-3) (in consideration)

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[IEC 62329-2:2006](#)

<https://standards.itih.ai/catalog/standards/iec/992c9ab6-7746-4cfd-b304-41080503cabf/iec-62329-2-2006>

HEAT-SHRINKABLE MOULDED SHAPES –

Part 2: Methods of test

1 Scope

This part of IEC 62329 gives methods of test for heat-shrinkable moulded shapes in a range of configurations and materials suitable for insulation, environmental sealing, mechanical protection and strain relief for connector/cable terminations and multi-way transitions.

The tests specified are designed to control the quality of the moulded shapes but it is recognized that they do not completely establish the suitability of moulded shapes for impregnation or encapsulation processes or other specialized applications. Where necessary, the test methods in this Part will need to be supplemented by appropriate impregnation or compatibility tests to suit the individual circumstances.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60093:1980, *Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials*

IEC 60212:1971, *Standard conditions for use prior to and during the testing of solid electrical insulating materials*

IEC 60216-4-1:2006, *Electrical insulating materials – Thermal endurance properties – Part 4-1: Ageing ovens – Single-chamber ovens*

IEC 60216-4-2:2000, *Electrical insulating materials – Thermal endurance properties – Part 4-2: Ageing ovens – Precision ovens for use up to 300 °C*

IEC 60243-1:1998, *Electric strength of insulating materials – Test methods – Part 1: Tests at power frequencies*

IEC 60250:1969, *Recommended methods for the determination of the permittivity and dielectric dissipation factor of electrical insulating materials at power, audio and radio frequencies including metre wavelengths*

IEC 60587:1984, *Test methods for evaluating resistance to tracking and erosion of electrical insulating materials used under severe ambient conditions*

IEC 60695-6-30:1996, *Fire hazard testing – Part 6: Guidance and test methods on the assessment of obscuration hazards of vision caused by smoke opacity from electrotechnical products involved in fires – Section 30: Small scale static method. Determination of smoke opacity. Description of the apparatus*

IEC 60695-11-10:1999, *Fire hazard testing – Part 11-10: Test flames – 50 W horizontal and vertical flame test methods*

IEC 60754-1:1994, *Test on gases evolved during combustion of materials from cables – Part 1: Determination of the amount of halogen acid gas*

IEC 60754-2:1991, *Test on gases evolved during combustion of materials from cables – Part 2: Determination of degree of acidity of gases evolved during the combustion of materials taken from electric cables by measuring pH and conductivity*

IEC 62329-1:2005, *Heat shrinkable moulded shapes – Part 1: Definitions and general requirements*

ISO 62:1999, *Plastics – Determination of water absorption*

ISO 105-A02:1993, *Textiles – Tests for colour fastness – Part A02: Grey scale for assessing changes in colour*

ISO 105-B01:1994, *Textiles – Tests for colour fastness – Part B01: Colour fastness to light: Daylight*

ISO 846:1997, *Plastics – Evaluation of the action of micro-organisms*

ISO 3261:1975, *Fire tests – Vocabulary*¹

ISO 4589-2:1996, *Plastics – Determination of burning behaviour by oxygen index – Part 2: Ambient-temperature test*

ISO 4589-3:1996, *Plastics – Determination of burning behaviour by oxygen index – Part 3: Elevated-temperature test*

3 Test conditions

Unless otherwise specified, all tests shall be made under standard ambient conditions according to IEC 60212; i.e. at a temperature between 15 °C and 35 °C and at ambient relative humidity.

In cases of dispute, the tests shall be carried out at a temperature of 23 °C ± 2 K and at (50 ± 5) % relative humidity.

When heating at elevated temperature is specified for a test procedure, the specimen shall be maintained for the prescribed period in a uniformly heated oven complying with either IEC 60216-4-1 or IEC 60216-4-2.

Where a test at low temperature is specified, the specification sheets of IEC 62329-3 may require it to be carried out at t °C or lower, where t is the requested temperature. In such cases the operator may carry out the test at the specified temperature or any lower temperature which is convenient. If, however, at a temperature below that specified, the specimen fails to meet the requirements, the test shall be repeated at the specified temperature, subject to a tolerance of ±3 K as specified in IEC 60212. If the specimen then passes, it shall be considered to have met the requirements.

¹ This standard has been withdrawn.

4 Standard test specimens

4.1 Moulded shape material specimens

Moulded shape material specimens shall be prepared from $(2 \pm 0,15)$ mm thick sheets, unless otherwise specified, and shall be prepared from the same heat-shrinkable material that is to be used to manufacture the heat-shrinkable moulded shapes. The dimensions of the sheet shall be sufficient to enable any of the relevant tests to be performed.

NOTE A suitable size has been found to be 150 mm x 150 mm.

4.2 Moulded shape compatibility specimens

See IEC 62329-1, Subclause 4.2, and Clause 31 of this standard.

5 Dimensions

5.1 Number of test specimens

Three specimens of each size and style shall be tested.

5.2 Procedure

Measure the moulded shapes in the as supplied condition and after unrestricted shrinkage as specified in IEC 62329-3. Carry out unrestricted shrinkage by conditioning in an oven for the time and temperature specified in IEC 62329-3. Remove the shapes from the oven and allow to cool naturally to the ambient temperature specified in Clause 3. The method of measurement can be mechanical, or optical. Wall thickness shall be measured to an accuracy of $\pm 0,05$ mm and internal diameter to an accuracy of $\pm 0,25$ mm. In the case of dispute an optical method shall be used.

5.3 Result

Report all measured values as the result.

6 Density

6.1 Number of test specimens

At least three specimens shall be tested, cut from a test sheet in accordance with 4.1.

6.2 Procedure

Any method for the determination of the density may be used which can ensure an accuracy of $\pm 0,01$ g/cm³.

6.3 Report

Record the method selected for the determination and report all measured values for density

6.4 Result

The result is the mean, unless specified otherwise in the specification sheets of IEC 62329-3.

7 Heat shock

7.1 Number of test specimens

Three specimens shall be tested.

7.2 Form of test specimens

Cut three specimens in accordance with Clause 10, from a test sheet in accordance with 4.1.

7.3 Procedure

The specimens shall be suspended vertically in an oven for $4\text{ h} \pm 10\text{ min}$ at the temperature specified in IEC 62329-3.

The specimens shall be removed and allowed to cool to room temperature. They shall then be visually examined for any signs of dripping, cracking or flowing. In addition, when so specified in IEC 62329-3 the specimens shall be tested for tensile strength and elongation at break.

7.4 Report

Report all results from the visual examination. Report all calculated values.

7.5 Result

The results for each property is the central value unless otherwise specified in the specification sheets of IEC 62329-3.

8 Bending at low temperature

8.1 Number and form of test specimens

http://standards.iteh.ai/ IEC 62329-2:2006 Cut three specimens from a test sheet in accordance with 4.1 approximately $150\text{ mm} \times 6\text{ mm}$.2006

8.2 Procedure

The specimens shall be suspended for $4\text{ h} \pm 10\text{ min}$ in a chamber maintained at the temperature specified in IEC 62329-3. While still at that temperature, they shall be wound without jerking for one complete turn in a close helix round a mandrel also at the same temperature and having a diameter specified in IEC 62329-3. The time to achieve one complete turn shall not be greater than 5 s. The specimens shall then be allowed to return to room temperature.

The specimens shall then be visually examined without magnification while still on the mandrel for signs of cracking.

8.3 Result

Report whether there is any cracking.

9 Dimensional stability on storage

9.1 Number of test specimens

Three shapes shall be tested.