

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE



**Measurement of smoke density of cables burning under defined conditions –  
Part 2: Test procedure and requirements**

**Mesure de la densité de fumées dégagées par des câbles brûlant dans des  
conditions définies –  
Partie 2: Procédure d'essai et exigences**

[IEC 61034-2:2005](https://standards.iteh.ai/standards/iec/4e7d60d6-6ac5-4399-8a0f-7f34d24d5167/iec-61034-2-2005)

<https://standards.iteh.ai/catalog/standards/iec/4e7d60d6-6ac5-4399-8a0f-7f34d24d5167/iec-61034-2-2005>



## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2013 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
Fax: +41 22 919 03 00  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

#### Useful links:

IEC publications search - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [csc@iec.ch](mailto:csc@iec.ch).

---

### A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

### A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

#### Liens utiles:

Recherche de publications CEI - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

La recherche avancée vous permet de trouver des publications CEI en utilisant différents critères (numéro de référence, texte, comité d'études,...).

Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Just Published CEI - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Restez informé sur les nouvelles publications de la CEI. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - [www.electropedia.org](http://www.electropedia.org)

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (VEI) en ligne.

Service Clients - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: [csc@iec.ch](mailto:csc@iec.ch).

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE



**Measurement of smoke density of cables burning under defined conditions –  
Part 2: Test procedure and requirements**

**Mesure de la densité de fumées dégagées par des câbles brûlant dans des  
conditions définies –  
Partie 2: Procédure d'essai et exigences**

[IEC 61034-2:2005](https://standards.iteh.ai/catalog/standards/iec/4e7d60d6-6ac5-4399-8a0f-7b34d24d5167/iec-61034-2-2005)

<https://standards.iteh.ai/catalog/standards/iec/4e7d60d6-6ac5-4399-8a0f-7b34d24d5167/iec-61034-2-2005>

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

ICS 13.220.40; 29.020; 29.060.20

ISBN 978-2-8322-0904-2

**Warning! Make sure that you obtained this publication from an authorized distributor.  
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

## CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions .....	6
4 Test apparatus .....	6
5 Test assembly .....	6
5.1 Test sample.....	6
5.2 Cable test piece selection and test sample assembly .....	7
5.3 Positioning of test sample .....	8
6 Test procedure .....	8
7 Evaluation of test results.....	9
8 Retest procedure .....	9
9 Test report.....	9
Annex A (informative) Guidance on the principles and use of smoke measurements .....	13
Annex B (informative) Recommended performance requirement.....	15
Bibliography.....	16
Figure 1 – Method of binding for bundles of test pieces .....	10
Figure 2 – Method of support of test sample .....	11
Figure 3 – Method of assembly of flat horizontal unit of non-circular cables.....	12

iteh Standards  
(<https://standards.iteh.ai>)  
Document Preview

<https://standards.iteh.ai/catalog/standards/iec/40740000-0ac5-4599-8a0f-1e4d24d5107/iec-61034-2-2005>

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

**MEASUREMENT OF SMOKE DENSITY OF CABLES  
BURNING UNDER DEFINED CONDITIONS –****Part 2: Test procedure and requirements**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

**This consolidated version of IEC 61034-2 consists of the third edition (2005) [documents 20/755/FDIS and 20/767/RVD], its corrigendum 1 (September 2006) and its amendment 1 (2013) [documents 20/1429/FDIS and 20/1444/RVD]. It bears the edition number 3.1.**

**The technical content is therefore identical to the base edition and its amendment and has been prepared for user convenience. A vertical line in the margin shows where the base publication has been modified by amendment 1. Additions and deletions are displayed in red, with deletions being struck through.**

International Standard IEC 61034-2 has been prepared by IEC technical committee 20: Electric cables.

The principal changes with respect to the previous edition are as follows:

- a) inclusion of cables down to 1 mm diameter;
- b) inclusion of non-circular cables;
- c) addition of guidance on testing cables above 80 mm diameter;
- d) delineation of elements of the test report;
- e) addition of guidance on the calculation for other parameters for fire safety engineering purposes;
- f) removal of minor differences with equivalent CENELEC work to allow parallel voting with that body.

It has the status of a group safety publication in accordance with IEC Guide 104.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

IEC 61034 consists of the following parts, under the general title *Measurement of smoke density of cables burning under defined conditions*,

Part 1 : Test apparatus

Part 2 : Test procedure and requirements

The committee has decided that the contents of the base publication and its amendment will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

[IEC 61034-2:2005](https://standards.itec.ai/catalog/standards/iec/4e7d60d6-6ac5-4399-8a0f-7b34d24d5167/iec-61034-2-2005)

<https://standards.itec.ai/catalog/standards/iec/4e7d60d6-6ac5-4399-8a0f-7b34d24d5167/iec-61034-2-2005>

**IMPORTANT – The “colour inside” logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this publication using a colour printer.**

## INTRODUCTION

The measurement of smoke density is an important aspect in the evaluation of the burning performance of cables as it is related to the evacuation of persons and accessibility for firefighting.

IEC 61034 is published in two parts, which together specify a method of test for measurement of smoke density of cables burning under defined conditions. Users of this test are reminded that the configurations of cable in the test (i.e. as test pieces or bundles of test pieces) may not represent actual installation conditions.

Part 1 gives details of the test apparatus and verification procedure to be used for the measurement of smoke density of the products of combustion of cables burnt under defined conditions. It includes details of a test enclosure of 27m<sup>3</sup> volume, a photometric system for light measurement, the fire source, smoke mixing method and a qualification procedure.

This Part 2 gives the test procedure, together with an informative annex giving recommended requirements for compliance where no specified requirement is given in the particular cable standard or specification. The measurement of smoke density is expressed in terms of minimum levels of light transmittance, and Annex A explains possibilities for using these values for fire safety engineering calculations.

**iTeh Standards**  
**(<https://standards.itih.ai>)**  
**Document Preview**

[IEC 61034-2:2005](https://standards.itih.ai/catalog/standards/iec/4e7d60d6-6ac5-4399-8a0f-7b34d24d5167/iec-61034-2-2005)

<https://standards.itih.ai/catalog/standards/iec/4e7d60d6-6ac5-4399-8a0f-7b34d24d5167/iec-61034-2-2005>

# MEASUREMENT OF SMOKE DENSITY OF CABLES BURNING UNDER DEFINED CONDITIONS –

## Part 2: Test procedure and requirements

### 1 Scope

This part of IEC 61034 provides details of the test procedure to be employed for the measurement of the density of smoke emitted from cables burning under defined conditions. It describes the means of preparing and assembling cables for test, the method of burning the cables, and gives recommended requirements for evaluating test results.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60695-4, *Fire hazard testing – Part 4: Terminology concerning fire tests*

IEC 60811-203, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 203: General tests – Measurement of overall dimensions*

IEC 61034-1, *Measurement of smoke density of cables burning under defined conditions – Part 1: Test apparatus*

IEC Guide 104:1997, *The preparation of safety publications and the use of basic safety publications and group safety publications*

ISO/IEC 13943:2000, *Fire safety – Vocabulary*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions in IEC 60695-4 apply, or if a term is not defined in IEC 60695-4 then the definition in ISO/IEC 13943 applies.

### 4 Test apparatus

The test procedure defined in this Part 2 of IEC 61034 shall be carried out using the test apparatus, i.e. test enclosure, photometric system and standard fire source, given in IEC 61034-1.

### 5 Test assembly

#### 5.1 Test sample

The test sample shall consist of one or more test pieces of cable, each  $1,00 \text{ m} \pm 0,05 \text{ m}$  long, which shall be carefully straightened and then conditioned for at least 16 h at  $23 \text{ °C} \pm 5 \text{ °C}$ .



## 5.2 Cable test piece selection and test sample assembly

### 5.2.1 Selection of number of test pieces

#### 5.2.1.0 General

The cable diameter shall be measured using the method given in IEC 60811-203. The measurement shall be made at each of three places, separated by at least 1 m.

The average of the three values obtained shall be rounded to obtain the overall diameter. If the calculation gives 5 or more for the second decimal figure, raise the first to the next number; thus, for example, 5,75 is rounded to 5,8 and 5,74 to 5,7.

The overall diameter obtained shall be used for the selection of the number of test pieces.

#### 5.2.1.1 Cables with an overall diameter ~~of greater than 5,0 mm or greater~~

For cables with an overall diameter ~~of greater than 5,0 mm or greater~~, the number of test pieces required to make up the test sample shall be in accordance with Table 1.

**Table 1 – Number of test pieces**

Overall diameter of the cable ( $D$ ) mm	Number of test pieces
$D > 40,0$	1
$20,0 < D \leq 40,0$	2
$10,0 < D \leq 20,0$	3
$5,0 < D \leq 10,0$	$N_1$
where $N_1 = \frac{45}{D} \text{ test pieces}$ The value of $N_1$ shall be rounded downwards to the integer to give the number of test pieces.	

#### 5.2.1.2 Cables with an overall diameter of less than **or equal to 5,0 mm**, but not less than **1,0 mm**

For cables with an overall diameter of less than **or equal to 5,0 mm**, but not less than **1,0 mm**, seven test pieces shall be formed into a bundle. The number of bundles ( $N_2$ ) required to make up the test sample shall be calculated according to the following formula:

$$N_2 = \frac{45}{3D}$$

The value of  $N_2$  shall be rounded downwards to the integer to give the number of bundles.

For each bundle, the seven test pieces shall be twisted together with a lay between  $20 D$  and  $30 D$  and bound with two turns of approximately 0,5 mm diameter wire in the centre and at every 100 mm each side from the centre (see Figure 1).

#### 5.2.1.3 Non-circular cables

The test sample for non-circular cables shall be a flat horizontal unit in which the minor axis of each test piece is presented to the fire source. ~~The following criteria for determination of the number of test pieces required to make up the test sample shall apply:~~

- ~~a) the nominal minor axis shall be used as the diameter ( $D$ ) for cables in which the major to minor axis ratio is equal to or less than 3;~~
- ~~b) half the circumference of the cable shall be used to calculate an equivalent diameter for cables in which the major to minor axis ratio lies between 3 and 5;~~
- ~~c) for cables in which the major to minor axis ratio exceeds 5, or the dimension of the minor axis is less than 2,0 mm, the formation of the assembly remains under consideration~~

The unit shall be bound with two turns of approximately 0,5 mm wire in the centre and at every 100 mm each side from the centre (see Figure 3). The number of test pieces required to make up the test sample shall be in accordance with Table 1, except that in the case of cables in which the overall diameter is less than or equal to 5,0 mm, the test pieces shall not be bundled and the number of test pieces in the flat horizontal unit calculated according to the formula  $N_1 = 45/D$ .

The following criteria for determination of the overall diameter ( $D$ ) to be used in the determination of the number of test pieces shall apply for cables in which the minor axis is 2,0 mm or greater:

- a) for cables in which the major to minor axis ratio is equal to or less than 3, the nominal minor axis shall be used as the overall diameter ( $D$ );
- b) for cables in which the major to minor axis ratio lies between 3 and 16, the overall diameter ( $D$ ) shall be taken as half the circumference of the cable divided by 3,14 ( $\pi$ ).

For cables in which the minor axis is less than 2,0 mm or the major to minor axis ratio exceeds 16, the test criteria shall be given in the product standard or, if not, agreed between manufacturer and purchaser.

### 5.2.2 Mounting of test sample

The test sample shall remain in situ during the test as follows:

- individual test pieces or bundles of test pieces shall be bound together at the ends, and at 300 mm from each end, at which place they shall be clamped to the support by means of wire binders.

NOTE Depending upon construction, test samples prepared from small cables or flexible cables may be subject to movement during the test. In these cases, it is also recommended that the test pieces or bundles are bound with two turns of approximately 0,5 mm diameter wire in the centre and at every 100 mm each side from the centre. Alternatively, the test pieces or bundles may be tensioned at one or both ends by means of an appropriate device, for example a spring or a weight.

### 5.3 Positioning of test sample

The tray containing the alcohol shall be supported above the ground surface to permit air circulation around and beneath the tray. The individual test pieces or the bundles of test pieces shall be laid touching in a horizontal position and centred above the tray so that the distance between the underneath of the test sample and the bottom of the tray is  $150 \text{ mm} \pm 5 \text{ mm}$  (see Figure 2).

## 6 Test procedure

NOTE Before each test, it may be necessary to clean the windows of the photometric system to regain 100 % light transmission after stabilization of the voltage (see also Clause A.2 of IEC 61034-1).

**6.1** Immediately before commencing a test, the temperature within the cube shall be in the range of  $25 \text{ °C} \pm 5 \text{ °C}$  when measured at the internal door surface at a height of 1,5 m to 2,0 m and a minimum of 0,2 m from the walls.

**6.2** Before a test, carry out one blank test as defined in Clause 8 of IEC 61034-1 to preheat the test enclosure if necessary.

**6.3** For the test, the fire source shall be as defined in Clause 6 of IEC 61034-1.

**6.4** With the test sample supported above the tray, start the air circulation and ignite the alcohol. Make sure that all persons leave the cube immediately, and that the door is closed.

**6.5** The test is considered as ended when there is no decrease in light transmittance for 5 min after the fire source has extinguished or when the test duration reaches 40 min.

**6.6** Record the minimum light transmittance. The light transmittance  $I_t$  shall be calculated as follows:

$$I_t = I_t/I_0$$

where

$I_t$  is the intensity of transmitted light;

$I_0$  is the intensity of incident light.

$I_t$  shall be expressed as a percentage.

NOTE If it is required to use information on smoke density for wider hazard evaluation or fire safety engineering purposes, it may be necessary to calculate other parameters. Guidance on such calculations is given in Annex A.

**6.7** Extract the combustion products at the end of each test.

## 7 Evaluation of test results

The requirement shall be given in the relevant cable specification.

For cables up to and including 80 mm overall diameter, the recorded minimum light transmittance (6.6) shall be taken as the cable light transmittance.

For cables above 80 mm overall diameter, the recorded minimum light transmittance (6.6) shall be normalized by multiplying by a factor of  $D/80$  (where  $D$  is the actual diameter in millimetres of the cable under test) and the resulting value shall be taken ~~as the cable light transmittance for determining compliance.~~

NOTE If no value is given in the relevant cable specification it is recommended that the recommendation in Annex B be adopted as a minimum.

## 8 Retest procedure

~~In case of dispute, a further two tests shall be undertaken using similar cables.~~

~~Both of these test results shall comply with Clause 7.~~

In the event of a failure, as judged by the requirements of the relevant standard, two further test samples, taken from the same cable length shall be tested. If both comply, the test shall be deemed successful.

## 9 Test report

The test report shall include the following information: