
Preskusne metode tovara na paleti - 1. del: Ugotavljanje trdnosti, povezovanja paletnih žbljev in drugih povezovalcev ter trakov (ISO 12777-1:1994)

Methods of test for pallet joints - Part 1: Determination of bending resistance of pallet nails, other dowel-type fasteners and staples (ISO 12777-1:1994)

Prüfungen von Verbindungen an Paletten - Teil 1: Bestimmung der Biegefestigkeit von Palettenägeln, Klammern und anderen dübelartigen Verbindungselementen (ISO 12777-1:1994)

(standards.iteh.ai)

Méthodes d'essai des assemblages de palettes - Partie 1: Détermination de la résistance à la flexion des clous et autres éléments de fixation de type cheville, et des clous cavaliers (ISO 12777-1:1994)

Ta slovenski standard je istoveten z: EN ISO 12777-1:1996

ICS:

21.060.50	Zatiči, žblji	Pins, nails
55.180.20	Večnamenske palete	General purpose pallets

SIST EN ISO 12777-1:1998**en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 12777-1:1998

<https://standards.iteh.ai/catalog/standards/sist/e40a3245-dbd4-4bd3-a038-8c70d80a13e9/sist-en-iso-12777-1-1998>

EUROPEAN STANDARD

EN ISO 12777-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 1996

ICS 55.180.20

Descriptors: See ISO document

English version

**Methods of test for pallet joints - Part 1:
Determination of bending resistance of pallet
nails, other dowel-type fasteners and staples
(ISO 12777-1:1994)**

Méthodes d'essai des assemblages de palettes
Partie 1: Détermination de la résistance à la
flexion des clous et autres éléments de
fixation de type cheville, et des clous
cavaliers (ISO 12777-1:1994)

Prüfungen von Verbindungen an Paletten - Teil
1: Bestimmung der Biegefestigkeit von
Palettenägeln, Klammern und anderen
dübelartigen Verbindungselementen
(ISO 12777-1:1994)

[SIST EN ISO 12777-1:1998](https://standards.iteh.ai/catalog/standards/sist/e40a3245-dbd4-4bd3-a038-8c70d80a13e9/sist-en-iso-12777-1-1998)

<https://standards.iteh.ai/catalog/standards/sist/e40a3245-dbd4-4bd3-a038-8c70d80a13e9/sist-en-iso-12777-1-1998>

This European Standard was approved by CEN on 1996-04-11. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of the International Standard from Technical Committee ISO/TC 51 "Pallets for unit load method of materials handling" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 261 "Packaging", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 1997, and conflicting national standards shall be withdrawn at the latest by February 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 12777-1:1994 has been approved by CEN as a European Standard without any modification.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 12777-1:1998](https://standards.iteh.ai/catalog/standards/sist/e40a3245-dbd4-4bd3-a038-8c70d80a13e9/sist-en-iso-12777-1-1998)

<https://standards.iteh.ai/catalog/standards/sist/e40a3245-dbd4-4bd3-a038-8c70d80a13e9/sist-en-iso-12777-1-1998>

INTERNATIONAL STANDARD

ISO
12777-1

First edition
1994-12-15

Methods of test for pallet joints —

Part 1:

Determination of bending resistance of pallet
nails, other dowel-type fasteners and staples

(standards.iteh.ai)

Méthodes d'essai des assemblages de palettes —

*Partie 1: Détermination de la résistance à la flexion des clous et autres
éléments de fixation de type cheville, et des clous cavaliers*



Reference number
ISO 12777-1:1994(E)

ISO 12777-1:1994(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 12777-1 was prepared by Technical Committee ISO/TC 51, *Pallets for unit load method of materials handling*.

ISO 12777 consists of the following parts, under the general title *Methods of test for pallet joints*:

- *Part 1: Determination of bending resistance of pallet nails, other dowel-type fasteners and staples*
- *Part 2: Testing of nails and staples for withdrawal and head pull-through resistance*
- *Part 3: Determination of bending strength*

© ISO 1994

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

In 1988 ISO/TC 51 requested ISO/TC 51/WG 2 to develop standard test methods for pallet joints. During the early meetings of WG 2 it became evident that the lack of International Standards on nail testing meant that fasteners (essential elements of pallet joints) could not be characterized sufficiently to enable worthwhile progress on full-joint testing. Although there were existing, or partially developed, nail testing principles, WG 2 considered that, in a practical situation where for quality control purposes or comparisons of nail quality reasonably accurate and rapid nail strength data were required, one, or both, of the two existing commercial nail testers was (were) better suited to the needs of pallet makers, pallet test laboratories and nail manufacturers.

Preliminary work by WG 2 led the manufacturers of both machines to make design modifications to improve accuracy. In November 1990, WG 2 appointed an *ad hoc* team of four members to evaluate the machines. The evaluation, carried out with the cooperation of the manufacturers/agents of each nail test machine, demonstrated that the technical requirements for nail test machines/principles were met by both machines.

<https://standards.iteh.ai/catalog/standards/sist/e40a3245-dbd4-4bd3-a038-8c710c09/correlat-12777-1-1998>

The good correlation between the ultimate tensile strength of steel and the results of nail bending tests disappears once threads are rolled on to nails. Nail bending resistance is critical to the performance of a nail and, for this reason, the bending resistance of finished nails is the recommended method for specifying pallet nails and staples.

Users should not automatically specify the highest grade of nail in a pallet design, any more than they would automatically specify the strongest available wood species. In general, it is only to improve the performance of a particular joint that is proving a weak link in a pallet design, or to build in a longer life, etc., that nail upgrading would take place. There are also many instances where a nail with a lower performance would be the best choice, such as in a pallet-mat subassembly constructed with clinched nails.

iTeh STANDARD PREVIEW

This page intentionally left blank
(standards.iteh.ai)

SIST EN ISO 12777-1:1998

<https://standards.iteh.ai/catalog/standards/sist/e40a3245-dbd4-4bd3-a038-8c70d80a13e9/sist-en-iso-12777-1-1998>

Methods of test for pallet joints —

Part 1:

Determination of bending resistance of pallet nails, other dowel-type fasteners and staples

1 Scope

This part of ISO 12777 describes test methods for the determination of the bending resistance of pallet nails, staples and other dowel-type fasteners.

It includes tests for the

- a) ultimate strength in static bending (three- and four-point loading methods),
- b) impact bend resistance (three-point loading method).

These test methods apply to all types of nails, including loose, collated or coil nails, up to 6 mm in diameter (round, square, fluted, twisted, plain or threaded) and may also be suitable for other fasteners such as staples.

2 Definition

For the purposes of this part of ISO 12777, the following definition applies.

2.1 bending resistance

(1) (primary static method): The ultimate strength determined in bending configuration using a three- or four-point loading method. It is measured as torque in newton metres.

(2) (supplementary impact method): The impact bend resistance under the application of a given load. It is measured in degrees as an angle of deformation.

3 Symbols

F	Applied force, in newtons
F_R	Force of reaction, in newtons
I	Impact load (impulse), in newton seconds
M	Applied torque, in newton metres
M_R	Opposing torque, in newton metres
l	Nail or staple length, in millimetres, under bending stress (dimension B to C in figures 1 and 3)
L	Effective length, in millimetres, of load actuator
α	Angular movement, in degrees
β	Angle of deformation, in degrees

4 Static bend tests (primary methods)

4.1 Three-point loading method

4.1.1 Principle

A nail, staple or other dowel-type fastener is clamped in such a way as to resist bending at two points A and B (see figure 1). A force is then applied to the unclamped portion of the nail at a set point C, using a pivoted bending actuator to which torque is applied. The maximum torque applied is recorded.